

Original citation:

Rhodes, D., Schönemann, R., Aryal, N., Zhou, Q., Zhang, Q. R., Kampert, Erik, Chiu, Y.-C., Lai, Y., Shimura, Y., McCandless, G. T., Chan, J. Y., Paley, D. W., Lee, J., Finke, A. D., Ruff, J. P. C., Das, S., Manousakis, E. and Balicas, L.. (2017) Bulk fermi surface of the Weyl type-II semimetallic candidate γ -MoTe₂. Physical Review B (Condensed Matter and Materials Physics), 96 (16).

Permanent WRAP URL:

<http://wrap.warwick.ac.uk/93409>

Copyright and reuse:

The Warwick Research Archive Portal (WRAP) makes this work by researchers of the University of Warwick available open access under the following conditions. Copyright © and all moral rights to the version of the paper presented here belong to the individual author(s) and/or other copyright owners. To the extent reasonable and practicable the material made available in WRAP has been checked for eligibility before being made available.

Copies of full items can be used for personal research or study, educational, or not-for-profit purposes without prior permission or charge. Provided that the authors, title and full bibliographic details are credited, a hyperlink and/or URL is given for the original metadata page and the content is not changed in any way.

Publisher statement:

© 2017 American Physical Society

Published version: <http://dx.doi.org/10.1103/PhysRevB.96.165134>

A note on versions:

The version presented here may differ from the published version or, version of record, if you wish to cite this item you are advised to consult the publisher's version. Please see the 'permanent WRAP url' above for details on accessing the published version and note that access may require a subscription.

For more information, please contact the WRAP Team at: wrap@warwick.ac.uk

Bulk Fermi-surface of the Weyl type-II semi-metal candidate γ -MoTe₂

D. Rhodes,^{1,2} R. Schönemann,¹ N. Aryal,^{1,2} Q. Zhou,^{1,2} Q. R. Zhang,^{1,2} E. Kampert,³
Y.-C. Chiu,^{1,2} Y. Lai,^{1,2} Y. Shimura,^{1,4} G. T. McCandless,⁵ J. Y. Chan,⁵ D. W. Paley,^{6,7}
J. Lee,⁸ A. D. Finke,⁸ J. P. C. Ruff,⁸ S. Das,^{1,2} E. Manousakis,^{2,1} and L. Balicas^{1,2,*}

¹*National High Magnetic Field Laboratory, Florida State University, Tallahassee-FL 32310, USA*

²*Department of Physics, Florida State University, Tallahassee-FL 32306, USA*

³*Dresden High Magnetic Field Laboratory (HLD-EMFL),*

Helmholtz-Zentrum Dresden-Rossendorf, 01328 Dresden, Germany

⁴*University of Tokyo, Institute of Solid State Physics, Kashiwa, Chiba 2778581, Japan*

⁵*The University of Texas at Dallas, Department of Chemistry and Biochemistry, Richardson, TX 75080 USA*

⁶*Department of Chemistry, Columbia University, New York, NY 10027 USA*

⁷*Columbia Nano Initiative, Columbia University, New York, NY 10027 USA*

⁸*CHESS, Cornell University, Ithaca, New York 14853, USA*

(Dated: August 22, 2017)

The electronic structure of semi-metallic transition-metal dichalcogenides, such as WTe₂ and orthorhombic γ -MoTe₂, are claimed to contain pairs of Weyl points or linearly touching electron and hole pockets associated with a non-trivial Chern number. For this reason, these compounds were recently claimed to conform to a new class, deemed type-II, of Weyl semi-metallic systems. A series of angle resolved photoemission experiments (ARPES) claim a broad agreement with these predictions detecting, for example, topological Fermi arcs at the surface of these crystals. We synthesized single-crystals of semi-metallic MoTe₂ through a Te flux method to validate these predictions through measurements of its bulk Fermi surface (FS) *via* quantum oscillatory phenomena. We find that the superconducting transition temperature of γ -MoTe₂ depends on disorder as quantified by the ratio between the room- and low-temperature resistivities, suggesting the possibility of an unconventional superconducting pairing symmetry. Similarly to WTe₂, the magnetoresistivity of γ -MoTe₂ does not saturate at high magnetic fields and can easily surpass 10⁶ %. Remarkably, the analysis of the de Haas-van Alphen (dHvA) signal superimposed onto the magnetic torque, indicates that the geometry of its FS is markedly distinct from the calculated one. The dHvA signal also reveals that the FS is affected by the Zeeman-effect precluding the extraction of the Berry-phase. A direct comparison between the previous ARPES studies and density-functional-theory (DFT) calculations reveals a disagreement in the position of the valence bands relative to the Fermi level ε_F . Here, we show that a shift of the DFT valence bands relative to ε_F , in order to match the ARPES observations, and of the DFT electron bands to explain some of the observed dHvA frequencies, leads to a good agreement between the calculations and the angular dependence of the FS cross-sectional areas observed experimentally. However, this relative displacement between electron- and hole-bands eliminates their crossings and, therefore, the Weyl type-II points predicted for γ -MoTe₂.

Keywords: Subject Areas: Condensed Matter Physics, Superconductivity

I. INTRODUCTION

The electronic structure of the transition-metal dichalcogenides (TMDs) belonging to the orthorhombic and non-centrosymmetric $Pmn2_1$ space group, e.g. WTe₂, were recently recognized as candidates for possible topologically non-trivial electronic states. For instance, their monolayer electronic bands were proposed to be characterized by a non-trivial $Z_2 = 1$ topological invariant based on the parity of their valence bands, making their monolayers good candidates for a quantum spin Hall insulating ground-state [1]. This state is characterized by helical edge states that are protected by time-reversal symmetry from both localization and elastic backscattering. Hence, these compounds could provide a platform for realizing low dissipation quantum

electronics and spintronics [1, 2].

However, the majority of gapped TMDs, such as semi-conducting MoS₂ or WSe₂, crystallize either in a trigonal prismatic coordination or in a triclinic structure with octahedral coordination [3, 4] as is the case of ReS₂. Those crystallizing in the aforementioned orthorhombic phase, e.g. WTe₂, are semi-metals albeit displaying remarkable transport properties such as an enormous, non-saturating magnetoresistivity [5]. Strain is predicted to open a band gap [1] in WTe₂, which might make it suitable for device development. In fact, simple exfoliation of its isostructural γ -MoTe₂ compound (where γ refers to the orthorhombic semi-metallic phase) into thin atomic layers was claimed to induce a band gap [6] in the absence of strain. Such a transition would contrast with band structure calculations finding that WTe₂ should remain semi-metallic when exfoliated down to a single atomic layer [7]. The insulating behavior reported for a few atomic layers of WTe₂ was ascribed to an increase in disorder due to its chemical instability in the presence of humidity

* balicas@magnet.fsu.edu

which would induce Anderson localization [8], although more recently it was claimed to be intrinsic from transport measurements on encapsulated few-layered samples [9].

Orthorhombic γ -MoTe₂ and its isostructural compound WTe₂ were also claimed, based on density functional theory calculations, to belong to a new class of Weyl semi-metals, called type-II, which is characterized by a linear touching between hole and electron Fermi surface pockets [10–12, 15]. As for conventional Weyl points [13, 14], these Weyl type-II points would also act as topological charges associated with singularities, i.e., sources and sinks, of Berry-phase pseudospin [10–12, 15] which could lead to anomalous transport properties. A series of recent angle-resolved photoemission spectroscopy (ARPES) measurements [16–23] claim to observe a good overall agreement with these predictions. These studies observe the band crossings predicted to produce the Weyl type-II points, which would be located slightly above the Fermi-level, as well as the Fermi arcs projected on the surface of this compound [16–23].

Here, motivated by the scientific relevance and the possible technological implications of the aforementioned theoretical predictions [1, 10–12, 15], we evaluate, through electrical transport and torque magnetometry in bulk single-crystals, the electronic structure at the Fermi level and the topological character of orthorhombic γ -MoTe₂. Our goal is to contrast our experimental observations with the theoretical predictions and the reported ARPES results in order to validate their findings. This information could, for example, help us predict the electronic properties of heterostructures fabricated from single- or a few atomic layers of this compound. An agreement between the calculated geometry of the FS of γ -MoTe₂ with the one extracted from quantum oscillatory phenomena, would unambiguously support the existence of Weyl nodes in the bulk [13, 14] and, therefore, the existence of related non-trivial topological surface states or Fermi arcs [10–12, 14, 15]. However, quantum oscillatory phenomena from γ -MoTe₂ single-crystals reveals a Fermi surface whose geometry is quite distinct from the one predicted by the DFT calculations based on its low temperature crystallographic structure. The extracted Berry-phase is found to be field-dependent. Still one does not obtain evidence for the topological character predicted for this compound when the Berry-phase is evaluated at low fields. Here, we show that shifts in the relative position of the electron and hole bands, implied by previous ARPES studies [16–23], can replicate the angular dependence of the observed Fermi surface cross-sectional areas. However, these band shifts imply that the valence and electron bands would no longer cross and, therefore, that γ -MoTe₂ would not display the predicted Weyl type-II semi-metallic state.

II. METHODS AND EXPERIMENTAL RESULTS

Very high quality single crystals of monoclinic β -MoTe₂ were synthesized through a Te flux method: Mo, 99.9999%, and Te 99.9999 % powders were placed in a quartz ampoule in a ratio of 1:25 heated up to 1050 °C and held for 1 day. Then, the ampoule was slowly cooled down to 900 °C and centrifuged. The “as harvested” single-crystals were subsequently annealed for a few days at a temperature gradient to remove the excess Te. Magneto-transport measurements as a function of temperature were performed in a Physical Property Measurement System using a standard four-terminal configuration. Measurements of the Shubnikov-de Haas (SdH) and the de Haas-van Alphen (dHvA) effects were performed in dilution refrigerator coupled to a resistive Bitter magnet, with the samples immersed in the ³He-⁴He mixture. Measurements of the dHvA-effect were performed *via* a torque magnetometry technique, i.e. by measuring the deflection of a Cu-Be cantilever capacitively. Electrical transport measurements in pulsed magnetic fields were performed at the Dresden High Magnetic Field Laboratory using a 62 T magnet with a pulse duration of 150 ms. The sample temperature was controlled using a ⁴He bath cryostat (sample in He atmosphere) with an additional local heater for temperatures above 4.2 K. Synchrotron based X-ray measurements were performed in three single-crystals at the CHESS-A2 beam line using a combination of photon energies and cryogenic set-ups. The crystallographic data was reduced with XDS [24]. The structures were solved with direct methods using SHELXS [25]. Outlier rejection and absorption correction was done with SADABS. Least squares refinement on the intensities were performed with SHELXL [25]. For additional detailed information on the experimental set-ups used, see Supplemental Information file [26].

As illustrated by Fig. 1(a), the as synthesized single-crystals display resistivity ratios $RRR = \rho(T = 300 \text{ K})/\rho(T = 2 \text{ K})$ ranging from 380 to > 2000 which is one to two orders of magnitude higher than the RRR values currently in the literature (see, for example, Ref. 27). Although not clearly visible in Fig. 1(a) due to its logarithmic scale, a hysteretic anomaly is observed in the resistivity around 240 K corresponding to the monoclinic to orthorhombic structural transition which stabilizes what we denominate as the orthorhombic γ -MoTe₂ phase. For a clearer exposure of this transition and related hysteresis, see Ref. 28. These single-crystals were subsequently measured at much lower temperatures allowing us to determine their superconducting transition temperature T_c . Remarkably, and as seen in Fig. 1(b), we find that T_c depends on sample quality, increasing considerably as the RRR increases, suggesting that structural disorder suppresses T_c . For these measurements, particular care was taken to suppress the remnant field of the superconducting magnet since the upper critical




FIG. 1. (a) Resistivity ρ , for currents flowing along the a -axis, as a function of the temperature T for three representative single crystals displaying resistivity ratios $\rho(300\text{ K})/\rho(2\text{ K})$ between 380 and $\gtrsim 1000$. (b) ρ as a function of T for each single-crystal indicating that T_c depends on sample quality: it increases from an average transition middle point value of ~ 130 mK for the sample displaying the lowest ratio to ~ 435 mK for the sample displaying the highest one. The apparent hysteresis is due to a non-ideal thermal coupling between the single-crystals, the heater and the thermometer. (c) ρ as a function of the field H applied along the c -axis at a temperature $T = 1.7$ K for a fourth crystal characterized by a resistivity ratio of ~ 207 . Notice i) the non-saturation of $\rho(H)$ and ii) that $\Delta\rho(\mu_0 H)/\rho_0 = (\rho(\mu_0 H) - \rho_0)/\rho_0$, where $\rho_0 = \rho(\mu_0 H = 0\text{ T}, T = 2\text{ K})$ surpasses $1.4 \times 10^6\%$ at $\mu_0 H = 60$ T. (d) ρ as a function of $\mu_0 H$ applied along the b -axis also at $T = 1.7$ K and for the same single-crystal. (e) Shubnikov-de Haas signal superimposed onto the magnetoresistivity for $\mu_0 H \parallel c$ -axis and for three temperatures, $T = 8$ K (blue line), 4.2 K (red line) and 1.7 K (black line), respectively. (f) Oscillatory signal (black line) superimposed onto the magnetic susceptibility $\Delta\chi = \partial(\tau/\mu_0 H)/\partial\mu_0 H$, where τ is the magnetic torque.

fields are rather small (see Supplemental Fig. S1 [26]). The sample displaying the highest RRR and concomitant T_c was measured in absence of a remnant field. To verify that these differences in T_c are not due to a poor thermal coupling between the sample and the thermometers, T_c was measured twice by increasing and decreasing T very slowly. The observed hysteresis is small relative to T_c indicating that the measured T_c s are not an artifact. The values of the residual resistivities ρ_0 depend on a careful determination of the geometrical factors such as the size of the electrical contacts. Therefore, the RRR provides a more accurate determination of the single-crystalline quality. In the past, the suppression of T_c by impurities and structural defects was systematically taken as evidence for unconventional superconductivity [29–31], e.g. triplet superconductivity [32] in Sr_2RuO_4 . Nevertheless, the fittings of the upper-critical fields H_{c2} to a conventional Ginzburg-Landau expression, shown in Fig. S1 [26], points towards singlet pairing.

We have also evaluated the quality of our single crystals through Hall-effect [28] and heat capacity measurements (see, Supplemental Fig. S2 [26]). Hall-effect reveals a sudden increase in the density of holes below

$T = 40$ K, suggesting a possible temperature-induced Lifshitz-transition. While the heat capacity reveals a broad anomaly around $T = 66$ K, well-below its Debye temperature ($\Theta_D \simeq 120$ K), that would suggest that the structural degrees of freedom continue to evolve upon cooling below $T = 100$ K. Given that such structural evolution could affect the electronic band structure predicted for γ - MoTe_2 [11, 12, 15], we performed synchrotron X-ray scattering down to ~ 12 K (see, Supplemental Fig. S3 [26]). We observe some variability in the lattice constants extracted among several single-crystals and a sizeable hysteresis in the range $125\text{ K} \leq T \leq 250\text{ K}$ associated with the structural transition observed at $T \simeq 250$ K, but no significant evolution in the crystallographic structure below 100 K. As we discuss below, there are negligible differences between the electronic bands calculated with the crystal structures collected at 100 K and at 12 K, respectively.

Figures 1(c) and 1(d) display the change in magnetoresistivity $\Delta\rho(\mu_0 H)/\rho_0 = (\rho(\mu_0 H) - \rho_0)/\rho_0$ as a function of the field $\mu_0 H$ for a crystal characterized by $RRR \sim 450$ when the electrical current flows along the crystalline a -axis and the field is applied either along the c - or the




FIG. 2. (a) Typical de Haas-van Alphen (red trace) and Shubnikov-de Haas (black trace) signals superimposed onto the magnetic torque and the magnetoresistivity respectively, for fields aligned along the c -axis of γ -MoTe₂ single-crystals at $T \simeq 30$ mK. The same panel shows the FFT spectra for each signal revealing just two main frequencies or FS cross-sectional areas. (b) dHvA and SdH signals and corresponding FFT spectra obtained from the same single-crystals for H aligned nearly along the a -axis of each single-crystal. (c) and (d), Amplitude of the peaks observed in the FFT spectra for $H||c$ -axis and as a function of T including the corresponding fits to the LK formula from which the effective masses are extracted. (e) and (f) Amplitude of two representative peaks observed in the FFT spectra for $H||a$ -axis and as a function of T with the corresponding fits to the LK formula to extract their effective masses.

b -axes, respectively. Similarly to WTe₂, for both orientations $\Delta\rho/\rho_0$ shows no sign of saturation under fields all the way up to 60 T while surpassing 1×10^6 % for $\mu_0 H||c$ -axis [5]. For WTe₂ such anomalous magnetoresistivity was attributed to compensation between the density of electrons and holes [5, 33, 34]. Nevertheless, there are a number of subsequent observations [35] contradicting this simple scenario, such as i) a non-linear Hall response [36], ii) the suppression of the magnetoresistivity at a pressure where the Hall response vanishes [37] (i.e. at perfect compensation), and iii) the observation of a pronounced magnetoresistivity in electrolyte gated samples with a considerably higher density of electrons with respect to that of holes [38]. It remains unclear if the proposed unconventional electronic structure [10–12] would play a role on the giant magnetoresistivity of WTe₂, while its measured FS differs from the calculated one [35]. In contrast, we have previously shown that γ -MoTe₂ indeed is a well compensated semi-metal [28]. The slightly smaller magnetoresistivity of γ -MoTe₂ relative to WTe₂ is attributable to heavier effective masses, according to de Haas-van Alphen-effect discussed

below, or concomitantly lower mobilities.

The best γ -MoTe₂ samples, i.e. those with $RRR \geq 2000$, display even more pronounced $\Delta\rho/\rho_0$ under just $\mu_0 H \simeq 10$ T. The oscillatory component superimposed on the magnetoresistivity corresponds to the Shubnikov-de Haas (SdH) effect resulting from the Landau quantization of the electronic orbits. Figure 1(e) shows the oscillatory, or the SdH signal as a function of inverse field $(\mu_0 H)^{-1}$ for three temperatures. The SdH signal was obtained by fitting the background signal to a polynomial and subtracting it. Notice how for this sample and for $\mu_0 H||c$ -axis, the SdH signal is dominated by a single frequency. However for all subsequent measurements performed under continuous fields (discussed below) one observes the presence of two main frequencies very close in value, each associated to an extremal cross-sectional area A of the FS through the Onsager relation $F = A(\hbar/2\pi e)$ where \hbar is the Planck constant and e is the electron charge. To illustrate this point, we show in Fig. 1(f) the oscillatory signal extracted from the magnetic torque, i.e. $\tau = \mathbf{M} \times \mu_0 \mathbf{H}$, or the de Haas-van Alphen effect (dHvA) collected from a γ -MoTe₂ single-crystal for

fields aligned nearly along its c -axis. Here $M = \chi\mu_0H$ is the magnetization and $\chi(\mu_0H, T)$ is its magnetic susceptibility. Figure 1(f) shows the oscillatory component of the magnetic susceptibility $\Delta\chi = \partial(\tau/\mu_0H)/\partial(\mu_0H)$. The envelope of the oscillatory signal displays the characteristic “beating” pattern between two close frequencies. This becomes clearer in the fast Fourier transform of the oscillatory signal shown below. According to the Lifshitz-Onsager quantization condition [39, 40], the oscillatory component superimposed onto the susceptibility is given by:

$$\Delta\chi[(B)^{-1}] \propto \frac{T}{B^{5/2}} \sum_{l=1}^{\infty} \frac{\exp^{-l\alpha\mu T_D/B} \cos(lg\mu\pi/2)}{l^{3/2} \sinh(\alpha\mu T/B)} \times \cos \left\{ 2\pi \left[\left(\frac{F}{B} - \frac{1}{2} + \phi_B \right) l + \delta \right] \right\} \quad (1)$$

where F is the dHvA frequency, l is the harmonic index, ω_c the cyclotron frequency, g the Landé g -factor, μ the effective mass in units of the free electron mass m_0 , and α is a constant. δ is a phase shift determined by the dimensionality of the FS which acquires a value of either $\delta = 0$ or $\pm 1/8$ for two- and three-dimensional FSs [39–41], respectively. ϕ_B is the Berry phase which, for Dirac and Weyl systems, is predicted to acquire a value $\phi_B = \pi$ [39–41]. Finally, $T_D = \hbar/(2\pi k_B\tau)$ is the so-called Dingle temperature from which one extracts τ or the characteristic quasiparticle scattering time.

In Supplementary Figs. S4 and S5 [26], we discuss the extraction of the Berry-phase of γ -MoTe₂ via fits to Eq. (1) of the oscillatory signal shown in Fig. 1(f). However, the geometry of the FS of γ -MoTe₂ evolves slightly as the field increases due to the Zeeman-effect, which precludes the extraction of its Berry phase. More importantly, one cannot consistently extract a value $\phi_B \simeq \pi$ when one limits the range in magnetic fields to smaller values in order to minimize the role of the Zeeman-effect. In other words, the dHvA-effect does not provide evidence for the topological character of γ -MoTe₂. Nevertheless, it does indicate that the Dingle temperature decreases as the field increases implying a field-induced increase in the quasiparticle lifetime. This effect should contribute to its large and non-saturating magnetoresistivity. We reported a similar effect for WTe₂ [35].

Since the Berry-phase extracted from the dHvA-effect does not provide support for a topological semi-metallic state in γ -MoTe₂, it is pertinent to ask if the DFT calculations predict the correct electronic band-structure and related FS geometry for this compound, since both are the departing point for the predictions of Refs. 10–12. To address this issue, we studied the dHvA-effect as a function of the orientation of the field with respect to the main crystallographic axes. Here, our goal is to compare the angular dependence of the cross-sectional areas determined experimentally, with those predicted by DFT.

Figures 2(a) and 2(b) display both the dHvA (red traces) and the SdH signals (black traces) measured in

two distinct single crystals and for two field orientations, respectively along the c - and the a -axes. As previously indicated, the dHvA and SdH signals were obtained after fitting a polynomial and subtracting it from the background magnetic torque and magnetoresistivity traces, respectively. The SdH signal was collected from a crystal displaying a $RRR \gtrsim 1000$ at $T \simeq 25$ mK under fields up to 18 T, while the dHvA one was obtained from a crystal displaying $RRR \gtrsim 2000$ at $T \simeq 35$ mK under fields up to 35 T. Both panels also display the Fast Fourier transform (FFT) of the oscillatory signal. For fields along the c -axis, one observes two main peaks at $F_\alpha = 231$ T and at $F_\beta = 242$ T, as well as their first- and second harmonics and perhaps some rather small frequencies which could result from imperfect background subtraction. We obtain the same two dominant frequencies regardless of the interval in H^{-1} used to extract the FFTs. Supplemental Fig. S6 [26] displays the dHvA signal for H aligned nearly along the b -axis along with the corresponding FFT spectra which are again dominated by two prominent peaks. The observation of just two main frequencies for $\mu_0H \parallel c$ -axis is rather surprising since, as we show below, DFT calculations, including the effect of the spin-orbit interaction, predict several pairs of electron-like corrugated cylindrical FSs along with pairs of smaller three-dimensional electron-like sheets in the First-Brillouin zone. Around the Γ -point, DFT predicts at least a pair of four-fold symmetric helix-like large hole sheets. This complex FS should lead to a rich oscillatory signal, contrary to what is observed. One might argue that the non-observation of all of the predicted FS sheets would be attributable to an experimental lack of sensitivity or to poor sample quality which would lead to low carrier mobility. Nevertheless, our analysis of the Hall-effect within a two-carrier model [28], yields electron- and hole-mobilities ranging between 10^4 and 10^5 cm²/Vs at low T s which is consistent with both the small residual resistivities and the large resistivity ratios of our measured crystals. Given that the magnetic torque is particularly sensitive to the anisotropy of the FS, such high mobilities should have allowed us to detect most of the predicted FSs, particularly at the very low T s and very high fields used for our measurements. Hence, we conclude that the geometry of the FS ought to differ considerably from the one predicted by DFT.

In Figs. 2(c) and 2(d) we plot the amplitude of the main peaks observed in the FFT spectra for fields along the c -axis as a function of the temperature. Red lines are fits to the Lifshitz-Kosevich (LK) temperature damping factor, i.e. $x/\sinh x$ with $x = 14.69\mu T/H$ and with μ being the effective mass in units of the free electron mass, from which we extract the masses associated with each frequency. As seen, for $H \parallel c$ -axis one obtains $\mu_\alpha = 0.85 m_0$ and $\mu_\beta = 0.8 m_0$, which contrasts with the respective values obtained for $H \parallel a$ -axis, namely $\mu_{\alpha,\beta} \simeq 1.5 m_0$, see Figs. 2(e) and 2(f). As previously mentioned for $\mu_0H \parallel b$ -axis, we observe two main frequencies, but by reducing the H^{-1} window to focus on the higher field




FIG. 3. (a) Electronic band-structures of γ -MoTe₂ calculated with and without the inclusion of spin-orbit coupling (SOC). These calculations are based on the crystallographic structure measured at $T = 100$ K. (b) Comparison between the calculated electronic bands based upon the crystallographic structures measured at $T = 100$ and $T = 12$ K, respectively. (c) and (d) Respectively, side and top views of the calculated FS. (e), (f), (g) and (h) Fermi surface sheets resulting from electron bands. Notice the marked two-dimensional character of several of the electron-like FS sheets. (i), (k) and (l), Hole-like sheets around the Γ -point.

region, we detect additional frequencies (See, Fig. S6 [26]) which are characterized by heavier effective masses, i.e. in the order of $2.5 - 2.9 m_0$. This indicates that γ -MoTe₂ displays a higher anisotropy in effective masses when compared to WTe₂ [35], although these masses are consistent with its sizeable γ_e coefficient. Supplemental Fig. S7 [26] displays several traces of the dHvA signal as functions of the inverse field for several angles between all three main crystallographic axes. These traces are used to plot the angular dependence of the FS cross-sectional

areas in order to compare these with the DFT calculated ones.

III. COMPARISON BETWEEN EXPERIMENTS AND THE DFT CALCULATIONS

Several recent angle-resolved photoemission spectroscopy (ARPES) studies [16–23] claim to find a broad agreement between the band structure calculations, the




FIG. 4. (a) Angular dependence of the FS cross-sectional areas or, through the Onsager relation, de Haas-van Alphen frequencies as with respect to the main crystallographic axes. (b) Experimentally observed dHvA spectra as a function of the frequency F for several angles θ between the c - and the b -axis and for several values of the angle $-\phi$ between the c - and the a -axes.

predicted geometry of the Fermi surface, the concomitant existence of Weyl type-II points [10–12], and the related Fermi arcs on the surface states of γ -MoTe₂. Several of these experimental and theoretical studies claim that the electronic structure of this compound is particularly sensitive to its precise crystallographic structure. Inter-growth of the $2H$ -phase or the temperature used to collect to X-ray diffraction data, typically around 100 to 230 K, are claimed to have a considerable effect on the calculations [12, 21]. Given the few frequencies observed by us, it is pertinent to ask if the mild evolution of the crystallographic structure as a function of the temperature shown in Fig. S3 [26] would affect the geometry of the FS of γ -MoTe₂. To address this question we performed a detailed angular-dependent study of the frequencies extracted from both the SdH and the dHvA effects in γ -MoTe₂ in order to compare these with the angular dependence of the FS cross-sectional areas predicted by the calculations.

In the subsequent discussion we compare the angular dependence of our dHvA frequencies with calculations performed with the Quantum Espresso [42] implementation of the density functional theory in the GGA framework including spin-orbit coupling (SOC). The Perdew-Burke-Ernzerhof (PBE) exchange correlation functional [43] was used with fully relativistic norm-conserving pseudopotentials generated using the optimized norm-conserving Vanderbilt pseudopotentials as described in Ref. 44. The $4s$, $4p$, $4d$ and $5s$ electrons of Mo and

the $4d$, $5s$ and $5p$ electrons of Te were treated as valence electrons. After careful convergence tests, the plane-wave energy cutoff was taken to be 50 Ry and a k -point mesh of $20 \times 12 \times 6$ was used to sample the reducible Brillouin Zone (BZ) used for the self-consistent calculation. The Fermi surfaces were generated using a more refined k -point mesh of $45 \times 25 \times 14$. FS sheets were visualized using the XCrysden software [45]. The related angular dependence of the quantum oscillation frequencies was calculated using the skeaf code [46]. As shown in Fig. 3 the results are very close to those obtained by using the VASP and the Wien2K implementations of DFT (see, Fig. S8 in SI [26]), and also to those reported by Refs. 11, 12, 16, and 23.

Figure 3(a) displays the electronic band structure of γ -MoTe₂, based on its structure determined at $T = 100$ K, with and without the inclusion of SOC. As previously reported [11, 12], electron- and hole-bands intersect along the $\Gamma - X$ direction at energies slightly above ε_F creating a pair of Weyl type-II points. Figure 3(b) shows a comparison between band structures based on the crystallographic lattices determined at 12 K and at 100 K, respectively. Both sets of electronic bands are nearly identical and display the aforementioned crossings between hole- and electron-bands thus indicating that the electronic structure remains nearly constant below 100 K. Figures 3(c) and 3(d) provide a side perspective and a top view of the overall resulting FS within BZ, respectively. The main features of the DFT calculations are the




FIG. 5. (a) ARPES energy distribution map along k_y for $k_x = 0$ from Ref. 23. (b) Derivative of the energy distribution map. Vertical blue lines indicate the diameter of the observed hole-pocket, with its area corresponding to a frequency $F \sim 0.33$ kT. (c) Ribbons obtained from our DFT calculations showing the k_z -projection for all bulk bands which are plotted along the same direction as the ARPES energy distribution map in (a). Different colors are chosen to indicate distinct bands. Purple dotted line corresponds to the original position of the Fermi level ϵ_F according to DFT, while the white one corresponds to the position of ϵ_F according to ARPES. Notice that the ARPES bands are shifted by ~ -50 meV with respect to the DFT ones. (d) ARPES energy distribution map corresponding to a cut along the k_x -direction with $k_y = 0$, from Ref. 21. Vertical red dotted lines indicate the diameter of the observed electron pockets or $\sim 0.2 \text{ \AA}^{-1}$. SS stands for “surface-state”. (e) DFT Ribbons showing the k_z -projection for all bulk bands plotted along the same direction as the ARPES EDM in (d). In both panels black lines depict the original position of ϵ_F while the yellow lines are guides to the eyes illustrating the difference in energy between the top of the deepest DFT calculated hole-band and its equivalent according to ARPES.

presence of two-dimensional electron pockets, labeled e_1 and e_2 in Figs. 3(e) and 3(f) and of large “star-shaped” hole-pockets near the Γ -point, labeled as the h_2 and the h_3 sheets in Figs. 3(k) and 3(l). These electron and hole pockets nearly “touch”. Due to the broken inversion symmetry, these bands are not Kramer’s degenerate, and hence the spin-orbit split partners of the corresponding electron and hole pockets are located inside the corresponding bigger sheets. The h_1 hole pocket and the e_3 and e_4 electron pockets are very sensitive to the position of ϵ_F disappearing when ϵ_F is moved by only ± 15 meV.

Figures 4(a) and 4(b) present the angular dependence of the calculated and of the measured FFT spectra of the oscillatory signal (raw data in Fig. S7 [26]), respectively. In this plot the Onsager relation was used to convert the theoretical FS cross-sectional areas into oscillatory frequencies. In Fig. 4(b) θ refers to angles between the c - and the a -axis, where $\theta = 0^\circ$ corresponds to $H \parallel c$ -axis, while ϕ corresponds to angles between the c - and the b -axis, again relative to the c -axis. As seen, there are

striking differences between both data sets with the calculations predicting far more frequencies than the measured ones. More importantly, for fields oriented from the c -axis towards either the a - or the b -axis, one observes the complete absence of experimental frequencies around ~ 1 kT which, according to the calculations, would correspond to the cross-sectional areas of the hole-pockets h_2 and h_3 . In addition, while many of the predicted electron orbits show a marked two-dimensional character, diverging as the field is oriented towards the a - or the b -axis, the experimentally observed frequencies show finite values for fields along either axis. This indicates that these orbits are three-dimensional in character, despite displaying frequencies close to those predicted for the e_1 and the e_2 pockets for fields along the c -axis. These observations, coupled to the non-detection of all of the predicted orbits, in particular the large hole h_2 and h_3 Fermi surfaces, indicate unambiguously that the actual geometry of the FS of γ -MoTe₂ is different from the calculated one. Notice that frequencies inferior to $F = 100$ T, which




FIG. 6. (a) Experimentally observed dHvA spectra as a function of F for several angles θ and $-\phi$, where the magenta and the blue lines act as guides to the eyes and as identifiers of respectively, electron- and hole-like orbits according to the shifted band structure. Clear blue line depicts a possible hole-orbit associated with very small peaks in the FFT spectra. (b) Angular dependence of the dHvA orbits, or frequencies on the FS resulting from the shifted bands in absence of spin-orbit coupling, where magenta and blue markers depict electron- and hole-like orbits on the FS, respectively. Notice the qualitative and near quantitative agreement between the calculations and the experimental observations. (d) Angular dependence of the dHvA frequencies for the shifted electron and hole-bands in the presence of spin-orbit coupling. Here, electron-orbits are depicted by magenta and orange markers while the hole ones are indicated by blue and clear blue markers. The experimental data are better described by the non spin-orbit split bands.

correspond to the smaller electron- and hole-pockets and which are particularly sensitive to the position of ε_F as previously mentioned, were not included in Fig. 4(a) for the sake of clarity.

The calculation shows a significant difference between the SOC-split theoretical bands, which is highlighted by the absence of a frequency around 0.5 kT associated with e_2 pocket, along with its presence in association with the e_1 pocket. This contrast between both orbits is due to the presence of a “handle-like” structure (see Fig. 3(e)) in e_1 which gives a maximum cross-section close to the BZ edge. However, at this position there is no maximum cross-section within the BZ for the e_2 pocket since its “handle” is missing (see Fig. 3(f)). This marked difference in topology between the FSs of both spin-orbit split partners indicates that the strength of the SOC provided by the DFT calculations tends to be considerably larger than the one implied by our experiments. In fact, from the twin peaks observed in the experimental FFT spectra having frequencies around 250 T for fields along the c -axis, which are likely to correspond to SOC-split bands due to their similar angular dependence, we can infer that the actual SO-splitting is far less significant than the value predicted by the calculations. We have investigated the possibility of an overestimation of the

strength of the SOC within our calculations which is the mechanism driving the DFT prediction of a large number of dHvA frequencies displaying remarkably different angular dependencies. For instance, we calculated the angular dependence of the FSs without the inclusion of SOC. This leads to just one, instead of a pair of distinct SOC-split bands, which in fact display angular dependencies very similar to those of orbits h_3 , e_1 and e_3 in Fig. 4(a). Notice that part of the discrepancy is attributable to the inter-planar coupling which is not well captured by the DFT calculations [47]. DFT suggests that this compound is van der Waals like by predicting several two-dimensional (i.e. cylindrical like) FS sheets, when the experiments indicate that the overall FS displays a marked three-dimensional character. This indicates that the inter-planar coupling is stronger than implied by DFT. In any case, from Figs. 4(a) and 4(b) and the above discussion, it is clear that there are significant discrepancies between the calculated and the measured FSs. Given that the proposed Weyl type-II scenario [10–12] hinges on a possible touching between electron- and hole-pockets, it is critical to understand their exact geometry, or the reason for the disagreement between predictions and experiments, before one can make any assertion on the existence of the Weyl type-II points in γ -MoTe₂.




FIG. 7. (a) Electronic band structure calculated with the inclusion of SOC after the hole-like bands have been shifted by -50 meV and the electron ones by $+35$ meV with the goal of reproducing the observed dHvA frequencies and their angular dependence. Notice that these shifts suppress the crossings between the electron- and hole-bands and therefore the Weyl type-II points of the original band structure. (b) Fermi surface resulting from these band-shifts. (c) FS top view. (d) and (e) Electron-like FS sheets. (f) and (g) Hole-like sheets.

To understand the source of the disagreement between calculations and our measurements, we now focus on a detailed comparison between our DFT calculations and a selection of ARPES studies. Figure 5(a) corresponds to data from Ref. 23 depicting an ARPES energy distribution map (EDM) along k_y while keeping $k_x = 0$. Figure 5(b) plots its derivative. In both figures the Γ -point corresponds to $k_y = 0$. According to the calculations, this EDM should reveal two valence bands intersecting ε_F around the Γ -point; the first leading to two small hole-pockets, or the h_1 sheets at either side of Γ , with the second SOC-split band producing the larger h_2 and h_3 sheets. Instead, ARPES observes just one band intersecting ε_F which leads to a single FS sheet of cross-sectional area $S_{\text{FS}} \sim \pi(0.1 \text{ \AA}^{-1})^2$ as indicated by the vertical blue lines in Fig. 5(b). This observation by ARPES questions the existence of the band (or of its intersection with ε_F) responsible for the large h_2 and h_3 hole-pockets with this band being the one previously reported to touch the electron band that produces the e_1 pocket and creating in this way the Weyl type-II points [16–18, 21, 22]. Notice that our dHvA measurements do not reveal any evidence for the original h_2 and h_3 sheets, thus, being in agreement

with this ARPES observation. Furthermore, the Onsager relation $F = S(\hbar/2\pi e)$ yields a frequency of ~ 330 T for S_{FS} which, in contrast, is close to the frequencies observed by us for $\mu_0 H \parallel c$ -axis. Figure 5(c) displays the band structure calculated “ribbons” obtained by projecting the k_z dependence of the bands onto the k_x - k_y plane. This representation of the band-structure provides a better comparison with the ARPES EDMs. As seen, there is a good overall agreement between the ARPES and the DFT bands, as previously claimed [16–18, 21, 22], except for the exact position of ε_F . The purple line depicts the position of ε_F according to the DFT calculations while the white line depicts the position of ε_F according to ARPES. A nearly perfect agreement between DFT and ARPES is achievable by shifting the DFT valence bands by ~ -50 meV, which is what ends suppressing the h_2 and h_3 FS hole sheets from the measured ARPES EDMs. As shown through Figs. 5(d) and 5(e), this disagreement between the ARPES and the DFT bands is observed in the different ARPES studies[21]. Figure 5(d) corresponds to an EDM along the k_x ($k_y = 0$) direction of the BZ. As shown in Fig. 5(e), DFT reproduces this EDM quite well. Nevertheless, as indicated by the yellow lines in both figures, which are positioned at the top of the deepest va-

lence band observed by ARPES, the ARPES bands are displaced by ~ -45 meV with respect to the DFT ones. Red dotted lines in Fig. 5(d) indicate the cross-sections of the observed electron pockets or $\sim \pi(0.1 \text{ \AA}^{-1})^2$. Therefore, to match our main dHvA frequencies, the electron bands would have to be independently and slightly displaced towards higher energies to decrease their cross-sectional area. To summarize, DFT and ARPES agree well on the overall dispersion of the bands of γ -MoTe₂, but not on their relative position with respect to ε_F .

Therefore, guided by ARPES, we shifted the overall valence bands of γ -MoTe₂, shown in Figs. 3(a) and 3(b), by -50 meV and the electron ones by +35 meV to recalculate the FS cross-sectional areas as a function of field orientation relative to the main crystallographic axes. The comparison between the measured dHvA cross-sectional areas and those resulting from the shifted DFT bands are shown in Fig. 6. Figure 6(a) displays the Fourier spectra, previously shown in Fig. 4(b), with superimposed colored lines identifying shifted electron (magenta) and hole (blue) orbits according to Fig. 6(b) which displays these frequencies as a function of field orientation for shifted non-SOC-split DFT bands. As seen, the qualitative and quantitative agreement is good, but not perfect. In contrast, Fig. 6(c) displays these orbits/frequencies as a function of field orientation for SOC-split DFT bands. Clearly, and as previously discussed, the approach used to evaluate the effect of the SOC in γ -MoTe₂ overestimates it for reasons that remain to be clarified.

Concerning the Weyl physics in γ -MoTe₂, the displacement of the bands, introduced here to explain our observations based on the guidance provided by previous ARPES studies, would eliminate the crossings between the electron- and the hole-bands as shown in Fig. 7(a). The very weak SOC implied by our study further undermines the argument in favor of a Weyl type-II semimetallic state in this compound. Finally, Figs. 7(b) to 7(g) display the geometry of the Fermi surface resulting from the shifted bands. Overall, the FS displays a distinctly more marked three-dimensional character, with the electrons and the-hole pockets remaining well-separated in k -space.

IV. CONCLUSIONS

In conclusion, quantum oscillatory phenomena reveal that the geometry of the Fermi surface of γ -MoTe₂ is quite distinct from the one predicted by previous electronic band-structure calculations. Our low-temperature structural analysis *via* synchrotron X-ray diffraction measurements indicates the absence of an additional structural transition below the monoclinic to orthorhombic one that would explain this disagreement, while heat-capacity measurements provide no evidence for an electronic phase-transition upon cooling. In contrast, a direct comparison between DFT calculations and the band-

structure reported by angle resolved photoemission spectroscopy reveals a disagreement on the position of the valence bands relative to the Fermi-level, with the experimental valence bands shifted by ~ -50 meV relative to the DFT ones. Therefore, one should be careful concerning the claims of a broad agreement between the calculations and the electronic bands revealed by ARPES measurements [16–21].

Here, we show that it is possible to describe the angular-dependence of the observed de Haas-van Alphen Fermi surface cross-sectional areas by shifting the position of the DFT bands relative to the Fermi level as indicated by ARPES. However, with this adjustment, the Weyl points, which result from band-crossings that are particularly sensitive to small changes in the lattice constants, are no longer present in the band-structure of γ -MoTe₂. Although our approach of modifying the band structure in order to obtain an agreement with both ARPES and de Haas-van Alphen experiments is not based on *ab-initio* calculations and has only a phenomenological basis, our findings do shed a significant doubt on the existence of the Weyl points in the electronic band structure of γ -MoTe₂. In addition, our measurements indicate that the DFT calculations overestimate the role of spin-orbit coupling in this compound. Hence, our work which combines DFT calculations with measurements of quantum oscillatory phenomena, strongly suggests that the approach of including the role of spin-orbit coupling in the DFT implementations needs to be significantly revised, particularly in what concerns layered compounds.

Finally, this study combined with the ARPES results in Ref. 48, indicate that there ought to be a Lifshitz-transition [49] upon W doping in the γ -Mo_{1-x}W_xTe₂ series, leading to the disappearance of the central hole pockets in γ -MoTe₂ in favor of the emergence of hole-pockets at either side of the Γ -point in γ -Mo_{1-x}W_xTe₂.

ACKNOWLEDGMENTS

We acknowledge helpful discussions with R. M. Osgood and A. N. Pasupathy. J.Y.C. is supported by NSF-DMR-1360863. L. B. is supported by DOE-BES through award DE-SC0002613 for experiments under high magnetic fields and at very low temperatures, and by the U.S. Army Research Office MURI Grant W911NF-11-1-0362 for the synthesis and physical characterization of two-dimensional materials and their heterostructures. We acknowledge the support of the HLD-HZDR, member of the European Magnetic Field Laboratory (EMFL). Research conducted at the Cornell High Energy Synchrotron Source (CHESS) is supported by the NSF & NIH/NIGMS via NSF award DMR-1332208. The NHMFL is supported by NSF through NSF-DMR-1157490 and the State of Florida.

- [1] X. F. Qian, J. W. Liu, L. Fu, and J. Li, *Quantum spin Hall effect in two-dimensional transition metal dichalcogenides*, *Science* **346**, 1344 (2014).
- [2] D. Pesin, and A. H. MacDonald, *Spintronics and pseudospintronics in graphene and topological insulators*, *Nat. Mater.* **11**, 409-416 (2012).
- [3] M. Chhowalla, H. S. Shin, G. Eda, L. -J. Li, K. P. Loh, and H. Zhang, *The chemistry of two-dimensional layered transition metal dichalcogenide nanosheets*, *Nat. Chem.* **5**, 263-275 (2013).
- [4] S. Z. Butler, S. M. Hollen, L. Cao, Y. Cui, J. A. Gupta, H. R. Gutiérrez, T. F. Heinz, S. S. Hong, J. Huang, A. F. Ismach, E. Johnston-Halperin, M. Kuno, V. V. Plashnitsa, R. D. Robinson, R. S. Ruoff, S. Salahuddin, J. Shan, L. Shi, M. G. Spencer, M. Terrones, W. Windl and J. E. Goldberger, *Progress, Challenges, and Opportunities in Two-Dimensional Materials Beyond Graphene*, *ACS Nano* **7**, 2898-2926 (2013).
- [5] M. N. Ali, J. Xiong, S. Flynn, J. Tao, Q. D. Gibson, L. M. Schoop, T. Liang, N. Haldolaarachchige, M. Hirschberger, N. P. Ong and R. J. Cava, *Large, non-saturating magnetoresistance in WTe_2* , *Nature* **514**, 205-208 (2014).
- [6] D. H. Keum, S. Cho, J. H. Kim, D. -H. Choe, H. -J. Sung, M. Kan, H. Kang, J. -Y. Hwang, S. W. Kim, H. Yang, K. J. Chang and Y. H. Lee, *Bandgap opening in few-layered monoclinic $MoTe_2$* , *Nat. Phys.* **11**, 482-486 (2015).
- [7] H. Y. Lv, W. J. Lu, D. F. Shao, Y. Liu, S. G. Tan, and Y. P. Sun, *Perfect charge compensation in WTe_2 for the extraordinary magnetoresistance: From bulk to monolayer*, *EPL* **110**, 37004 (2015).
- [8] L. Wang, I. Gutiérrez-Lezama, C. Barreteau, N. Ubrig, E. Giannini, and A. F. Morpurgo, *Tuning magnetotransport in a compensated semimetal at the atomic scale*, *Nat. Commun.* **6**, 8892 (2015).
- [9] Z. Fei, T. Palomaki, S. Wu, W. Zhao, X. Cai, B. Sun, P. Nguyen, J. Finney, X. Xu, and D. H. Cobden, *Edge conduction in monolayer WTe_2* , *Nat. Phys.* **13**, 677 (2017).
- [10] A. A. Soluyanov, D. Gresch, Z. Wang, Q. Wu, M. Troyer, X. Dai and B. A. Bernevig, *A New Type of Weyl Semimetals*, *Nature* **527**, 495-498 (2015).
- [11] Y. Sun, S.C. Wu, M. N. Ali, C. Felser, and B. Yan, *Prediction of the Weyl semimetal in the orthorhombic $MoTe_2$* , *Phys. Rev. B* **92**, 161107 (2015).
- [12] Z. Wang, D. Gresch, A. A. Soluyanov, W. Xie, S. Kushwaha, X. Dai, M. Troyer, R. J. Cava, and B. A. Bernevig, *$MoTe_2$: A Type-II Weyl Topological Metal*, *Phys. Rev. Lett.* **117**, 056805 (2016).
- [13] H. M. Weng, C. Fang, Z. Fang, B. A. Bernevig, and X. Dai, *Weyl Semimetal Phase in Noncentrosymmetric Transition-Metal Monophosphides*, *Phys. Rev. X* **5**, 011029 (2015).
- [14] S. Y. Xu, I. Belopolski, N. Alidoust, M. Neupane, G. Bian, C. Zhang, R. Sankar, G. Chang, Z. Yuan, C. -C. Lee, S. -M. Huang, H. Zheng, J. Ma, D. S. Sanchez, B. Wang, A. Bansil, F. Chou, P. P. Shibayev, H. Lin, S. Jia, M. Z. Hasan, *Discovery of a Weyl fermion semimetal and topological Fermi arcs*, *Science* **349**, 613-617 (2015).
- [15] T. R. Chang, S. -Y. Xu, G. Chang, C. -C. Lee, S. -M. Huang, B. Wang, G. Bian, H. Zheng, D. S. Sanchez, I. Belopolski, N. Alidoust, M. Neupane, A. Bansil, H. -T. Jeng, H. Lin, and M. Z. Hasan, *Prediction of an arc-tunable Weyl Fermion metallic state in $Mo_xW_{1-x}Te_2$* , *Nat. Commun.* **7**, 10639 (2016).
- [16] L. Huang, T. M. McCormick, M. Ochi, Z. Zhao, M. -T. Suzuki, R. Arita, Y. Wu, D. Mou, H. Cao, J. Yan, N. Trivedi, and A. Kaminski, *Spectroscopic evidence for type II Weyl semimetal state in $MoTe_2$* , *Nat. Mater.* **15**, 1155-1160 (2016).
- [17] K. Deng, G. Wan, P. Deng, K. Zhang, S. Ding, E. Wang, M. Yan, H. Huang, H. Zhang, Z. Xu, J. Denlinger, A. Fedorov, H. Yang, W. Duan, H. Yao, Y. Wu, S. Fan, H. Zhang, X. Chen and S. Zhou, *Experimental observation of topological Fermi arcs in type-II Weyl semimetal $MoTe_2$* , *Nat. Phys.* **12**, 1105 (2016).
- [18] J. Jiang, Z. K. Liu, Y. Sun, H. F. Yang, R. Rajamathi, Y. P. Qi, L. X. Yang, C. Chen, H. Peng, C. -C. Hwang, S. Z. Sun, S. -K. Mo, I. Vobornik, J. Fujii, S. S. P. Parkin, C. Felser, B. H. Yan, Y. L. Chen, *Observation of the Type-II Weyl Semimetal Phase in $MoTe_2$* , *Nat. Commun.* **8**, 13973 (2017).
- [19] A. Liang, J. Huang, S. Nie, Y. Ding, Q. Gao, C. Hu, S. He, Y. Zhang, C. Wang, B. Shen, J. Liu, P. Ai, L. Yu, X. Sun, W. Zhao, S. Lv, D. Liu, C. Li, Y. Zhang, Y. Hu, Y. Xu, L. Zhao, G. Liu, Z. Mao, X. Jia, F. Zhang, S. Zhang, F. Yang, Z. Wang, Q. Peng, H. Weng, X. Dai, Z. Fang, Z. Xu, C. Chen, X. J. Zhou, *Electronic Evidence for Type II Weyl Semimetal State in $MoTe_2$* , arXiv:1604.01706 (2016).
- [20] N. Xu, Z. J. Wang, A. P. Weber, A. Magrez, P. Bugnon, H. Berger, C. E. Matt, J. Z. Ma, B. B. Fu, B. Q. Lv, N. C. Plumb, M. Radovic, E. Pomjakushina, K. Conder, T. Qian, J. H. Dil, J. Mesot, H. Ding, M. Shi, *Discovery of Weyl semimetal state violating Lorentz invariance in $MoTe_2$* , arXiv:1604.02116 (2016).
- [21] A. Tamai, Q. S. Wu, I. Cucchi, F. Y. Bruno, S. Ricco, T. K. Kim, M. Hoesch, C. Barreteau, E. Giannini, C. Bernard, A. A. Soluyanov, F. Baumberger, *Fermi arcs and their topological character in the candidate type-II Weyl semimetal $MoTe_2$* , *Phys. Rev. X* **6**, 031021 (2016), and references therein.
- [22] I. Belopolski, D. S. Sanchez, Y. Ishida, X. C. Pan, P. Yu, S. Y. Xu, G. Q. Chang, T. R. Chang, H. Zheng, N. Alidoust, G. Bian, M. Neupane, S. M. Huang, C. C. Lee, Y. Song, H. Bu, G. Wang, S. Li, G. Eda, H.-T. Jeng, T. Kondo, H. Lin, Z. Liu, F. Song, S. Shin and M. Z. Hasan, *Discovery of a new type of topological Weyl fermion semimetal state in $Mo_xW_{1-x}Te_2$* , *Nat. Commun.* **7**, 13643 (2016).
- [23] S. Thirupathaiyah, R. Jha, B. Pal, J. S. Matias, P. K. Das, P. K. Sivakumar, I. Vobornik, N. C. Plumb, M. Shi, R. A. Ribeiro, and D. D. Sarma, *$MoTe_2$: An uncompensated semimetal with extremely large magnetoresistance*, *Phys. Rev. B* **95**, 241105(R) (2017).
- [24] W. Kabsch, *XDS*, *Acta Cryst.* **D66**, 125 (2010).
- [25] G. M. Sheldrick, *A short history of SHELX*, *Acta Cryst. A* **64**, 112 (2008).
- [26] See supplemental material at <http://link.aps.org/>
- [27] Y. Qi, P. G. Naumov, M. N. Ali, C. R. Rajamathi, W. S. Schnelle, O. Barkalov, M. Hanfland, S. -C. Wu, C. Shekhar, Y. Sun, V. Süß, M. Schmidt, U. Schwarz, E. Pippel, P. Werner, R. Hillebrand, T. Förster, E. Kam-

- pert, S. Parkin, R. J. Cava, C. Felser, B. Yan and S. A. Medvedev, *Superconductivity in Weyl semimetal candidate $MoTe_2$* , Nat. Commun. **7**, 11038 (2016).
- [28] Q. Zhou, D. Rhodes, Q. R. Zhang, S. Tang, R. Schönemann, and L. Balicas, *Hall effect within the colossal magnetoresistive semimetallic state of $MoTe_2$* , Phys. Rev. B **94**, 121101(R) (2016).
- [29] A. P. Mackenzie, R. K. W. Haselwimmer, A. W. Tyler, G. G. Lonzarich, Y. Mori, S. Nishizaki, and Y. Maeno, *Extremely strong dependence of superconductivity on disorder in Sr_2RuO_4* , Phys. Rev. Lett. **80**, 161-164 (1998).
- [30] S. Nakatsuji, K. Kuga, Y. Machida, T. Tayama, T. Sakakibara, Y. Karaki, H. Ishimoto, S. Yonezawa, Y. Maeno, E. Pearson, G. G. Lonzarich, L. Balicas, H. Lee and Z. Fisk, *Superconductivity and quantum criticality in the heavy-fermion system β - $YbAlB_4$* , Nat. Phys. **4**, 603-607 (2008).
- [31] M. Tsujimoto, Y. Matsumoto, T. Tomita, A. Sakai, S. Nakatsuji, *Heavy-Fermion Superconductivity in the Quadrupole Ordered State of PrV_2Al_{20}* , Phys. Rev. Lett. **113**, 267001 (2014).
- [32] A. P. Mackenzie, and Y. Maeno, *The superconductivity of Sr_2RuO_4 and the physics of spin-triplet pairing*, Rev. Mod. Phys. **75**, 657-712 (2003).
- [33] I. Pletikosić, M. N. Ali, A. V. Fedorov, R. J. Cava, and T. Valla, *Electronic Structure Basis for the Extraordinary Magnetoresistance in WTe_2* , Phys. Rev. Lett. **113**, 216601 (2014).
- [34] A. B. Pippard, *Magnetoresistance in Metals* (Cambridge University, Cambridge, 1989).
- [35] D. Rhodes, S. Das, Q. R. Zhang, B. Zeng, N. R. Pradhan, N. Kikugawa, E. Manousakis, and L. Balicas, *Role of spin-orbit coupling and evolution of the electronic structure of WTe_2 under an external magnetic field*, Phys. Rev. B **92**, 125152 (2015).
- [36] Y. Luo, H. Li, Y. M. Dai, H. Miao, Y. G. Shi, H. Ding, A. J. Taylor, D. A. Yarotski, R. P. Prasankumar, and J. D. Thompson, *Hall effect in the extremely large magnetoresistance semimetal WTe_2* , Appl. Phys. Lett. **107**, 182411 (2015).
- [37] D. Kang, Y. Zhou, W. Yi, C. Yang, J. Guo, Y. Shi, S. Zhang, Z. Wang, C. Zhang, S. Jiang, A. Li, K. Yang, Q. Wu, G. Zhang, L. Sun and Z. Zhao *Superconductivity emerging from a suppressed large magnetoresistant state in tungsten ditelluride*, Nat. Commun. **6**, 7804 (2015).
- [38] Y. L. Wang, K. F. Wang, J. Reutt-Robey, J. Paglione, and M. S. Fuhrer, *Breakdown of compensation and persistence of nonsaturating magnetoresistance in gated WTe_2 thin flakes*, Phys. Rev. B **93**, 121108 (2016).
- [39] Y. B. Zhang, Y. W. Tan, H. L. Stormer, P. Kim, *Experimental observation of the quantum Hall effect and Berry's phase in graphene*, Nature **438**, 201-204 (2005).
- [40] H. Murakawa, M. S. Bahramy, M. Tokunaga, Y. Kohama, C. Bell, Y. Kaneko, N. Nagaosa, H. Y. Hwang, Y. Tokura, *Detection of Berry's Phase in a Bulk Rashba Semiconductor*, Science **342**, 1490-1493 (2013).
- [41] I. A. Luk'yanchuk, and Y. Kopelevich, *Phase Analysis of Quantum Oscillations in Graphite*, Phys. Rev. Lett. **93**, 166402 (2004).
- [42] P. Giannozzi, S. Baroni, N. Bonini, M. Calandra, R. Car, C. Cavazzoni, D. Ceresoli, G. L. Chiarotti, M. Cococcioni, I. Dabo, A. Dal Corso, S. de Gironcoli, S. Fabris, G. Fratesi, R. Gebauer, U. Gerstmann, C. Gougousis, A. Kokalj, M. Lazzeri, L. Martin-Samos, N. Marzari, F. Mauri, R. Mazzarello, S. Paolini, A. Pasquarello, L. Paulatto, C. Sbraccia, S. Scandolo, G. Sclauzero, A. P. Seitsonen, A. Smogunov, P. Umari and R. M. Wentzcovitch, *QUANTUM ESPRESSO: a modular and open-source software project for quantum simulations of materials*, J. Phys.: Condens. Matter **21**, 395502 (2009).
- [43] J. P. Perdew, K. Burke, M. Ernzerhof, *Generalized Gradient Approximation Made Simple*, Phys. Rev. Lett. **77**, 3865-3868 (1996).
- [44] D. R. Hamann, *Optimized norm-conserving Vanderbilt pseudopotentials*, Phys. Rev. B **88**, 085117 (2013).
- [45] A. Kokalj, *Computer graphics and graphical user interfaces as tools in simulations of matter at the atomic scale*, Comp. Mater. Sci. **28**, 155-168 (2003). Code available at <http://www.xcrysden.org/>.
- [46] P. M. C. Rourke, and S. R. Julian, *Numerical extraction of de Haas-van Alphen frequencies from calculated band energies*, Comp. Phys. Commun. **183**, 324 (2012).
- [47] H. -J. Kim, S. -H. Kang, I. Hamada, and Y. -W. Son, *Origins of the structural phase transitions in $MoTe_2$ and WTe_2* , Phys. Rev. B **95**, 180101(R) (2017).
- [48] D. Rhodes, D. A. Chenet, B. E. Janicek, C. Nyby, Y. Lin, W. Jin, D. Edelberg, E. Mannebach, N. Finney, A. Antony, T. Schiros, T. Klarr, A. Mazzoni, M. Chin, Y. -c. Chiu, W. Zheng, Q. R. Zhang, F. Ernst, J. I. Dadap, X. Tong, J. Ma, R. Lou, S. Wang, T. Qian, H. Ding, R. M. Osgood, Jr, D. W. Paley, A. M. Lindenberg, P. Y. Huang, A. N. Pasupathy, M. Dubey, J. Hone, and L. Balicas, *Engineering the structural and electronic phases of $MoTe_2$ through W substitution*, Nano Lett. **17**, 1616 (2017).
- [49] Y. Wu, N. H. Jo, M. Ochi, L. Huang, D. Mou, S. L. Bud'ko, P. C. Canfield, N. Trivedi, R. Arita, and A. Kaminski, *Temperature induced Lifshitz transition in WTe_2* , Phys. Rev. Lett. **115**, 166602 (2015).

Supplemental Material for manuscript titled “**Bulk Fermi-surface of the Weyl type-II semi-metal candidate γ -MoTe₂**”

D. Rhodes^{1,2}, R. Schönemann,^{1,3} N. Aryal,^{1,2} Q. Zhou,^{1,2} Q. R. Zhang,^{1,2} E. Kampert,³ Y.-C. Chiu,^{1,2} Y. Lai,^{1,2} Y. Shimura,^{1,4} G. T. McCandless,⁵ J. Y. Chan,⁵ D. W. Paley,^{6,7} J. Lee,⁸ A. D. Finke,⁸ J. P. C. Ruff,⁸ S. Das,^{1,2} E. Manousakis,^{2,1} and L. Balicas^{1,2*}

¹National High Magnetic Field Laboratory, Tallahassee-FL 32310, USA

²Department of Physics, Florida State University, Tallahassee-FL 32306, USA

³Dresden High Magnetic Field Laboratory (HLD-EMFL),

Helmholtz-Zentrum Dresden-Rossendorf, 01328 Dresden, Germany

⁴University of Tokyo, Institute of Solid State Physics, Kashiwa, Chiba 2778581, Japan

⁵The University of Texas at Dallas, Department of Chemistry and Biochemistry, Richardson, TX 75080 USA

⁶Department of Chemistry, Columbia University, New York, NY 10027 USA

⁷Columbia Nano Initiative, Columbia University, New York, NY 10027 USA

⁸CHESS, Cornell University, Ithaca, New York 14853, USA

A. Anisotropy in superconducting upper critical fields




Fig. S1. Anisotropy in superconducting upper critical fields for a γ -MoTe₂ single-crystal. (a), Superconducting upper critical fields H_{c2} for a γ -MoTe₂ single-crystal (sample #2 or blue trace in Fig. 1 (b)) as a function of the temperature T and for fields applied along all three main crystallographic axes. Solid lines are fits to a Ginzburg-Landau expression $H_{c2}^i(T) = \phi_0 / (2\pi\xi_i(0)\xi_k(0))[(1-t^2)/(1+t^2)]$, ϕ_0 is the quantum of magnetic flux, $\xi_i(0)$ is the zero temperature superconducting coherence length along a certain crystallographic axis, and t is the reduced temperature T/T_c . (b) Anisotropy in upper critical fields $\gamma = H_{c2}^a / H_{c2}^j$, for fields applied along the a - and the c -axis (violet markers) and for fields along the a - and the b -axis (pink markers), respectively. Notice how γ decreases slightly upon decreasing T , suggesting multi-band superconductivity.

B. Hall-effect in γ -MoTe₂: carrier compensation and possible Lifshitz transition as a function of temperature

Given the enormous, non-saturating magnetoresistance displayed by γ -MoTe₂, which is ascribed to nearly perfect electron-hole compensation [S1, S2, S3], as claimed to be the case for WTe₂, we plot its density of electron and holes as determined from Hall-effect measurements [S4]. Our detailed, two-band analysis of the Hall response of γ -MoTe₂ can be found in Ref. [S4].




Fig. S2. (a) Absolute value of the Hall constant $|R_H|$ measured under a field $H = 9$ T as a function of the temperature. Brown arrow indicates the temperature $T \sim 240$ K where the monoclinic to orthorhombic transition occurs. Blue arrow indicates the temperature below which a sharp increase is observed in the Hall response, suggesting a crossover or a possible electronic phase-transition. (b) Ratio between the density of holes n_h and the density of electrons n_e as a function of T and as extracted from a two-band analysis of the Hall-effect. Notice how n_h increases very quickly below 40 K reaching parity with n_e below ~ 15 K. Hence, the Hall-effect indicates that this compound becomes nearly perfectly compensated at low temperatures. (c) Heat capacity C normalized by the temperature T and as a function of T for a β , γ -MoTe₂ single-crystal. A broad anomaly is observed at $T_{\max} \approx 66$ K around which μ_h is seen to increase abruptly. At low T s, C/T saturates at $\gamma \approx 2.6$ mJ/molK² which corresponds to the electronic contribution to C/T . Inset: C/T as a function of T^2 . Red line is a linear fit from which one extracts the phonon coefficient \mathcal{S} in $C/T \propto \mathcal{S}T^3$ which yields a Debye temperature $\Theta_D \approx 120$ K.

As seen in Fig. S2 (a), the Hall-effect yields two important observations: two anomalies in its temperature dependence (measured under $\mu_0 H = \pm 9$ T), the first associated with the monoclinic to orthorhombic transition (indicated by the brown arrow) and the second yielding a sharp increase in the Hall constant below ~ 80 K (blue arrow) which leads to a very sharp increase in the density holes making the system almost perfectly compensated below 30 K (see Fig. S2 (b)). In fact, at low temperatures the Hall resistivity is basically linear all the way up to $\mu_0 H = 9$ T indicating that γ -MoTe₂ is better compensated than WTe₂, see e.g. Ref. [S5]. A sharp increase in the Hall constant at lower T s is suggestive of an

electronic phase-transition akin to the temperature-dependent Lifshitz-transition [S6] reported for WTe_2 . To evaluate this hypothesis, we performed heat capacity measurements in a $\beta\text{-MoTe}_2$ single-crystal. Figure S2 (c) displays the specific heat C , normalized by the temperature and as a function of T in a logarithmic scale. C/T displays a broad anomaly around $T \cong 66$ K roughly at the same T where one observes a sharp increase in the Hall-constant. Extrapolation to $T = 0$ K yields a sizeable electronic contribution term $\gamma_e \cong 2.6$ mJ/molK², a surprising value for a semi-metal characterized by a relatively small density of carriers. For instance, metallic copper which contains a $\sim 10^2$ larger density of carriers yields $\gamma_e \cong 0.69$ mJ/molK². Therefore, the large γ_e suggests a relatively high density of states at the Fermi level which is consistent with the observation of superconductivity. The broad anomaly cannot be reconciled with either a first- or a second-order phase-transition. Instead, it suggests a crossover between two regimes, and since it occurs at temperatures where C/T is dominated by phonons, we speculated that the crystallographic structure would evolve upon cooling below $T = 100$ K. The Hall-effect, on the other hand, indicates that the electronic structure would be affected by the evolution of the lattice upon cooling. However, our detailed low temperature synchrotron based structural analysis does not support this scenario, see Fig. S3 below.

C. Crystallographic structure as a function of the temperature.

Three single-crystals were measured at the CHESS-A2 beam line. Crystal 1 was measured with 19.9 keV incident photons (with an energy bandwidth of ~ 2 eV). This crystal, had dimensions of $\sim 100 \times 30 \times 10$ μm^3 , and was fully bathed by a nitrogen gas jet when subjected to the 200×200 μm^2 incident beam. For sample 2, the incident beam was reduced to 80×80 μm^2 in to illuminate fewer grains from a larger crystal (few mm long) characterized by significant structural disorder. The temperature of this sample was controlled using a closed-cycle cryostat. The diffracted X-rays were recorded using a Pilatus3 300 K area detector mounted on the 2θ arm of a 4-circle diffractometer.




Fig. S3. (a), (b), (c) $\gamma\text{-MoTe}_2$ lattice constants a , b and c as functions of the temperature T . (d), (e), (f) Angles α , β and γ between the lattice vectors as functions of T . Black markers depict sample 1, colored markers were collected from samples 2 (in pink) and 3 (in blue).

A third crystal of dimensions $\sim 80 \times 20 \times 5 \mu\text{m}^3$ was measured with 55 keV photons and a 6 Mega-pixel photon counting area detector. The single-crystal was continuously rotated over 370° during shutterless data collection, with 0.1° of rotation integrated into each frame. Three complete datasets were collected by varying the position of the detector relative to the incident beam. Reflections from the reduced datasets were scaled and merged together for structure solution and refinement. Diffraction data at $T = 115 \text{ K}$ was collected with a nitrogen cryostream system to bathe the crystal in a stream of cold gas. Data at $T = 12 \text{ K}$ was collected in a similar fashion using a helium cryostream. For both setups the temperatures of the cold stream were confirmed with a silicon diode sensor immediately prior to the measurements.

We investigated the temperature evolution of the crystalline-structure by performing single-crystal synchrotron X-ray diffraction measurements at low temperatures; Fig. S3 displays the lattice constants and the angles between lattice vectors as functions of the temperature for $7 \text{ K} \leq T \leq 200 \text{ K}$ as collected from three single crystals sample 1 (black dots) and samples 2 and 3 (colored markers). Unit cell parameters were co-refined by collecting three-dimensional center-of-mass measurements in reciprocal space of a set of 4 Bragg peaks, measured in temperature intervals of 5 K upon cooling. Within the sphere of confusion of the instrument all angles between lattice vectors approach 90° as T is lowered below 150 K and as expected for an orthorhombic structure. To summarize, synchrotron X-ray diffraction confirms that the crystallographic structure of $\gamma\text{-MoTe}_2$ is temperature dependent down to $\sim 125 \text{ K}$, with this compound displaying a remarkable negative thermal expansion coefficient along the b - and the c -axes. Perhaps more important, little dependence on temperature is observed below $\sim 100 \text{ K}$. The pronounced deviations with respect to orthorhombicity observed in the range of temperatures $150 \text{ K} \leq T \leq 250 \text{ K}$, are probably a manifestation of the hysteresis associated with the structural transition at $\sim 250 \text{ K}$.

Low temperature structural parameters of $\gamma\text{-MoTe}_2$ resulting from synchrotron X-ray scattering:

Orthorhombic space group #31 or $Pmn2_1$ with $\alpha = \beta = \gamma = 90^\circ$

$T = 115 \text{ K} : a = 3.463 \text{ \AA}, b = 6.326 \text{ \AA}, c = 13.878 \text{ \AA}$

Atom	X	Y	Z	site
Te1	0.00000	0.85960	1.02325	2a
Te2	0.00000	0.21033	0.77018	2a
Te3	0.50000	0.36298	1.06678	2a
Te4	0.50000	0.71658	0.81359	2a
Mo5	0.00000	0.47030	0.92545	2a
Mo6	0.50000	0.10570	0.91135	2a

$T = 12 \text{ K} : a = 3.464 \text{ \AA}, b = 6.315 \text{ \AA}, c = 13.884 \text{ \AA}$

Atom	X	Y	Z	site
Te1	0.00000	0.86030	1.02332	2a
Te2	0.00000	0.21070	0.77028	2a
Te3	0.50000	0.36360	1.06682	2a
Te4	0.50000	0.71710	0.81347	2a
Mo5	0.00000	0.47060	0.92537	2a
Mo6	0.50000	0.10560	0.91139	2a

D. Determination of the Berry phase




Fig. S4. Given that the magnetic torque for a layered system is given by $\tau = (\chi_{xx} - \chi_{zz})H^2/2 \sin 2\theta$, where χ_{xx} is the component of the magnetic susceptibility for fields applied along a planar direction and χ_{zz} is the component of the susceptibility for fields applied along the inter-planar direction with θ being the angle between the magnetic field and the inter-planar direction, the sign of τ is actually θ -dependent. Therefore, the phase of the oscillatory signal (observed at high fields) superimposed onto τ (black trace) is also θ dependent.

The correct phase is determined *via* a comparison with the magnetic susceptibility, $\chi_{zz} = \partial M_z / \mu_0 \partial H$, as measured with a SQUID magnetometer (blue trace, low fields). As seen, both traces are nearly in-phase. The relatively small deviation in their respective phases is due to the difference in angle between the magnetic field and c -axis of the crystal for either measurement: torque, which requires an angle, was measured at $\theta \sim 3^\circ$, while susceptibility $\theta \sim 0^\circ$.

Figure S4 displays the oscillatory signal superimposed onto the magnetic torque (black trace) of γ -MoTe₂ for fields nearly along its c -axis as a function of the inverse field. To this trace we have superimposed the oscillatory signal measured in a SQUID magnetometer for fields also aligned nearly along the c -axis. The goal of this figure is to demonstrate that the oscillations from both measurements are nearly in phase, given that the sign of the torque signal is angle dependent, and therefore that we can extract the correct values of the Berry-phase of γ -MoTe₂ through fits of the oscillatory signal to Lifshitz-Kosevich formalism.

Figure S5 displays the oscillatory signal superimposed onto the derivative of the magnetic torque (black trace) as a function of inverse field along with fits (red traces) to four Lifshitz-Kosevich oscillatory components performed over an increasing range in $(\mu_0 H)^{-1}$. Two of these components describe the main fundamental frequencies observed for this orientation while the other two depict their first harmonics, respectively. The objective of these fits is to evaluate the Berry-phase and therefore the topological character of γ -MoTe₂. As seen through the four panels of Fig. S5, one obtains $F_\alpha = 240.4$ T and $F_\beta = 259$ T for the fundamental frequencies and for fields below 10 T, but they are observed to continuously evolve as the field interval is increased, i.e. F_α increases to 244.3 T while F_β decreases slightly to 256.6 T when one fits the entire fit range. Meanwhile, and assuming constant values for the effective masses (shown

below and in the main text), one observes the Dingle temperatures to decrease as the fit progressively includes the whole field range. For example, T_D^α decreases from 3.3 K to 1.9 K.




Fig. S5. From left to right and from top to bottom: fits (red lines) of the de Haas van Alphen signal superimposed onto the magnetic susceptibility (as extracted from the derivative of the magnetic torque τ with respect to $\mu_0 H$) to four Lifshitz-Kosevich oscillatory components. The four components describe the two fundamental frequencies F_α and F_β observed for fields applied along the c -axis along with their first harmonics. Notice that the fundamental frequencies shift as the interval in $\mu_0 H^{-1}$ increases. The obtained Berry phases $\phi_B^{\alpha,\beta}$ and extracted Dingle temperatures $T_d^{\alpha,\beta}$ are also field-dependent. Hence, the electronic structure of γ -MoTe₂ is affected by the Zeeman-effect which prevents the extraction of its Berry phase. Notice however, that the Berry-phases extracted at the lowest fields are distinct from π and therefore at odds with the prediction of a Weyl type-II semi-metallic state in γ -MoTe₂.

Similarly, the phase-factors from which one extracts the Berry phases $\phi_B^{\alpha,\beta}$ are also found to be strongly field-dependent. The values of $\phi_B^{\alpha,\beta}$ indicated in the figure were calculated assuming minima and maxima extremal-cross-sectional areas, respectively, and a three-dimensional FS. In summary, the geometry of the Fermi surface of γ -MoTe₂ evolves as a function of the field due to the Zeeman-effect, which precludes the extraction of its Berry phase. However, even at the lowest fields the values of $\phi_B^{\alpha,\beta}$ differ from π indicating that it is not a topological compound.

E. Angular dependence of the de Haas van Alphen signal and anisotropy of the effective masses.




Fig. S6. Oscillatory signal and carrier effective masses for fields along the b -axis. (a) Oscillatory component of the Haas van Alphen effect, superimposed onto the magnetic torque as a function of the inverse field H^{-1} and for several values of T . Here, H was aligned nearly along the b -axis. (b) FFT spectra taken from a window in H ranging from 20 to 35 T. (c), (d), (e), and (f), Amplitude of selected peaks observed in the FFT spectrum as a function of T . Red lines are fits to the Lifshitz-Kosevich expression from which we extract the effective masses indicated in each panel.




Fig. S7. Oscillatory component, or the Haas van Alphen effect, superimposed onto the magnetic torque as a function of the inverse field H^{-1} and for several angles between the c -axis and the other two crystallographic axes. This data was collected at 35 mK and was used to extract the fast Fourier-transform spectra as a function of the angle displayed in Figs. 4(b) and 6(a) within the main text.




Fig. S8. Fermi surface of γ -MoTe₂ according to the VASP implementation with the inclusion of spin-orbit coupling. (a) Hole-like Fermi surfaces around the Γ -point. In contrast to the Wien2K implementation, VASP predicts small hole-like Fermi surfaces at Γ . In addition, the larger four-fold symmetric hole-like surfaces would touch the boundary of the first Brillouin zone. This is attributable to a different position of the Fermi energy relative to the Wien2K implementation. (b) Electron-like Fermi surfaces. In contrast to Wien2K, VASP predicts small electron ellipsoids in addition to three sets of cylindrical electron-like Fermi surfaces at the X-point. (c) Fermi surface cross-sectional areas as functions of the angle of rotation of the external magnetic field relative to the crystallographic axes.

References-

- [S1] M. N. Ali, J. Xiong, S. Flynn, J. Tao, Q. D. Gibson, L. M. Schoop, T. Liang, N. Haldolaarachchige, M. Hirschberger, N. P. Ong and R. J. Cava, *Large, non-saturating magnetoresistance in WTe₂*, Nature **514**, 205-208 (2014).
- [S2] I. Pletikosić, M. N. Ali, A. V. Fedorov, R. J. Cava, and T. Valla, *Electronic Structure Basis for the Extraordinary Magnetoresistance in WTe₂*, Phys. Rev. Lett. **113**, 216601 (2014).
- [S3] Z. Zhu, X. Lin, J. Liu, B. Fauqué, Q. Tao, C. Yang, Y. Shi, and K. Behnia, *Quantum Oscillations, Thermoelectric Coefficients, and the Fermi Surface of Semimetallic WTe₂*, Phys. Rev. Lett. **114**, 176601 (2015).
- [S4] Q. Zhou, D. Rhodes, Q. R. Zhang, S. Tang, R. Schönemann, and L. Balicas, *Hall effect within the colossal magnetoresistive semimetallic state of MoTe₂*, Phys. Rev. B **94**, 121101(R) (2016).
- [S5] Y. Luo, H. Li, Y. M. Dai, H. Miao, Y. G. Shi, H. Ding, A. J. Taylor, D. A. Yarotski, R. P. Prasankumar, and J. D. Thompson, *Hall effect in the extremely large magnetoresistance semimetal WTe₂*, Appl. Phys. Lett. **107**, 182411 (2015).
- [S6] Y. Wu, N. H. Jo, M. Ochi, L. Huang, D. Mou, S. L. Bud'ko, P. C. Canfield, N. Trivedi, R. Arita, and A. Kaminski, *Temperature induced Lifshitz transition in WTe₂*, Phys. Rev. Lett. **115**, 166602 (2015).