

Sains Malaysiana 40(1)(2011): 75–78

## Ion Conductive Polymer Electrolyte Membranes and Simulation of Their Fractal Growth Patterns

(Membran Polimer Elektrolit Konduksian Ion dan Simulasi Pola-pola Pertumbuhan Fraktal)

S. AMIR\*, S.A. HASHIM ALI & N.S. MOHAMED

### ABSTRACT

*Due to their high ionic conductivity, solid polymer electrolyte (SPE) systems have attracted wide spread attention as the most appropriate choice to fabricate all-solid-state electrochemical devices, namely batteries, sensors and fuel cells. In this work, ion conductive polymer electrolyte membranes have been prepared for battery fabrication. However, fractals were found to grow in these polymer electrolyte membranes weeks after they were prepared. It was believed that the formation of fractal aggregates in these membranes were due to ionic movement. The discovery of fractal growth pattern can be used to understand the effects of such phenomenon in the polymer electrolyte membranes. Digital images of the fractal growth patterns were taken and a simulation model was developed based on the Brownian motion theory and a fractal dialect known as L-system. A computer coding has been designed to simulate and visualize the fractal growth.*

*Keywords: Fractal; polymer electrolytes; simulation*

### ABSTRAK

*Disebabkan kekonduksian ionik yang tinggi, sistem polimer elektrolit pepejal (SPE) telah menarik perhatian meluas sebagai pilihan paling sesuai untuk memfabrikasi alat elektrokimia keadaan pepejal sepenuhnya, iaitu bateri, pengesan dan sel bahan bakar. Dalam kerja penyelidikan ini, membran polimer elektrolit konduksian ion telah disediakan untuk penyediaan bateri. Bagaimanapun, fraktal telah didapati tumbuh dalam membran polimer elektrolit ini beberapa minggu selepas disediakan. Adalah dipercayai pembentukan agregat fraktal dalam membran ini ialah disebabkan oleh pergerakan ion. Penemuan corak pertumbuhan fraktal boleh digunakan bagi memahami kesan fenomena pergerakan ion dalam membran polimer elektrolit. Imej-imej digital pola-pola pertumbuhan fraktal telah diambil dan satu model simulasi dibangunkan berasaskan teori pergerakan Brown dan dialek fractal dikenali sebagai L-sistem. Pengekodan komputer telah direkabentuk bagi mensimulasi dan menggambarkan pertumbuhan fraktal.*

*Kata kunci: Elektrolit polimer; fraktal; simulasi*

### INTRODUCTION

By definition, an ion-conducting polymer is a polymeric material that exhibits high ionic conductivity but low electronic conductivity (Horie et al. 2004). Potential applications for conducting polymers are numerous in devices such as fuel cells, supercapacitors, sensors, electrochromic displays and solar cells (Stephan 2006). Since metals are toxic and can damage the environment (Harun et al. 2007), conducting polymers are the better alternatives.

Hence, many researchers have been putting their time and effort to produce improved polymer electrolyte materials especially in the development of batteries. However, for quite some time, polymer electrolytes have also been found to be sort of media for fractal growth (Amir et al. 2008; Chandra 1996; Chandra & Chandra 1994).

Electrochemical electrodeposition (Barkey 1991), electrochemical polymerization (Chandra 1996) and diffusion limited aggregation growth structures of many

metal aggregates in the presence of a magnetic field as external stimuli (Kaufmann et al. 1987) have been well suited with many fractal growth models. Thereof, a few group of researchers (Amir et al. 2007; Amir 2008; Amir et al. 2010; Mohamed & Arof 2001; Okubo et al. 1993) have also reported the formation of fractals without using any external stimuli. In this work, fractals were observed in two polymer electrolyte systems, Poly(vinylidene fluoride-co-hexafluoropropylene)/Poly(ethylmethacrylate)-ammonium trifluoro- methane sulfonate (PVDF-HFP/PEMA-NH<sub>4</sub>CF<sub>3</sub>SO<sub>3</sub>) dispersed with Cr<sub>2</sub>O<sub>3</sub> and polyethylene oxide-ammonium iodide (PEO-NH<sub>4</sub>I). It was indicated that the growth of these fractals is due to the diffusion of ions in the host polymer matrices. The objectives of this work are to study the fractal growth in ion conductive polymer electrolyte membranes and to simulate the fractal observed using suitable techniques. For that purpose, a computerize based model has been created to simulate and visualize the growth of these fractal patterns.

## MATERIALS AND METHODS

### PREPARATION OF MATERIALS

The polymer electrolyte membranes used as media to culture fractals were prepared separately by using the solution casting method. In this preparation, PEO ( $M_w = \sim 6 \times 10^5$ ) and  $\text{NH}_4\text{I}$  were weighed according to the desired PEO: $\text{NH}_4\text{I}$  weight ratios and dissolved in 100 mL methanol while PVDF-HFP, PEMA and  $\text{NH}_4\text{CF}_3\text{SO}_3$  of fixed w% ratio were dissolved in N-N dimethyl formamide (DMF) using digital magnetic stirrers. Appropriate weight percentage of  $\text{Cr}_2\text{O}_3$  in nanosize was added specifically to the PVDF-HFP, PEMA and  $\text{NH}_4\text{CF}_3\text{SO}_3$  solutions. In each preparation, the solution was stirred for a few hours until homogeneous solutions were obtained. The solution that had completely dissolved was then cast into petri dishes and left to dry slowly at room temperature in a dark and dry place for several weeks. After drying, fractal patterns were observed and their digital images were taken.

### SIMULATION METHODS

A fractal dialect called L-systems (Prusinkiewicz & Lindenmayer 2004) was implemented into the simulation applying the 'Brownian motion' theory. L-Systems rules' recursive nature leads to self-similarity and its simple string-based commands allow easy description of such complex geometric patterns particularly fractal growth patterns. By increasing the recursion level, a form slowly, grows' and becomes more complex, as can be seen in diffusion-limited aggregation (DLA) models (Witten & Sander 1981) and natural-looking organic forms. The rules of the L-system grammar are applied iteratively starting from the initial state which is called the axiom and a set of production rules.

To compare the simulation with the real patterns obtained, one vital aspect would be the calculation of their fractal dimension values. The box-count method was used to calculate the fractal dimension of the DLA structure

identified in this research as a clear representation of a random fractal that generates a stochastic fractal growth pattern (Kleinert 2004).

### DISCUSSION

The fractal patterns in PVDF-HFP/PEMA- $\text{NH}_4\text{CF}_3\text{SO}_3$ - $\text{Cr}_2\text{O}_3$  and PEO- $\text{NH}_4\text{I}$  polymer electrolyte membranes are shown in Figure 1. Their digital photos were taken, pre-processed via an image processing software and uploaded to the fractal dimension determination computer software tool (Suki et al. 2007). From Figure 1, it is observed that fractals are formed at different nucleation centers and then grew in certain directions away from the nucleation sites. They grew irregularly and in an unpredictable motion which can be attributed to the Brownian motion of aggregating species.

For simulation purposes, six fractal aggregates each from PVDF-HFP/PEMA- $\text{NH}_4\text{CF}_3\text{SO}_3$ - $\text{Cr}_2\text{O}_3$  and PEO- $\text{NH}_4\text{I}$  polymer electrolyte membranes were selected. Their respective simulated patterns are shown in Figure 2.

The fractal dimensions for all of the experimentally cultured and simulated fractals are listed in Tables 1 and 2. The tables show that the fractal dimension values of the experimentally cultured fractals are in good agreement with the fractal dimension values obtained from their respective simulated ones.

### CONCLUSION

Other than being potential materials for applications in various electrochemical devices, ion conductive polymer electrolyte membranes are also suitable for the study of fractals. The growth of fractals observed in this study is due to the random motion of aggregating species. Evidently, the simulation model which is based on the Brownian motion theory and a fractal dialect known as L-system is congruent to fractals cultured in the ion conductive polymer membranes. Further research is to be carried out




FIGURE 1. Digital images of the fractal patterns observed in (a) PVDF-HFP/PEMA- $\text{NH}_4\text{CF}_3\text{SO}_3$ - $\text{Cr}_2\text{O}_3$  and (b) PEO- $\text{NH}_4\text{I}$  membranes




FIGURE 2. The simulated fractal patterns

TABLE 1. Fractal dimension values of the experimentally cultured fractal patterns as shown in Figure 1(a) and their respective simulated fractal patterns, Figure 2(a)

Cultured Fractals	Fractal Dimension	Simulated Fractals	Fractal Dimension
Fig. 1(a)(i)	$1.718 \pm 0.045$	Fig. 2(a)(i)	$1.720 \pm 0.043$
Fig. 1(a)(ii)	$1.731 \pm 0.042$	Fig. 2(a)(ii)	$1.735 \pm 0.046$
Fig. 1(a)(iii)	$1.749 \pm 0.043$	Fig. 2(a)(iii)	$1.753 \pm 0.042$
Fig. 1(a)(iv)	$1.743 \pm 0.049$	Fig. 2(a)(iv)	$1.748 \pm 0.047$
Fig. 1(a)(v)	$1.757 \pm 0.041$	Fig. 2(a)(v)	$1.753 \pm 0.045$
Fig. 1(a)(vi)	$1.786 \pm 0.046$	Fig. 2(a)(vi)	$1.771 \pm 0.041$

TABLE 2. Fractal dimension values of the experimentally cultured fractal patterns as shown in Figure 1(b) and their respective simulated fractal patterns, Figure 2(b)

Cultured Fractals	Fractal Dimension	Simulated Fractals	Fractal Dimension
Fig. 1(b)(i)	$1.714 \pm 0.051$	Fig. 2(b)(i)	$1.723 \pm 0.045$
Fig. 1(b)(ii)	$1.753 \pm 0.042$	Fig. 2(b)(ii)	$1.755 \pm 0.042$
Fig. 1(b)(iii)	$1.741 \pm 0.035$	Fig. 2(b)(iii)	$1.746 \pm 0.043$
Fig. 1(b)(iv)	$1.748 \pm 0.045$	Fig. 2(b)(iv)	$1.745 \pm 0.041$
Fig. 1(b)(v)	$1.759 \pm 0.052$	Fig. 2(b)(v)	$1.757 \pm 0.044$
Fig. 1(b)(vi)	$1.778 \pm 0.054$	Fig. 2(b)(vi)	$1.769 \pm 0.048$

to improve the computer algorithm used in the simulation model in order to get better results.

#### REFERENCES

- Amir, S. 2008. Modeling and Simulation of Fractal Growth Pattern, M.Phil. Thesis, University of Malaya.
- Amir, S., Mohamed, N.S. & Hashim Ali, S.A. 2007. Simulation of the Fractal Patterns in Polymer Membranes. *Proceeding in IEECI 2007*: 919-922.
- Amir, S., Mohamed, N.S. & Hashim Ali, S.A. 2008. Simulation of Complex Geometric Patterns in Polymer Films. *Matematika, Special Edition, Part 1*: 207-211.
- Amir, S., Mohamed, N.S. & Hashim Ali, S.A. 2010. Simulation model of the fractal patterns in ionic conducting polymer films. *Cent. Eur. J. Phys.* 8(1): 150-156.
- Barkey, D. 1991. Morphology selection and the concentration boundary layer in electrochemical deposition. *J. Electrochem. Soc.* 138: 2912-2917.
- Chandra, A. 1996. Anion clustering and fractal pattern growth in ion conducting polymeric matrix. *Solid State Ionics* 86-88: 1437-1442.
- Chandra, A. & Chandra, S. 1994. Experimental observation of large-size fractals in ion-conducting polymer electrolyte films, *Physical Review B* 49(1): 633-636.
- Harun, M.H., Saion, E., Kassim, A., Yahya, N. & Mahmud, E. 2007. Conjugated conducting polymers: A brief overview. *UCSI Academic Journal: Journal for the Advancement of Science & Arts* 2: 63-68.
- Horie, K., Barón, M., Fox, R.B., He, J., Hess, M., Kahovec, J., Kitayama, T., Kubisa, P., Maréchal, E., Mormann, W., Stepto, R.F.T., Tabak, D., Vohlídal, J., Wilks, E.S. & Work, W. J. 2004.

- Definitions of terms relating to reactions of polymers and to functional polymeric materials (IUPAC Recommendations 2003). *Pure Appl. Chem.* 76(4): 889-906.
- Kaufmann, J.H., Nazzari, A.I. & Melroy, O.R. 1987. Onset of fractal growth: Statics and dynamics of diffusion-controlled polymerization. *Phys. Rev. B* 35: 1881-1890.
- Kleinert, H. 2004. *Path Integrals in Quantum Mechanics, Statistics, Polymer Physics, and Financial Markets*. 4th edition. Singapore: World Scientific.
- Mohamed, N.S. & Arof, A.K. 2001. Fractal like dendritic crystals of lithium tetrafluoroborate in chitosan acetate films. *Malaysian Journal of Analytical Sciences* 6(1): 71-74.
- Okubo, S., Mogi, I., Kido, G. & Nakagawa, Y. 1993. Effect of high magnetic fields on fractal growth of silver metal-forest. *Fractals* 1: 425-429.
- Prusinkiewicz, P. & Lindenmayer, A. 2004. *The Algorithmic Beauty of Plants*. Springer-Verlag.
- Stephan, A.M. 2006. Review on gel polymer electrolytes for lithium batteries. *European Polymer Journal* 42(1): 21-42.
- Suki, M.N., Mohamed, N.S., Hashim Ali, S.A. & Zainuddin, R. 2007. The role of image processing in measuring fractal dimension. *Malaysian Journal of Science*: 23-33.
- Witten Jr, T.A. & Sander, L.M. 1981. Diffusion-limited aggregation, a kinetic critical phenomenon. *Phys. Rev.Lett.* 47: 1400-1403.

S. Amir\* & N.S. Mohamed  
Pusat Asasi Sains  
University of Malaya  
50603 Kuala Lumpur  
Malaysia

S.A. Hashim Ali  
Institute of Mathematical Sciences  
Faculty of Science  
University of Malaya  
50603 Kuala Lumpur  
Malaysia

\*Corresponding author; email:shahizat@um.edu.my

Received: 7 December 2009  
Accepted: 15 July 2010