

BINDING AGENT FOR BIODEGRADABLE COMPRESSION MOLDED RICE
STRAW FILLED RICE BRAN PACKAGING PRODUCTS

SHARIFAH ADZILA BINTI SYED ABU BAKAR

A project report submitted in partial fulfillment of
requirements for the award of the degree of
Master of Science (Polymer Technology)

Faculty of Chemical and Natural Resources Engineering
Universiti Teknologi Malaysia

JULY 2009

*I dedicated this entire work to my beloved family especially my father,
Syed Abu Bakar Bin Syed Abdul Rahman and my mother, Sumaliah Binti Awang and
also to my friends for their support and encouragement
throughout this project*

ACKNOWLEDGEMENT

First of all, thanks to Allah Almighty for giving me health and afford to finish this thesis. I would also like to take this opportunity to express my sincere appreciation to my supervisor, Assoc. Prof. Dr. Wan Aizan Bt Wan Abdul Rahman, for encouragement, guidance, and friendship. Without her continued support and interest, this thesis would not have been the same as presented here.

Further more, I would also like to acknowledge my fellow postgraduate students and also my colleagues for their supportive, and commitment in helping me throughout the completion of this project. I also extended to people who contributed to the success of this thesis especially to laboratory technicians

Last but not least, I wish to thank all the persons that have direct or indirectly contributed their support and help in preparing this thesis which without them, this thesis would not exist. Thank you very much.

ABSTRACT

Rice bran (RB) has been used as a natural fibre in polyolefin which results in lower mechanical properties and low interfacial adhesion that need a coupling agent or binder at higher loading. Rice bran (RB) and rice straw (RS) which both is low cost materials were developed in the processing of biodegradable packaging by using compression moulding technique. Glycerol, rice starch and polyvinyl acetate (PVAc) have been used as binding agent in this study where their physical (mechanical, chemical, and thermal) properties were studied base on the percentage of binding agent used in RB/RS. Rice starch and PVAc increased the tearing strength and tensile strength of RB/RS. This was continued by fracture surface analysis using inverted microscopy where RS is clearly visible of phase separated without binding agent as compared to RS with binding agent. Although rice starch and PVAc exhibited good mechanical properties, but they showed poor water resistance because of high in hydrophilic molecular structure. Starch influenced the rapid thermal degradation of RB/RS. By incorporation of PVAc in RB/RS, thermal stability property is increased.

ABSTRAK

Dedak (RB) telah digunakan sebagai fiber semulajadi di dalam polyolefin yang menghasilkan ciri-ciri mekanikal dan lekatan antara permukaan yang rendah dan memerlukan agen pengangkuk atau agen pengikat pada bebanan tinggi. Kedua-dua dedak (RB) dan jerami padi (RS) yang merupakan bahan kos rendah telah digunakan di dalam proses pembungkusan biodegradasi dengan menggunakan kaedah acuan mampatan. Dalam kajian ini gliserol, kanji beras dan polivinil asetat (PVAc) telah digunakan sebagai agen pengikat di mana ciri-ciri fizikalnya (mekanikal, kimia dan terma) dikaji berdasarkan peratus agen pengikat yang digunakan di dalam RB/RS. Kanji beras dan PVAc meningkatkan kekuatan carikan dan kekuatan tegangan RB/RS. Hasil ujian ini disambung melalui analisis mikroskop berbalik di mana permukaan retak sampel dari ujian tegangan menunjukkan struktur fasa pemisahan RS tanpa agen pengikat boleh dilihat dengan jelas berbanding struktur RS dengan agen pengikat. Walaupun kanji beras dan PVAc mempamerkan ciri-ciri mekanikal yang baik tetapi bahan-bahan ini rintangan air yang rendah disebabkan struktur molekul hidrofilik yang tinggi. Kanji mempengaruhi kadar degradasi terma RB/RS menjadi lebih cepat. Dengan penggabungan PVAc di dalam RB/RS membantu meningkatkan kestabilan ciri-ciri terma.

TABLE OF CONTENTS

CHAPTER	TITLE	PAGE
	TITLE PAGE	i
	DECLARATION	ii
	DEDICATION	iii
	ACKNOWLEDGEMENT	iv
	ABSTRACT	v
	ABSTRAK	vi
	TABLE OF CONTENTS	vii
	LIST OF TABLES	ix
	LIST OF FIGURES	x
	LIST OF ABBREVIATION AND SYMBOLS	xi
	LIST OF APPENDICES	xii
1	INTRODUCTION	1
	1.1 Background of Studies	1
	1.2 Problem Statements	3
	1.3 Objectives	5
	1.4 Scope of Study	5
2	LITERATURE REVIEW	6
	2.1 Biopolymer	6
	2.2 Biodegradable Packaging	11
	2.3 Rice-Starch Based Blends	13

2.4	Rice-Waste Based Blends	15
2.5	Rice Bran	16
2.6	Rice Straw	18
2.7	Glycerol and Polyvinyl Acetate (PVAc)	22
3	METHODOLOGY	24
3.1	Introduction	24
3.2	Materials	24
3.2.1	Rice Bran	24
3.2.2	Rice Straw	25
3.2.3	Glycerol	26
3.2.4	Rice Starch	26
3.2.5	Polyvinyl Acetate (PVAc)	27
3.3	Compounding Formulation	28
3.3.1	Preparation of RB/RS Sample	29
3.4	Compression Molding Process	29
3.5	Mechanical Tests	30
3.5.1	Tearing Test	30
3.5.2	Tensile Test	31
3.6	Water Absorption Test	32
3.7	Thermal Analysis	34
3.7.1	Thermogravimetric Analysis (TGA)	34
3.8	Microscopy Analysis	34
4	RESULTS AND DISCUSSION	36
4.1	Tearing Test	36
4.1.1	Effect of Glycerol (Gly) on Rice Straw (RS) Filled Rice Bran (RB)	36
4.1.2	Effect of Rice Starch on Rice Straw (RS) filled Rice Bran (RB)	38
4.1.3	Effect of Polyvinyl Acetate (PVAc) on Rice Straw (RS) filled Rice Bran	39
4.1.4	Effect of Mixed Polyvinyl Acetate	

	(PVAc) on Rice Straw (RS) filled Rice Bran (RB)	39
4.2	Tensile Properties	40
4.2.1	Effect of Polyvinyl Acetate (PVAc) On Rice Straw (RS) filled Rice Bran (RB)	40
4.2.2	Effect of Rice Starch on Rice Straw (RS) filled Rice Bran (RB)	41
4.2.3	Effect of Mixed Polyvinyl Acetate (PVAc) with Rice Starch on Rice Straw (RS) filled Rice Bran (RB)	42
4.2.4	Comparison between Rice Starch, Polyvinyl Acetate (PVAc) and Mixed Rice Starch /PVAc Binders	44
4.3	Water Absorption	46
4.4	Thermogravimetric Analysis (TGA)	47
4.5	Microscopy Analysis	49
4.5.1	Rice Straw (RS) filled Rice Bran (RB)	50
4.5.2	Effect of Polyvinyl Acetate (PVAc) on Rice Straw (RS) filled Rice Bran (RB)	51
4.5.3	Effect of Rice Starch on Rice Straw (RS) filled Rice Bran (RB)	52
4.5.4	Effect of Mixed Rice Starch Polyvinyl Acetate (PVAc) on Rice Straw (RS) filled Rice Bran (RB)	53
5	CONCLUSION AND RECOMMENDATIONS	54
5.1	Conclusion	55
5.2	Recommendation	56
	REFERENCES	57

LIST OF TABLES

TABLES NO.	TITLE	PAGE
2.1	Comparative Properties of bio-derived polymers and comparison with Polyethylene and Polystyrene	12
2.2	Substance density for softwood, rice straw and rice hulls based on elemental density analysis	20
2.3	Structural composition of rice straw as compared with softwood	20
2.4	Composition, structure, and properties of rice straw fibers	21
3.1	Compounding formulation for rice straw filled rice bran	28

LIST OF FIGURES

FIGURES NO.	TITLE	PAGE
2.1	Life cycle of biodegradation process	8
2.2	Example of biodegradable packaging product	12
2.3	Rice bran after milling process	18
2.4	Rice straw after harvest	18
3.1	Rice Bran	25
3.2	Rice Straw	25
3.3	Glycerol	26
3.4	Rice Starch	27
3.5	Chemical formula for PVAc	27
3.6	PVAc Emulsion	28
3.7	Waring Commercial Blender	29
3.8	Wabash V200 hot press (Wabash ID) Compression Molding	30
3.9	Elemendorf Tearing Strength Tester	31
3.10	LRX 2.5KN tensile tester	32
3.11	Equation for percent of water absorption	33
3.12	Water absorption of rice straw filled rice bran	33
3.13	Perkin Elmer TGA	34
3.14	Inverted Microscope-Leica DM IRM	35
4.1	RB/RS with different percentage of Glycerol	36
4.2	RB/RS with different percentage of Rice Starch	38
4.3	RB/RS with different percentage of PVAc	39

4.4	RB/RS with different percentage of mixed PVAc with rice starch	40
4.5	Different Percentage of PVAc in RB/RS	41
4.6	Different Percentage of Rice Starch in RB/RS	42
4.7	Different Percentage of Mixed Polyvinyl Acetate (PVAc) with Rice Starch in RB/RS	44
4.8	Effect of different binders percentage on RB/RS	46
4.9	Effect of different binders percentage on RB/RS	47
4.10	Water Absorption of Various Binding Agent at different percentage	48
4.11	TGA of RB/RS, Rice Starch/RB/RS, and PVAc/RB/RS	49
4.12	Fracture surface of RB/RS at 200X magnification	51
4.13	Fracture surface of PVAc/ RB/RS at 200X magnification	52
4.14	Fracture surface of Rice Starch/RB/RS at 200X magnification	53
4.15	Fracture surface of PVAc/Rice Starch RB/RS at 200X magnification	54

LIST OF ABBREVIATIONS

BOD	-	Biochemical Oxygen Demand
CH ₄	-	Methane
CMC	-	Carboxymethylcellulose
CO ₂	-	Carbon Dioxide
EAA	-	Ethylene Acrylic Acid
GP	-	Gas Permeability
GS	-	Gelatinised Starch
HB	-	Hydroxy-butyrate
HV	-	Hydroxy-valerate
PVAc	-	Polyvinyl Acetate
RB	-	Rice bran
RHDPE	-	Recycle High Density Polyethylene
RS	-	Rice straw
TPIP	-	1,4-trans-polyisoprene
TPS	-	Thermoplastic Starch
VHDPE	-	Virgin High Density Polyethylene
WVTR	-	Water Vapor Transmission Rate

LIST OF SYMBOLS

E	-	Tensile Modulus
g	-	Gram
KN	-	Kilo Newton
T _g	-	Glass transition Temperature
T _m	-	Melting Temperature
ρ	-	Density
μm	-	Micrometer

CHAPTER 1

INTRODUCTION

1.1 Background of Studies

Nowadays the used of synthetic polymer has been restricted because they are not non-totally recyclable and/or biodegradable so they pose serious ecological problems (Sorrentino et al., 2007). To overcome this problem, a big effort to extend the shelf life and enhance food quality while reducing packaging waste has encouraged the exploration of new bio-based packaging materials, such as edible and biodegradable films from renewable resources (Tharanathan, 2003). The use of these materials, due to their biodegradable nature, could at least to some extent solve the waste problem. However, like conventional packaging, bio-based packaging must serve a number of important functions, including containment and protection of food, maintaining its sensory quality and safety, and communicating information to consumers (Robertson, 1993).

Unfortunately, so far the use of biodegradable films for food packaging has been strongly limited because of the poor barrier properties and weak mechanical properties shown by natural polymers (Andrea Sorrentino et al., 2006). Until now, bioplastics contain more than 50% weight of renewable resources. Many bioplastics are mixes or blends containing synthetic components, such as polymers and additives, to improve the functional properties of the finished product and to expand the range of application (Valentina Siracusa et al., 2008).

Previously there were a lot of studies on biodegradable packaging base on biopolymer incorporated with synthetic polymer such as starch base with polyolefin and natural fiber with polyolefin. This biodegradable packaging was not totally degraded by environment due to the synthetic polymer still remain in these packaging materials. Besides that, the other problems also aroused where the starch usually incompatibles with polyolefin due to its polar structure and hydrophilic property which leads to water absorption. These properties make the mechanical properties of packaging decrease as well as chemical properties.

Fiber-reinforced composites are increasingly used due to their relative cheapness compared to conventional materials and their potential to be recycled. As a result natural fiber reinforced plastics are of interest as a replacement for synthetic fiber reinforced plastics in an increasing number of industrial sectors including the automotive industry, packaging, and furniture production. Generally, cellulose-based biofibers, including cotton, flax, hemp, jute and sisal, and wood fibers are used to reinforce plastics due to their relative high-strength, high stiffness and low density. Because of their annual renewability, agricultural crops-residues can be a valuable source of natural fibers. There are an estimated 500 million tones of agricultural residues available in North America alone each year (Ayse et al., 2007). Few comparative studies have been so far conducted using various rice straw components to reinforce polymer composites. Previous research on biodegradable packaging has mainly focused on rice husk and whole rice straw fiber-reinforced thermoplastic composites. Ishak et al. (2001) and Premalal et al. (2002) studied the hydrothermal aging and mechanical properties of rice husk/polypropylene (Fei Yao et al., 2007).

On the other hand, Panthapulakkal et al. (2005) and Marti-Ferrer et al. (2006) presented the effect of coupling agents on properties of rice husk/HDPE composites and rice husk/block copolymer polypropylene, respectively. For whole rice straw/polymer composites, Grozdanov et al. (2006) studied the rice straw/maleated-polypropylene composite containing 20 and 30wt% rice straw by extrusion and compression molding which results in higher tensile modulus (E) for composites containing higher rice straw content. Kamel (2004) studied rice straw/PVC composite with bagasse lignin as a coupling agent. The obtained composite showed

REFERENCES

- A.C. Chang, T. Inge, L. Tau, A. Hiltner, E. Baer. Tear strength of ductile polyolefin films. *Polymer Engineering and Science*. Technology Publications. Nov,2002.
- A.G. Pedroso, D.S. Rosa. (2005). Mechanical, thermal and morphological characterization of recycled LDPE/corn starch blends. *Carbohydrate Polymers*. 59, 1-9.
- Albertsson, A.C. & Karlsson, S. (1994). Chemistry and biochemistry of polymer biodegradation. In *Chemistry and Technology of Biodegradable Polymers*, ed. G.J.L. Griffthn, Blackie Academic & Professional, London. (7-17).
- Alejandro Rodriguez , Ana Moral , Luis Serrano , Jalel Labidi , Luis Jimenez. (2007). Rice straw pulp obtained by using various methods. *Bioresource Technology*. 99, 2881–2886.
- Allison Calhoun, Andrew J. Peacock. *Polymer Chemistry: Properties and Applications*. Published by Hanser Verlag. 149; 2006.
- Andrea Sorrentino, Giuliana Gorrasi and Vittoria. (2006). Potential perspectives of bio-nanocomposites for food packaging applications. *Trends in Food Science & Technology*. 18, 84-95.
- Arvanitoyannis, I. S. (1999). Totally and partially biodegradable polymer blends based.

on natural synthetic macromolecules: preparation, physical properties, and potential as food packaging materials. *Journal of Macromolecular Science, Reviews in Macromolecular Chemistry and Physics*, C39 (2). 205-271.

Ayşe Alemdar , Mohini Sain. (2007). Biocomposites from wheat straw nanofibers: Morphology, thermal and mechanical properties. *Composites Science and Technology*. 68, 557–565.

B. De Wilde and J. Boelens. (1998). Prerequisites for biodegradable plastic materials for acceptance in real-life corn posting plants and technical aspects. *Polymer Degradation and Stability*. 59, 7- 12.

Carmen M.O. Muller , Fabio Yamashita , Joao Borges Laurindo. (2008). Evaluation of the effects of glycerol and sorbitol concentration and water activity on the water barrier properties of cassava starch films through a solubility approach. *Carbohydrate Polymers*. 72, 82–87.

Catia Bastioli. . *Handbook of Biodegradable Polymer*. Rapra Technology Limited. 13; 2005

Daniela Schlemmer , Maria J.A. Sales , Ines S. Resck. (2008). Degradation of different polystyrene/thermoplastic starch blends buried in soil. *Carbohydrate Polymers*. 75, 58–62.

David R. Coffin and Marshall L. Fishman. (1994). Physical and Mechanical Properties of Highly Plasticized Pectin/Starch Films. *Journal of Applied Polymer Science*. 54, 1311-1320.

D. Zuchowska, D. Hlavataa , R. Steller , W. Adamiak, W. Meissner. (1999). Physical structure of polyolefin-starch blends after ageing. *Polymer Degradation and Stability*. 64, 339-346.

- E.H. Park, E.R. George, M.A. Moldoon, A. Flammino. (1994). Thermoplastic starch blends with polyvinyl alcohol: processability, physical properties, and biodegradability. *Polymer News*. 19, 230–238.
- Eleni Psomiadou, Ioannis Arvanitoyannis, Costas G. Biliaderis, Hiromasa Ogawa, Norioki Kawasaki. (1996). Biodegradable films made from low density polyethylene (LDPE), wheat starch and soluble starch for food packaging applications. Part 2. *Carbohydrate Polymers*. 33, 227-242.
- E.M. Teixeira, A.L. Da Ro'z , A.J.F. Carvalho, A.A.S. Curvelo. (2007). The effect of glycerol/sugar/water and sugar/water mixtures on the plasticization of thermoplastic cassava starch. *Carbohydrate Polymers*. 69, 619–624
- Endres, H.J., Pries, A. (1995). Mechanische Eigenschaften starkegefüllter Polymerverbunde. *Starch Starke*. 47, 384-393.
- F.A. Abdel-Mohdy , E.S. Abdel-Halim , Y.M. Abu-Ayana , S.M. El-Sawy. (2008). Rice straw as a new resource for some beneficial uses. *Carbohydrate Polymers*. 7, 44-51.
- Fei Yao, Qinglin Wu, Yong Lei, Yan jun Xu. (2007). Rice straw fiber-reinforced high-density polyethylene composite: Effect of fiber type and loading. *Industrial crops and products*. 28, 63-72.
- F. X. Budi Santosa, and Graciela Wild Padua. (1999). Tensile Properties and Water Absorption of Zein Sheets Plasticized with Oleic and Linoleic Acids. *J. Agric. Food Chem*. 47, 2070-2074.
- Griffthn, G.J.L. (1994). Chemistry and Biochemistry of Polymer Degradation. *In Chemistry and Technology of Biodegradable polymers*. Blackie Academic & Professional, London. 135-149.

- Grozdanov, A., Buzarovska, A., Bogoeva-Gaceva, G., Avella, M., Errico, M.E, Gentile, G. (2006). Rice straw as an alternative reinforcement in polypropylene composites. *Agron. Sustain. Dev.* 26, 251–255.
- G. Sivalingam, R. Karthik, Giridhar Madras. (2004). Blends of poly(3-caprolactone) and poly(vinyl acetate): mechanical properties and thermal degradation. *Polymer Degradation and Stability.* 84, 345-351.
- Gurpreet Kaur Chandi, D.S. Sogi. (2005). Functional properties of rice bran protein concentrates. *Journal of Food Engineering.* 79, 592–597.
- Hamada, J. S. (2000). Characterization and functional properties of rice bran proteins modified by commercial exoproteases and endoproteases. *Journal of Food Science.* 65, 305–310.
- Ishak, Z.A.M., Yow, B.N., Ng, B.L., Khalil, H., Rozman, H.D. (2001). Hygrothermal aging and tensile behavior of injection-molded rice husk-filled polypropylene composites. *J. Appl. Polym. Sci.* 81, 742–753.
- Ioannis Arvanitoyannisa, Costas G. Biliaderis, Hiromasa Ogawab, Norioki Kawasaki. (1998). Biodegradable films made from low-density polyethylene (LDPE), rice starch and potato starch for food packaging applications: Part 1. *Carbohydrate Polymers.* 36, 89- 104.
- Ioannis Arvanitoyannis , Ioannis Kolokuris , Atsuyoshi Nakayama and Seichi Aiba. (1997). Preparation and study of novel biodegradable blends based on gelatinized starch and 1,4-transpolyisoprene (gutta percha) for food packaging or biomedical applications. *Carbohydrate Polymers.* 34, 291-302.
- Jan B. van Beilen, Yves Poirier. (2007). Prospects for Biopolymer Production in Plants. *Adv. Biochem Engin/Biotechnology.* 107, 133–151.
- Johnsy George, R. Kumar, C. Jayaprahash, A. Ramakrishna, S. N. Sabapathy, A. S. Bawa. (2005). Rice Bran-Filled Biodegradable Low-Density Polyethylene Films:

Development and Characterization for Packaging Applications. *Journal of Applied Polymer Science*. 102, 4514–4522.

Juliano, B. O. *Rice Chemistry and Technology*; AACC: St. Paul, MN, 1985.

Karina Petersen, Per Vñggemose Nielsen, Grete Bertelsen, Mark Lawther, Mette B. Olsen, Nils H. Nilssonk and Grith Mortenseny. (1999). Potential of biobased materials for food packaging. *Trends in Food Science & Technology*. 10, 52-68.

Kamel, S. (2004). Preparation and properties of composites made from rice straw and poly(vinyl chloride) (PVC). *Polymer Advance Technology*. 15, 612–616.

Karina Petersen, Per Vnggemose Nielsen, Grete Bertelsen, Mark Lawther, Mette B. Olsen, Nils H. Nilssonk and Grith Mortensen. (1999). Potential of biobased materials for food packaging. *Trends in Food Science & Technology*. 10, 52-68.

Kirwan, M. J., & Strawbridge, J. W. (2003). Plastics in food packaging. *Food Packaging Technology*. 174-240.

Krochta, J.M. and Mulder-Johnston, de C. (1997). *Food Technology*. 51, 61-74.

Krochta, J. M., & Sothornvit, R. (2001). Plasticizer effect on mechanical properties of b-lactoglobulin films. *Journal of Food Engineering*. 50, 149–155.

Krupp, L.R., & Jewell, W. (1992). Biodegradability of modified plastic films in controlled biological environments. *Environ. Sci. Technology*. 26, 193-198.

Lawton, J.W.Fanta, C.F. (1994). Glycerol plasticized films prepared from starch-poly(vinylalcohol) mixtures: effect of poly(ethylene co-acrylic acid). *Carbohydrate Polymer*. 23, 275-280.

Lourdin, D., della Valle, G., & Colonna, P. (1995). Influence of amylase content on starch films and foams. *Carbohydrate. Polymer*. 27, 261-270.

- Mali, S., Sakanaka, L. S., Yamashita, F., & Grossmann, M. V. E. (2005). Water sorption and mechanical properties of cassava starch films and their relation to plasticizing effect. *Carbohydrate Polymers*. 60, 283–289.
- Maolin Zhai, Fumio Yoshii, Tamikazu Kume (2003). Radiation modification of starch-based plastic sheets. *Carbohydrate Polymers*. 52, 311–317.
- Marti-Ferrer, F., Vilaplana, F., Ribes-Greus, A., Benedito-Borrás, A., Sanz-Box, C. (2006). Flour rice husk as filler in block copolymer polypropylene: effect of different coupling agents. *J. Appl. Polym. Sci.* 99, 1823–1831.
- Martina Wollerdorfer, Herbert Bader (1996). Influence of natural fibres on the mechanical properties of biodegradable polymers. *Industrial Crops and Products*. 8, 105–112.
- Matthew D. Summers. (2000). Fundamental Properties of Rice Straw in comparison with Softwoods. *For the requirements of ESPM 286: Physical Properties of Wood, Professor Frank Beall*.
- Narendra Reddy, and Yiqi Yang. (2006). Properties of High-Quality Long Natural Cellulose Fibers from Rice Straw. *J. Agric. Food Chem.* 54, 8077-8081.
- O. Myllymaeki, P. Mylläe rinen. Forssell, T. Suortti, K. Lae hteenkorva, R. Ahvenainen and K. Poutanen. (1998). Mechanical and Permeability Properties of Biodegradable Extruded Starch/polycaprolactone Films. *Packaging Technology and Science*. 11, 265-274.
- Otey, F.H.Mark, A.M.Mehltretter, C.L.Russell, C.R. (1974). Starch-based film for degradable agricultural mulch. *2nd. Eng. Chem. Prod. Res. Develop.* 13, 90-92.
- Pan, Z., Cathcart, A., Wang, D. (2005). Thermal and chemical treatment to improve adhesive property of rice bran. *Ind. Crops Prod.* 22, 233–240.

- Paul A. Dell, and William G. Kohlman. (1994). Effects of Water Content on the Properties of Starch/ Poly (ethylene-vinyl alcohol) Blends. *Journal of Applied Polymer Science*. 52, 353-363.
- Peanasky, J.S., Long, J.M. and Wool, R.P. (1991). Percolation effects in degradable polyethylene-starch blends. *Journal Polymer. Science.: Part B Polymer. Physic*. 29, 565-579.
- Premalal, H.G.B., Ismail, H., Baharin, A. (2002). Comparison of the mechanical properties of rice husk powder filled polypropylene composites with talc filled polypropylene composites. *Polymer Testing*. 21, 833–839.
- Qing-Xin Zhang, Zhong-Zhen Yu , Xiao-Lin Xie , Kimiyoshi Naito, Yutaka Kagawa. (2007). Preparation and crystalline morphology of biodegradable starch/clay nanocomposites. *Polymer* . 48, 7193-7200.
- Q.S.H. Chui, C. Franciscone, J.A.F. Baptista, D.S. Rosa. (2007). An interlaboratory comparison of the melt flow index: Relevant aspects for the participant laboratories. *Polymer Testing*. 26, 576–586.
- Robertson, G. L. (Ed.). Food packaging. *Principles and practice*. NY: Marcel Dekker. New York. 1993.
- Sang Kyoo Lim, Tae Won Son, Dong Won Lee, Bong Kuk Park, Kyu Min Cho. (2000). Novel Regenerated Cellulose Fibers from Rice Straw. *Journal of Applied Polymer Science*. 82, 1705–1708.
- Scott, G., & Wiles, D. M. (2001). Reviews e programmed-life plastics from polyolefins: a new look at sustainability. *Biomacromolecules*. 2, 615-622.
- Shogren, R.L. (1993). Complexes of starch with telechelic poly(ϵ -caprolactone) phosphate. *Carbohydrate Polymer*. 22, 93-98.

- Sorrentino, A.Gorrasi, & Vittoria V. (2007). Potential perspectives of bio-nanocomposites for food packaging applications. *Trends in Food Science & Technology*. 18, 84-95.
- Suzana Mali, Maria Victoria E. Grossmann, Maria A. Garcia, Miriam N. Martino, and Noemi E. Zaritzky. (2004). Barrier, mechanical and optical properties of plasticized yam starch films. *Carbohydrate Polymers*. 56, 129-135.
- Tharanathan, R. N. (2003). Review of biodegradable films and composite coatings: past, present and future. *Trends in Food Science & Technology*. 14, 71-78.
- Thawien Bourtoom, Manjeet S. Chinnan. (2008). Preparation and properties of rice starch-chitosan blend biodegradable film. *LWT - Food Science and Technology*. 41, 1633-164.
- U. Funke, W. Bergthaller & M. G. Lindhauer (1998). Processing and characterization of biodegradable products based on starch. *Polymer Degradation and Stability*. 59, 293-296.
- Valentina Siracusa, Pietro Rocculi, Santina Romani and Marco Dalla Rosa (2008). Biodegradable polymers for food packaging: a review. *Trends in Food Science & Technology*. 19, 634-643.
- Wen-Long Dai. (2003). Blendability and processing methodology of an environmental material rice-hush/PVA composite. *Materials Letters*. 57, 3128-3136.
- W.H. Wang, X.Q. Zhang and X.P. Li. (2008). A novel natural adhesive from rice bran. *Pigment & Resin Technology*. 37, 229-233.
- Wool, R.P. Perspectives on degradable plastics. *Proceedings of symposium on corn-based degradable plastics*. University of Iowa, Iowa. 1989.

- Wool, R.P. The science and engineering of polymer composite degradation. *In Degradable Polymers, eds. G. Scott & D. Gilead, Chapman & Hall, London.* 138-152; 1995.
- Xiao fei Ma, Peter R. Chang ,Jiugao Yu. (2008). Properties of biodegradable thermoplastic pea starch/carboxymethyl cellulose and pea starch/microcrystalline cellulose composites. *Carbohydrate Polymers.* 72, 369–375.
- Yue Li, Charles F., Shoemaker, Jianguo Ma, Xueran Shen, Fang Zhong. (2008). Paste viscosity of rice starches of different amylose content and carboxymethylcellulose formed by dry heating and the physical properties of their films. *Food Chemistry.* 109, 616–623.
- Zhongli Pan, Anna Cathcart , Donghai Wang. (2005). Thermal and chemical treatments to improve adhesive property of rice bran. *Industrial Crops and Products.* 22, 233–240.
- Zhongli Pan, Anna Cathcart, Donghai Wang. (2005). Properties of particleboard bond with rice bran and polymeric methylene diphenyl diisocyanate adhesives. *Industrial Crops and Products.* 23, 40–45.