



New dynamical mode in magnetic nanoparticles

Lefmann, Kim; Garde, J.; Hedegård, P.; Kuhn, Luise Theil; Ancona, S.N.; Bahl, Christian; Frandsen, Cathrine; Mørup, Steen

Publication date:
2008

[Link back to DTU Orbit](#)

Citation (APA):
Lefmann, K., Garde, J., Hedegård, P., Kuhn, L. T., Ancona, S. N., Bahl, C. R. H., ... Mørup, S. (2008). New dynamical mode in magnetic nanoparticles. Abstract from Danish Physical Society Annual Meeting 2008, Nyborg Strand, Denmark.

DTU Library

Technical Information Center of Denmark

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

New dynamical mode in magnetic nanoparticles

By Kim Lefmann (1,2)

and

J. Garde (1), P. Hedegård (1), L. Theil Kuhn (2,3), S.N. Ancona (2),
C.R.H. Bahl (2,3), C. Frandsen (4), S. Mørup (4)

(1) Niels Bohr Institute, KU

(2) Materials Research Department, Risø-DTU

(3) Department of Solid State Chemistry and Fuel Cells, Risø-DTU

(4) Institute of Physics, DTU

Presentation type: talk

The magnetism of nanoparticles is essentially different from that of the corresponding bulk materials, both concerning structure and dynamics. The dominant type of excitations is an in-phase coherent precession ($q=0$) of all spins in the effective anisotropy field, known as collective magnetic excitations (CME). Another type is the flipping of the full particle moment, also known as superparamagnetism (SPM). The latter is important for applications in magnetic data storage, since it effectively causes the nanoparticle to lose its memory.

Using inelastic neutron scattering, the authors have over the last decade studied a number of features of the dynamics of antiferromagnetic nanoparticles, and have e.g. directly observed CME and SPM. Although the theory was developed for ferromagnets, it seems to apply to antiferromagnets as well.

In this work we have studied the common mineral hematite (α -Fe₂O₃). For nanoparticles of $d=8$ nm, our observations were surprising. We expected a minor decrease of CME frequency with increasing temperature due to anharmonicities in the potential. Instead, we observed a 60% increase in frequency.

In order to resolve this apparent discrepancy, we performed classical numerical simulations of the spin dynamics in a nanoparticle. To simulate the heat bath, we used Langevin dynamics, which yields the temperature on an absolute scale.

The simulations reproduce the experimental data surprisingly well; in particular the increase in precession frequency. We find that, with increasing temperature, the angle between the two sublattice magnetisations deviates from 180 degrees. The resulting torque from the exchange interactions causes a fast rotation of both sublattices. We hence have discovered a new, exchange driven dynamic mode in antiferromagnetic nanoparticles.