



Formation and subdivision of deformation structures

Jakobsen, Bo; Poulsen, Henning Friis; Lienert, U.; Almer, J.; Shastri, S.D.; Sørensen, Henning Osholm; Gundlach, Carsten; Pantleon, Wolfgang

Publication date:
2006

Document Version
Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

Citation (APA):
Jakobsen, B., Poulsen, H. F., Lienert, U., Almer, J., Shastri, S. D., Sørensen, H. O., ... Pantleon, W. (2006). Formation and subdivision of deformation structures. Abstract from 36. Danske krystallografmøde; 8. DANSYNC Årsmøde; 4. DANSSK årsmøde, Odense, Denmark.

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Formation and subdivision of deformation structures

Bo Jakobsen,^a Henning F. Poulsen,^a Ulrich Lienert,^b Jonathan Almer,^b Sarvjit D.


Shastri,^b Henning O. Sørensen,^a Carsten Gundlach^a & Wolfgang Pantleon^a

^a *Materials Research Department, Risø National Laboratory, 4000 Roskilde*

^b *APS, Argonne National Laboratory, Argonne, IL 60439, USA*

During plastic deformation of metals and alloys, dislocations arrange in ordered patterns. How and when these self-organization processes take place has remained elusive, as *in situ* observations have not been feasible. Here we present an X-ray diffraction method, providing data on the dynamics of individual, deeply embedded dislocation structures.^[1] First results relate to the tensile deformation of pure copper. Structural elements with a size of 1 μm are found to form during deformation already at 0.4 % strain. Unexpectedly, the dislocation-free regions show intermittent dynamics, e.g. appearing and disappearing with proceeding deformation, even displaying transient splitting behaviour. Insight into these processes is vital for optimizing the strength and mechanical performance of deformed materials as well as an understanding of work-hardening.

[1] B. Jakobsen *et al.* *Science* (2006), *in print*.



Dansk Neutron Sprednings Selskab

DANSK

Danish Neutron Scattering Society



36th Danish Crystallographic Meeting
8th DANSYNC Meeting
4th DANSSK Meeting

16–17 May 2006

University of Southern Denmark, Odense

