



Ultra-high angular resolution 3DXRD for observing bulk subgrains and their dynamics (talk)

Jakobsen, Bo; Lienert, U.; Almer, J.; Poulsen, Henning Friis; Pantleon, Wolfgang

Published in:
14th International Conference on the Strength of Materials

Publication date:
2006

Document Version
Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

Citation (APA):
Jakobsen, B., Lienert, U., Almer, J., Poulsen, H. F., & Pantleon, W. (2006). Ultra-high angular resolution 3DXRD for observing bulk subgrains and their dynamics (talk). In 14th International Conference on the Strength of Materials: Final program and abstracts (pp. 156-156). [ics-199] [s.l.]: International Committee of International Conference on the Strength of Materials.

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Ultra-high Angular Resolution 3DXRD for Observing Bulk Subgrains and their Dynamics

B. Jakobsen¹, U. Lienert², J. Almer², H.F. Poulsen¹ and W. Pantleon¹

¹Center for Fundamental Research: Metal Structures in Four Dimensions, Materials Research Department, Risø National Laboratory, Roskilde, Denmark.

²Argonne National Laboratory, Advanced Photon Source, Argonne, Illinois, USA.

A novel technique is presented that for the first time enables the direct investigation of the dynamics on the subgrain scale inside deeply embedded bulk grains. The technique is a variant of the 3DXRD technique [1] and is based on the setup for peak shape analysis developed previously [2]. By a unique optics at beam line 1-ID at the Advanced Photon Source (APS), an ultra-high angular resolution ($\approx 0.003^\circ$) was achieved, with a vertically focused (full width at half maximum $25\mu\text{m}$) hard X-ray beam (52keV). By using an area detector and rocking the sample around the axis perpendicular to the scattering plane a full 3 dimensional reciprocal space map of a diffraction peak is obtained.

At low angular resolution, diffraction peaks from individual grains in a deformed metal appear as smooth, broad, continuous distributions, both in the radial (2θ) and in the azimuthal directions. With the ultra high angular resolution this distribution breaks up into distinct spots superimposed on a cloud of low intensity. These spots are interpreted as coming from individual subgrains. The size of the entities giving rise to the distinct spots are (based on intensities) around $1\mu\text{m}$, which is consistent with the subgrain size found from transmission electron microscopy, thus supporting this interpretation. From the reciprocal space maps information about orientation and strain distribution of the subgrains can be gathered.

As this technique is non-destructive, it is possible to perform *in-situ* experiments, where either statistical properties or individual subgrains are followed during straining, hence giving a possibility to probe the dynamics on the subgrain scale. Such experiments will allow answering fundamental questions regarding structure formation processes during plastic deformation such as: Do subgrains exist during deformation or do they first appear when straining is stopped? How does the grain refinement process take place? How does the orientation distribution within the grain evolve during straining?

First static and dynamics results are presented demonstrating the strength of this novel technique. Further applications and experiments using the technique will be discussed.

1. H.F. Poulsen. *Crystall. Rev.* (2004) **10**, 29-43

2. W. Pantleon, H.F. Poulsen, J. Almer, U. Lienert. *Materials Science and Engineering A* (2004) **387-389**, 339-342

Keywords: X-ray diffraction, line broadening, plastic deformation, subgrain formation, refinement.

Contact Information: Bo Jakobsen, Center for Fundamental Research: Metal Structures in Four Dimensions, Materials Research Department, Risø National Laboratory, Frederiksborgvej 399, DK-4000 Roskilde, Denmark,
Phone: +45 4677 5876, Fax: +45 4677 5758, Email: bo.jakobsen@risoe.dk



Final Program and Abstracts

14th International Conference on the Strength of Materials

(Fundamental Aspects of the Deformation and Fracture of Materials)

4-9 June 2006

Grand New World Hotel, Xi'an, P. R. China



Organized by:

International Committee of International Conference on the Strength of Materials (ICSMA)

State Key Laboratory for Mechanical Behavior of Materials, Xi'an Jiaotong University, P.R. China

Shenyang National Laboratory for Materials Science, IMR, CAS, P.R. China

Sponsored by:



National Natural Science Foundation of China (NSFC)

Ministry of Education, P.R. China.

Material Research Society of China (C-MRS), P.R. China

Xi'an Jiaotong University (XJTU), P.R. China

Institute of Metal Research (IMR), CAS, P.R. China

Xi'an Municipal Bureau of Science & Technology, P.R. China