



## Chip scale interferometry - a micro fluidic platform for biochemical sensing (poster)

Sørensen, H.S.; Latham, J.C.; Markov, D.A.; Bornhop, D.J.; Andersen, Peter E.; Larsen, N.B.

*Publication date:*  
2005

*Document Version*  
Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

*Citation (APA):*  
Sørensen, H. S., Latham, J. C., Markov, D. A., Bornhop, D. J., Andersen, P. E., & Larsen, N. B. (2005). *Chip scale interferometry - a micro fluidic platform for biochemical sensing (poster)*. Abstract from Annual meeting of the Danish Optical Society 2005, Roskilde, Denmark.

---

### General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

# Chip Scale Interferometry – A micro fluidic platform for biochemical sensing

**Henrik Schiøtt Sørensen**

*Department of Optics and Plasma Research, Risø National Laboratory, DK-4000 Roskilde, Denmark,*

[henrik.schioett.soerensen@risoe.dk](mailto:henrik.schioett.soerensen@risoe.dk)

When illuminating a micro fluidic channel with a coherent laser, a highly modulated fringe pattern occurs perpendicular to the channel. The bright and dark spots shift their angular position when changing the refractive index of the sampled liquid inside the channel. Monitoring this shift is the basis of this sensor. Performed in fused silica capillary tubes has been able to detect changes in the refractive index at  $10^{-8}$  level. Here is presented modelling and platform development of this sensor. The optical train of the capillary tube has been investigated by a ray-tracing model, which has shown good correlation with the experimental data, including the possibility to perform absolute measurement of the refractive index with high accuracy. An analytical solution to Maxwell's equations has also been developed to further describe the capillary system, including protein-binding studies on the glass surface. This analytical model has shown to describe the directly backscattered fringe pattern with higher accuracy. The interferometric sensor has been under constant development in the last 10 years. One major step is to change from capillary tubes and into the micro fluidic network scenario.

Normal photolithography processes and following casting of the microstructures usually results in rectangular shaped micro flow system. Those flow chips have been fabricated in elastomer material (PDMS) and has shown good experimental results on biochemical sensing, such as DNA-hybridization and protein-protein interaction. The reproducibility of these measurements depends critically on the flow channel dimensions. Hence, improvements in performance and system integration are predicted by transferring the well-defined capillary geometry to a polymer chip-based system with a high degree of accuracy and reproducibility. A final goal is to perform chip scale interferometry (CSI) with as high sensitivity as capillaries and all the advantages of micro fluidic advances including mixing of samples. Our channel systems are based on isotropic etching through narrow entry lines defined by photolithographic procedures. Photolithography has traditionally been employed for the generation

of rectangular or triangular shaped channels. However, in this study we demonstrate its unconventional combination with isotropic wet etching in fused quartz and in silicon to form well-defined semicircular channels of cross-sectional dimensions of  $100\mu\text{m}$ . A number of optimizations of the etching mask have been performed for achieving a satisfactory geometry of the flow system. For the etching in fused quartz a metal mask has been used comprising a thin Cr layer for adhesion and a thick layer of Au for mechanical stability, using buffered HF as etchant. Etch channels in silicon were defined by a patterned  $\text{Si}_3\text{N}_4$  layer, using a mixture of HF, nitric acid, and acetic acid as etchant. The etched channels have been characterized by microscopy performed on PDMS replicas and by 3D profilometric measurements. The structure, a half circle, is electroplated into a nickel replica that is subsequently used as mold for injection molding. Multiple thermoplastic flow chips have been fabricated and assembled for chip scale interferometry. The CSI-sensor has shown detection limits of  $Dn = 1 \times 10^{-5}$ , well in the range of monitoring biological relevant samples.