

Technical University of Denmark



## Towards an optimisation and standardisation of the structural and magnetic arrangements of Iron-Oxide Nanoparticles for biomedical applications

González-Alonso, D.; Bender, P.; Fernández-Díaz, M. T. ; Gavilán, H. ; Morales, M. P. ; Fock, Jeppe; Bogart, L.K.; Zeng, L.; Grüttner, C.; Gehrke, N.; Fornara, A. ; Barquín, L. Fernández ; Johansson, C.

*Publication date:*  
2017

*Document Version*  
Peer reviewed version

[Link back to DTU Orbit](#)

*Citation (APA):*  
González-Alonso, D., Bender, P., Fernández-Díaz, M. T., Gavilán, H., Morales, M. P., Fock, J., ... Johansson, C. (2017). Towards an optimisation and standardisation of the structural and magnetic arrangements of Iron-Oxide Nanoparticles for biomedical applications. Abstract from Nanomaterials Applied to Life Sciences 2017, Gijón, Spain.

**DTU Library**  
Technical Information Center of Denmark

---

### General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

## Towards an optimisation and standardisation of the structural and magnetic arrangements of Iron-Oxide Nanoparticles for biomedical applications

D. González-Alonso<sup>1,\*</sup>, P. Bender<sup>1</sup>, M. T. Fernández-Díaz<sup>2</sup>, H. Gavián<sup>3</sup>, M. P. Morales<sup>3</sup>, J. Fock<sup>4</sup>, L. K. Bogart<sup>5</sup>, L. Zeng<sup>6</sup>, C. Grüttner<sup>7</sup>, N. Gehrke<sup>8</sup>, A. Fornara<sup>9</sup>, L. Fernández Barquín<sup>1</sup>, and C. Johansson<sup>10</sup>

<sup>1</sup>Departamento CITIMAC, Universidad de Cantabria, 39005 Santander, Spain

<sup>2</sup>Institut Laue-Langevin ILL, LSS, 38042 Grenoble, France

<sup>3</sup>Instituto de Ciencia de Materiales de Madrid, CSIC, 28049 Madrid, Spain

<sup>4</sup>Technical University of Denmark, 2800 Kongens Lyngby, Denmark

<sup>5</sup>Healthcare Biomagnetics Laboratory, UCL, 21 Albemarle Street, W1S 4BS London, UK

<sup>6</sup>Department of Applied Physics, Chalmers University of Technology, SE-41296 Gothenburg, Sweden

<sup>7</sup>Micromod Partikeltechnologie GmbH, Friedrich-Barnewitz-Str. 4, D-18119 Rostock, Germany

<sup>8</sup>NanoPET Pharma GmbH, D-10115 Berlin, Germany

<sup>9</sup>RISE, Box 5607, SE-11486 Stockholm, Sweden

<sup>10</sup>RISE Acreo, P.O. Box 53071, SE-40014 Göteborg, Sweden

Over the last years, iron-oxide nanoparticles (IONPs) have experienced an ever-increasing interest due to the range of possibilities to apply them in biomedicine such as drug delivery, contrast agents for magnetic resonance imaging, and hyperthermia in cancer treatment [1]. To achieve a successful application it is mandatory to standardise procedures and to define key structural and magnetic parameters. The only way to derive such information is to proceed characterising thoroughly the IONPs, especially when single- and multi-core nanoparticles are involved [2].

In this contribution we combine TEM, magnetization measurements, Mössbauer, X-ray and neutron diffraction results to investigate the structural and magnetic properties for a selected IONP samples regarding their size and core arrangement, e.g., Single-core, multi-core and flower shape [3]. The selected IONP samples present a median core size and particle size ranging from ca. 9 nm and ca. 50nm, up to ca. 15 and ca. 250 nm, respectively. Structural characterisation is essential to help us to interpret the static and dynamic behaviour in DC-magnetisation measurements and AC-susceptibility studies [3, 4]. The ZFC-FC measurements show a wide range of blocking temperature peaks, with the blocking temperature being substantially larger for the smaller particles. We interpret this to be the result of the smaller core-to-core distance between adjacent and the effect this has on the dipole-dipole interaction. Room temperature Mössbauer spectra show, within nano time-scale, that all samples are below their superparamagnetic blocking temperature. In addition, samples with similar core sizes exhibit different magnetic relaxation effects due to core arrangement effects, and underlying different exchange interaction between the cores suppressing the superparamagnetic relaxation of the IONPs [3, 5]. Rietveld refinement of both nuclear and magnetic structures has been carried out by using a standard inverse spinel model with a  $Fd-3m$  space group and surmising the samples are a mixing of a maghemite and magnetite phases. All samples reveal a ferrimagnetic behaviour. This enable us to calculate the magnetization values of our IONP samples through the neutron diffraction data measured at room temperature, which indeed are in good agreement with literature [6]. With this we obtain a complete picture of the properties that an IONP ensemble can display depending on their size and core arrangement.

### Acknowledgements

This work was supported by EU NMP FP7 project NanoMag (grant no. 604448). We gratefully acknowledge the ILL for provision of neutron beam-time at the instrument D2B [7].

### References

- [1] Q. Pankhurst et al. *J. Phys. D* **36** (2003) R167; A. K. Gupta and M. Gupta, *Biomaterials* **26** (2005) 3995.
- [2] W. Wu et al. *Science and technology of advanced materials* **16** (2015) 023501; F. Ludwig et al., *IEEE Transactions on Magnetics* **50** (2014) 5300204.
- [3] H. Gavián et al., *Part. Part. Syst. Charact.* **34** (2017) 1700094; P. Bender et al., *Sci. Rep.* **7** (2017) 45990.
- [4] S. M. Yusuf et al., *Phys. Rev. B* **74**, 224428 (2006); N. Rinaldi-Montes et al., *Nanotechnology* **26** (2015) 305705.
- [5] C. Frandsen and S. Morup, *Phys. Rev. Lett.* **94** (2005) 027202.
- [6] C. Pecharromán et al., *Phys. Chem. Miner.* **22** (1995) 21; J.P. Wright et al., *Phys. Rev. B* **66** (2002) 214422; J.M.D. Coey, *Magnetism and Magnetic Materials* (2010) Cambridge University Press; J. Fock et al., *J. Phys. D: Appl. Phys.* **50** (2017) 265005.
- [7] D. Alba Venero et al. (2015). Defining key structural and magnetic parameters for standardising magnetic Fe-oxide nanoparticles for biomedical applications. Institut Laue-Langevin (ILL) doi:[10.5291/ILL-DATA.5-31-2427](https://doi.org/10.5291/ILL-DATA.5-31-2427).