

J Mater Sci (2014) 49:3780–3784
DOI 10.1007/s10853-014-8089-3

Comminution limit (CL) of particles and possible implications for pumped storage reservoirs

J. E. Field · M. Farhat · S. M. Walley

Received: 7 December 2013 / Accepted: 29 January 2014 / Published online: 13 February 2014
© Springer Science+Business Media New York 2014

Abstract Comminution (fragmentation) of solid particles is important in a range of technologies. An interesting effect is the so-called comminution limit (CL), which is effectively a brittle/ductile transition. Above the CL particles fail by fracture. However, as particle size decreases the amount of stored energy in the particle also decreases and eventually there is no longer sufficient stored energy in the particle to propagate a crack and the particle flows plastically. The CL depends on the hardness, H , and the toughness, K_{Ic} . In mountainous countries, two-reservoir systems are used to generate and store power. When power is needed, water runs through the turbines to the lower reservoir. If there is excess power, water is pumped to the upper reservoir. This recycling of liquid through the turbines can break up entrained particles. Previous work in this area has been primarily concerned with sedimentation of the particles. The research reported in this paper uses the CL to calculate the particle sizes produced for different materials including different rock types. Interestingly, the particle sizes predicted mainly fall in the range where they sediment near the upper water surface. In such cases, the surface layers become opaque to sunlight and plant and animal life will be affected. It is suggested that the CL provides additional information which would assist

research in this area. Where H and K_{Ic} are not known for a particular rock type they should be measured.

Introduction

Pumped storage power plants (PSPPs) allow storing and generating electricity by moving water back and forth between upper and lower reservoirs through a single reversible turbine. Such highly flexible hydraulic schemes fit well in today's liberalized electricity market. Reversible turbines may be operated in generating mode when electricity demand is high and may be switched to pumping mode within a few minutes when the electricity price is low. PSPPs also offer storage capacity for new renewable energy production such as solar and wind power. For these reasons, PSPPs are expected to play a major role in the future energy mix with a growing number of planned projects worldwide. Nevertheless, PSPP development is raising concerns related to its impact on the environment due to the fate of solid particles exchanged between the reservoirs and possible chemical and physical changes produced as they undergo multiple passages through the turbines. Solid particles may impact the turbine blades or other surfaces at high speed. They may also experience large stresses due to cavitation. As a result, solid particles can fracture and their size distribution may move to lower values. The particles will then be acted upon by gravity and will sediment. Large particles will sink quickly to the bottom of the reservoir. But, other particles will sediment in layers or be so small that they remain in the surface layers; see, for example [1]. All of this may lead to a deep change of the reservoir's geomorphology and water turbidity with dramatic consequences on the fauna and flora.

J. E. Field · S. M. Walley (✉)
Cavendish Laboratory, Department of Physics, University of
Cambridge, J J Thomson Avenue, Cambridge CB3 0HE, UK
e-mail: smw14@cam.ac.uk

J. E. Field
e-mail: jef1003@cam.ac.uk

M. Farhat
Hydraulic Machines Laboratory, EPFL, Lausanne, Switzerland

Not surprisingly, sedimentation processes have been studied in some detail including the effect of the lakes being frozen in winter, the temperature of the layers changing by ~ 20 °C over the year and particularly large amounts of sediment being added when streams and rivers flood.

A recent paper by Bonalumni et al. [2] gives reliable data and is an excellent summary of earlier research on sedimentation effects reported in [3–14].

However, there is little discussion in the literature published on this topic about particle fragmentation (comminution) and, in particular, about the so-called comminution limit (CL). The present paper discusses some of these issues, including the benefits of being able to predict better the response of the particles and their sizes at the CL.

It should be noted that although the loading of a particle during impact is predominantly compressive, there are various mechanisms that can give rise to tensile failure, for example, Hertzian fracture around the contact area [15, 16], indirect tensile stresses produced by axial compression as in the Brazilian test [17–19] and spall caused by compressive stress waves reflecting at boundaries [20–22].

Comminution

Comminution of solids is important in a range of technologies, for example, in rock blasting and mining which produce particles of centimetre size to be used for the extraction of metals, coal, cement manufacture, etc. At the other extreme, the pharmaceutical industry requires powders of chosen size, micron to millimetre dimensions, for the manufacture of tablets or additives to liquids to control the properties as in suntan lotions. A supermarket has packages containing a wide variety of powders, sugars, flour, coffee granules, etc., where the particle size of the powder is all important.

The disciplines needed for understanding particles and their production involve those of fracture and strength including techniques for measurement of the effects of strain rate on strength properties. Finally, the acquisition of data is required for modelling comminution.

Comminution limit (CL)

One of the more interesting properties of comminution is the so-called ‘comminution limit’ which has been researched by many groups both theoretically and practically [18, 19, 23–32]. The basic physics is that as particles of brittle materials are stressed to failure they eventually become impossible to break and instead fail plastically. This brittle-ductile transition is the CL. One way of considering the process is that there is no longer sufficient stored energy in

the particle to propagate a crack across the particle and so the particle flows plastically. Steier and Schönert [25] used a micro-compression test apparatus and scanning electron microscopy to study particles of quartz, limestone and polystyrene of micron dimensions. As their micrographs show, there is increasing evidence of plastic flow as the particles become smaller.

A particle which has deformed plastically will have changed shape but not size (material has not been lost). The CL for a particular material depends on the hardness, H , or yield strength, Y , as $H \sim 3Y$ (see [33]) and toughness, K_{Ic} . The magnitude of the limit can vary from a few tens of microns down to ~ 30 – 50 nm for diamond. It should be emphasized that diamond only deforms plastically under very particular loading conditions. However, in a study of diamond polishing, Hird and Field [31] obtained micrographs showing spherical particles on the polished surface of ~ 30 nm size. They also showed that there are plastic grooves of similar width on polished diamond surfaces. Diamond has the lowest CL for any material due to its very high hardness.

Models for the CL

Various models have been proposed for the size of the limit based on somewhat different assumptions. As mentioned above, H can be replaced by $3Y$, where Y is the yield stress.

(a) Kendall’s [19, 27] calculates the critical diameter of the crack produced, d_c .

$$d_c \approx 48(K_{Ic}/H)^2 = 32ER/3Y^2 \tag{1}$$

where E is Young’s modulus and is the fracture energy.

The analysis depends on solving a quadratic and choosing between large and small values of d_c .

(b) Hagan’s [29, 30] is based on nucleation, where d is the size of crack produced.

$$d \approx 30(K_{Ic}/H)^2. \tag{2}$$

(c) Ours involves an energy argument. Consider a cubical particle of side length d , which is loaded in compression.

$$\text{The stored energy, } \xi = 0.5(\sigma \epsilon d^3). \tag{3}$$

But, $E = \sigma/\epsilon$, so $\xi = 0.5(\sigma^2 d^3/E)$ where σ is the stress, ϵ is the strain and E is the modulus. The energy required to fracture the particle and produce two fracture surfaces is

$$\xi_F = 2\gamma d^2, \tag{4}$$

where γ is the fracture surface energy.

For $\xi < \xi_F$, there is not enough energy to fracture the particle and so plastic flow results. Using Eqs. (3) and (4), this criterion may be written as

Table 1 Comparison of the CL for different materials

Materials	Hagan's model for d (μm)
Polystyrene	2800
KCl	295
NaCl	32
Sapphire/ Al_2O_3	3.3
Quartz/ SiO_2	1.1
Soda-lime glass	0.5
MgO	0.6

Table 2 CL, d , for different rock types (minerals) using Hagan's model, and the K_{IC} and H figures from Whitney et al. [34]

Name	Formula	Micro-hardness H (GPa)	Toughness K_{IC} (MPa $\text{m}^{1/2}$)	d (μm)
Orthoclase	KAlSi_3O_8	6.9	1.1	0.76
Sillimanite	Al_2SiO_5	11.0	1.6	0.63
Quartz	SiO_2	12.1	1.5	0.46
Garnet	$\text{Ca}_3\text{Al}_2\text{SiO}_3\text{O}_{12}$	13.2	1.2	0.24
Cubic zirconia	ZrO_2	16.7	1.5	0.24

$$\frac{\sigma^2 d^3}{2E} > 2\gamma d^2. \quad (5)$$

Thus,

$$d > \frac{4\gamma E}{\sigma^2}. \quad (6)$$

But, $K_{\text{IC}}^2 = 2E\gamma$.

Therefore, $d = 2K_{\text{IC}}^2/\sigma^2$.

At yield, $\sigma = Y$ with $H \approx 3Y$.

Therefore,

$$d = (K_{\text{IC}}/Y)^2 = 18(K_{\text{IC}}/H)^2. \quad (7)$$

One of the referees has pointed out that the above analysis has the benefit of being a fairly straightforward dimensional argument, but is not formally correct as fracture does not only depend on energy.

Typical values for CL $d/\mu\text{m}$

The Tables below give values of the CL, d , for a range of materials. Table 1 contains data quoted by Hagan [29, 30].

The data in the Tables are interesting since they show a wide range of values for d . Not surprisingly, the largest value of d is for a polymer (polystyrene) and the smallest diamond of 30–50 nm. The underlined numbers are mean values.

Table 3 Other materials (Hagan's model used)

	H (GPa)	K_{IC}	d (μm)
Diamond	90	3.4–5 (<u>4.2</u>)	0.04
Ge	8.5	0.6	0.115
Si	2.2	0.94	5.5
ZnS	1–2.5 (<u>1.8</u>)	0.75–1 (<u>0.9</u>)	7.5
Al_2O_3	12	2.5–4 (<u>3.3</u>)	2.2
Calcite	Kendall	Calcite	0.8–1.0

Solids such as ionic or covalent crystals have reasonably precise values since their hardness and toughness values are well documented. However, values for minerals and other geological materials are not always easily obtained. There are a great many papers which contain data on hardness or toughness, but those that give both are relatively small in number. The paper by Whitney et al. [34] is an exception, and their results are analysed in Table 2.

Sedimentation velocities in water

Sedimentation is a key concept which has been extensively used for studying lakes and reservoirs. If we know the particle size, sedimentation equations can be used to calculate sedimentation velocities. Large particles will progress to the bottom of lakes, while smaller particles will remain in the upper levels [1, 2] and potentially affect the turbidity and ecology of the surface layers. The relevant equations can be found in many books. The one used here is due to Zapryanov and Tabakova [35] (Table 3).

Stokes' drag equation gives,

$$\text{Force} = 6\pi\mu au, \quad (8)$$

where μ is the kinematic viscosity, a is the particle radius and u is the sedimentation velocity.

The sedimentation velocity is given by,

$$\frac{\Delta u}{u_0} = \frac{3\sqrt{2}}{2}\Phi^{0.5}, \quad (9)$$

where $\Delta u = u_0 - u$, u is the mean sedimentation velocity of the particles, u_0 is the velocity for an isolated particle and Φ is the volume occupied by the particles. Solving for u gives:

$$u = u_0 \left(1 - \frac{3\sqrt{2}}{2}\Phi^{0.5} \right). \quad (10)$$

However, the second term can usually be ignored so that $u \approx u_0$.

Now, a rigid spherical particle of radius a and density ρ_p falls under gravity in an unbounded fluid with velocity

Table 4 Effect of particle size on sedimentation velocity and time for particle fall

Particle size ($a = d/2$)	Sedimentation velocity, u (m s ⁻¹)	Time (s) for particle to fall 10 m
25 nm	2.1×10^{-9}	5×10^9
0.5 μm	8.3×10^{-7}	1.2×10^7
1.0 μm	3.3×10^{-6}	3×10^6
5.0 μm	8.3×10^{-5}	1.2×10^5
10.0 μm	3.3×10^{-4}	3×10^4
100 μm	3.3×10^{-2}	3×10^2
300 μm	0.3	3

Note that 1 day = 8.64×10^4 s

$$u_0 = \frac{2a^2(\rho_p - \rho)g}{9\mu}, \tag{11}$$

where ρ_p and ρ are the particle and fluid densities assumed to be $\rho_p = 2.5 \times 10^3 \text{ kg m}^{-3}$ and $\rho = 1.0 \times 10^3 \text{ kg m}^{-3}$ throughout, g is the acceleration due to gravity and μ is the dynamic viscosity = $1.002 \times 10^{-3} \text{ Pa s}$.

The values in Table 4 were obtained using Eq. (11). They give sedimentation velocities ranging from diamond with critical radius $a = 25 \text{ nm}$ up to $a = 300 \mu\text{m}$. The third column in Table 4 gives the times for particles to sink 10 m. 5 μm particles take about 1 day, 1 μm particles about 1 month and smaller particles very long times.

Conclusions

In cases where liquid is pumped up and down between reservoirs, multiple impacts of entrained particles with the turbine surfaces will take place. Earlier research in this area has been mainly focussed on sedimentation effects. However, the so-called comminution limit has not been applied to this particular problem, although it is used in many other technologies.

This paper notes that attempts have been made to analyse the CL effect which is essentially a brittle/ductile transition. When expressed in terms of H and K_{Ic} , the different models are reasonably close. Calculations for the size of the particles at the CL range from $\approx 50 \text{ nm}$ for diamond to $2800 \mu\text{m}$ for polystyrene. For various other brittle materials and rock types, the range is from ≈ 0.24 to $16 \mu\text{m}$.

Using sedimentation equations, it is shown that in many cases the particles at the CL will remain in the surface layers causing opaque and turbid layers which will adsorb sunlight and affect the ecology of plant and animal life.

There are several cases where the values of H and K_{Ic} are either not known or only one is for a particular material. In such cases, measurement is needed.

If the present ideas are correct, particles will reduce in size down to the CL limit. This suggests that efforts to reduce the impact stresses between particles and the turbine surfaces would be worth making since the larger particles sediment at lower levels.

In conclusion, it is suggested that research in this area could usefully consider the CL approach which gives added physical insight. Overall, the effect of opaque layers in lakes and reservoirs needs further study.

Acknowledgements Professor J. E. Field thanks Dr M Farhat for the invitation to visit École Polytechnique Fédérale, Lausanne where this research was undertaken. Support from the Swiss National Science Foundation (Project 2100-063842.00-1) is acknowledged.

References

1. Shishacov N (1938) Mosaic blocks of silicate glasses. *Tech Phys USSR* 5:666–675
2. Bonalumi M, Anselmetti FS, Kaegi R, Wuest A (2011) Particle dynamics in high-Alpine proglacial reservoirs modified by pumped-storage operation. *Water Resour Res* 47:W09523
3. Miracle RD, Gardner A (1980) Review of the literature on the effects of pumped storage operations on Ichthyofauna. In: Clugston JP (ed) *Proceedings of the Clemson workshop on environmental impacts of pumped storage hydroelectric operations*. US Fish and Wildlife Service, Washington DC, pp 40–53
4. Potter DU, Stevens MP, Meyer JL (1982) Changes in physical and chemical variables in a new reservoir due to pumped-storage operations. *Water Resour Res* 18:627–633
5. Bezinge A (1987) Glacial meltwater streams, hydrology and sediment transport: the case of the grande dixence hydroelectricity scheme. In: Gurnell AM, Clark MJ (eds) *Glacio-fluvial sediment transfer: an alpine perspective*. Wiley, Chichester, pp 473–498
6. Hofmann A, Dominik J (1995) Turbidity and mass concentration of suspended matter in lake water: a comparison of two calibration methods. *Aquat Sci* 57:54–69
7. Davies-Colley RJ, Smith DG (2001) Turbidity, suspended sediment, and water clarity: a review. *J Amer Water Resour Assoc* 37:1085–1101
8. Bunn SE, Arthington AH (2002) Basic principles and ecological consequences of altered flow regimes for aquatic biodiversity. *Environ Manage* 30:492–507
9. Bühler J, Siegenthaler C, Wüest A (2005) Turbidity currents in an Alpine pumped-storage reservoir. In: Lee JHW, Lam KH (eds) *Environmental hydrology and sustainable water management*. A.A Balkema, Rotterdam, pp 239–244
10. Finger D, Schmid M, Wüest A (2006) Effects of upstream hydropower operation on riverine particle transport and turbidity in downstream lakes. *Water Resour Res* 42:W08429
11. Anselmetti FS, Buhler R, Finger D, Girardclos S, Lancini A, Rellstab C, Sturm M (2007) Effects of Alpine hydropower dams on particle transport and lacustrine sedimentation. *Aquat Sci* 69:179–198
12. Chanudet V, Filella M (2007) The fate of inorganic colloidal particles in Lake Brienz. *Aquat Sci* 69:199–211
13. Jaun L, Finger D, Zeh M, Schurter M, Wüest A (2007) Effects of upstream hydropower operation and oligotrophication on the light regime of a turbid peri-alpine lake. *Aquat Sci* 69:212–226
14. Anderson MA (2010) Influence of pumped-storage hydroelectric plant operation on a shallow polymictic lake: predictions from 3-D hydrodynamic modeling. *Lake Reserv Manag* 26:1–13

15. Frank FC, Lawn BR (1967) On the theory of Hertzian fracture. *Proc R Soc Lond A* 299:291–306
16. Sargent GA, Chen Y-L, Conrad H (1989) Hertzian fracture of pyrex glass in impact loading. In: Ludema KC (ed) *Wear of materials*. American Society of Mechanical Engineers, New York, pp 339–347
17. Hobbs DW (1964) The tensile strength of rocks. *Int J Rock Mech Min Sci* 1:385–396
18. Rumpf H, Schönert K (1972) Die Brucherscheinungen in Kugeln bei elastischen sowie plastischen Verformungen durch Bruchbeanspruchung. *Dechema Monograph* 69:51–86
19. Kendall K (1978) Complexities of compression failure. *Proc R Soc Lond A* 361:245–263
20. Hopkinson B (1914) The effects of the detonation of gun-cotton. *Trans North-East Coast Inst Eng Shipbuild* 30:199–217
21. Bowden FP, Brunton JH (1961) The deformation of solids by liquid impact at supersonic speeds. *Proc R Soc Lond A* 263:433–450
22. Kolsky H, Rader D (1968) Stress waves and fracture. In: Liebowitz H (ed) *Fracture*, vol 1. Academic, New York, pp 533–569
23. Boddy RGHB (1943) Microscope observations of the crushing of coal. *Nature* 151:54
24. Parish BM (1967) Effect of rank and particle size on plastic behaviour of coal. *Br J Appl Phys* 18:233–240
25. Steier K, Schönert K (1972) Verformung und Bruchphänomene unter Druckbeanspruchung von sehr kleinen Körnern aus Kalkstein, Quarz und Polystyrol. *Dechema Monograph* 69:167–192
26. Puttick KE (1979) Energy scaling, size effects and ductile-brittle transitions in fracture. *J Phys D Appl Phys* 12:L19–L23
27. Kendall K (1978) The impossibility of comminuting small particles by compression. *Nature* 272:710–711
28. Karihaloo BL (1979) A note on complexities of compression failure. *Proc R Soc Lond A* 368:483–493
29. Hagan JT (1979) Micromechanics of crack nucleation during indentations. *J Mater Sci* 14:2975–2980
30. Hagan JT (1981) Impossibility of fragmenting small particles: brittle–ductile transition. *J Mater Sci* 16:2909–2911
31. Hird JR, Field JE (2004) Diamond polishing. *Proc R Soc Lond A* 460:3547–3568
32. Williamson DM, Proud WG (2011) The conch shell as a model for tougher composites. *Int J Mater Eng Innov* 2:149–164
33. Tabor D (1951) *The hardness of metals*. Clarendon Press, Oxford
34. Whitney DL, Broz M, Cook RF (2007) Hardness, toughness, and modulus of some common metamorphic minerals. *Am Min* 92:281–288
35. Zapryanov Z, Tabakova S (1999) *Dynamics of bubbles, drops, and particles*. Kluwer, Dordrecht