

J. C. Conesa, P. Wahnón, R. Lucena, P. Palacios, I. Aguilera, F. Fresno, Y. Seminovski

*Instituto de Catálisis y Petroleoquímica, CSIC, Marie Curie 2, 28049 Madrid, Spain

#Instituto de Energía Solar, Univ. Politécnica de Madrid, Ciudad Universitaria s/n, Madrid, Spain

jcconesa@icp.csic.es

The intermediate band (IB) solar cell (Fig. 1) has been proposed [1] to increase photovoltaic efficiency by a factor above 1.5, based on the absorption of two sub-bandgap photons to promote an electron across the bandgap. To realize this principle, that can be applied also to obtain efficient photocatalysis with sunlight, we proposed in recent years several materials where a metal or heavy element, substituting for an electropositive atom in a known semiconductor that has an appropriate band gap width (around 2 eV), forms inside the gap the partially filled levels needed for this aim. After studying Ga(As,P) with Ga partially substituted by Ti or Cr [2], we proposed several systems that could be made in thin film form:

a) Ti- or Cr- substituted CuGaS_2 or similar chalcopyrite (Fig. 2), where the thermodynamics of formation is seen to be less disfavoured than e.g. insertion of Mn in GaAs [3];

b) In_2S_3 and other sulphides containing octahedral In, which when doped with Ti or V form also the IB according to quantum calculations [4] (Fig. 3). The V-doped In_2S_3 material is particularly promising. Being based on a binary compound host, controlling its stoichiometry should be easy. In addition In_2S_3 , with $E_g = 2.0$ eV, is used as buffer layer in thin film CIGS PV cells, so that the known technology to make it in thin film form could be used. Besides, we have synthesized it in nanocrystalline form [5] and shown that its optical absorption spectrum has the features predicted by quantum calculations for the IB structure (Fig. 4). Furthermore, recent photocatalytic tests made with it [6] show that the V dopant extends its spectral response down to the IR range without increasing recombination, which would decrease its efficiency.

c) Octahedral Sn^{IV} sulphide and other similar compounds show also, according to DFT modeling (Fig. 5), the formation of an IB with the desired characteristics when V, Nb or similar metals are introduced at Sn sites [7]. The experimental synthesis of such sulphide is in progress, and first results obtained show optical absorption spectra matching again the expectations for an IB material (Fig. 6).

d) Another class of IB materials consists of Si heavily doped with certain elements. With Ti as dopant the desired IB electronic structure appears (Fig. 7) if Ti lies at interstitial sites [8]. Such material has been prepared by ion implantation methods, and its electrical properties [9] show uncommon features that can be explained assuming the formation of a partially filled band a few tenths of eV below the conduction band, as predicted by the DFT calculations. Although its band gap is not optimum to get high efficiency, it can serve as benchmark to study the behaviour of IB materials in single-crystal form. We could also show that substitution of Si by S or Se, accompanied by hole doping, provides an IB material as well [10].

e) Finally we showed with DFT calculations that a clathrate-type silicon polymorph, that in pure form has $E_g = 1.9$ eV and for which some thin film preparation recipes exist, forms an IB material when a metal as Ag is occluded in its cavities or some of its Si atoms are substituted by a transition metal as V [11] (Fig. 8).

References:

- [1] Luque and A. Martí, Phys. Rev. Lett. 78 (1997) 5014
- [2] P. Palacios et al. Phys. Rev. B 73 (2006) 085206; *ibid.* J. Chem. Phys. 124 (2006) 014711
- [3] P. Palacios et al. Thin Solid Films 515 (2007) 6280; *ibid.* J. Phys. Chem. C 112 (2008) 9525
- [4] P. Palacios et al. Phys. Rev. Lett. 101 (2008) 046403
- [5] R. Lucena et al. Chem. Mater. 20 (2008) 5125
- [6] R. Lucena and J.C. Conesa, in preparation

- [7] P. Wahnón et al., in preparation
- [8] K. Sánchez et al. Phys. Rev. B 79 (2009) 165203
- [9] G. González-Díaz et al., Solar En. Mater. Solar Cells 93 (2009) 1668
- [10] K. Sánchez et al. Phys. Rev. B 82 (2010) 165201
- [11] P. Wahnón et al., in preparation

Figures:




Figure 1: TFB Scheme of operation of an intermediate band photovoltaic cell




Figure 2: Density of states (computed with DFT) of CuGaS_2 with Ga partially substituted by Cr




Figure 3: Density of states (computed with DFT) of In_2S_3 with octahedral in partially substituted by V




Figure 4: Experimental diffuse reflectance spectrum of pure and V-doped nanocrystalline In_2S_3




Figure 5: Density of states (computed with DFT) of SnS_2 with Sn partially substituted by V




Figure 6: Experimental diffuse reflectance spectrum of V-doped nanocrystalline SnS_2




Figure 7: Density of states (computed with DFT) of Si with Ti located in an interstitial site




Figure 8: Estructure of Si clathrate, and density of states computed for it when V substitutes for Si atoms in the lattice

INDEX: INVITED CONTRIBUTIONS

	pag
Michaël Grätzel (EPFL, Switzerland) <i>"The advent of mesosocopic solar cells"</i>	505
Antonio Luque (Univ Politécnica de Madrid, Spain) <i>"Nanotechnology for more efficient photovoltaics: the quantum dot intermediate band solar cell"</i>	513
Emilio Mendez (Brookhaven National Laboratory, USA) <i>"Nanotechnology for the Energy Challenge"</i>	-

INDEX: INVITED CONTRIBUTIONS (OMNT SESSION)

	pag
Kazuhito Kinosita (Waseda Univ., Japan) <i>"A rotary molecular motor with amazing performance"</i>	-
Ana Moore (Arizona Univ., USA) <i>"Design of Photoelectrochemical Cells for the Splitting of Water and Production of Fuel"</i>	521
Nicolas Tetreault (EPFL, Switzerland) <i>"Title not available"</i>	-

INDEX: KEYNOTE CONTRIBUTIONS

	pag
Juan Bisquert (Universitat Jaume I, Spain) <i>"Dynamics and distribution of photogenerated carriers in organic solar cells and in dye solar cells"</i>	489
Fernando Briones (IMM-CNM-CSIC, Spain) <i>"Molecular Beam Epitaxy (MBE), a versatile tool to integrate model semiconductor nanostructures into advanced solar cell concepts"</i>	491
Alejandro A. Franco (CEA-LITEN, France) <i>"Title not available"</i>	-
David Fuertes Marron (UPM, Spain) <i>"Chalcopyrite-based nanostructures: new prospects for highly efficient photovoltaic devices"</i>	499
Jordi Martorell (ICFO, Spain) <i>"New routes for the fabrication of Organic Photovoltaic Cells"</i>	519
Xavier Obradors (ICMAB-CSIC, Spain) <i>"Chemical solution approaches to self-assembled and nanocomposite superconducting and ferromagnetic films"</i>	523
Taro Toyoda (The Univ of Electro-Communications, Japan) <i>"Characterization of Optical Properties of Semiconductor Quantum Dot-Sensitized Solar Cells together with Ultrafast Carrier Dynamic Propertie"</i>	527

INDEX: KEYNOTE CONTRIBUTIONS (OMNT SESSION)

	pag
Franck Artzner (CNRS – IPR, France) <i>"Bio-inspired scaffolds to manufacture nanomaterials :nanotubes & Quantum Dots arrays"</i>	487
Frédéric Favier (CNRS – ICG, France) <i>"Title not available"</i>	-
Christophe Lethien (CNRS – IEMN, France) <i>"Silicon nanowires and nanopillars arrays for lithium-ion battery and micro-battery: overview, challenges and perspectives"</i>	511
Pere Roca i Cabarrocas (CNRS – LPICM, France) <i>"Title not available"</i>	-