

Construction of a ^3He magnetic force microscope with a vector magnet

Jinho Yang, Ilkyu Yang, Yun Won Kim, Dongwoo Shin, Juyoung Jeong, Dirk Wulferding, Han Woong Yeom, and Jeehoon Kim

Citation: *Review of Scientific Instruments* **87**, 023704 (2016); doi: 10.1063/1.4941959

View online: <http://dx.doi.org/10.1063/1.4941959>

View Table of Contents: <http://scitation.aip.org/content/aip/journal/rsi/87/2?ver=pdfcov>

Published by the [AIP Publishing](#)

Articles you may be interested in

[Design of a self-aligned, wide temperature range \(300 mK-300 K\) atomic force microscope/magnetic force microscope with 10 nm magnetic force microscope resolution](#)

Rev. Sci. Instrum. **85**, 103705 (2014); 10.1063/1.4897147

[Stroboscopic imaging of an alternating magnetic field from a perpendicular magnetic recording head by frequency-modulated magnetic force microscopy](#)

Appl. Phys. Lett. **100**, 222405 (2012); 10.1063/1.4720508

[Design of a variable temperature scanning force microscope](#)


Rev. Sci. Instrum. **80**, 083704 (2009); 10.1063/1.3212561

[Nanoscale modification of electrical and magnetic properties of \$\text{Fe}_3\text{O}_4\$ thin film by atomic force microscopy lithography](#)

Appl. Phys. Lett. **85**, 1811 (2004); 10.1063/1.1784884

[A combined magneto-optic magnetic force microscope study of Co/Pd multilayer films](#)

J. Appl. Phys. **81**, 3846 (1997); 10.1063/1.364729



Call for Nominations

Recognize Those Utilizing Science
to Innovate American Business

Nominate Proven Leaders for the 2016 AIP
Prize for Industrial Applications of Physics

More Information // www.aip.org/industry/prize
Deadline // July 1, 2016
Questions // assoc@aip.org

sponsored by
General Motors

AIP
American Institute
of Physics

Construction of a ^3He magnetic force microscope with a vector magnet

Jinho Yang,^{1,2} Ilkyu Yang,¹ Yun Won Kim,^{1,a)} Dongwoo Shin,^{1,2} Juyoung Jeong,^{1,2}
 Dirk Wulferding,¹ Han Woong Yeom,^{1,2} and Jeehoon Kim^{1,2,b)}

¹Center for Artificial Low Dimensional Electronic Systems, Institute for Basic Science, 77 Cheongam-Ro,
 Nam-Gu, Pohang 790-784, South Korea

²Department of Physics, Pohang University of Science and Technology, Pohang 790-784, South Korea

(Received 7 December 2015; accepted 1 February 2016; published online 17 February 2016)

We constructed a ^3He magnetic force microscope operating at the base temperature of 300 mK under a vector magnetic field of 2-2-9 T in the x - y - z direction. Fiber optic interferometry as a detection scheme is employed in which two home-built fiber walkers are used for the alignment between the cantilever and the optical fiber. The noise level of the laser interferometer is close to its thermodynamic limit. The capabilities of the sub-Kelvin and vector field are demonstrated by imaging the coexistence of magnetism and superconductivity in a ferromagnetic superconductor ($\text{ErNi}_2\text{B}_2\text{C}$) at $T = 500$ mK and by probing a dipole shape of a single Abrikosov vortex with an in-plane tip magnetization. © 2016 AIP Publishing LLC. [<http://dx.doi.org/10.1063/1.4941959>]

I. INTRODUCTION

Atomic force microscopy (AFM) is one of the most versatile imaging techniques at the nanoscale. Magnetic force microscopy (MFM),¹ a variant of AFM with a magnetized tip, plays an important role in studying the formation of magnetic domains in magnetic materials,²⁻⁴ vortex dynamics in superconductors,⁵⁻¹² and exotic spin structures such as skyrmions.¹³ So far, several home-built low-temperature MFMs have been operated down to the ^4He temperature within a single axis magnet.^{3,14-18} On the other hand, MFM apparatus operating under high demanding conditions, such as sub-Kelvin temperatures and vector magnetic fields, are rare,^{19,20} although they are useful for understanding unconventional (e.g., heavy fermion) superconductivity²¹ and quantum/molecular magnetism at the nanoscale under extreme conditions.²² At present, the demand for a sub-Kelvin MFM is high for investigating f -electron physics as a recent scanning tunneling microscopy study resolves the competition of f - and d -electrons in heavy fermion systems.^{23,24} In addition, the use of a vector magnet allows further insight into anisotropy in superconductivity such as non-uniform pairing symmetry and magnetic penetration depth.²⁵

In this article, we report the construction of a ^3He MFM with a vector field of 2-2-9 T for the x - y - z direction and a base temperature of $T = 300$ mK. We calibrate the system's stray field by imaging Abrikosov vortices as a function of field and demonstrate its low temperature and vector field capabilities by resolving the coexistence of superconductivity and magnetism in a ferromagnetic superconductor at $T = 500$ mK, as well as by imaging the change of a single vortex shape depending on the direction of the tip magnetization. Our ^3He MFM system allows investigating phenomena emerging under extreme conditions such as superconductivity in heavy

fermions, anisotropic superconductivity, and the interplay of magnetism and superconductivity.

II. INSTRUMENTATION

A. ^3He cryostat insert and Dewar with a vector magnet

We employ a custom-built ^3He cryostat and a low-loss Dewar with a vector magnet from Janis, LLC [see Fig. 1(a)]. The outer jacket of the Dewar is evacuated to a pressure lower than 10^{-5} Torr prior to cool down. The liquid ^4He consumption is about 10 l a day without magnetic field applied. To minimize the effect of heat radiation, baffles are installed inside the displacer. The heat load from electrical wires has been minimized by winding them around thermal anchors which are attached to the 1-K pot. We control the sample temperature via charcoal, 1-K pot, and ^3He pot [see Fig. 1(a)]. The base temperature ($T = 300$ mK) of the ^3He pot is reached within 4 hours from $T = 4$ K and remains for 8 hours if initially all 25 L of ^3He gas was condensed. The three-axis vector magnet is located at the bottom of the Dewar as shown in Fig. 1(a) and immersed in liquid ^4He cryogen. We can apply the vector field of 2-2-9 T in the x - y - z direction, with a field homogeneity of $\pm 0.1\%$ over a sphere of 1 cm diameter at the sample position. The electronics for the vector magnet are supplied by Cryomagnetics, Inc., and controlled by a home-made LabVIEW-based program.

B. MFM head

The MFM head consists of three parts: (i) the tip stage, (ii) the sample stage, and (iii) the scanner and x , y , z coarse positioners.

1. Tip stage

The tip stage consists of the cantilever, an optical fiber, and two fiber walkers, as shown in Fig. 1(a). It detaches conveniently from the MFM head, allowing an easy replacement of a cantilever. The cantilever is secured via a Be-Cu spring which

^{a)}Present address: Division of Physical Metrology, Korea Research Institute of Standards and Science, Daejeon 305-340, South Korea.

^{b)}Electronic mail: jeehoon@postech.ac.kr




FIG. 1. (a) Schematic cross section for the front view of the whole MFM system, a zoom-in on the MFM head, and a zoom-in on the tip stage. (b) Top view of the sample stage.

also establishes an electrical connection for electric scanning probe microscopy modes such as conducting AFM, electric force microscopy, and Kelvin force microscopy. We use an optical interferometric system for measuring the cantilever motion that is directly proportional to the force between the tip and sample. A mechanism to optimize the alignment between the cantilever and the fiber end is of importance for low temperature applications.²⁶ Therefore, we adopt two compact home-built walkers to control the relative position of the fiber and the tip in the x - z direction: x for the cantilever's center in width and z for the fiber-tip distance. The intensity and sensitivity of the MFM signal can be maximized by the following procedure: First, the x walker locates the fiber at the middle of the cantilever to achieve the maximum signal intensity. Then, the z walker regulates the tip-fiber position to achieve a maximum sensitivity (described in detail in Section II C).

2. Sample stage

The sample stage is attached directly to the ^3He pot via four Cu rods, allowing a good thermal anchoring. Note that the sample stage is firmly fixed and static while the tip stage is mounted onto the scanner and walkers. This way we achieve an optimal cooling of the samples to base temperature. A horizontal sliding mechanism for replacing the sample holder ensures a safe and easy mounting procedure. The Au-plated Cu sample holder has a resistive heater element (a 9- Ω chip resistor for surface mount) and a cernox temperature sensor for an additional temperature control together with the ^3He -pot control. We can study several samples during a single cool down with our multi-sample stage [see Fig. 1(b)] due to

the large walking range of the piezo-walkers. This not only avoids lengthy warm-up and cool-down procedures for changing samples but it also allows to perform comparative studies among the installed samples under consistent conditions, such as the geometry of the cantilever, and the tip magnetization. The sample holder is grounded electrically to the MFM head [see Fig. 1(a)].

3. Scanner and walkers

In general, a piezo-tube scanner, routinely used in scanning tunneling microscope, offers a simple, cost-efficient, and rigid scanning solution in spite of a cross talk between z and x - y motions as well as a small scan range in the z direction. For MFM applications, the large scan area is required to image the μm -size magnetic domains. We therefore employ a compact, commercially available Attocube scanner (AN-Sxyz100). Its principle is based on a piezo-driven lever arm mechanism and each axis is decoupled from one another. It offers a scan range of $50 \times 50 \times 24 \mu\text{m}^3$ at 300 K and $30 \times 30 \times 15 \mu\text{m}^3$ at 4 K, respectively. We use three Attocube walkers (Attocube, ANPx101/RES, ANPz/RES) with a travel distance of 5 mm each for a coarse positioning. An electrical connection to the scanner and walkers is established through a home-built 24-pin connector at the bottom of the head [see Fig. 1(a)]. Manganin wires with low thermal and electrical conductivity and Cu wires are used for the scanner and the piezo-walkers, respectively, because the high resistance of manganin wires results in a large decay time constant, which is detrimental for the performance of a stick-slip walker. The decay time constant of a driving voltage should be as small as 10 μs for a stick-slip

walker: For example, the capacitance of the Attocube walker is $5 \mu\text{F}$, requiring the wire resistance as small as 2Ω .

We use a standard sample (TGXYZ01/NM from MikroMasch with 20 nm step height and $3 \mu\text{m}$ step width) for calibrating the scanner in x , y , and z directions at room- and base temperature. A resulting topographic image obtained at room temperature is shown in Fig. 2(a). In Fig. 2(b), we show the MFM image of a hard disk drive obtained in amplitude-modulation mode at ambient conditions with the tip-lift height of 100 nm. Individual magnetic bits are clearly resolved.

An alternative route to calibrate the z -motion of the scanner utilizes the optical interferometric system. By intentionally misaligning the fiber with respect to the tip, we can illuminate the sample rather than the back of the cantilever. The resulting interference signal as presented in Fig. 2(c) is obtained by scanning the z -range. Since the wavelength of the laser is fixed and well-defined we can easily and accurately determine the scanner's temperature-dependent performance, summarized in Fig. 2(d): With increasing temperature, the walking distance of the scanner increases, leading to a growing deviation between nominal and actual value. From these datapoints, we can extract the scanning distance per applied bias at a given temperature.

C. Optical interferometric system

The optical interferometer system provides a stable, low-noise environment for the detection of a cantilever motion.^{26–29} We use a 2×2 coupler with an intensity ratio of 9:1 (Gould Fiber Optics). A solid state laser (S3FC1550, Thorlabs) with a wavelength of $\lambda = 1550 \text{ nm}$ offers a good control of tempera-

ture and power. The photon energy of the laser ($\lambda = 1550 \text{ nm} \approx 0.8 \text{ eV}$) is smaller than the band gap of a Si cantilever ($E_g \approx 1.1 \text{ eV}$), and thus transfers less heat than a laser of smaller wavelength. We minimize the laser fluctuation by adjusting the laser power and temperature by monitoring the stability of the interferogram. The adjusted laser power delivered to the cantilever is as small as $40 \mu\text{W}$ to avoid a direct cantilever heating. The laser power and temperature on operation are typically 0.34 mW and $23 \text{ }^\circ\text{C}$, respectively. Note that such optimal parameters may vary even with the same laser model. We use angled physical contact (APC) plugs for all optical connections to minimize undesired reflections from optical connectors though the laser and the photo-detector have built-in physical contact (PC) plugs. Therefore, we use a custom spec adaptor to connect PC with APC. The schematic diagram for the interferometer system is depicted in Fig. 3. The incident laser beam passes through an optical isolator (Thorlabs IO-H-1550APC) to discriminate any side bands and is split into two beams via an optical coupler. 90% of the incident beam goes into the photo-detector (new focus model 2117) through an attenuator and serves as a reference signal (blue dotted lines in Fig. 3). The remaining 10% is fed into the microscope head, where it partly transmits through the cleaved fiber end, and reflects at the cantilever. The remaining part of the beam is reflected at the fiber end and interferes with the reflected light from the back of cantilever within the fiber; this interference signal is fed into the coupler (see Fig. 3). Both the reference and the interference signal are fed into the balanced photo-detector, which allows the DC part of the interference signal to be zero since it is subtracted from the interference. Thus, the removal of the DC signal results in a




FIG. 2. (a) Topographic image of the calibration sample from MikroMasch. (b) MFM signal from a disassembled hard disk drive. (c) Interferometer signal as a function of the nominal z -scanner motion for various temperatures. (d) Nominal / actual scanning distance vs. temperature (black squares) together with the scanner's operating parameters (red circles).




FIG. 3. Schematics of the optical interferometric system.

wide dynamic span of an amplifier allowing an increase of the DC gain as well as the subtraction of DC laser fluctuations. The interference intensity measured by a photo-detector is as follows:

$$I = I_1 - I_2 \cos\left(\frac{4\pi D}{\lambda}\right), \quad (1)$$

where I_1 is the laser power and I_2 is proportional to I_1 multiplied by the optical visibility of the system, D is the fiber-cantilever distance, and λ is the wavelength of the laser.¹⁸ For a fixed wavelength, the intensity change due to the cantilever motion is the most sensitive when $4\pi D/\lambda$ is close to a multiple of $\pi/2$, because the variation in intensity due to the change of D is maximum at these points: For example, $\frac{dI}{dD}$ is maximized when $4\pi D/\lambda$ is a multiple of $\pi/2$. Therefore we regulate the fiber-cantilever distance at these crossing points by the fiber piezo. Here we note that another method successfully applied to optimize the interferometer operating point is by slightly modifying the laser's wavelength, e.g., by controlling its operating temperature.²⁹ While this simple approach requires no additional mechanical parts such as internal fiber walkers, the response is rather slow as every slight change of laser temperature necessitates a certain time period of stabilization. In addition, only a large tip-fiber distance results in a large enough interferometer sweep. Our method, in contrast, allows for fast and stable sweeps, and can operate at any initial tip-fiber distance.

III. CHARACTERIZATION AND PERFORMANCE

A. Vibration isolation and noise characterization

In order to minimize the mechanical noise, our microscope will be installed into a newly constructed vibration isolation laboratory at the Institute for Basic Science in Pohang, as shown in Fig. 4. A 20-ton concrete block resting on the heavy duty damping springs serves as the base for our system. Three pneumatic legs standing on the concrete block carry a home-built triangular wooden table filled with lead bricks of 800 kg to further lower the system's resonance frequency. The ^3He cryostat insert is fixed on the table, and the Dewar with a vector magnet moves up and down for experiments through the rectangular pit.




FIG. 4. Schematics of the vibration isolation laboratory.

We characterize the thermal noise level of our microscope as follows:³⁰

$$\delta f^{\min} = \sqrt{\frac{f_0 k_B T B}{2\pi k Q A^2}}, \quad (2)$$

where f_0 , k_B , T , B , k , Q , and A are resonance frequency, Boltzmann constant, temperature, measurement bandwidth, spring constant, quality factor, and oscillation amplitude, respectively. Based on our typical operation parameters ($f_0 = 75195$ Hz, $B = 100$ Hz, $k = 2.8$ N/m, $Q = 48554$, and $A = 4.8$ nm) at $T = 4.2$ K, the minimum detectable frequency shift is $\delta f^{\min} = 4.6$ mHz, and the corresponding minimal detectable force gradient is

$$\left| \frac{\partial F_z^{\min}}{\partial z} \right| = 2k \cdot \frac{\delta f^{\min}}{f_0} = 3.4 \cdot 10^{-7} \text{ N/m}. \quad (3)$$

The measured background, as shown by the red profile line in Fig. 5(a), varies by about $7.4 \cdot 10^{-7}$ N/m, which only deviates by a factor of 2 from the thermodynamic noise limit. Additional noise fluctuations can be attributed to electrical noise, mechanical vibrations, and possible magnetic inhomogeneities at the measurement position. The MFM signal magnitude of an Abrikosov vortex in the Nb film [black profile line in Fig. 5(a)] exceeds the noise level by a factor of about 40, which is comparable to the previous report.¹⁸

B. MFM results

Here we present two experimental results demonstrating the performance of our home-built ^3He MFM. The images of Abrikosov vortices obtained in a Nb film highlight the vector magnet capability. The simultaneous image of ferromagnetism and superconductivity at $T = 500$ mK in $\text{ErNi}_2\text{B}_2\text{C}$ proves the sub-Kelvin operation.




FIG. 5. (a) Abrikosov vortices in a superconducting Nb film imaged with an out-of-plane magnetized MFM tip. Line profiles of the vortex and the background are presented as black and red solid lines. (b) Vortices imaged at the same sample position with an in-plane magnetized MFM tip. The insets in (a) and (b) indicate the magnetic field direction of the tip and vortex. (c) Four representative MFM images obtained at different magnetic fields. (d) Number of vortices on a $10 \times 10 \mu\text{m}^2$ area as a function of the out-of-plane applied magnetic field. All images were taken at $T = 4.2$ K and with a tip-sample distance of 300 nm.

1. Vector magnet experiments

The images of vortices in Fig. 5, obtained from a Nb film, show the vector magnet capability of our MFM. The Nb thin film was grown on a Si substrate via electron beam deposition with a film thickness and critical temperature of 300 ± 5 nm and $T_c = 8.8$ K, respectively. The tip was magnetized along the z direction, perpendicular to the surface of the Nb film, by applying a magnetic field of 10 kOe larger than the tip coercive field (~ 300 Oe). We field-cool the sample from $T = 12$ K (above T_c) in the presence of a few Oersted magnetic fields. Due to local pinning centers, the penetrating flux quanta can be trapped within the scan frame, while the sample remains in the pure Meissner state. The resulting MFM image is shown in Fig. 5(a); the inset sketches the field lines from a single vortex. The vortex image with an in-plane tip magnetization is shown in Fig. 5(b) after polarizing the tip magnetization along the in-plane direction by a vector magnet. The scan areas in Figs. 5(a) and 5(b) are identical. The MFM signal of a vortex resembles a dipole, which is in contrast to the monopole signal of an out-of-plane tip magnetization directions [see Fig. 5(a)]. The two different vortex images result from the two different tip magnetizations. In general, the force gradient is positive for an attractive interaction between the tip and vortex as it is negative for a repulsive interaction. The tip magnetized with an in-plane field experiences both positive and negative force gradients as it crosses a single vortex, which results in dipole-like vortex as shown in Fig. 5(b). This result displays a good demonstration of a vector field effect.

Imaging vortices as a function of applied field allows us to estimate the stray field of our setup. The vortex images at four different magnetic fields are shown in Fig. 5(c). Note that the polarity of the vortices changes the sign with field, as indicated by the MFM contrast. The number of vortices per scan frame as a function of fields is shown in Fig. 5(d). The experimental flux quantum Φ_{exp} can be obtained from Fig. 5(d) as follows: $n = \frac{1}{\Phi_{exp}A} B + B_{stray}$, where n is the number of vortices for a scan area of A and B_{stray} is the stray field. We find a stray field of $B_{stray} = +6.7$ G, and for a given area of $A = 100 \mu\text{m}^2$, we obtain $\Phi_{exp} = 20.02 \pm 0.84 \text{ G } \mu\text{m}^2$, which is in good agreement with the theoretical quantum flux of $\Phi_0 = h/2e \approx 20.67 \text{ G } \mu\text{m}^2$.

2. Ultra-low temperature experiments

In order to demonstrate the low temperature capability, we investigate magnetism in $\text{ErNi}_2\text{B}_2\text{C}$, a magnetic superconductor, at the sub-Kelvin temperature.³¹ It turns superconducting below $T_c = 10.5$ K and develops a weak ferromagnetic order below $T_{WFM} = 2.3$ K within the superconducting phase. The MFM image shown in Fig. 6(a) was obtained at $T = 500$ mK and clearly shows magnetic stripes as well as Abrikosov vortices (dark spots), indicating a coexistence of magnetism and superconductivity. At temperatures higher than T_{WFM} , the bright stripes vanish as shown in Figs. 6(b) and 6(c), signaling the fading of the magnetic order upon reaching the ferromagnetic transition. At elevated temperatures, the vortices tend to be mobile by overcoming local pinning potentials, which allows a manipulation of vortices via the




FIG. 6. (a) MFM image of the magnetic superconductor $\text{ErNi}_2\text{B}_2\text{C}$, obtained at $T = 500$ mK. (b) and (c) Subsequent images obtained on the same scan area at 1.0 K and 5.0 K, respectively. All images were taken with a tip-sample distance of 700 nm. (d) Comparison of Meissner force curves from $\text{ErNi}_2\text{B}_2\text{C}$ at 500 mK (dashed black curve) and a reference sample (Nb, solid red curve) to determine λ_L .³¹

tip magnetic moment upon scanning. This is evident from the smeared-out vortex lines in Fig. 6(c). The absolute values of the local London penetration depth (λ_L) can be obtained through a comparative Meissner technique, as shown in Fig. 6(d).^{32–34} When the sample is in the superconducting state, the magnetic tip experiences a Meissner force which grows algebraically with decreasing the tip-sample distance. Using a comparative method, one can extract the absolute value of λ_L by overlaying the Meissner force curve of the sample (dashed black curve) with that of a Nb reference sample (solid red curve), $\lambda_{L,\text{Nb}} = 110$ nm. The addition of the shifted distance of 100 nm to $\lambda_{L,\text{Nb}}$ leads to a penetration depth in $\text{ErNi}_2\text{B}_2\text{C}$ of $\lambda_{L,\text{ENBC}} = 210$ nm. This straightforward method to measure λ_L , one of the two intrinsic superconducting parameters, at sub-Kelvin temperatures under a vector field allows further investigation of exotic superconductivity together with anisotropy.

IV. SUMMARY

In summary, we constructed a ^3He MFM operating at a base temperature of 300 mK under vector magnetic fields of $\mathbf{H}_{xyz} = 2\text{-}2\text{-}9$ T. We employed a low-noise fiber interferometer system with a noise level close to its thermodynamic limit. The sub-Kelvin and vector field capabilities of the apparatus were demonstrated by imaging the shape change of the Abrikosov vortices from monopole to dipole according to the rotation of the tip magnetization from out-of-plane to in-plane in a Nb film and by resolving the coexistence of magnetism and superconductivity in $\text{ErNi}_2\text{B}_2\text{C}$ at $T = 500$ mK. Our ^3He MFM opens the door to investigate magnetism in exotic superconducting phenomena emerging at sub-Kelvin temperatures, such as magnetically mediated superconductivity in heavy fermion systems and the nonlinear Meissner effect with an anisotropic pairing symmetry. It furthermore allows us to study the anisotropy of unconventional magnetic domains in a vector magnetic field.

ACKNOWLEDGMENTS

This work was supported by the Institute for Basic Science (IBS), Grant No. IBS-R014-D1.

- ¹Y. Martin and H. K. Wickramasinghe, *Appl. Phys. Lett.* **50**, 1455 (1987).
- ²J. Jeong, I. Yang, J. Yang, O. E. Ayala-Valenzuela, D. Wulferding, J.-S. Zhou, J. B. Goodenough, A. de Lozanne, J. F. Mitchell, N. Leon, R. Movshovich, Y. H. Jeong, H. W. Yeom, and J. Kim, *Phys. Rev. B* **92**, 054426 (2015).
- ³M. Liebmann, A. Schwarz, S. M. Langkat, and R. Wiesendanger, *Rev. Sci. Instrum.* **73**, 3508 (2002).
- ⁴A. Schwarz, M. Liebmann, U. Kaiser, R. Wiesendanger, T. W. Noh, and D. W. Kim, *Phys. Rev. Lett.* **92**, 077206 (2004).
- ⁵A. Moser, H. J. Hug, I. Parashikov, B. Stiefel, O. Fritz, H. Thomas, A. Baratoff, H.-J. Güntherodt, and P. Chaudhari, *Phys. Rev. Lett.* **74**, 1847 (1995).
- ⁶A. Volodin, K. Temst, C. Van Haesendonck, Y. Bruynseraede, M. I. Montero, and I. K. Schuller, *Europhys. Lett.* **58**, 582 (2002).
- ⁷A. Schwarz, U. H. Pi, M. Liebmann, R. Wiesendanger, Z. G. Khim, and D. H. Kim, *Appl. Phys. Lett.* **88**, 012507 (2006).
- ⁸M. Roseman and P. Grütter, *J. Appl. Phys.* **91**, 8840 (2002).
- ⁹U. H. Pi, A. Schwarz, M. Liebmann, R. Wiesendanger, Z. G. Khim, and D. H. Kim, *Phys. Rev. B* **73**, 144505 (2006).
- ¹⁰L. Luan, O. M. Auslaender, D. A. Bonn, R. Liang, W. N. Hardy, and K. A. Moler, *Phys. Rev. B* **79**, 214530 (2009).
- ¹¹E. W. J. Straver, J. E. Hoffman, O. M. Auslaender, D. Rugar, and K. A. Moler, *Appl. Phys. Lett.* **93**, 172514 (2008).
- ¹²I. Yang, J. Yang, D. Wulferding, S. Chung, H. Yeom, K. Kim, and J. Kim, “Confinement of projective vortices via an extra dimension” (unpublished).
- ¹³P. Milde, D. Köhler, J. Seidel, L. M. Eng, A. Bauer, A. Chacon, J. Kinder-vater, S. Mühlbauer, C. Pfleiderer, S. Buhrandt, C. Schütte, and A. Rosch, *Science* **340**, 1076 (2013).
- ¹⁴H. J. Hug, Th. Jung, and H.-J. Güntherodt, *Rev. Sci. Instrum.* **63**, 3900 (1992).
- ¹⁵R. Euler, U. Memmert, and U. Hartmann, *Rev. Sci. Instrum.* **68**, 1776 (1997).
- ¹⁶M. Roseman and P. Grütter, *Rev. Sci. Instrum.* **71**, 3782 (2000).
- ¹⁷T.-M. Chuang and A. de Lozanne, *Rev. Sci. Instrum.* **78**, 053710 (2007).
- ¹⁸E. Nazaretski, K. S. Graham, J. D. Thompson, J. A. Wright, D. V. Pelekhov, P. C. Hammel, and R. Movshovich, *Rev. Sci. Instrum.* **80**, 083704 (2009).
- ¹⁹D. V. Pelekhov, J. B. Becker, and G. Nunes, *Rev. Sci. Instrum.* **70**, 114 (1999).
- ²⁰Ö. Karci, M. Dede, and A. Oral, *Rev. Sci. Instrum.* **85**, 103705 (2014).
- ²¹P. Thalmeier, G. Zwicknagl, G. Sparn, and F. Steglich, “Superconductivity in heavy fermion compounds,” in *Frontiers in Superconducting Materials*, edited by A. V. Narlikar (Springer Verlag, 2005), p. 109.

- ²²S. Sachdev, *Nat. Phys.* **4**, 173 (2008).
- ²³P. Aynajian, E. H. da Silva Neto, A. Gyenis, R. E. Baumbach, J. D. Thompson, Z. Fisk, E. D. Bauer, and A. Yazdani, *Nature* **486**, 201 (2012).
- ²⁴M. P. Allan, F. Massee, D. K. Morr, J. Van Dyke, A. W. Rost, A. P. Mackenzie, C. Petrovic, and J. C. Davis, *Nat. Phys.* **9**, 468 (2013).
- ²⁵D. Xu, S. K. Yip, and J. A. Sauls, *Phys. Rev. B* **51**, 16233 (1995).
- ²⁶A. Oral, R. A. Grimple, H. Ö. Özer, and J. B. Pethica, *Rev. Sci. Instrum.* **74**, 3656 (2003).
- ²⁷D. Rugar, H. J. Mamin, R. Erlandsson, J. E. Stern, and B. D. Terris, *Rev. Sci. Instrum.* **59**, 2337 (1988).
- ²⁸D. D. Smith, J. A. Marohn, and L. E. Harrell, *Rev. Sci. Instrum.* **72**, 2080 (2001).
- ²⁹K. J. Bruland, J. L. Garbini, W. M. Dougherty, S. H. Chao, S. E. Jensen, and J. A. Sidles, *Rev. Sci. Instrum.* **70**, 3542 (1999).
- ³⁰T. R. Albrecht, P. Grütter, D. Horne, and D. Rugar, *J. Appl. Phys.* **69**, 668 (1991).
- ³¹D. Wulferding, I. Yang, J. Yang, M. Lee, H. C. Choi, S. L. Bud'ko, P. C. Canfield, H. W. Yeom, and J. Kim, *Phys. Rev. B* **92**, 014517 (2015).
- ³²J. H. Xu, J. H. Miller, Jr., and C. S. Ting, *Phys. Rev. B* **51**, 424 (1995).
- ³³Q. Lu, K. Mochizuki, J. T. Markert, and A. de Lozanne, *Physica C* **371**, 146 (2002).
- ³⁴J. Kim, L. Civale, E. Nazaretski, N. Haberkorn, F. Ronning, A. S. Sefat, T. Tajima, B. H. Moeckly, J. D. Thompson, and R. Movshovich, *Supercond. Sci. Technol.* **25**, 112001 (2012).