



**UNIVERSITI PUTRA MALAYSIA**

**DESIGN, ANALYSIS AND FABRICATION OF GLASS  
FIBER-REINFORCED PA 6,6 COMPOSITE AUTOMOTIVE  
CLUTCH PEDALS**

**SHARIFAH IMIHEZRI BT. SYED SHAHARUDDIN**

**FK 2005 64**

**DESIGN, ANALYSIS AND FABRICATION OF GLASS FIBER-REINFORCED  
PA 6,6 COMPOSITE AUTOMOTIVE CLUTCH PEDALS**

**By**

**SHARIFAH IMIHEZRI BT. SYED SHAHARUDDIN**

**Thesis Submitted to the School of Graduate Studies, Universiti Putra Malaysia,  
In Fulfilment of Requirements for the Degree of Master of Science**

**October 2005**



**To Dad and Mom**



Abstract of thesis presented to the Senate of Universiti Putra Malaysia in fulfillment of the requirements for the degree of Master of Science

**DESIGN, ANALYSIS AND FABRICATION OF GLASS FIBER-REINFORCED  
PA 6,6 COMPOSITE AUTOMOTIVE CLUTCH PEDALS**

By

**SHARIFAH IMIHEZRI BT. SYED SHAHARUDDIN**

**October 2005**

**Chairman: Associate Professor Mohd. Sapuan Salit, PhD, P.Eng.**

**Faculty: Engineering**

A study of injection number and location is important since it often affects product quality such as weld line and shrinkage as well as process quality such as molding efficiency. This study is also critical because unlike any other processing parameters such as filling speed, pressure and temperature that could be modified instantly, gate location is permanent and any modification equals to increase in cost and time.

The main objective of this research is to simulate and analyze the effects of increasing number of gates for a clutch pedal using short glass fiber reinforced PA 6,6. The research compares the effects of a single gated and a double gated mould. A prototype of the composite clutch pedal model is then fabricated and compared with the simulation works.

In order to achieve the above-mentioned objectives, two numerical softwares will be used in this study. Moldflow Plastic Insight (MPI) software is used to investigate the effects of mold design on fill time, pressure, temperature, weld line, air traps and fiber

orientation and distribution while LUSAS software is used to analyze stress distribution for pedal profiles and rib patterns.

The studies show that there are many advantages and disadvantages associated with the design of single and double gated mold. Firstly, a mold designed with a single gate is advantageous in terms of flow balance, fill time and weld line since it provides a more balanced flow, shorter fill time and shorter length of weld line compared to a double gated mold. However, a double gated mold precedes a single gated mold in terms of injection pressure, part shrinkage and trapped air. The study revealed that a double gated mold reduces the required injection pressure as well as pressure variation, hence a lower volumetric shrinkage. Such design also produces less amount of trapped air. Finally, the comparison study of simulation and actual model showed great consistency in terms of fill time, air traps and weld line formations.

Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia sebagai memenuhi keperluan untuk ijazah Master Sains

**REKAAN, ANALISIS DAN FABRIKASI KOMPOSIT PA 6,6 BERTETULANG GENTIAN KACA BAGI INJAK CEKAM AUTOMOTIF**

Oleh

**SHARIFAH IMIHEZRI BT. SYED SHAHARUDDIN**

**Oktober 2005**

**Pengerusi: Profesor Madya Mohd. Sapuan Salit, PhD., P.Eng.**

**Fakulti: Kejuruteraan**

Penyelidikan mengenai bilangan dan lokasi suntikan adalah penting kerana ia mempengaruhi kualiti produk seperti garisan penemuan, pengecutan dan juga kualiti proses seperti kecekapan pengacuan. . Kajian ini juga adalah mustahak kerana berbeza dengan elemen-elemen pemprosesan lain seperti kelajuan suntikan, tekanan dan suhu yang boleh diubah dengan mudah, lokasi suntikan adalah tetap dan sebarang perubahan yang dilakukan akan mengakibatkan peningkatan dari segi kos dan masa.

Objektif utama penyelidikan ini adalah untuk menjalankan simulasi dan mengkaji kesan-kesan akibat peningkatan jumlah suntikan acuan bertetulang bagi injak cekam automotif menggunakan komposit PA 6,6 bertetulang gentian kaca. Kajian ini membandingkan kesan-kesan rekaan acuan berdasarkan satu suntikan dan dua suntikan. Contoh-sulung komposit gentian kaca ini turut dihasilkan untuk tujuan perbandingan dengan hasil penyelakuan yang dijalankan.

Bagi mencapai objektif-objektif yang disebutkan diatas, dua kaedah perisian berangka utama telah digunakan. Perisian Moldflow Plastic Insight (MPI) digunakan untuk mengkaji kesan-kesan rekaan acuan keatas masa pengisian, tekanan, suhu, garisan penemuan, kandungan udara yang terperangkap dan penghalaan serta pengagihan gentian kaca manakala perisian LUSAS digunakan untuk mengkaji sebaran tegasan bagi susuk cekam dan rangka rusuk.

Hasil daripada kajian ini menunjukkan jumlah suntikan bagi acuan iaitu satu atau dua mempunyai kelemahan dan kelebihan yang tersendiri. Pertama, keputusan penyelakuan menunjukkan acuan dengan satu suntikan mempunyai kelebihan daripada segi keseimbangan pengaliran bahan, masa pengisian dan garisan penemuan kerana ia menghasilkan pengaliran bahan yang seimbang, pengisian masa yang singkat dan garis penemuan yang pendek. Namun, rekaan acuan dengan dua suntikan mendahului rekaan satu suntikan daripada segi tekanan suntikan, pengecutan produk dan jumlah udara yang terperangkap. Rekaan ini mengurangkan tekanan suntikan yang diperlukan dan variasi tekanan; oleh itu, pengecutan isi produk dapat dikurangkan. Ia juga mengurangkan jumlah udara yang terperangkap. Akhir sekali, kajian perbandingan diantara penyelakuan dan contoh-sulung menunjukkan keputusan yang konsisten dari segi masa pengisian, udara yang terperangkap dan garisan penemuan.

## ACKNOWLEDGEMENTS

Praise be to ALLAH the ALMIGHTY in giving me the help, patience and guidance to override all obstacles in order to complete this thesis.

Firstly, I would like to express my sincerest thanks to the chairman of the supervisory committee, Assoc. Prof. Ir. Dr. Mohd. Sapuan Salit for the endless support, ideas, hospitality and encouragement throughout the course of this research. My profound gratitude is also dedicated to Assoc. Prof. Dr. Shamsuddin Sulaiman and Assoc. Prof. Dr. Megat Mohamad Hamdan Megat Ahmad for their technical advice and comments. I thank them all for their patience in reading, revising and commenting my thesis, and I thank their constructive advices and guidance.

Secondly, I am also most grateful to the Universiti Putra Malaysia for the financial supports concede to my study. I would like to thank the staff of Institute of Advanced Technology and the staff of Department of Mechanical and Manufacturing Engineering for availing their computing facilities to conduct this work and continuous assistance.

Continuous appreciation is also extended to colleagues and to all those who contributed directly or indirectly to the success of this work, may ALLAH bless them all.



I certify that an Examination Committee met on 6<sup>th</sup> October 2005 to conduct the final examination of Sharifah Imihezri Syed Shaharuddin on her Master of Science thesis entitled “Design, Analysis and Fabrication of Glass Fiber-Reinforced PA 6,6 Composite Automotive Clutch Pedals” in accordance with Universiti Pertanian Malaysia (Higher Degree) Act 1980 and Universiti Pertanian Malaysia (Higher Degree) Regulations 1981. The Committee recommends that the candidate be awarded the relevant degree. Members of the Examination Committee are as follows:

**Napsiah Ismail, PhD**  
Associate Professor  
Faculty of Engineering  
Universiti Putra Malaysia  
(Chairman)

**Abdul Aziz Jaafar, PhD**  
Lecturer  
Faculty of Engineering  
Universiti Putra Malaysia  
(Internal Examiner)

**Ahmad Samsuri Mokhtar, PhD**  
Lecturer  
Faculty of Engineering  
Universiti Putra Malaysia  
(Internal Examiner)

**Azman Hassan, PhD**  
Associate Professor  
Faculty of Chemical and Natural Resources Engineering  
Universiti Teknologi Malaysia  
(External Examiner)



---

**HASANAH MOHD. GHAZALI, PhD**  
Professor/Deputy Dean  
School of Graduate Studies  
Universiti Putra Malaysia

Date: 19 JAN 2006

This thesis submitted to the Senate of Universiti Putra Malaysia and has been accepted as fulfillment of the requirement for the degree of Master of Science. The members of the Supervisory Committee are as follows:

**Mohd. Sapuan Salit, PhD, P.Eng.**

Associate Professor  
Faculty of Engineering  
Universiti Putra Malaysia  
(Chairman)

**Shamsuddin Sulaiman, PhD**

Associate Professor  
Faculty of Engineering  
Universiti Putra Malaysia  
(Member)

**Megat Mohd. Hamdan Megat Ahmad, PhD**

Associate Professor  
Faculty of Engineering  
Universiti Putra Malaysia  
(Member)




---

**AINI IDERIS, PhD**  
Professor/Deputy Dean  
School of Graduate Studies  
Universiti Putra Malaysia

Date: 07 FEB 2006

## DECLARATION

I hereby declare that the thesis is based on my original work except for quotations and citations which have been duly acknowledged. I also declare it not has been previously or concurrently submitted for any other degree at UPM or other institutions.



---

**SHARIFAH IMIHEZRI BT. SYED SHAHARUDDIN**

Date: 18 DECEMBER 2005

## TABLE OF CONTENTS

		<b>Page</b>
<b>DEDICATION</b>		ii
<b>ABSTRACT</b>		iii
<b>ABSTRAK</b>		v
<b>ACKNOWLEDGEMENTS</b>		vii
<b>APPROVAL</b>		viii
<b>DECLARATION</b>		x
<b>LIST OF TABLES</b>		xiv
<b>LIST OF FIGURES</b>		xv
<b>LIST OF ABBREVIATIONS</b>		xix
<b>CHAPTER</b>		
1	INTRODUCTION	
	1.1 Overview	1.1
	1.2 Problem Statement	1.2
	1.3 Objectives of the Research	1.3
	1.4 Scope and Structure of Work	1.5
2	LITERATURE REVIEW	
	2.1 Introduction	2.1
	2.2 Classification of Polymeric Based Materials	2.2
	2.2.1 Thermosetting Polymer	2.2
	2.2.2 Thermoplastic Polymer	2.3
	2.3 Classification of Reinforcements	2.5
	2.4 Short Glass Fiber Reinforced Polyamide (SGFRP) Composites	2.6
	2.4.1 Fiber Orientation and Distribution	2.7
	2.4.2 Effects of Fiber Concentration	2.12
	2.4.3 Effects of Fiber Length	2.13
	2.5 The Effects of Mold Design	2.13
	2.5.1 Effects of Gate Design	2.14
	2.5.2 Effects of Runner System	2.16
	2.5.3 Effects of Cooling Channel	2.17
	2.6 The Effects of Processing Parameter	2.17
	2.7 Composite Pedal System	2.21
	2.8 Mold Flow Simulation Programs	2.22
	2.9 Closure	
	2.26	

<b>3</b>	<b>METHODOLOGY</b>	
3.1	Introduction	3.1
3.2	LUSAS Simulation Program	3.2
	3.2.1 Outline of LUSAS Simulation Program	3.2
	3.2.2 LUSAS Pre-Processing	3.3
	3.2.3 LUSAS Finite Element Solver	3.4
	3.2.4 LUSAS Results Processing	3.5
3.3	Moldflow Plastic Insight (MPI) Simulation Program	3.5
	3.3.1 Outline of MPI Simulation Program	3.6
	3.3.2 MPI Flow Analysis	3.7
	3.3.3 MPI Modeling Prerequisites	3.9
	Midplane Mesh	3.9
	Material and Processing Selection	3.12
	Injection Location Selection	3.14
3.4	Mold Fabrication Method	3.15
	3.4.1 Computer Numerical Control (CNC) Machine	3.15
	3.4.2 Electric Discharge Machining (EDM) Machine	3.15
3.5	Closure	3.16
<b>4</b>	<b>PRELIMINARY DESIGN RESULTS</b>	
4.1	Introduction	4.1
4.2	LUSAS Simulation Results	4.2
	4.2.1 Clutch Pedal Profile Results	4.2
	4.2.2 “V” and “X” Rib Results	4.4
4.3	MPI Simulation Results	4.4
	4.3.1 Fill Time Results	4.6
	4.3.2 Pressure Results	4.11
	4.3.3 Air Trap Results	4.13
	4.3.4 Weld Line Results	4.13
	4.3.5 Average Fiber Orientation Results	4.14
4.4	Comparison between “V” Rib and “X” Rib	4.17
4.5	Closure	4.18
<b>5</b>	<b>COMPOSITE CLUTCH PEDAL SIMULATION RESULTS</b>	
5.1	Introduction	5.1
5.2	Fill Time Results	5.2
5.3	Pressure Results	5.7
5.4	Temperature Results	5.11
5.5	Air Trap Results	5.13
5.6	Weld Line Results	5.17
5.7	Average Fiber Orientation Results	5.19
5.8	Comparison between Single Gated Mold and Double Gated Mold	5.22
5.9	Closure	5.24

6	COMPOSITE CLUTCH PEDAL FABRICATION RESULTS	
6.1	Introduction	6.1
6.2	Mold Design	6.1
	6.2.1 General Mold Components	6.2
	6.2.2 Clutch Pedal Mold Components	6.2
	6.2.3 Injection Molding Machine	6.7
6.3	Injection Molding Parameter Set Up	6.8
6.4	Comparison between Simulated and Actual Molded Product	6.11
6.5	Closure	6.17
7	CONCLUSIONS AND RECOMMENDATIONS FOR FURTHER WORK	
7.1	Conclusions	7.1
7.2	Recommendations for Further Work	7.3
	REFERENCES	R.1
	APPENDICES	A.1
	BIODATA OF THE AUTHOR	B.1

**LIST OF TABLES**

<b>Table</b>		<b>Page</b>
4.1	Comparison between “V” and “X” rib	4.17
5.1	Comparisons between single and double injection location	5.23
6.1	Heat temperature zones for the barrel	6.9
6.2	Various injection speed for the product	6.9
7.1	Advantages and Disadvantages of “V” Rib and “X” Rib	7.1
7.2	Advantages and Disadvantages of Single Gate and Double Gates	7.2

## LIST OF FIGURES

<b>Figure</b>	<b>Page</b>
1.1 Overview of the structure of research	1.7
2.1 Stress strain behavior of selected reinforcing fibers (Henkel and Pense, 2002)	2.6
2.2 Stress-strain graph with fibers oriented in the direction of strain and transversal to strain (Davies et al., 2002)	2.8
2.3 Fountain flow in injection molded part (Anon, 1999)	2.9
2.4 Shell core structure (Anon, 1999)	2.9
2.5 Converging and diverging flow. (Anon, 1996)	2.10
2.6 Variation of “ $f_p$ ” properties correspondingly from 0 to 1 (Anon 1999)	2.11
2.7 Tensile strength of a glass reinforced plastic versus glass content (by weight) in the fiber direction (Mayer, 1993)	2.12
2.8 Analysis model and gate locations (Kim et al., 2003)	2.15
2.9 Predicted flow front for each gate location: (a) Case 1, (b) Case 2, (c) Case 3, (d) Case 4. (Kim et al., 2003)	2.16
2.10 Light micrograph showing the wide variation in fiber length after injection molding (Matthew and Rawlings, 1994)	2.18
2.11 Predicted fiber orientation and distribution for (a) slow filling case and (b) fast filling case (Lee et al, 1997)	2.20
2.12 Polymeric-based composite automotive pedal box system (Sapuan, 2005)	2.22
2.13 Clamp force profile (Nardin et al, 2002)	2.23
2.14 Short shot for Simulation 6 (Nardin et al, 2002)	2.24
2.15 Fiber orientation in flow direction at 20mm from the gate (Zainuddin, 2002)	2.25



3.1	Outline of LUSAS simulation model	3.3
3.2	LUSAS model for an “I” and “T” clutch profile	3.4
3.3	LUSAS model of meshed elements for “X” and “V” rib	3.4
3.4	Outline of MPI simulation program	3.7
3.5	Flow regions during the injection molding process (Anon, 1996)	3.8
3.6	Midplane model of “V” and “X” rib	3.10
3.7	Meshed model of “V” and “X” rib	3.11
3.8	A midplane model of the clutch pedal	3.11
3.9	A midplane mesh model for the clutch pedal	3.12
3.10	Material selection using MPI	3.13
3.11	Process selection using MPI	3.13
3.12	Single and double injection locations for the clutch pedal model	3.14
4.1	An ‘I’ profile cross section with a maximum stress of 11.07 MPa	4.3
4.2	A ‘T’ profile cross section with a maximum stress of 33.20 MPa	4.3
4.3	Stress contour for (a) “V” rib and (b) “X” rib	4.6
4.4	Smooth and contoured fill time results for (a,b)“V” rib and (c,d) “X” rib	4.8
4.5	Flow distribution for (a)“V” rib (side view) and (b) “X” rib (side view)	4.9
4.6	Radial flow pattern for (a) “V” rib (top view) (b) “X” rib (top view)	4.10
4.7	Pressure distribution for (a) “V” rib and (b) “X” rib	4.11
4.8	Velocity/pressure plot for “V” rib	4.12
4.9	Velocity/pressure plot for “X” rib	4.12
4.10	Location of air trap for “V” and “X” rib	4.13

4.11	Weld line location for (a) “V” rib and (b) “X” rib	4.14
4.12	Top view of the average fiber orientation for “V” rib and “X” rib	4.15
4.13	Front view of the average fiber orientation for “V” rib and “X” rib	4.16
4.14	Model representation using AutoCAD	4.18
5.1	Fill time fractions for single gate and double gates design	5.4
5.2	(a) Fill time results for single gate location (b) Contoured fill pattern for single gate location	5.5
5.3	(a) Fill time results for double gate location (b) Contoured fill pattern for double gate location	5.6
5.4	Figure 5.4: Time taken by the polymer melt to fill the sprue and runner system	5.7
5.5	(a) A single gated mold with pressure (end of fill) of 61.31 MPa (b) Pressure contour indicating location of pressure variation	5.9
5.6	(a) A double gated mold with pressure (end of fill) of 60.73 MPa (b) Pressure contour indicating location of pressure variation	5.10
5.7	Pressure variation for single and double gates at similar pressure points	5.11
5.8	Temperature results for (a) Single injection location (b) double injection location	5.14
5.9	Area of shear stress for single and double injection location	5.15
5.10	Location of air traps for single and double injection location	5.16
5.11	Locations of weld lines for single and double injection location	5.18
5.12	(a) Average fiber orientation for single gated mold. (b) Average fiber orientation for double gated mold	5.20
5.13	Fibers are highly oriented at the edges and reduces as it moves inwards	5.21
6.1	Components of two plate mold	6.3
6.2	Layout of insert blocks and mold parting line	6.4
6.3	Clutch pedal mold assembly	6.5

6.4	Location of ejector pins	6.5
6.5	Location of runner system and gates	6.6
6.6	Mounted mold set	6.6
6.7	Basic diagram of injection molding machine (Strong, 2000)	6.7
6.8	Injection molding machine, Kawaguchi 265	6.8
6.9	(a) Samples produced at temperature of T1 (290 °Celsius) (b) Samples produced at T2 (315 °Celsius)	6.10
6.10	Burnt marks for samples produced at (a) T1 and (b) T2	6.10
6.11	Samples produced at (a) low speed and (b) high speed	6.13
6.12	Actual automotive clutch pedal fabricated from steel	6.13
6.13	Actual model of glass fiber reinforced PA 6,6 composite automotive clutch pedal	6.13
6.14	Simulated model of glass fiber reinforced PA 6,6 composite automotive clutch pedal	6.14
6.15	Location of weld line in the simulated model	6.14
6.16	The location of weld line (indicated by the white line)	6.15
6.17	Locations of trapped air in the simulated model	6.16
6.18	Locations of burnt mark	6.16

**LIST OF ABBREVIATIONS**

S <sub>g</sub> FRIMT	Short glass fiber reinforced injection molded thermoplastic
MPI	Moldflow Plastic Insight
LUSAS	Finite element analysis software
PA (6,6)	Polyamide 6,6
SGFRP	Short Glass Fiber Reinforced Polyamide
$f_p$	Distribution of fiber orientation
EDM	Electric Discharge Machining (EDM) Machine
CNC	Computer Numerical Control
NC	Numerical Control

# CHAPTER 1

## INTRODUCTION

### 1.1 Overview

The last twenty years have seen an escalating interest in fiber reinforced polymeric based composite. This is due to its high strength to weight ratio, dimensional stability and resistance to heat, cold, moisture and corrosion. Polymeric based composite offers potential for lower conversion costs from intermediate material forms into final end-use parts by process automation and indefinite storage life that facilitates the logistics of the manufacturing procedure (Sapuan and Sharuddin, 2003).

For various reasons, many composites are reinforced by short fiber instead of continuous fiber. Matthew and Rawlings (1994) explained that continuous fibers are more expensive than other forms of reinforcement. Furthermore the manufacturing processes for continuous fiber reinforced composites tend to be slow and inflexible. For instance, processing techniques such as hand lay up, filament winding and autoclave are suitable for short runs or one off requirements of high performance high-priced products.

Finally, such interest is also caused by the advent of computer simulation packed with a multitude of analysis programs. Engineers no longer do the task of product analysis and product design separately; instead the task has been integrated

and can be done simultaneously by a sole engineer. Furthermore these user- friendly analysis programs permit a designer to evaluate not only the form and function of a design but also the manufacturability of that design at the early stage in the design cycle (Reifschneider, 2000). This concurrent design approach is essential for polymeric based composite since processing affects fiber orientation distribution, which in turn greatly affects the mechanical properties of the composite.

This product design approach has replaced much of the prototyping of the past. This is preferable since it reduced the rework involved in product design, time and cost of production. The use of such analysis programs by product designers is one of the latest developments in the time compression trend within manufacturing (Reifschneider, 2000).

## **1.2 Problem Statement**

In previous years, many injection-molded molds have been designed by mold makers based on their intuition and experience alone. It is also a common practice that molds are made on iterative basis in which product prototypes are produced repetitively in order to identify mold problems. Hence the correlation between product design and mold design are mostly overlooked or ignored. Such tendency creates problems in which parts become overly designed and an increase in manufacturing time. This product development scenario is not acceptable since future global demands require shorter transformation time from on paper design into market.

Due to this scenario, it is hoped that this simulation study will shed some light on the relation between product design and mold design, product quality and ease of manufacturability especially for composite products. A study of injection numbers and locations is important since it easily affects product quality such as weld line and air trap formation; fill time and fiber orientation distribution. This study is also important since unlike other processing parameters such as filling speed, pressure and temperature that could be modified instantly, the gate location is permanent and any modification equals to increase in cost and time. Furthermore, works pertaining to relationship between design of injection mold and product process and product quality is still scarce especially for glass fiber reinforced composite automotive clutch pedal.

Finally, such study is also aligned with the current worldwide needs to reduce human dependency on steel due to depleting ore resources and unstable market price. Thus more steel products have been designed from polymer composite. Such approach also benefits the automotive industry since it improves fuel economy by reducing the weight of automotive parts. This is achievable with the use of strong, lightweight polymer composites.

### **1.3 Objectives of the Research**

The main objective of the research is to simulate and analyze the effects of increasing number of gates for a clutch pedal mold using short glass fiber reinforced polyamide 6,6 (PA 6,6). This study involves the use of two finite element analysis softwares, LUSAS and Moldflow Plastic Insight (MPI). MPI software is used

extensively to investigate the effects of mold design on fill time, pressure, temperature, weld line, air traps and fiber orientation and distribution while LUSAS software is used to a lesser extent to analyze stress distribution for pedal profiles and rib patterns.

The clutch pedal is then fabricated using injection molding. The resultant model is then compared with the simulation results.

Thus the overall objectives of this research can be simply summarized as follows:

1. To design a short glass fiber reinforced polyamide 6, 6 clutch pedal for injection molding. The design process also involves comparison study between “V” and “X” rib based on:
  - Stress
  - Weight
  - Fill time
  - Pressure
  - Air Trap
  - Weld line
  - Average fiber orientation
  - Cost
  - Ease of manufacturing
2. To study the effects of gating number on:
  - fill time
  - pressure distribution



- temperature
- weld line
- air traps
- fiber orientation distribution

3. To compare simulated results and actual product

#### **1.4 Scope and Structure of Work**

The first chapter presents the background for this research which includes a brief introduction to short glass fiber reinforced injection molded thermoplastic (S<sub>g</sub>FRIMT), objectives and significance of this study. The structure of the study is given in Figure 1.1. The study undertaken involves the use of LUSAS and MPI Software for analysis.

Chapter 2 discusses briefly literatures related to mechanical property, design, manufacturing and mold considerations for polymeric based composites in accordance with their importance and relevance.

Chapter 3 outlines the overall simulation plan and procedures. This chapter also includes a description of the software tools used to carry out the simulation analysis.

Chapter 4 describes the preliminary design results from MPI and LUSAS simulations namely on clutch pedal profiles (“I” and “T” sections) and rib designs