

Technical University of Denmark



## Measured resolved shear stresses and active slip systems in austenitic steel

Winther, Grethe; Juul, Nicolai Ytterdal; Oddershede, Jette

*Publication date:*  
2017

*Document Version*  
Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

*Citation (APA):*

Winther, G., Juul, N. Y., & Oddershede, J. (2017). Measured resolved shear stresses and active slip systems in austenitic steel. Abstract from 18th International Conference on Textures of Materials (ICOTOM 18), St. George, Utah, United States.

### DTU Library

Technical Information Center of Denmark

---

#### General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

## Measured resolved shear stresses and active slip systems in austenitic steel

G. Winther<sup>1</sup>, N. Ytterdal Juul<sup>1</sup> and J. Oddershede<sup>2</sup>

<sup>1</sup>*Department of Mechanical Engineering, Technical University of Denmark, Kgs. Lyngby, Denmark.*

<sup>2</sup>*Xnovo Technology ApS, Køge, Denmark.*

With the purpose of determining the critically stressed slip systems in a tensile deformed austenitic stainless steel, the full stress tensor is measured for 150 individual bulk grains using 3DXRD microscopy at CHESS. The measured stress states are further compared to the theoretical Bishop-Hill states. In the elastic regime, the resolved shear stresses exhibit quite large variations between grains of similar orientation. On average, however, the resolved shear stresses agree well with the Schmid factors for uniaxial tension. In the plastic regime at 1% elongation, about half of the grains were close to a Bishop-Hill state. The orientation dependence of the Bishop-Hill state was, however, not exactly as expected. The other half of the grains was closer to the applied uniaxial stress, in between two Bishop-Hill stress states, or in some cases none of these. Comparison to finite-element crystal plasticity simulations only qualitatively agree.