

Секция 7. Химия и химическая технология на иностранном языке

According to the results of the tests, only the sample number 2 meets the requirements of USS 305-2013 "Diesel fuel. Technical Specifications"

References

1. USS 2177-99 "Petroleum products. Methods for determination of distillation characteristics".
2. USS 3900-85 "Petroleum and petroleum products. Methods for determination of density".
3. USS 32139-2013 "Petroleum and petroleum products. Determination of sulfur content by method of energy dispersive X-ray fluorescence spectrometry".
4. USS 33-2000 "Petroleum products. Transparent and opaque liquids. Determination of kinematic viscosity and calculation of dynamic viscosity".
5. USS R ISO 8178-5-2009 "Reciprocating internal combustion engines. Exhaust emission measurement. Part 5. Test fuels".
6. USS 27768-88 "Diesel fuel. Determination of cetane index by calculation method".
7. USS 305-2013 "Diesel fuel. Technical Specifications".

[7] for all properties that have been investigated, and can be used as commercial diesel fuel.

NICKEL COATINGS OBTAINED FROM NON-AQUEOUS ELECTROLYTES FOR HIGHLY SOLUBLE PCMS

M.J. Cruz¹, D.S. Kharitonov²

Scientific supervisor – assistant I.V. Makarova²

¹Department of Chemical Engineering and Mineral Processing and Center for Advanced Study on Lithium and Industrial Minerals (CELIMIN), University of Antofagasta

²Belarusian State Technological University
Sverdlova 13a str., antihovich.irina@gmail.com

In last decade a significant interest in the application of phase change materials (PCMs) systems has been growing, since latent heat storage systems can provide high storage capacity and isothermal behaviors [1]. However, all PCMs can react with aqueous solutions meaning the porous shell material is not good barrier for protection of PCM core from being dissolved in aqueous solution. Thus, changing of solvent [2, 3] makes it possible to obtain metal shell on the salt surface. This work proposes the technique of encapsulating the PCM core in a metal structure shell (macroencapsulation).

Sodium nitrate has been chosen as the PCM (Sociedad Química y Minera de Chile). The procedure of obtaining the core-shell structure was as follows: Sodium nitrate was first coated with hydrophobic layer, then with graphite and, finally, with copper from standart sulphate bath ($\text{CuSO}_4 \cdot 5\text{H}_2\text{O}$ 200 g/dm³, H_2SO_4 100 g/dm³). Top nickel layer was electrodeposited using aqueous and ethanol bathes. The main compounds of electrolytes were $\text{NiCl}_2 \cdot 6\text{H}_2\text{O}$ (200 g/dm³), HCl (0,11 mol/dm³). The density of ethanol was 0.8 g/cm³. Electrodeposition was performed at 50 °C using a current density of 2.5 A/dm².

Cathodic polarizations curves in non-aqueous and aqueous solvents were obtained by linear polar-

ization with potential scan rate of 0.005 V/s. Linear Tafel ranges ($\eta = a + b \log i$) of polarization curves corresponded to the charge transfer were used as a rate-determining step of Ni^{2+} reduction. The slopes of the linear regions were 0.12±0.001 V/dec and 0.10±0.001 V/dec for the non-aqueous and aqueous bathes, respectively. The determined slopes values differed slightly from the theoretical value (0.12 V/dec) and indicates electrochemical stage as being the limiting one. Nickel electrodeposition onto copper substrate in presence of different solvents does not significantly change the b value indicating the charge transfer reaction is not controlled by the type of solvent.

It was found by the thermokinetic method that in the overpotential range from 0.1 to 0.4 V the process is limited by the electrochemical stage. There was a tendency of decreasing the effective activation energy at overpotential of 0.4 V by 40 kJ/mol when the aqueous solvent is replaced by a non-aqueous. In the overpotential region of 0.5–1.5 V, the value of the activation energy depends on the change of the potential, which may indicate diffusion as the limiting stage.

It is established that the current efficiency gradually decreases with increasing of the current density. Current efficiency in non-aqueous bath was

Table 1. Properties of nickel coatings obtained from aqueous and non-aqueous solutions

		Aqueous electrolyte	Non-aqueous electrolyte
Microhardness, HV		483	550
Porosity, pores on cm ² (thickness of Ni 6/9/15 μm)		30/19/15	28/24/21
Microroughness R _a , nm / Maximum height, nm on the surface with dimensions of	20×20 μm	188/1680	164/1780
	4×4 μm	35/310	54/470
	0.8×0.8 μm	19.8/170	31.7/282

20% higher than in aqueous one and indicates the occurring of the secondary reaction of hydrogen evolution.

Solvent plays a great role in the appearance of electrodeposited nickel coatings. Those obtained from non-aqueous and aqueous bathes have dark grey color and light grey color, respectively. Both solvents allow to obtain uniform coating with good adhesion. Nickel coating deposited from aqueous bath had a lot of small defects in form of pitting. The initiation of pits on the cathode surface can be attributed to the formation of hydrogen bubbles on the cathode surface, which adheres to the surface of the deposit. This, in turn, limits the deposition of metal at that point and the metal deposit continues to grow around it resulting in a pit at the location of the bubble. Due to it is coating is uneven. All the nickel coatings were found to be free from pores and cracks with nearly smooth surfaces.

References

1. Sharma S.S., Sagara Kazunobu // *International Journal of Green Energy*, 2005.– V.2.– P.1–56.
2. K. Neuróhr, L. Pogány, B.G. Tóth, A. Révész, I. Bakonyi, L. Peter // *Journal of Electrochemical Society*, 2015.– V.162(7).– P.D256–D264.
3. D. Thiemig, A. Bund // *Applied Surface Science*, 2009.– V.255.– P.4164–4170.

PROPERTIES STUDY OF POLYMERIC PETROLEUM RESINS THAT CONTAIN A NITROGEN GROUP

S.I. Gamzatova, L.A. Mikheeva

The research adviser is Candidate of Chemical Sciences, Associate Professor L.I. Bondaletova

National Research Tomsk Polytechnic University
634050, Russia, Tomsk, 30 Lenin Avenue, snezhana.gamzatova@gmail.com

Most petrochemical plants generate significant amounts of intermediate products and by-products of refining, which do not find adequate application. Some of the by-products continue to be waste, whereas other could be used as raw stock to obtain new substances and materials. These by-products consist of fraction of liquid pyrolysis products, which are used for production of petroleum polymer resins (PPR_s).

The EDX analysis revealed that the deposited layer consists of pure Ni. Besides Ni, only Cu was found as a major constituent which belonging to the substrate. XRD analysis revealed stable fcc crystal structure of Ni. AFM analysis showed a surface spotted with relatively large, flat or pyramidal crystals, above a layer of roundish particles with a maximum height 1680 nm suggesting that crystal growth from non-aqueous bath occurs with fast nucleation, followed by a preferential growth on active sites. Changing of solvent strongly modifies the growth characteristics and the crystal habit. On the surface appears sharp grains.

Main properties of nickel coatings obtained from aqueous and non-aqueous solutions are shown in Table.

Kinetic features and properties of nickel coatings were established during electrodeposition from electrolytes with various solvents.

In this work, C₉ fraction and dicyclopentadiene fraction (DPF) are the raw stock for PPR_s. The fraction C₉ consists of saturated hydrocarbons, such as benzene, toluene, xylene, propylbenzene, ethylbenzene, ethylmethylbenzene and unsaturated hydrocarbons, such as cyclopentadiene, styrene, vinyltoluene, α-methylstyrene, β-methylstyrene, dicyclopentadiene, methylcyclopentadiene, and indene [1]. DPF fraction also include saturated and