

PDF hosted at the Radboud Repository of the Radboud University Nijmegen

The following full text is a preprint version which may differ from the publisher's version.

For additional information about this publication click this link.

<http://hdl.handle.net/2066/83810>

Please be advised that this information was generated on 2017-12-06 and may be subject to change.

A theoretical analysis of the chemical bonding and electronic structure of graphene interacting with Group IA and Group VIIA elements

M. Klintonberg,^{1,*} S. Lebègue,² M. I. Katsnelson,³ and O. Eriksson¹

¹ *Department of Physics and Materials Science, Uppsala University, Box 530, SE-75121, Uppsala, Sweden*

² *Laboratoire de Cristallographie, Résonance Magnétique et Modélisations (CRM2, UMR CNRS 7036) Institut Jean Barriol, Nancy Université BP 239, Boulevard des Aiguillettes 54506 Vandoeuvre-lès-Nancy, France*

³ *Institute for Molecules and Materials, Radboud University Nijmegen, Heyendaalseweg 135, NL-6525 AJ, Nijmegen, The Netherlands*

(Dated: January 21, 2010)

We propose a new class of materials, which can be viewed as graphene derivatives involving Group IA or Group VIIA elements, forming what we refer to as graphXene. We show that in several cases large band gaps can be found to open up, whereas in other cases a semimetallic behavior is found. Formation energies indicate that under ambient conditions, sp^3 and mixed sp^2/sp^3 systems will form. The results presented allow us to propose that by careful tuning of the relative concentration of the adsorbed atoms, it should be possible to tune the band gap of graphXene to take any value between 0 and 6.4 eV.

PACS numbers: 71.15.-m, 71.15.Mb, 71.20.Nr

A new derivative of graphene was recently reported[1], where hydrogenation turned graphene, a recently discovered two-dimensional C based material,[2–6] into what is referred to as graphane. This compound was actually studied theoretically before the material was synthesized, and the materials phase stability as well as electronic properties (in particular the presence of a gap) were predicted from first principles theory[7, 8]. In the GGA-based calculations of Ref.7, 8 it was found that graphane has every C atom attached to a H atom, and that the H atoms are bonded alternating on both sides of the C layer. Furthermore, it was found that graphane is a semiconductor with a rather wide energy gap (3.5 eV). Subsequent calculations based on the GW approximation,[9, 10] which are supposed to result in more accurate band gaps, reported on a gap-value of 5.2 eV.[11]

In the experimental study[1] graphane was indeed found to have a band gap of the electron states. Hence, it was demonstrated that the adsorption of hydrogen turned highly conductive graphene into insulating graphane. The reason a band gap opens up when hydrogen is adsorbed on graphene is that sp^2 bonded C atoms can achieve a higher degree of sp^3 bonding. In this case three of the four covalent sp^3 bonds are saturated by C atoms and the fourth covalent bond is saturated by an H atom. The reason for the change in conductivity is in accordance to expectations for sp^3 bonded carbon (e.g. diamond), which is an insulator. On an electronic structure level the transition to an insulator is connected to the fact that the p_z orbitals, which in graphene form conducting states (called π and π^*) at the Fermi level, participate in graphane in strong covalent σ bonds, with a gap between bonding and anti-bonding states. This finding is illustrated in the theoretical work

of Refs.1, 7 and from the adsorption of single hydrogen atoms on graphene.[12] Moreover, in Ref. 13, the scattering of electrons in graphene by clusters of impurities is studied and for reviews on experimental work on alkali metals on graphite, see Refs. 14–17.

The possibility to open up a band gap in graphene derivatives, like graphane, is very important when considering the potential of this material for electronics applications. A natural question which then arises is if other atomic species of the Group IA elements can produce a similar behavior, potentially with a slightly smaller band gap, which is more suitable for electronics applications. It is also possible that Group VIIA atoms can adsorb on graphene, to form sp^3 bonds with the C atoms and with a gap in the electronic structure. For the case of single impurities, the difference in chemical bonding has been analyzed in Ref. 18. It was found that alkali metals (except Li) form purely ionic bonds, with very small difference in total energies between different positions (on the top of a carbon atom, in the middle of the bridge between two C atoms, in the center of a C-hexagon), and the same for halogens (except F). This seems to be in agreement with the present results on complete coverage. We have here investigated the possibility of a gaped electronic structure by performing ab-initio calculations of the geometry and electronic structure for the Group IA and Group VIIA elements adsorbed on graphene, and we will refer to this new material as graphXene (where X represents a Group IA or Group VIIA element). The theoretical calculations have been done using the generalized gradient approximation (GGA) and the GW approximation. For simplicity we have only considered the so called chair geometry[7] in our calculations, i.e. with one adatom attached on each C atom, alternating being above or below the C atoms (for a figure of the geome-

try see Fig.1 of Ref.7). We have considered several cases, for instance with Group IA elements on both sides of the C network, and with Group VIIA elements on both sides of the C network. We have also considered mixed cases where Group IA atoms are above the C network and Group VIIA atoms are below the C network.




FIG. 1: (Color online) Geometry of the C - X bonding (X is a Group IA or Group VIIA element, yellow atom, C atoms are blue). The bond-angles for the C-C and C-X bond are defined as ϕ_{C-C} and ϕ_{C-X} , respectively.

We have used the VASP[19] (Vienna Ab-initio simulation package), implementing the projector augmented waves (PAW) method[20], to compute the ground state geometry and the electronic structure. We obtained a reliable geometry of the structure by optimizing atomic positions, using the generalized gradient approximation (GGA). For all the calculations, we have used a 500 eV cut-off for the wavefunction. During the optimization of the structures, a k-point grid[21] of $12 \times 12 \times 1$ was used.

Density functional theory (DFT) is a ground-state theory and can therefore not treat excited states. [22] Equally important is that DFT does not differentiate between the two potentials V_{N-1} and V_N that should be seen by occupied- and unoccupied states, respectively. Moreover, self-interaction is not included and V_{XC} does not include non-local effects nor energy- and electron density dependencies. To calculate accurate band gaps a more reliable method is needed and here we use the all-electron GW implementation based on the FP-LMTO method by Ref.23. The GW approximation of Hedin[9, 10] can be derived in a systematic way from many-body perturbation theory, and it is common to take an LDA or GGA calculation as the starting point. The result from the theoretically complex derivation is

$$E_{i,k}^{QP} = E_{i,k}^{LDA} + \langle i, k | \Sigma(E_{i,k}^{QP}) - V_{XC}^{LDA} | i, k \rangle$$

which is the quasi-particle energy resulting from first order perturbation expansion of an operator, that is

made from the difference between the self-energy operator ($\Sigma = iGW$) and the LDA exchange-correlation potential (V_{XC}^{LDA}). G and W is the LDA Green's function and screened Coulomb interaction, respectively. W is related to RPA polarization via the dielectric function. In this work a one-shot GW is used and we have

$$E_{i,k}^{QP} = E_{i,k}^{LDA} + Z_{i,k} \langle i, k | \Sigma(E_{i,k}^{LDA}) - V_{XC}^{LDA} | i, k \rangle$$

The quasi-particle renormalization factor $Z_{i,k}$ is given by

$$Z_{i,k} = \frac{1}{1 - \langle i, k | \frac{\partial}{\partial \omega} \Sigma(E_{i,k}^{QP}) | i, k \rangle}$$

and is around 0.9 in our calculations.

There are several reviews of the GWA method in the literature [24–27]. Consensus is that GWA improve the bandgap of semiconductors and insulators and the calculated GWA bandgap is often within 10% of experiment.

In general one may expect that depending on the element which is attached to the C atom of the graphene network, a varying degree of sp^3 and sp^2 bonding will occur. The best way to characterize the degree of sp^3 or sp^2 bonding may be to use the bond angles between C-C of the graphene network as well as the bond angle between the adatom and the C atoms, i.e. the C-X angle. These angles are shown in Fig.1, where the C-C angle is labeled ϕ_{C-C} and the C-X angle is labeled ϕ_{C-X} . For a purely sp^2 bonded system ϕ_{C-C} is 120 degrees and ϕ_{C-X} is 90 degrees. For a purely sp^3 bonded system ϕ_{C-C} is the same as ϕ_{C-X} , with a value of ~ 109.5 degrees. For intermediate cases one will observe bond angles somewhere in between these two extreme cases.

In Table I we list the calculated bond angles for all the systems investigated in this study. It may be seen that elemental adsorption with the same chemical species on both sides of the graphene sheet produce a situation with ideal sp^2 bonding for Cl, Br and I adsorption. In the cases of adsorption of Na, K, Rb and Cs one observes a chemical bonding which is almost of pure sp^2 , whereas for Li one observes an even mixture between sp^3 and sp^2 bonding. When H or F are adsorbed, bonds which are mostly of sp^3 character are observed. Among the mixed systems, the combination of H on one side and F on the other side, or Cl on the other side, produce a situation with dominant sp^3 bonding. We will below refer to these cases as HF and HCl adsorption, respectively. A combination of Li and F, as well as Li and H, results in similar scenarios, but with a higher degree of sp^2 bonding. It is interesting to note that Li and H, and possibly Li and F appear to be semi-metals. Judging from Table I, we speculate that the transition in bond angle from semiconducting (or insulating) to semi-metallic is at around 114° for the C-C-C bond. Finally we note that a combination of H and Br produce a situation which reflects a bonding closer to pure sp^2 character.

C ₂ XY	(a)	CC	CX	CY	Φ_C	Φ_X	bond type	Gap GGA	Gap GW	E ^F
C ₂ H ₂	2.54	1.54	1.11		111	107	sp ³	3.49	5.74	-0.11
C ₂ Li ₂	2.58	1.53	2.02		116	77	mix	wm		-0.64
C ₂ Na ₂	2.67	1.54	2.63		120	88	sp ²	m		0.08
C ₂ K ₂	2.82	1.65	2.67		118	81	sp ²	m		0.97
C ₂ Rb ₂	2.86	1.67	3.01		118	81	sp ²	m		1.29
C ₂ Cs ₂	2.94	1.72	2.92		118	82	sp ²	m		1.79
C ₂ F ₂	2.61	1.58	1.38		111	108	sp ³	3.10	7.4	-0.81
C ₂ Cl ₂	2.57	1.47	3.81		121	90	sp ²	m		0.41
C ₂ Br ₂	2.69	1.55	4.18		120	90	sp ²	m		0.58
C ₂ I ₂	2.87	1.66	3.99		120	90	sp ²	m		1.21
C ₂ HF	2.57	1.56	1.10	1.39	111	108	sp ³	3.11	6.38	-0.47
C ₂ HCl	2.77	1.66	1.10	1.76	112	107	sp ³	0.87	2.91	0.41
C ₂ HX ^a	2.65	1.60	1.39	1.80	112	107	sp ³	0.26		-0.08
C ₂ HBr	2.68	1.57	1.13	3.70	118	98	sp ²	m		0.72
C ₂ LiF	2.59	1.55	2.16	1.44	114	105	mix	wm		-0.39
C ₂ LiH	2.58	1.53	2.19	1.14	115	104	mix	sm	0.30 ^b	0.01

^aX=Cl, F alloyed 50-50

^bUsing GGA gives semi-metallic behavior for C₂LiH and with the GW correction a small in-direct gap opens up between K (VB) and Γ (CB).

TABLE I: Geometrical and electronic structure data for all systems examined. Bond distances are given in [\AA], angles in [$^\circ$], lattice constant (a) in [\AA], gap energies in [eV], and formation energy in eV/atom. Interatomic bond lengths are denoted C-C between carbon atoms and C-X (or C-Y) for other bond distances. The systems that show a band gap are all direct gap. C₂LiH is a semi-metal (sm), C₂LiF is a borderline case sm/weak-metal and rest are metallic (m) or weak-metals (wm) at the GGA level.

The energy of formation (E^F in Table I) is calculated using $E^F = E_t(\text{graphXene}) - E_t(\text{graphene}) - E_t(X) - E_t(Y)$ where E_t is the total energy, graphXene=C₂XY where X,Y is one of H, Li, K, Na, Rb, Cs, F, Cl, Br or I. Note that $E_t(\text{graphene})$ is the total energy per unit cell, i.e. for two C atoms. It is seen from Table I that all sp³ systems except C₂HCl have negative energies of formation, indicating that the compounds will form. The material C₂HCl will form if alloyed with 50% F (lower F concentrations have not been investigated).

Moreover, if the reference state of the X or Y atoms is not the gas phase at ambient conditions, but a gas phase at elevated pressure (P) and temperature (T), a term proportional to $k_B T \ln P$, enters the expression for the free energy, in such a way as to stabilize the phase with X and Y adsorbed on the graphene layer[28]. Hence it is possible to stabilize some of the materials listed in Table I, even if $E^F > 0$.

In the cases with dominant sp³ bonding it is expected that a gap opens up, whereas for the intermediate cases the situation is less clear. The electronic structures of the presently studied systems show that a band gap opens up for H adsorption on both sides of the carbon layer as well as for F adsorption on both sides. The band structure of H adsorption has been shown before[7] and for this




FIG. 2: (Color online) Band structure of graphene with F on both sides of the C layer, in a chair geometry using GGA. Circles show the GW corrected energies. The rigid shift of the unoccupied states is seen when the lowest GGA conduction band is plotted but shifted to fit the GW values (dotted line with crosses).




FIG. 3: (Color online) Band structure of graphene with H on one side and F on the other of the C layer, in a chair geometry, using GGA theory. Circles show the GW corrected energies. The rigid shift of the unoccupied states is seen when the lowest GGA conduction band is plotted but shifted to fit the GW values (dotted line with crosses).

reason we do not repeat this electronic structure here. However, we show the calculated energy bands of F adsorption in Fig.2. The general shape of the energy band structure is the same for the GGA and GW calculation, except for a nearly rigid shift of the unoccupied states in the GW calculation, so as to open up a larger band gap. This nearly *rigid* shift is illustrated in Fig.2 (for F on both sides of the graphene layer) and Fig.3 (for F on one side and H on the other side of the graphene layer),

by comparing quasi-particle GW-energies (circles) with the energies obtained by shifting rigidly the bottom of the conduction band from the GGA calculation (crosses). Both materials show a shifted GGA band structure which coincides with the GW bands. This shift is in accordance with Fig. 1 (for diamond) of the ground-breaking paper by Hybertsen and Louie [29]. An additional evidence for the nearly rigid shift in the GW calculation is illustrated in Fig. 4, which shows the quasi-particle energies plotted against the Kohn-Sham eigenvalues for C_2HF . From least-squares fitting (full lines) the valence bands and conduction bands are found to have the slopes 1.00 and 1.14, respectively. A slope of 1.0, with no scatter of the data around the fitted line, would indicate a perfect rigid shift for electron states of any k-point, and the data in Fig.4 gives good evidence for that the GW states are shifted more or less rigidly.




FIG. 4: (Color online) Quasi particle energies plotted against the Kohn-Sham eigenvalues for C_2HF . The full lines show the least squares fit for the valence bands (VB) and conduction bands (CB), respectively.

For the adsorption with different chemical species on the two sides of the C layer, both H-C-F and H-C-Cl are found to display band gaps. Since the two materials have electronic structures which are rather similar, we show only the GGA electronic structure of H-C-F in Fig.3. The H-C-F system has a direct, 3.11 eV band gap, as is seen from Fig.3. In GW theory this band gap is 6.38 eV. The H-C-Cl case results in a smaller direct, band GGA gap of 0.87 eV, which opens up to 2.91 eV from GW theory. Therefore, a whole range of bandgaps can be induced in graphene by carefully choosing the chemical species of the adatoms. One can even go further by using not only two kind of dopants, but three: the alloyed structure H-C-(Cl_{1/2}F_{1/2}), gives a GGA gap of 0.26 eV, which is very different from 0.87 eV of H-C-Cl and 3.11 eV of H-C-F. This result demonstrates that the relationship between the different elements concentration and the bandgap is

non trivial, but on the other hand, this leads to more flexibility to obtain the desired value for the band gap, a key quantity in view of using graphene in electronic devices.

In conclusion, we have demonstrated, using accurate GGA and GW calculations, that a reasonable band gap can be opened up for graphene derivatives with Group IA and Group VIIA elements, forming a new class of materials we refer to as graphXene. Depending on adatoms, graphXene forms sp^2 bonds, sp^3 bonds or a mixed sp^2/sp^3 binding. Several of the proposed materials have formation energies which suggest a stable configuration, where in general the sp^3 and mixed sp^2/sp^3 systems should be experimentally observed. We point out that although not all systems investigated here have a formation energy at ambient conditions which suggests that they should form, it is likely that elevated temperature and pressure will stabilize them.

The most important conclusion of our study is that a careful mixing of different dopants of the graphene layer enables a tuning of the band gap from 0 to ~ 6.4 eV, a result which has obvious technological ramifications. For the sp^3 bonded, gaped systems, the C-C-C angle is close to 109.5° . For the sp^2 bonded systems the C-C-C angle is 120° , or just below this value. The intermediate cases are semi-metallic and we speculate that the semiconducting (insulating) \rightarrow semi-metallic transition appears for a C-C-C angle which is around 114° .

M.K. and O.E. acknowledges support from the Swedish Research Council (VR), Swedish Foundation for Strategic Research (SSF), the Swedish National Allocations Committee (SNIC/SNAC), and the Göran Gustafsson Stiftelse. O.E. also acknowledge support from ERC. S. L. acknowledges financial support from ANR PNANO Grant ANR-06-NANO-053-02 and ANR Grant ANR-07-BLAN-0272, and GENCI-CINES/CCRT for computer time.

* Mattias.Klintenberg@fysik.uu.se (Corresponding author)

- [1] D. C. Elias et al. Science **323**, 610 (2009).
- [2] K. S. Novoselov et al, Science **306**, 666 (2004).
- [3] A. K. Geim and K. S. Novoselov, Nature Mater. **6**, 183 (2007).
- [4] M. I. Katsnelson, Mater. Today **10**, 20 (2007).
- [5] A. H. Castro Neto, F. Guinea, N. M. R. Peres, K. S. Novoselov, and A. K. Geim, Rev. Mod. Phys. **81**, 109 (2009).
- [6] M. I. Katsnelson, K. S. Novoselov, and A. K. Geim, Nature Phys. **2**, 620 (2006).
- [7] J. O. Sofo, A. S. Chaudhari, and G. D. Barber, Phys. Rev. B **75**, 153401 (2007).
- [8] D. W. Boukhvalov, M. I. Katsnelson, and A. I. Lichtenstein, Phys. Rev. B **77**, 035427 (2008).
- [9] L. Hedin, Phys. Rev. **139**, A796 (1965).
- [10] L. Hedin and S. Lundquist, in *Solid State Physics*, edited

- by H. Ehrenreich, F. Seitz, and D. Turnbull (Academic, New York, 1969), Vol. 23, p. 1.
- [11] S. Lebegue, M. Klintonberg, O. Eriksson, M. I. Katsnelson, Phys. Rev. B **79**, 245117 (2009).
- [12] O. Wessely, M. I. Katsnelson, A. Nilsson, A. Nikitin, H. Ogasawara, M. Odellius, B. Sanyal and O. Eriksson, Phys. Rev. B **76**, 161402(R) (2007).
- [13] M. I. Katsnelson, F. Guinea and A. K. Geim, Phys. Rev. B **79**, 195426 (2009).
- [14] R. D. Diehl and R. McGrath, Surf. Sci. Rep. **23**, 43 (1996).
- [15] C. Binns, S. H. Baker, C. Demangeat, and J. C. Parlebas, Surf. Sci. Rep. **34**, 107 (1999).
- [16] D. Q. Yang and E. Sacher, Surf. Sci. **516**, 43 (2002).
- [17] M. Caragiu and S. Finberg, J. Phys.: Condens. Matter **17**, R995 (2005).
- [18] T. O. Wehling, M. I. Katsnelson, A. I. Lichtenstein, arXiv:0903.2006.
- [19] G. Kresse and D. Joubert, Phys. Rev. B. **59**, 1758 (1999).
- [20] P. E. Blöchl, Phys. Rev. B **50**, 17953 (1994).
- [21] H. J. Monkhorst and J. D. Pack, Phys. Rev. B **13**, 5188 (1976).
- [22] P. Hohenberg and W. Kohn, Phys. Rev. B **864**, 136 1964 ; W. Kohn and L. J. Sham, *ibid.* A **1133**, 140 1965 .
- [23] T. Kotani and M. van Schilfhaarde, Solid State Commun. **121**, 461 (2002).
- [24] F. Aryasetiawan and O. Gunnarsson, Rep. Prog. Phys. **61**, 237-312 (1998).
- [25] W. G. Aulbur, L. Jönsson, and J. W. Wilkins, 'Quasiparticle calculations in solids', in Solid State Physics; edited by H. Ehrenreich and F. Spaegen, vol **54**.
- [26] G. Onida, L. Reining, and A. Rubio, Rev. Mod. Phys. **74**, 601 (2002).
- [27] F. Aryasetiawan, "Advances in Condensed Matter Science;" edited by I. V. Anisimov (Gordon and Breach 2000).
- [28] See e.g. T. Wassmann, et al. Phys. Rev. Lett. **101**, 096402-1 (2008).
- [29] M. S. Hybertsen and S. G. Louie, Phys. Rev. B **34**, 5390 (1986).