

ID Design Press, Skopje, Republic of Macedonia
 Open Access Macedonian Journal of Medical Sciences. 2018 Sep 25; 6(9):1742-1755.
<https://doi.org/10.3889/oamjms.2018.378>
 eISSN: 1857-9655
Dental Science - Review



Contemporary Dental Ceramic Materials, A Review: Chemical Composition, Physical and Mechanical Properties, Indications for Use

Emilija Bajraktarova-Valjakova^{1*}, Vesna Korunoska-Stevkovska¹, Biljana Kapusevska¹, Nikola Gigovski¹, Cvetanka Bajraktarova-Misevska¹, Anita Grozdanov²

¹Faculty for Dental Medicine, Ss Cyril and Methodius University of Skopje, Skopje, Republic of Macedonia; ²Faculty of Technology and Metallurgy, Ss Cyril and Methodius University of Skopje, Skopje, Republic of Macedonia

Abstract

Citation: Bajraktarova-Valjakova E, Korunoska-Stevkovska V, Kapusevska B, Gigovski N, Bajraktarova-Misevska C, Grozdanov A. Contemporary Dental Ceramic Materials, A Review: Chemical Composition, Physical and Mechanical Properties, Indications for Use. Open Access Maced J Med Sci. 2018 Sep 25; 6(9):1742-1755. <https://doi.org/10.3889/oamjms.2018.378>

Keywords: CAD/CAM; Chemical composition; Glass-ceramics; Mechanical properties; Resin-matrix ceramic; Zirconia

***Correspondence:** Emilija Bajraktarova-Valjakova, Faculty for Dental Medicine, Ss "Cyril and Methodius University" of Skopje, Skopje, Republic of Macedonia. E-mail: emibaj@yahoo.com

Received: 12-Aug-2018; **Revised:** 08-Sep-2018; **Accepted:** 09-Sep-2018; **Online first:** 24-Sep-2018

Copyright: © 2018 Emilija Bajraktarova-Valjakova, Vesna Korunoska-Stevkovska, Biljana Kapusevska, Nikola Gigovski, Cvetanka Bajraktarova-Misevska, Anita Grozdanov. This is an open-access article distributed under the terms of the Creative Commons Attribution-NonCommercial 4.0 International License (CC BY-NC 4.0)

Funding: This research did not receive any financial support

Competing Interests: The authors have declared that no competing interests exist

BACKGROUND: The high esthetic expectations from the prosthodontic restorations have directed the qualitative development of the materials towards the all-ceramic materials that are capable of replacing porcelain-fused-to-metal systems.

AIM: This article reviews the literature covering the contemporary all-ceramic materials and systems with a focus on the chemical composition and materials' properties; also it provides clinical recommendations for their use.

RESULTS: The glass-matrix ceramics and polycrystalline ceramics are presented, as well as recently introduced machinable materials, all-zirconia and resin-matrix ceramics. The specific properties of zirconia, such as transformation toughening, stabilisation of the crystallographic structure, low-temperature degradation and factors affecting the zirconia's ageing, are emphasised.

CONCLUSION: The favourable properties of the resin-matrix ceramics, such as modulus of elasticity similar to dentin, shock-absorbing characteristics and high resilience and fracture resistance, are also covered in this article.

Introduction

Technological development in the dental industry, particularly in the field of ceramic materials, enabled the production of metal-free restorations made up of all-ceramic materials [1]. The qualitative improvements provided ceramic materials with many advantages over the porcelain-fused-to-metal system such as excellent esthetic appearance due to favourable optical properties (translucency and transparency), natural tooth color and chromatic stability, biocompatibility, chemical inertness and low thermal conductivity, optimal mechanical properties such as high flexural strength and fracture toughness, as well as wear resistance and low abrasive properties [2].

Consequently, all-ceramic materials can be used for manufacturing of all kind of single-tooth restorations [3] [4] such as veneers, inlays, onlays, crowns and posts; lithium disilicate ceramic can be used for production of 3-unit bridges (in the anterior and premolar region), whereas multi-unit bridges can be made up only by stabilized zirconia; ceramic materials with a resin matrix inside, are especially suitable for the production of crowns over the implants or tooth restorations in a region where high masticatory pressure is generated [5] [6].

This article reviews the current literature regarding the all-ceramic materials, represents the recently proposed classification system [7] based on the phase or phases present in materials' chemical composition; presents already established as well as recently developed and introduced materials, their

properties and clinical indications. Glass-ceramics have superior optical properties [8] [9] [10], stabilized zirconia, referred to as “ceramic steel” [11] not only because of the phenomenon called “tension expansion”, but including other properties such as the highest strength, high fracture toughness and Vickers hardness [12] [13] [14], whereas so-called “hybrid ceramics” appeared to have advantages in terms of fracture resistance, high resilience and shock-absorbing properties, milling efficiency, polishability and accuracy-less marginal chipping [5] [15] [16].

The purpose of this review is to help therapists take into consideration not only the patients requirements, but material features as well, when choosing a ceramic material, so all-ceramic restorations with high reliability and long-term clinical success can be made.

Dental Ceramics – Chemical Composition

For a long time, ceramic materials have been defined as compounds of metallic and non-metallic elements consisting of oxides, nitrides, carbides, and silicates [17]. Most of the ceramics used in dentistry were primarily based on silicon that usually occurs in the form of silica (silicon dioxide), due to the silicon's high oxygen affinity or as silicates compounds [18].

The increasing use of polycrystalline ceramics (with no silicon in their composition), and the introduction of so-called ‘hybrid’ ceramics imposed the need for a new classification system [7]. According to this classification system, all-ceramic and ceramic-like restorative materials can be categorised into three groups: (1) glass-matrix ceramics, (2) polycrystalline ceramics, and (3) resin-matrix ceramics, depending on the phase/phases present in their chemical composition. “Glass-matrix ceramics” are nonmetallic inorganic ceramic materials that contain a glass phase, while “polycrystalline ceramics” are defined as nonmetallic inorganic ceramic materials that do not contain glass, but only a crystalline phase. In the third group - “resin-matrix ceramics” are included materials that have a polymer matrix, containing predominantly inorganic refractory compounds [7]. Different phases present in materials’ chemical composition affects the sensitivity of the ceramic material to the hydrofluoric acid when etching (as a surface treatment method before adhesive luting) to achieve stronger resin-ceramic bond [19].

Glass-Matrix Ceramics

The first group, glass-matrix ceramics, is further divided into three subgroups: feldspathic ceramics, synthetic ceramics, and glass-infiltrated

ceramics.

Feldspathic ceramics

The traditional type of dental ceramics are feldspar-based, composed of the significant amount of feldspar (KAlSi_3O_8), quartz (SiO_2), and kaolin ($\text{Al}_2\text{O}_3 \cdot 2\text{SiO}_2 \cdot 2\text{H}_2\text{O}$). Feldspar is a greyish crystalline mineral that can be found in rocks rich with iron and mica. Feldspar rocks are grounded, and after using strong magnets to remove iron compounds, it is milled to obtain the purest powder. Quartz or silica (SiO_2) is the matrix component (55–65%) responsible for the translucency of the restoration. As it is not a strong material, 20–25% alumina (Al_2O_3) is added as a reinforcing component. Kaolin is a hydrated aluminium silicate that is used in a limited amount (4%) as it has opaque properties, unlike the human teeth which are translucent. It is used in the composition of dental ceramics as it binds the loosely held ceramic particles together [18] [20].

VITABLOCS® from VITA Zahnfabrik are the most used feldspar-based CAD/CAM ceramics with an average grain size of $4\mu\text{m}$ and flexural strength of 154MPa. In 1985 first inlay was produced made of VITA Mark I, whereas in 1991 VITA has promoted Mark II, a monochromatic material with improved chemical composition and physical properties. To imitate the natural colours of the tooth, VITA has introduced next generations: VITABLOCS® TriLuxe (2003) and TriLuxe forte (2007). VITABLOCS® TriLuxe includes three, while TriLuxe forte four layers of different shade intensity from the cervical to the incisal edge, especially suitable for veneers, partial and full crowns in the anterior region. Further improvement in a replica of the shade gradient of natural teeth between the dentin and the edge areas, has been succeeded with VITABLOCS® RealLife (2010), multichromatic feldspar ceramic with different colour intensity in three dimensions [21].

Numerous micropores and channels of different sizes with irregular ceramic particles can be observed on the surface of VITA Mark II after surface etching with hydrofluoric acid; such a modified surface micromorphology is suitable for capturing of a composite luting cement [19] [22].

Synthetic glass-ceramics

To remain less dependent on natural resources of raw materials, the so-called “synthetic” glass-ceramics are invented, with a greater presence of crystalline phase that reduces the possibility of crack formation, or the propagation is slowed down if it has already occurred [7]. The presence of the crystals improves the mechanical properties of the ceramic.

The microstructure of glass-ceramics comprises dispersed crystalline phase (crystals)

surrounded by a translucent glassy phase (matrix). The glassy phase possesses the usual properties of glass such as translucency, brittleness and non-directional fracture pattern. The crystalline phase improves light scattering and opacity, thereby colour adaptation of transparent glassy phase to dental hard tissues (enamel and dentin), and provides the ceramic material with strength, stability during firing and resistance to stresses that occur in the mouth [18].

The crystals are "artificially" created by controlled nucleation and crystallisation. The size and distribution of the crystals are determined by the composition and processing of the base glass and the subsequent heat treatment. This process allows "tailor-made" materials to be produced, which exhibit homogeneous structure, good optical properties, appropriate wear characteristics, as well as optimal strength [23] [24].

The final mechanical properties of the synthetic glass ceramics are determined by two groups of factors: intrinsic and extrinsic. Intrinsic factors are crystal size, number and geometry, the distribution pattern of the crystals (homogeneity), as well as thermal expansion/contraction matching between the crystal phase and glassy matrix. Long-term performance of the material also depends on the extrinsic factors such as fabrication conditions and conditions of the oral environment: humidity (stress corrosion), variations of the pH level, thermo shocks, cyclic loading and peak loads that can reach extremely high levels when hard objects are accidentally encountered during mastication [25].

Leucite-reinforced, lithium disilicate, zirconia-reinforced lithium silicate, and fluorapatite-based ceramics are representatives of synthetic glass-ceramics.

Leucite-reinforced ceramic (IPS Empress CAD, Ivoclar Vivadent) consists of leucite crystals (35–45 vol%) that are homogeneously distributed into the glassy matrix. Leucite crystals are created by the controlled firing of feldspar at 1150°C. Potassium aluminium silicate is disintegrated into leucite and two molecules of silica:



The process is known as surface crystallisation, in which the crystals grow slowly along the grain boundaries towards the centre of the grain [26].

Due to the high silica content (60–65 wt%) this ceramic has improved translucency, fluorescence and opalescence, while the crystalline content is responsible for the flexural strength of 160 MPa and ability to absorb the fracture energy that results in arrested or slowed down crack propagation. The diameter of the leucite crystals ($KAlSi_2O_6$) is 1–5 μm [27] [28].


IPS Empress CAD is monochromatic ceramic,

with the need for further characterisation of the milled restoration, whereas IPS Empress CAD Multi is polychromatic, with high intensity of chroma and opacity in the cervical area and high level of translucency in the incisal region [29].

As a glass-ceramic, the best surface treatment method before adhesive luting is HF-acid etching. The acid dissolves the leucite crystals more quickly than the glassy matrix resulting in a surface with honeycomb-like appearance [22] [27] [30].

Another leucite-reinforced ceramic is Paradigm C, introduced in 2006 by 3M ESPE.

Lithium disilicate ceramic (IPS e.max CAD, Ivoclar Vivadent) is comprised of approximately 70 vol% of crystalline phase incorporated in the glassy matrix. In the process of production, ceramic is cast in transparent glass ingots that contain lithium orthosilicate. The process of partial crystallisation that follows leads to the formation of 40% platelet-shaped lithium metasilicate crystals (with the average size of 0.2–1.0 μm), Li_2SiO_3 , embedded in a glassy phase. It is a so-called intermediate crystalline phase or 'blue' state, with 130 ± 30 MPa flexural strength, in which the blocks can easily be milled in CAM unit. Milled restorations are tempered at 850°C and eventually lithium disilicate crystals - $Li_2Si_2O_5$ are formed [31] [32] [33], which impart the milled restoration with the final shade and flexural strength of 360 ± 60 MPa:



Randomly-oriented, densely distributed, elongated fine-grained lithium disilicate crystals, 1.5 μm in length, scattered with shallow irregularities become visible after dissolving the glassy matrix by etching the surface with hydrofluoric acid (HF) [19] [22] [30].

Zirconia-reinforced lithium silicate is glass-ceramic material enriched with highly dispersed zirconia, developed in close cooperation between Degudent, VITA and Fraunhofer Institute for Silicate Research [34]. After breaking up the partnership, Dentsply and VITA continued with their research which, in 2013, resulted in the introduction of Celtra Duo™ (Dentsply, Degudent) and VITA Suprinity® (VITA Zahnfabrik).

Production of the ceramic blanks and fabrication of the restoration go through three stages similar to those of lithium disilicate ceramic. In the first stage, the melted material is moulded, and the block is in the glass state. Nucleation/precrySTALLISATION is a subsequent thermal pretreatment in which crystals start to form and grow, and the glass features ceramic properties. In this stage, the material contains only lithium metasilicate crystals and is easy to mill in the CAM unit. The final crystallisation stage is short heat treatment at 840°C for 8 min in which the restoration exhibits its final colour and physical properties. The crystalline phase consists of 25% lithium metasilicate

(Li_2SiO_3) and 11% lithium disilicate ($\text{Li}_2\text{Si}_2\text{O}_5$) crystals. During the last two stages, zirconia acts as a nucleating agent but remains dissolved in the glassy matrix [25] [35] [36].

Despite the high silica content of 55-65 wt%, these ceramics have improved flexural strength of 370-420 MPa after glazing, due to the lithia (15–21 wt%) and particularly zirconia (8–12 wt%) content (approximately ten times more zirconium dioxide than in traditional CAD/CAM glass-ceramic) [37].

The specific composition has a positive effect on the optical properties of the material; consequently, aesthetic appearance 'as a natural tooth' of the restoration (natural opalescence, fluorescence and pronounced chameleon effect) is achieved. The lithium silicate crystallites in Celtra with a size of 0.5-0.7 μm corresponds to the wavelength range of natural daylight thus mimicking the opalescence behaviour of the tooth enamel, and together with the high glass content are responsible for the fluorescence of the restoration [38].

Values for the fracture toughness ($2.31 \pm 0.17 \text{ MPa m}^{0.5}$), flexural strength ($443.63 \pm 38.90 \text{ MPa}$), elastic modulus ($70.44 \pm 1.97 \text{ GPa}$) and hardness ($6.53 \pm 0.49 \text{ GPa}$) of Vita Suprinity are significantly higher compared to lithium disilicate ceramic [39].

Dissolving of the glassy matrix using hydrofluoric acid before adhesive luting of the restoration made up from zirconia-reinforced lithium silicate causes exposure of the homogeneously and densely arranged bean-like lithium silicate crystals [19] [22].

Fluorapatite glass-ceramics (IPS e.max Ceram and IPS e.max ZirPress, Ivoclar Vivadent) contain fluorapatite crystals $\text{Ca}_5(\text{PO}_4)_3\text{F}$ in various sizes embedded into the glassy matrix; the crystals, responsible for material's opalescence, are less than 300 nm in length and 100 nm in diameter, whereas crystals along the longitudinal axis are larger, 2–5 μm in length and less than 300 nm in diameter. IPS e.max Ceram is a nano-fluorapatite layering ceramic in the form of a powder, used for the production of veneers or as veneering material for glass or oxide ceramics, whereas IPS e.max ZirPress are pressable ingots suitable for the production of veneers and veneering of zirconia substructures using press-on-zirconia technique [40] [41].

The flexural strength of IPS e.max Ceram is significantly lower than IPS e.max ZirPress due to the pores present in the material, result of an air-bubbles' incorporation during mixing the ceramic powder with the mixing liquid [42]. Having high silica content of approximately 60 wt% and very low alumina content of $\approx 12 \text{ wt\%}$, the flexural strength is lower (only 90-110 MPa) compared to other all-ceramic materials, which means that they can't be used for the production of the substructure of the restorations [40] [41].

Further development of glass ceramics is

aiming to fulfil the protective requirements of the dental materials. **Fluorophlogopite glass ceramic** seems to have similar properties to other glass ceramics regarding mechanical properties, milling efficiency and etchability, but further on, this material possesses biocompatible property such as fluoride releasing. The flexural strength is approx. 120 MPa, the Weibull modulus is higher, while the Vickers hardness is lower compared to feldspar-based, lithium disilicate and resin-matrix ceramic [43].

Glass-Infiltrated ceramics

The glass-infiltrated ceramics belong to a group of ceramic-glass interpenetrating phase composites as they have at least two interpenetrating phases intertwined throughout the material [15]. The ceramic material is fabricated utilising the slip-casting or CAD/CAM technique. A slurry of densely packed ceramic particles is sintered to a refractory dye (if using the slip-casting technique) or the ceramic powder is dry pressing into a mould and compacted to produce a ceramic block (if using CAD/CAM technique) that are subsequently milled in CAM unit. The porous ceramic skeleton is infiltrated with lanthanum glass in a second firing, thus increasing the strength of the restoration [44].

Optical properties and final strength of the ceramic depends on the chemical composition of the porous core. *VITA In-CeramTM SPINELL*, consisted of alumina and magnesia (MgAl_2O_4), had the lowest strength (400 MPa) but very high translucency, thus indicated for single crowns in the anterior region. The alumina content in *VITA In-CeramTM ALUMINA* has reached 80% obtaining optimal translucency and strength (500 MPa) of the material, therefore indicated for single crowns in the anterior and posterior region, and for production of 3-unit bridges in the anterior region. Due to the alumina core strengthened with zirconia, *VITA In-CeramTM ZIRCONIA* had highest bending strength (600 MPa) compared to other glass-infiltrated ceramics and was indicated for single crowns in posterior region and 3-unit bridges no matter of the localisation [45]. No statistically significant difference has been found in the biaxial flexural strength and fracture toughness between In-Ceram ALUMINA and In-CeramTM ZIRCONIA [46].

The acid etching with HF acid did not change the superficial microstructure of these ceramics [30] [47] [48]. The use of this class of materials is abandoned due to the complexity and sensitivity of the manufacturing process, as well as the increased popularity of lithium disilicate ceramic and zirconia.

Polycrystalline ceramics

The main characteristic of ceramics classified in this group is a fine-grain crystalline structure without

the glassy phase. The crystals are densely arranged into regular arrays, thus reducing the crack propagation, providing the material with high strength and fracture toughness [44]. The absence of the glassy matrix is the reason for ceramics' resistance to surface etching with hydrofluoric acid [49] [50].

Alumina

Aluminium oxide (Al_2O_3) is a naturally occurring mineral (corundum, bauxite) with a high Mohs hardness of 9. It is used in engineering as an abrasive material, cutting tools, electronic substrates, whereas in medicine, due to its biocompatibility, low friction and excellent wear and corrosion resistance, is used as a bone replacement material (production of hip joint balls) [51]. For years crystalline aluminium oxide has also been used to increase the stability of dental ceramics (so-called "dispersion strengthening").

Alumina exhibits the highest resistance to hydrolysis compared to other ceramic materials, low thermal conductivity and high flexural strength (> 500 MPa). The alumina blocks (consisting of 99.5% Al_2O_3) are initially manufactured partially sintered which allows easy processing-milling. Shrinkage, which occurs during the subsequent sintering process, can be exactly calculated, so precision-fit structures are obtained. Since grinding does not cause phase transformation in the structure, restorations can be reshaped in the sintered condition, with no need of subsequent regenerative firing [52].

With an elastic modulus of 380 GPa [53], alumina is prone to bulk fractures [54]. Furthermore, the increased use of materials with improved mechanical properties, such as stabilised zirconia and its feature for transformation toughening (thus the ability for crack "repairing"), has led to a decreased use of alumina.

Procera[®] AllCeram from Nobel Biocare (the first fully dense polycrystalline ceramic) and In-Ceram[®] AL, a product of VITA Zahnfabrik, are representatives of this type of ceramic.

Zirconia

Zirconium (Zr) is a shiny silvery metal. It is relatively soft and flexible when in a highly pure form. Its most important compound is zirconium dioxide ZrO_2 , chemically an oxide and technologically a ceramic material. About 0.02% of the earth crust comprises of zirconia, with the largest deposits in Brazil and South Africa as baddeleyite (monoclinic zirconia) and high proportion in Australia and India where can be found as zircon (ZrSiO_4) sands [55]. Zirconia was discovered by the German chemist Martin Heinrich Klaproth in 1789 [13].

Pure zirconia is a polymorphic material that occurs in three crystallographic structures depended

on the material's temperature. This phenomenon is known as allotropy since different structures have the same chemical composition but a different atomic arrangement. When cooling down from the molten state, following phases can be observed: cubic (*c*) from 2680°C, the melting point, to 2370°C; tetragonal (*t*) from 2370°C to 1170°C; and monoclinic (*m*) from 1170°C to room temperature [13] [56] [57] [58]. The spontaneous transformation from the *t* phase (higher material density) to the more-stable *m* (lower material density) phase is associated with a volume increase of 3% to 5%. Occurred tension (during the cooling phase after sintering) inside of the restoration made of pure ZrO_2 results in numerous microcracks, which will eventually lead to premature failure of the restoration [59] [60].

In the distant 1929, Ruff et al., [61] [62] have discovered that the tetragonal, or even the cubic form of zirconia could be retained metastable at room temperatures by alloying pure zirconia with other cubic oxides. Since then, numerous oxygen biocompatible compounds have been proposed as a zirconia stabilizers, used to relocate the phase transformation towards lower temperatures, thus preventing the catastrophic failure of the restorations made of zirconia: MgO [63] [64] [65] CaO [66], CeO₂ [67], Al_2O_3 [68] and Y₂O₃ [66] [69].

In 1975, Hannink et al., [69], proposed that the *t*-*m* transformation followed by volume expansion could be used to enhance the fracture toughness of partially stabilised zirconia-based materials. In 1976, Claussen and Steeb [70] had explained this mechanism as "oriented nucleation of microcracks". When a restoration containing metastable *t*-zirconia is subject to an external source of energy, as for example in the case of a tensile stress, temperature shock, an overloading in patient with parafunction, or in contact with water at low temperatures (condition occurring over time known as "low temperature degradation" LTD) [71] [72], the cracks may occur. Zirconium oxide grains are transformed from their tetragonal to the monoclinic form accompanied by a volumetric expansion of the grains thus restricting the crack. Since this expansion is constrained by the surrounding material, the net result is compressive stress on the surfaces of the crack, which propagation is thus hindered, eventually preventing the failure of the zirconia restoration [71] [73]. This is the reason why this phenomenon is called "phase transformation toughening" [69] [70] [71] [72] [73].

As "tension expansion" is a phenomenon otherwise known only in the case of steel, zirconium oxide was also referred to as "ceramic steel" [11].

In their review paper, Lughì and Sergo [71] summarising the scientific data concluded that the main factors affecting the zirconia ageing are the stabiliser type (oxides) and its content, the grain size and the residual stress. The most appropriate stabiliser is Y₂O₃ when added between 3.5 and 8

mol%. Theoretical density of the material should be more than 99%, with the grain size less than 0.3 μ m and negligible monoclinic content. Residual tensile stress should be less than 300 MPa [71].

The most widely used stabiliser is Y₂O₃ in the content of 3 mol% (corresponds to 5.1% by weight) for the stabilisation of a tetragonal and 8 mol% for the stabilisation of a cubic form of Y-TZP [71]. It is well known that Y-TZP is prone to LTD in the presence of water. To date, there are several proposed mechanisms [60] [74] [75] that explain this phenomenon, but none of them is confirmed. Anyway, some facts are accepted regarding the origin and spreading of the micro-cracks: *t*-*m* grain transformation starts from the surface of the material and then proceeds inward, causing a surface uplift [76] [77] and creating microcracks [78], that enables water penetration below the surface. Propagation of the *t*-*m* grain transformation into the material [79], leads to the development of major cracks [78] that eventually ends with a catastrophic failure of the restoration. Low-temperature degradation of the Y-TZP has encouraged researchers to look for other stabilisers; aluminium trioxide, Al₂O₃, seems to have a crucial role in the ageing stability of Y-TZP ceramics and is used in very low content, with alumina particles optimally distributed within the zirconia material. It can be added independently of yttria stabiliser and its content, in the amount of 0.25 wt% having a higher degradation retarding effect to Y-TZP ceramics than 2 or 5 wt% of alumina addition, which have a comparable effect. According to Zhang et al., the apparent activation energy for the degradation process is increased by adding alumina in higher content [68].

Stabilization by cerium oxide provides better thermal stability and resistance to 'low-temperature degradation' than Y-TZP. CeO₂ gives zirconia the best properties regarding phase transformation although it is needed in larger amount comparing to Y₂O₃ to maintain the same degree of stability [80]. A Ce-TZP material with 8 mol% of ceria was characterised by less than 10% monoclinic content on the surface after 360 h water storage at 80°C [81]. When containing more than 12 mol% ceria, the system is almost non-transformable [82]. Another positive effect of adding ceria to zirconia is the pseudo-plastic behaviour of this compound (Ce-TZP can bend before fracturing) that is the most expressed feature among all other ceramic materials [83]. The major drawback of Ce-TZP ceramic materials that are commercially available is the chemical instability of Ce⁴⁺ that can be relatively easily reduced to Ce³⁺, which does not have the same stabilising ability toward *t*-zirconia [84]. On the other hand, CeO₂ is yellow, affecting the colour of the final Ce-TZP restoration from light yellow to almost brownish, that may even become dark grey due to the high concentration of oxygen vacancies [84] [85].

Schmauder and Schubert [86] have shown that stress plays a critical role in the *t*-*m*

transformation of zirconia grains as it does not occur in stress-free zones of the material, even if it contains an insufficient amount of stabiliser. As mentioned before, stress can be "applied" (tensile stress, temperature shock, an overloading in patient with parafunction), but it may also appear as a "residual stress" occurring during fabrication process of the restoration when it is fired at high temperature and then cooled down to room temperature, during sintering or veneering with materials having a different coefficient of thermal expansion (CTE) [71]. The residual stress has so-called "autocatalytic effect" that can be explained by prolonged *t*-*m* transformation. When some *t*-zirconia grains transforms to *m*-phase for any reason, zirconia becomes two-phase material with *m*-zirconia in compression and the remnant *t*-zirconia in tension; it is assumed that for every 10 vol% of *t*-*m* transformation, the tensile stress in the remnant *t*-zirconia increases by 250 MPa [87]. Because of this tensile stress, *t*-zirconia will be more prone to further transformation to *m*-zirconia. Experimentally, it was confirmed that the tensile stress initiated by *t*-*m* transformation as a result of the material bending, could reach a value of 700 MPa [88]. The outcome is slow increasing of the monoclinic content inside the zirconia.

Another factor that influences the stability of the tetragonal phase and LTD is an average size of the zirconia grains. Reducing the grain size (GS) has a beneficial effect on the stability of the zirconia-based materials; a reduction below a certain critical value has a potential of fully inhibiting LTD [71]. When at room temperature, the grains' critical size of pure zirconia powder is in the range of 5–10 nm, whereas in 1.5 Y-TZP powders it is about 90nm [89]. Anyway, when solid, dense zirconia material is observed, "the *t*-form can be stable even if the grains are much larger than the critical GS identified above for powders"; however, zirconia GS should be less than 300 nm to prevent LTD over a period [71]. Exact calculation of optimal GS in a solid material is complex, as the effect of different stabilisers and their content, as well as strain energy, should also be taken into consideration.

Sintering process, temperature and the dwell time influence the ageing stability of zirconia as well. Hallmann et al., [90], didn't find *t*-*m* phase transformation when Y-TZP has been sintered at a temperature of 1350°C. The diffusion-controlled *t*-*m* phase transformation initiated at 1450°C and became remarkable when the sintering temperature was increased to 1600°C [90]. Similarly, Inokoshi et al., [91] have demonstrated that increasing the sintering temperatures and elongating the dwell time (2 or 4 hours), increased the ZrO₂ grain size and decreased yttria content in the remaining tetragonal grains, which eventually lead to a higher sensitivity to LTD of Y-TZP ceramics. The best resistance to low-temperature degradation can be achieved by sintering at 1450°C with a one h dwell time [91]. According to Hjerpe et al., the bi-axial flexural strength of zirconia was not

affected by decreasing the sintering time or thermocycling, although the amount of monoclinic phase on the surface of zirconia was increased after thermocycling and water storage [92].

The effect of increased sintering temperature (from 1350°C to 1550°C) on the LTD sensitivity can be explained by the following mechanism: it causes increasing of the average size of the tetragonal ZrO₂ grains, whereas increasing content of the cubic zirconia grains that are enriched with yttrium concomitantly results in a decreased yttrium content as a stabilizer in the remaining tetragonal grains [93].

However, decreasing the sintering temperature to obtain 3Y-TZPs resistant to LTD, leads to the creation of a material with moderate mechanical properties, i.e. lower fracture toughness. To improve surface degradation resistance, Zhang et al., [94] proposed a new way of material production, incorporating stabiliser by coating yttria in the starting powder of 3Y-TZP, a method different than co-precipitation. Optimization of the mechanical properties can be achieved by adding 0.25 wt% Al₂O₃ that allows sintering at a lower temperature to obtain a higher LTD resistance without compromising the hardness and the fracture toughness. The improved LTD resistance in such material could be attributed to the segregation of Al³⁺ at the grain boundary and the heterogeneously distributed Y³⁺ stabiliser [94].

But, not only sintering conditions influence the LTD behaviour of the zirconia materials. Surface treatments (ST) of dental zirconia conducted before adhesive luting, have a great impact on the monoclinic content and thereby ageing sensitivity, i.e. degrading susceptibility. Some monoclinic grains have been observed after sandblasting the surface, with no particular influence of the abrasive particles' size on the LTD of Y-TZP [90]. Anyway, the effect of surface treatment mostly depends on the chemical composition-oxides used as stabilisers. Inokoshi et al., have shown that ST improved the ageing resistance of Y-TZP zirconia, although the highest monoclinic volume fraction was observed in Al₂O₃ sandblasted zirconia. The LTD behaviour of Ce-TZP/Al₂O₃ zirconia (with higher initial monoclinic volume fraction after ST, but stronger ageing resistance compared to the Y-TZP zirconia) was not affected by conducted treatments. Y-TZP/alumina (Y-TZP/Al₂O₃) zirconia showed a strong ageing resistance when the surface was left untreated; insignificant degradation was observed after ST [95].

All the factors mentioned above influence the crystallographic structure of the zirconia when at room temperature. The grains' transformation from tetragonal to monoclinic form is a one-way process, meaning that "once it takes place, the crack-hindering effect cannot be exploited for limiting further fractures" [2]. Restorations made of zirconia with monoclinic state of the grains are more prone to catastrophic failure. The solution for such a negative outcome has

been found in the so-called "regeneration firing" that is conducted after final adjustment of the already sintered restoration. Annealing the material in the temperature range 900–1000°C for a short time, induces the reverse phase transformation from monoclinic back to tetragonal form [96].

Beside LTD, shading of the zirconia frameworks before sintering also has a negative effect on the biaxial strength and surface microhardness. Some reductions in bi-axial flexural strength, as well as dimensional changes, are seen when colouring zirconia in green-stage form. Shaded zirconia has lost less weight after sintering than un-shaded, indicating that colourant particles have been incorporated in the crystal structure of the material. The shrinkage of zirconia during sintering is also diminished by shading, which "might have clinical effects as the marginal accuracy, fit and cement thickness of the shaded is different to the un-shaded substructures" [97].

There are different types of zirconia materials depending on the zirconia's grains phase statement (composition), but only three are used in dentistry: (1) *partially stabilized zirconia (PSZ)*, a two-phase material with the tetragonal phase (transformable *t*-zirconia grains) precipitated into the cubic matrix, where stabilization is accomplished by magnesia [44] [71]; there is only one available MgO-PSZ product for the dental market, Denzir-M® by Dentronic AB, Skellefteå, Sweden, suitable for hard machining. (2) *Zirconia toughened composites (ZTC)* - a matrix with high elastic modulus embedding transformable *t*-zirconia grains; the most used matrix is alumina, so the material is known as zirconia-toughened alumina (ZTA) (this material is mostly used for the medical prostheses fabrication) [98]. (3) *Tetragonal zirconia polycrystals (TZP)* - the whole material consists of transformable *t*-zirconia grains. Stabilized with yttria as Y-TZP, has been used in dentistry for production of orthodontic ceramic brackets [99] and endodontic posts [100] since the early 1990s, as well as fixed restorations since the later 1990s [101]. PSZ and ZTC are two-phase materials, whereas TZP is a single-phase [71].

As mentioned before, zirconia blocks for the CAD/CAM technology could be used in their pre-sintered or sintered state. For better quality of the restoration, it is better if *pre-sintered* chalk-like blocks are used (in so-called '*green*' stage), with porosity in their microstructure (50% for IPS e.max ZirCAD), so the milling process is easier, the average milling time is reduced, and the milling tools can be used longer. After milling in the CAM system, enlarged crown and bridge substructures undergo sintering process (1350–1500°C). During the sintering, shrinking of the restorations (20–25%) occurs, causing the structure densification to more than 99%, so the final properties of the material are achieved [102].

Zirconia blocks for computer-aided-

manufacturing can also be obtained from the manufacturers as industrially sintered; *hot iso-static pressed 'HIP' zirconia* (known as 'white blocks'). This material is in its final high strength and is characterised by a constant grading and better homogeneity, with no need of further sintering after milling [103]. According to Stawarczyk et al., hipped zirconia has the highest flexural strength compared to several pre-sintered zirconia materials tested after sintering [104]. Anyway, milling time is longer and wear of the milling tools is higher compared to milling of pre-sintered zirconia blocks [53]. The most important thing when milling hipped zirconia is substantial amounts of surface and structural defects caused by diamond burs, which negatively impact the permanent strength and durability of the ceramic.

Zirconia-based materials have the highest strength, fracture resistance, fracture toughness and Vickers hardness among all other ceramic materials: high fracture toughness of 6–15 MPa·m^{-0.5}, flexural strength of more than 900 MPa, high Vickers hardness of 1200–1350 HVN, high thermal expansion of more than 10·10⁻⁶ K⁻¹, very low thermal conductivity of less than 2 W/mK (vs. 200 W/mK for gold alloy, and 40 W/mK for base metal), and a good thermo-shock resistance of $\Delta T=400\text{--}500^{\circ}\text{C}$ [105].

Resin-Matrix Ceramics

In the last six years, a new category of dental materials has been promoted, hybrids, consisting of an organic matrix highly filled with ceramic particles [6] [7] [15] [106].

These materials can be included in a classification system of dental ceramics [7] as the 2013 version of the American Dental Association Code on Dental Procedures and Nomenclature [107] defines the term porcelain/ceramic as "pressed, fired, polished, or milled materials containing predominantly inorganic refractory compounds - including porcelains, glasses, ceramics, and glass-ceramics". The former version (2012) of the referred code, didn't allow materials with resin matrix to be classified as ceramic materials, as it has defined porcelain/ceramic as "non-metal, non-resin inorganic refractory compounds processed at high temperatures (600°C and above) and pressed, polished, or milled, including porcelains, glasses, and glass-ceramics". As these hybrid ceramics are composed predominantly (> 50% by weight) of inorganic compounds, it would be justified if they are taken into consideration while making systematisation of dental ceramic materials.

First, of them, Lava Ultimate from 3M ESPE has been marketed as '**Resin Nano Ceramic**' (RNC) as it contains nanoceramic particles (nanomer and nanocluster particles) bound in a highly cross-linked polymeric matrix. Lava Ultimate contains two types of nanomers that are monodispersed, nonaggregated

and nonagglomerated: silica nanomers of 20 nm diameter and zirconia nanomers of 4 to 11 nm in diameter. The nanocluster particles (with the average size of 0.6–10.0 μm) are synthesized and composed of 20 nm silica nanomers and 4–11 nm zirconia nanomers. Nano-dimension of the particles, allows a high proportion of ceramic filler (approximately 80% by weight) to be incorporated into the resin. Both of them, nanomers and nanoclusters are treated with a silane coupling agent so that chemical bonds can be provided between ceramic particles and the resin matrix. The material is processed several hours in a special heat treatment process, which results in highly cured material, so there is no need of further firing after milling [108].

Specific composition and production technology resulted in a material with higher flexural strength (200 MPa), fracture and wear resistance than composite materials (provided by nanoclusters), and with significantly improved polishability and optical properties (because of the nanoparticles). The polymeric resin as a matrix contributes to some properties that composites have: the material is not brittle and is fracture resistant, with shock absorbing characteristics. Despite a high ceramic content, this material is not recommended for the production of crowns, but only for inlays, onlays and veneers [108].

Intact resin matrix with embedded ceramic nano-particles could be observed after HF etching of the material's surface [19] [22].

Taking into consideration a specific structure and composition of the spongy bone and dentin, consisted of relatively weak and brittle inorganic constituents and organic matrix that provides elasticity, a novel kind of interpenetrating phase material has been developed [15] [109] referred as '**Polymer Infiltrated Ceramic Network**' (PICN).

VITA Enamic from VITA, have two 3-dimensional network structures interpenetrating one to another; the dominant fine-structure feldspar ceramic network (86% by weight or 75% by volume) is strengthened by a polymer network consisting of methacrylate polymer (14% by weight or 25% by volume). The blocks are manufactured in few steps: first, the ceramic powder is initially compressed into blocks followed by a sintering process to obtain a porous ceramic network. Next, a ceramic base structure is conditioned with a coupling agent. The conditioned porous inorganic network is finally infiltrated with a monomer mixture, followed by heat-induced polymerisation to create a polymer network. Both of the networks are interconnected through the chemical bonds obtained by the coupling agent [15] [110].

To reproduce the natural shade gradient, in 2017, VITA has started production of the VITA Enamic multiColor, blocks with six finely nuanced layers, from cervical to incisal area [111].

Table 1: Composition, properties and clinical indications of CAD/CAM blocks as published by representative manufacturers

Ceramic type	Product name Manufacturer	Chemical Composition mass%	Flexural strength MPa	Modulus of elasticity GPa	Clinical indications					
Feldspar	VITABLOCS®	iO ₂	56-64	154	45	veneers, inlays, onlays, partial crowns, anterior and posterior crowns, as a veneering CAD/CAM material for multi-unit bridge substructure made of oxide ceramic				
	VITA Zahnfabrik: Mark I (1985)	I ₂ O ₃	20-23							
	Mark II (1991)	La ₂ O ₃	6-9							
	VITA Triluxe (2003)	CaO	6-8							
	VITA Triluxe forte (2007)	CaO	0.3-0.6							
VITA RealLife (2010)	iO ₂	0.0-0.1	<0.1							
Leucite	IPS Empress CAD, Ivoclar Vivadent (2006)	SiO ₂	60.0-65.0	160	62	veneers, inlays, onlays, partial crowns, anterior and posterior crowns				
	IPS Empress CAD Multi	Al ₂ O ₃	16.0-20.0							
		K ₂ O	10.0-14.0							
		Na ₂ O	3.5-6.5							
		BaO, CaO, CeO ₂ , B ₂ O ₃ , TiO ₂ pigments	0.5-7.0 0.2-1.0							
Lithium-disilicate	IPS e.max CAD, Ivoclar Vivadent (2006)	SiO ₂	57.0-80.0	360±40	95	veneers, inlays, onlays, partial crowns, anterior and posterior crowns, 3-unit bridges (anterior and premolar), hybrid abutments, hybrid abutment crowns; 3-unit posterior bridges, as a veneering CAD/CAM material of multi-unit bridge substructure made of IPS e.max ZirCAD				
		Li ₂ O	11.0-19.0							
		K ₂ O	< 13							
		P ₂ O ₅	< 11							
		ZnO	< 8.0							
		MgO	< 8.0							
		pigments	< 5.0							
			< 0.5							
			< 8							
			< 8							
Lithium-silicate	Celtra Duo, Dentsply (2013)	ZrO ₂	10	370	70	veneers, inlays, onlays, partial crowns, anterior and posterior crowns, implant-supported crown				
		VITA Suprinity®, VITA Zahnfabrik (2013)	SiO ₂				56-64			
			Li ₂ O				15-21			
			ZrO ₂				8-12			
			P ₂ O ₅				3-8			
	Al ₂ O ₃		1-4							
	Zirconia	Vita In-Ceram® YZ, VITA Zahnfabrik (2002)	ZrO ₂	91-94	>900	210 GPa	primary telescope crowns, anterior and posterior crowns, anterior and posterior bridge (up to 2 pontics), cantilever bridges			
			Y ₂ O ₃	4-6						
			HfO ₂	2-4						
			Al ₂ O ₃	<0.1						
SiO ₂			<0.1							
Lava™ Frame Zirconia, 3M ESPE (2001)	ZrO ₂	<0.1		>1100	210	anterior and posterior crowns, splinted crowns up to 4 units, implant abutments, crowns on implant abutments, 3-unit inlay and onlay bridges, cantilever bridges, anterior adhesive bridges, 3-4 unit bridges, long-span and curved bridges				
	Y ₂ O ₃									
	Al ₂ O ₃									
	ZrO ₂	87-95								
	Y ₂ O ₃	4-6								
IPS e.max ZirCAD, Ivoclar Vivadent (2006)	HfO ₂	1-5	900±50	210	anterior and posterior crowns, primary telescope crowns, implant superstructures, 3-unit bridges (anterior, premolar and posterior), multiple-unit bridges, inlay bridge frameworks					
	Al ₂ O ₃	0-1								
	other oxides									
	ZrO ₂	>90								
	Y ₂ O ₃	3								
All Zirconia	Lava™ Plus High Translucency Zirconia, 3M ESPE (2012)	ZrO ₂	>90	>1100	210	anterior and posterior crowns, splinted crowns up to 4 units, implant abutments, crowns on implant abutments, primary crowns, 3-unit inlay and onlay bridges, cantilever bridges, anterior adhesive bridges, 3-4 unit bridges, long-span and curved bridges				
		Y ₂ O ₃	3							
		Al ₂ O ₃	0.1							
		ZrO ₂	5							
		Y ₂ O ₃	<3							
	Cercon® ht True Color, Dentsply, Degudent (2015)	HfO ₂	<1	1200	210	anterior and posterior crowns, primary telescope crowns, multi-unit bridges				
		Al ₂ O ₃								
		SiO ₂								
		ZrO ₂	>99							
		Y ₂ O ₃	4.5-6.0							
Zenostar® Full Contour Zirconia, Wieland Dental/Ivoclar Vivadent (2013)	HfO ₂	<5	1200±200	210	anterior and posterior crowns, primary telescope crowns, multi-unit bridges (as frameworks or full-contour)					
	Al ₂ O ₃	<1								
	Hybride	Lava™ Ultimate CAD/CAM Restorative, 3M ESPE (2011)				Ceramic:	%	204	13	veneers, inlays, onlays
						ZrO ₂				
						SiO ₂				
Resin:			%							
Bis-GMA, UDMA, Bis-EMA, TEGDMA										
VITA Enamic®, VITA Zahnfabrik (2013) Vita Enamic® multiColor (2017)	Ceramic network:	SiO ₂	wt%:	150-160	30	veneers, inlays, onlays anterior and posterior crowns, implant-supported crowns				
		Al ₂ O ₃	58-63							
		Na ₂ O	20-23							
		K ₂ O	9-11							
		B ₂ O ₃	4-6							
		CaO	0.5-2							
		ZrO ₂	0.3-0.6							
		KaO	< 1							
		TiO ₂	< 1							
		Polymer network:	<0.1							
UDMA										
TEGDMA	66									
CERASMART™, GC (2014)	Ceramic network:	SiO ₂	71	231	210	veneers, inlays, onlays anterior and posterior crowns, implant-supported crowns				
		Barium glass Monomer:								
		Bis-MEPP	29							
		UDMA								
		DMA								

Bis-GMA: bisphenol A diglycidylether methacrylate; Bis-MEPP: 2,2-Bis(4-methacryloyloxyphenyl)propane; UDMA: urethane dimethacrylate; TEGDMA: triethylene glycol dimethacrylate; Bis-EMA: ethoxylated bisphenol-A dimethacrylate; DMA: dimethacrylate.

The flexural strength of this two-phase material can reach a value of about 150–160 MPa, significantly higher than that of a porous ceramic (below 30 MPa) and polymer (135 MPa) alone [112]. The superior flexural strength of the resin-infiltrated ceramic material compared to the single components implies a reinforcement mechanism of the polymer network to the dominant ceramic network [106] [112]. Elastic modulus, hardness, and fracture toughness values are as follows: 30.14 GPa, 2.59 GPa, and 1.72 MPa·m^{-0.5} respectively [5], all of them between those obtained for human dentin and enamel. With the highest filler content (73.1 mass %) compared to other hybrid ceramics and composites, Vita Enamic has the highest Vickers hardness of 189.8 [113]. Moreover, VITA Enamic has similar two-body and tooth-brushing wear characteristic to natural enamel [114]. All these features, together with the possibility material to be milled very thin thus preserving the tooth structures, are in favour of using this material in patients with erosions where tooth preparation is not recommended [115].

HF etching of VITA Enamic causes dissolving of the superficial ceramic network, so that acrylic polymer network became visible with scattered irregular ceramic particles [19] [22].

The third, CERASMART™ from GC, referred to as “**Flexible Nano Ceramic**”, is composed of relatively small and uniformly distributed particles of alumina-barium-silicate embedded in a polymer matrix [116]. The flexural strength (approx. 242 MPa) is significantly higher, whereas the flexural modulus (10.0 GPa) and Vickers hardness (approx. 64.1 HV) are significantly lower than Lava Ultimate (170.5 MPa / 14.5 GPa / 97.9 HV) and VITA Enamic (140.7 MPa / 28.5 GPa / 189.8HV) respectively [113]. The modulus of resilience of 3.07 ± 0.45 MPa is the highest, and the margin edge roughness of 60 ± 16 µm is the lowest compared to other ceramics or hybrid materials [117].

All hybrids have a modulus of elasticity similar to dentin, and modulus of resilience significantly higher than feldspar-based and glass-ceramics, thus significantly higher stress can be absorbed without permanent deformation or failure. That is why hybrids are the most recommended materials for fabrication of crowns over implants, where the periodontal ligament (tissue that acts as a shock absorber) is already lost.

Milling time in the CAM unit is shorter compared to other ceramic materials, with longer lifetime on the milling burs. There is no need for sintering or crystallization firing after milling; final gloss and smoothness of the restoration can be achieved by surface polishing. Hybrids are wear resistant and “gentle” to the opposite dentition [115]. Restorations can be easily repaired in the mouth, although these materials are characterized by virtually no chipping.

Clinical Indications

Feldspar-based and leucite-reinforced ceramics according to their low flexural strength (154MPa and 160MPa respectively) are indicated for single tooth restorations such as veneers, inlays, onlays, partial crowns, and anterior and posterior crowns. Beside the listed, zirconia-reinforced lithium silicate (420 MPa) can also be used for the fabrication of implant-supported crowns. Having the high crystalline content, specific microstructure and flexural strength of 360–400 MPa, lithium disilicate ceramic can be used not only for single tooth restorations but the fabrication of hybrid abutments, hybrid abutment crowns and three-unit bridges as well (up to the second premolar as the terminal abutment). Due to the polymer content, low flexural strength (150–240 MPa) and high resilience, hybrid ceramics can be used only for single tooth restorations such as veneers, inlays and onlays (Lava Ultimate), as well as for anterior and posterior crowns and implant-supported crowns (VITA Enamic and Cerasmart).

Densely sintered, high-purity alumina can be used for primary elements of conical and telescopic crowns, crowns in the anterior and posterior area, as well as for bridges only in the anterior area with no more than 1 pontic (due to the average high flexural strength of 500 MPa).

Yttria-stabilized zirconia (with high flexural strength of more than 900 MPa) is indicated for fabrication of anterior and posterior crowns, implant abutments, implant abutments crowns, primary telescope crowns, 3-unit inlay and onlay bridges, cantilever bridges with minimum two abutment teeth and maximum of one pontic of no more than one premolar width, anterior adhesive bridges, as well as multi-unit long-span (up to 14 units) and curved bridges with a maximum of four pontics next to one another in the anterior area, and a maximum of three pontics (DC-Zircon) next to one another between abutment teeth in the posterior area. Some of them (Lava™ Plus High Translucency Zirconia, 3M ESPE) are indicated for clinical situations with limited interocclusal space, as well as when the tooth-preserving preparation is needed (minimum 0.5 mm occlusal wall thickness). CAD/CAM ceramic materials, their chemical composition, some properties and clinical indications as claimed by the respective manufacturers are presented in Table 1.

Conclusion

Although it seems that current ceramic materials could “cover” every clinical situation where

single-tooth restoration and fixed partial dentures are indicated for use, there are some limitations that should be taken seriously. All-ceramic restorations are not recommended in patients with insufficient remaining natural tooth substance (short clinical crowns), sub-gingival preparations (mainly for adhesive luting), inadequate oral hygiene, and patients diagnosed with excessive masticatory functions, in particular teeth grinders and clencher.

The future of all-ceramic materials is bright. Further improvements in chemical composition, internal structure, grain-size decreasing to nano dimensions and improved protocols for industrial production and laboratory processing, all of them will for sure lead to a material with extraordinary features fulfilling the esthetic, mechanical and biocompatible demands.

References

- Bajraktarova Valjakova E, Guguvcevski Lj, Korunoska Stevkovska V, Gigovski N, Kapusevska B, Mijoska A, Bajevska J, Bajraktarova Misevska C, Grozdanov A. Dental ceramic materials, part I: Technological development of all-ceramic dental materials. *Macedonian Stomatological Review*. 2018; 41(1-2):30-4.
- Zarone F, Russo S, Sorrentino R. From porcelain-fused-to-metal to zirconia: Clinical and experimental considerations. *Dent Mater*. 2011; 27(1):83-96. <https://doi.org/10.1016/j.dental.2010.10.024> PMID:21094996
- Conrad HJ, Seong W-J, Pesun IJ. Current ceramic materials and systems with clinical recommendations: A systematic review. *J Prosthet Dent*. 2007; 98(5):389-404. [https://doi.org/10.1016/S0022-3913\(07\)60124-3](https://doi.org/10.1016/S0022-3913(07)60124-3)
- Bajraktarova Valjakova E. [Evaluation of the bonding effectiveness of luting composites to different ceramic CAD/CAM materials - in vitro study] [dissertation]. Faculty of Dentistry, University Ss Cyril and Methodius; 2014. [Macedonian]
- He LH, Swain M. A novel polymer infiltrated ceramic dental material. *Dent Mater*. 2011; 27(6):527-34. <https://doi.org/10.1016/j.dental.2011.02.002> PMID:21371744
- Silva LH, Lima E, Miranda RBP, Favero SS, Lohbauer U, Cesar PF. Dental ceramics: a review of new materials and processing methods. *Braz Oral Res*. 2017; 31(suppl):e58:133-46.
- Gracis S, Thompson VP, Ferencz JL, Silva NRFA, Bonfante EA. A new classification system for all-ceramic and ceramic-like restorative materials. *Int J Prosthodont*. 2015; 28(3):227-35. <https://doi.org/10.11607/ijp.4244> PMID:25965634
- Barizon KT, Bergeron C, Vargas MA, Qian F, Cobb DS, Gratton DG, Geraldini S. Ceramic materials for porcelain veneers. Part I: Correlation between translucency parameters and contrast ratio. *J Prosthet Dent*. 2013; 110(5):397-401. <https://doi.org/10.1016/j.prosdent.2013.06.008> PMID:23998620
- Barizon KT, Bergeron C, Vargas MA, Qian F, Cobb DS, Gratton DG, Geraldini S. Ceramic materials for porcelain veneers: part II. Effect of material, shade, and thickness on translucency. *J Prosthet Dent*. 2014; 112(4):864-70. <https://doi.org/10.1016/j.prosdent.2014.05.016> PMID:24969410
- Oh S, Shin SM, Kim H-J, Paek J, Kim S-J, Yoon TH, Kim S-Y. Influence of glass-based dental ceramic type and thickness with identical shade on the light transmittance and the degree of conversion of resin cement. *Int J Oral Sci*. 2018; 10(5):1-6. <https://doi.org/10.1038/s41368-017-0005-7>
- Garvie RC, Hannink RH, Pascoe RT. Ceramic Steel? *Nature*. 1975; 258(5537):703-4. <https://doi.org/10.1038/258703a0>
- Guazzato M, Albakry M, Ringer SP, Swain MV. Strength, fracture toughness and microstructure of a selection of all-ceramic materials. Part II. Zirconia-based dental ceramics. *Dent Mater*. 2004; 20(5):449-56. <https://doi.org/10.1016/j.dental.2003.05.002> PMID:15081551
- Monaco C. Zirconia in dentistry [dissertation]. Faculty of engineering: University of Bologna; 2014.
- Turp V, Tuncelli B, Sen D, Goller G. Evaluation of hardness and fracture toughness, coupled with microstructural analysis, of zirconia ceramics stored in environments with different pH values. *Dent Mater J*. 2012; 31(6):891-902. <https://doi.org/10.4012/dmj.2012-005> PMID:23207192
- Coldea A. Chapter II: Literature review. In: Suitability of Polymer-Infiltrated-Ceramic-Networks for CAD/CAM based dental restorative materials [dissertation]. University of Otago, New Zealand; 2014.
- Facenda JC, Borba M, Corazza PH. A literature review on the new polymer-infiltrated ceramic-network material (PICN). *J Esthet Restor Dent*. 2018 Feb 5. <https://doi.org/10.1111/jerd.12370> PMID:29399950
- Van Noort R. Introduction to dental materials. 3rd edn. Elsevier, Philadelphia 2007.
- Ho GW, Matinlinna JP. Insights on ceramics as dental materials. Part I: Ceramic material types in dentistry. *Silicon*. 2011; 3(3):109-15. <https://doi.org/10.1007/s12633-011-9078-7>
- Bajraktarova Valjakova E, Grozdanov A, Guguvcevski Lj, Korunoska-Stevkovska V, Kapusevska B, Gigovski N, Mijoska A, Bajraktarova Misevska C. Acid etching as surface treatment method for luting of glass-ceramic restorations, part I: Acids, application protocol and etching effectiveness. *Open Access Maced J Med Sci*. 2018; 6(3):568-73. <https://doi.org/10.3889/oamjms.2018.147> PMID:29610622 PMID:PMC5874387
- Darvel BW. Materials science for dentistry. 8th edn. Hong Kong. 2006.
- https://www.vitanorthamerica.com/datei.php?src=download/Support/Instructions-For-Use/Machinables/VITABLOCS-for-CEREC_inLab-Working-Instructions_1455E.pdf
- Bajraktarova Valjakova E, De Munck J, Yoshihara K, Misevska C, Grozdanov A, Peumans M, Van Meerbeek B. Micro-morphological changes of various CAD-CAM blocks after different surface treatments. 47th Meeting of CED-IADR, Antalya, Turkey; 2015. Abstr. No. 0576.
- Denry I. Recent advances in ceramics for dentistry. *Crit Rev Oral Biol Med*. 1996; 7(2):134-43. <https://doi.org/10.1177/10454411960070020201>
- Shenoy A, Shenoy N. Dental ceramics: An update. *J Conserv Dent*. 2010; 13(4):195-203. <https://doi.org/10.4103/0972-0707.73379> PMID:21217946 PMID:PMC3010023
- Denry I, Holloway JA. Ceramics for dental applications: A review. *Materials*. 2010; 3(1):351-68. <https://doi.org/10.3390/ma3010351> PMID:PMC5525170
- Holand W, Beall GH. Glass-Ceramic Technology. 2nd ed. Hoboken, NJ: Wiley, American Ceramic Society, Westerville, OH, USA, 2012: 440.
- <https://www.ivoclarvivadent.com/zoou-website/media/document/12207/IPS+Empress+CAD>
- Giordano R, McLaren EA. Ceramics overview: classification by microstructure and processing methods. *Compend Contin Educ Dent*. 2010; 31(9):682-8. PMID:21197937
- <https://www.ivoclarvivadent.com/zoou-website/media/.../IPS+Empress+CAD++Denti...>
- Borges GA, Sophr AM, de Goes MF, Sobrinho LC, Chan DC. Effect of etching and airborne particle abrasion on the microstructure of different dental ceramics. *J Prosthet Dent*. 2003; 89(5):479-88. [https://doi.org/10.1016/S0022-3913\(02\)52704-9](https://doi.org/10.1016/S0022-3913(02)52704-9)

31. Kracek FC. The binary system Li₂O - SiO₂. *J Phys Chem.* 1930;34(12); 2641-50. <https://doi.org/10.1021/j150318a001>
32. Culp L, McLaren EA. Lithium disilicate: the restorative material of multiple options. *Compend Contin Educ Dent.* 2010; 31(9):716-25. PMID:21197940
33. <https://www.ivoclarvivadent.com/zoolu-website/media/document/9793/IPS+e-max+CAD>
34. https://www.vita-zahnfabrik.com/pressemitteilungen_detail_ru,,52571,detail.print
35. Kruger S, Deubener J, Ritzberger C, Holand W. Nucleation kinetics of lithium metasilicate in ZrO₂-bearing lithium disilicate glasses for dental application. *Int J Appl Glass Sci.* 2013; 4(1):9-19. <https://doi.org/10.1111/ijag.12011>
36. Denry I, Kelly JR. Emerging ceramic-based materials for dentistry. *J Dent Res.* 2014; 93(12):1235-42. <https://doi.org/10.1177/0022034514553627> PMID:25274751 PMID:PMC4237640
37. <https://panadent.co.uk/wp-content/uploads/2014/10/Vita-Suprinity-Technical-and-Scientific-Document.pdf>
38. https://www.dentsply.com/content/dam/dentsply/pim/manufacture/Restoration/Indirect_Restoration/Ceramics/CAD_CAM_Ceramic/s/CELTRA_DUO/BRO_Celtra_Duo_EN_2017_08.pdf
39. Elsaka SE, Elnaghy AM. Mechanical properties of zirconia reinforced lithium silicate glass-ceramic. *Dent Mater.* 2016; 32(7):908-14. <https://doi.org/10.1016/j.dental.2016.03.013> PMID:27087687
40. <https://www.ivoclarvivadent.com/zoolu-website/media/document/.../IPS+e-max+Cera...>
41. <https://www.ivoclarvivadent.com/zoolu-website/media/.../40689/IPS+e-max+ZirPress>
42. Peng JY, Luo XP, Zhang L. Flexural strength and open porosity of two different veneering ceramics for zirconia framework. *Int J Appl Ceram Tech.* 2015; 12(2):383-9. <https://doi.org/10.1111/ijac.12158>
43. Leung BT, Tsoi JK, Matinlinna JP, Pow EH. Comparison of mechanical properties of three machinable ceramics with an experimental fluorophlogopite glass ceramic. *J Prosthet Dent.* 2015; 114(3):440-6. <https://doi.org/10.1016/j.prosdent.2015.02.024> PMID:26013069
44. Li RWK, Chow TW, Matinlinna JP. Ceramic dental biomaterials and CAD/CAM technology: State of the art. *J Prosthodont Res.* 2014; 58(4):208-16. <https://doi.org/10.1016/j.jpor.2014.07.003> PMID:25172234
45. http://www.cerec.co.il/downloads/vita_in_ceram.pdf
46. Guazzato M, Albakry M, Swain MV, Ironside J. Mechanical properties of In-Ceram Alumina and In-Ceram Zirconia. *Int J Prosthodont.* 2002; 15(4):339-46. PMID:12170847
47. Lu YC, Tseng H, Shin YH, Lee SY. Effects of surface treatments on bond strength of glass-infiltrated ceramic. *J Oral Rehabil.* 2001; 28(9):805-13. <https://doi.org/10.1046/j.1365-2842.2001.00735.x>
48. Özcan M, Alkumru HN, Gemalmaz D. The effect of surface treatment on the shear bond strength of luting cement to a glass-infiltrated alumina ceramic. *Int J Prosthodont.* 2001; 14(4):335-9. PMID:11508088
49. Valandro LF, Della Bona A, Antonio Bottino M, Neisser MP. The effect of ceramic surface treatment on bonding to densely sintered alumina ceramic. *J Prosthet Dent.* 2005; 93(3):253-9. <https://doi.org/10.1016/j.prosdent.2004.12.002> PMID:15775926
50. Kern M, Wegner SM. Bonding to zirconia ceramic: Adhesion methods and their durability. *Dent Mater.* 1998; 14(1):64-71. [https://doi.org/10.1016/S0109-5641\(98\)00011-6](https://doi.org/10.1016/S0109-5641(98)00011-6)
51. Ben-Nissan B, Choi AH, Cordingley R. Alumina ceramics. In: *Bioceramics and their clinical applications.* Kokubo T edit., Woodhead Publishing LTD, Cambridge, UK, 2008:223-242. <https://doi.org/10.1533/9781845694227.2.223>
52. Tsotsos S, Giordano R. CEREC inLab: Clinical Aspects, Machine and Materials. *CJDT Spectrum* January/February. 2003:64-8.
53. Guess PC, Schultheis S, Bonfante EA, Coelho PG, Ferencz JL, Silva NR. All-ceramic systems: Laboratory and clinical performance. *Dent Clin North Am.* 2011; 55(2):333-52. <https://doi.org/10.1016/j.cden.2011.01.005> PMID:21473997
54. Scherrer SS, Quinn GD, Quinn JB. Fractographic failure analysis of a Procera AllCeram crown using stereo and scanning electron microscopy. *Dent Mater.* 2008; 24(8):1107-13. <https://doi.org/10.1016/j.dental.2008.01.002> PMID:18314187 PMID:PMC2504694
55. Subbarao EC. Zirconia- an overview. In: Heuer AH, Hobbs LW, editors. *Advances in Ceramics.* The American Ceramic Society, Westerville, 1981:1-24.
56. Garvie RC, Nicholson PS. Phase analysis in zirconia systems. *J Am Ceram Soc.* 1972; 55(6):303-5. <https://doi.org/10.1111/j.1151-2916.1972.tb11290.x>
57. Kisi EH, Howard CJ. Crystal structures of zirconia phases and their inter-relation. *Key Eng Mater.* 1998; 153-154:1-36. <https://doi.org/10.4028/www.scientific.net/KEM.153-154.1>
58. Kelly JR, Denry I. Stabilized zirconia as a structural ceramic: An overview. *Dent Mater.* 2008; 24(3):289-98. <https://doi.org/10.1016/j.dental.2007.05.005> PMID:17624420
59. Denry I, Kelly R. State of the art of zirconia for dental applications. *Dent Mater.* 2008; 24(3):299-307. <https://doi.org/10.1016/j.dental.2007.05.007> PMID:17659331
60. Chevalier J, Gremillard L, Virkar AV, Clarke DR. The tetragonal-monoclinic transformation in zirconia: lessons learned and future trends. *J Am Ceram Soc.* 2009; 92(9):1901-20. <https://doi.org/10.1111/j.1551-2916.2009.03278.x>
61. Ruff O, Ebert F. Refractory ceramics: I. The forms of zirconium dioxide. *Z Anorg Allg Chem.* 1929; 180(1):19-41. <https://doi.org/10.1002/zaac.19291800104>
62. Ruff O, Ebert F, Stephan E. Contributions to the ceramics of highly refractory materials: II. System zirconia-lime. *Z Anorg Allg Chem.* 1929; 180(1):215-24. <https://doi.org/10.1002/zaac.19291800122>
63. Porter DL, Heuer AH. Microstructural development in MgO-partially stabilized zirconia (Mg-PSZ). *J Am Ceram Soc.* 1979; 62(5-6):298-305. <https://doi.org/10.1111/j.1151-2916.1979.tb09484.x>
64. Garvie RC, Urbani C, Kennedy DR, McNeuer JC. Biocompatibility of magnesia-partially stabilized zirconia (Mg-PSZ) ceramics. *J Mater Sci.* 1984; 19(10):3224-8. <https://doi.org/10.1007/BF00549808>
65. Heuer AH. Transformation toughening in ZrO₂-containing ceramics. *J Am Ceram Soc.* 1987; 70(10):689-98. <https://doi.org/10.1111/j.1151-2916.1987.tb04865.x>
66. Fassina P, Zaghini N, Bukat A, Piconi C, Greco F, Piantelli S. Yttria and calcia partially stabilized zirconia for biomedical applications. In: Ravaglioli A, Krajewski A, editors. *Bioceramics and the human body.* London and New York: Elsevier Applied Science, 1992:223-9. https://doi.org/10.1007/978-94-011-2896-4_29
67. Tanaka K, Tamura J, Kawanabe K, Nawa M, Oka M, Uchida M, Kokubo T, Nakamura T. Ce-TZP/Al₂O₃ nanocomposite as a bearing material in total joint replacement. *J Biomed Mater Res B: Appl Biomater.* 2002; 63(3):262-70. <https://doi.org/10.1002/jbm.10182> PMID:12115757
68. Zhang F, Vanmeensel K, Inokoshi M, Batuk M, Hadermann J, Van Meerbeek B, Naert I, Vleugels J. Critical influence of alumina content on the low temperature degradation of 2-3 mol% yttria-stabilized TZP for dental restorations. *J Eur Ceram Soc.* 2015; 35(2):741-50. <https://doi.org/10.1016/j.jeurceramsoc.2014.09.018>
69. Hannink RHJ, Kelly PM, Muddle BC. Transformation toughening in zirconia-containing ceramics. *J Am Ceram Soc.* 2000; 83(3):461-87. <https://doi.org/10.1111/j.1151-2916.2000.tb01221.x>

70. Claussen N, Steeb J. Toughening of ceramic composites by oriented nucleation of microcracks. *J Am Ceram Soc.* 1976; 59(9-10):457-8. <https://doi.org/10.1111/j.1151-2916.1976.tb09524.x>
71. Lugh V, Sergo V. Low temperature degradation-aging-of zirconia: A critical review of the relevant aspects in dentistry. *Dent Mater.* 2010; 26(8):807-20. <https://doi.org/10.1016/j.dental.2010.04.006> PMID:20537701
72. Ban S, Sato H, Suehiro Y, Nakahishi H, Nawa M. Biaxial flexure strength and low temperature degradation of Ce-TZP/Al₂O₃ nanocomposite and Y-TZP as dental restoratives. *J Biomed Mater Res B: Appl Biomater.* 2008; 87(2):492-8. <https://doi.org/10.1002/jbm.b.31131> PMID:18491411
73. Porter DL, Heuer AH. Mechanisms of toughening partially stabilized zirconia (PSZ). *J Am Ceram Soc.* 1977; 60(3-4):183-4. <https://doi.org/10.1111/j.1151-2916.1977.tb15509.x>
74. Lange FF, Dunlop GL, Davis BI. Degradation during ageing of transformation-toughened ZrO₂-Y₂O₃ materials at 250°C. *J Am Ceram Soc.* 1986; 69(3):237-40. <https://doi.org/10.1111/j.1151-2916.1986.tb07415.x>
75. Yoshimura M, Noma T, Kawabata K, Somiya S. Role of H₂O on the degradation process of Y-TZP. *J Mater Sci Lett.* 1987; 6(4):465-7. <https://doi.org/10.1007/BF01756800>
76. Deville S, Chevalier J, Fantozzi G, Torrecillas R, Bartolom JF, Moya JS. Atomic force microscopy study of the surface degradation mechanisms of zirconia based ceramics. *Ceram Eng Sci Proc.* 2004; 25:289-94. <https://doi.org/10.1002/9780470291191.ch44>
77. Deville S, Chevalier J, Dauvergne C, Fantozzi G, Bartolom JF, Moya JS, Torrecillas R. Microstructural investigation of the aging behavior of (3Y-TZP)-Al₂O₃ composites. *J Am Ceram Soc.* 2005; 88(5):1273-80. <https://doi.org/10.1111/j.1151-2916.2005.00221.x>
78. Lee JK, Kim H. Surface crack initiation in 2Y-TZP ceramics by low temperature aging. *Ceram Int.* 1994; 20(6):413-8. [https://doi.org/10.1016/0272-8842\(94\)90028-0](https://doi.org/10.1016/0272-8842(94)90028-0)
79. Li J-F, Watanabe R, Zhang B-P, Asami K, Hashimoto K. X-ray photoelectron spectroscopy investigation on the low-temperature degradation of 2 mol% ZrO₂-Y₂O₃ ceramics. *J Am Ceram Soc.* 1996; 79(12):3109-12. <https://doi.org/10.1111/j.1151-2916.1996.tb08084.x>
80. Tani E, Yoshimura M, Somiya S. Revised phase diagram of the system ZrO₂-CeO₂ below 1400 C. *J Am Ceram Soc.* 1983; 66(7):506-10. <https://doi.org/10.1111/j.1151-2916.1983.tb10591.x>
81. Sato T, Shimada M. Transformation of ceria-doped tetragonal zirconia polycrystals by annealing in water. *Am Ceram Soc Bull.* 1985; 64:1382-4.
82. Tsukuma K. Mechanical properties and thermal stability of CeO₂/sub₂ containing tetragonal zirconia polycrystals. *Am Ceram Soc Bull.* 1986; 65(10):1386-9.
83. Tsukuma K, Shimada M. Strength, fracture toughness and Vickers hardness of CeO₂-stabilized tetragonal ZrO₂ polycrystals (Ce-TZP). *J Mater Sci.* 1985; 20(4):1178-84. <https://doi.org/10.1007/BF01026311>
84. Heussner K-H, Claussen N. Strengthening of ceria-doped tetragonal zirconia polycrystals by reduction-induced phase transformation. *J Am Ceram Soc.* 1989; 72(6):1044-6. <https://doi.org/10.1111/j.1151-2916.1989.tb06267.x>
85. Sergo V, Schmid C, Meriani S, Evans AG. Mechanically induced darkening of alumina/ceria-stabilized zirconia composites. *J Am Ceram Soc.* 1994; 77(11):2971-6. <https://doi.org/10.1111/j.1151-2916.1994.tb04533.x>
86. Schmauder S, Schubert U. Significance of internal stresses for the martensitic transformation in yttria-stabilized tetragonal zirconia polycrystals during degradation. *J Am Ceram Soc.* 1986; 69(7):534-40. <https://doi.org/10.1111/j.1151-2916.1986.tb04789.x>
87. Sergo V, Pompe W, Clarke DR. Deformation bands in ceria-stabilized tetragonal zirconia/alumina: I. Measurement of internal stresses. *J Am Ceram Soc.* 1995; 78(3):633-40. <https://doi.org/10.1111/j.1151-2916.1995.tb08224.x>
88. Sergo V, Clarke DR. Deformation bands in ceria-stabilized tetragonal zirconia/alumina: II. Stress-induced aging at room temperature. *J Am Ceram Soc.* 1995; 78(3):641-4. <https://doi.org/10.1111/j.1151-2916.1995.tb08225.x>
89. Suresh A, Mayo MJ, Porter WD, Rawn CJ. Crystallite and grain-size-dependent phase transformations in yttria-doped zirconia. *J Am Ceram Soc.* 2003; 86(2):360-2. <https://doi.org/10.1111/j.1151-2916.2003.tb00025.x>
90. Hallmann L, Mehl A, Ulmer P, Reusser E, Stadler J, Zenobi R, Stawarczyk B, Özcan M, Hammerle CHF. The influence of grain size on low-temperature degradation of dental zirconia. *J Biomed Mater Res. Part B.* 2012; 100B(2):447-56. <https://doi.org/10.1002/jbm.b.31969> PMID:22121144
91. Inokoshi M, Zhang F, De Munck J, Minakuchi S, Naert I, Vleugels J, Van Meerbeek B, Vanmeensel K. Influence of sintering conditions on low-temperature degradation of dental zirconia. *Dent Mater.* 2014; 30(6):669-78. <https://doi.org/10.1016/j.dental.2014.03.005> PMID:24698437
92. Hjerpe J, Vallittu PK, Fröberg K, Lassila LVJ. Effect of sintering time on bi-axial strength of zirconium dioxide. *Dent Mater.* 2009; 25(2):166-71. <https://doi.org/10.1016/j.dental.2008.05.011> PMID:18632146
93. Chevalier J, Deville S, Münch E, Jullian R, Lair F. Critical effect of cubic phase on aging in 3 mol% yttria-stabilized zirconia ceramics for hip replacement prosthesis. *Biomaterials.* 2004; 25(24):5539-45. <https://doi.org/10.1016/j.biomaterials.2004.01.002> PMID:15142736
94. Zhang F, Vanmeensel K, Inokoshi M, Batuk M, Hadermann J, Van Meerbeek B, Naert I, Vleugels J. 3Y-TZP ceramics with improved hydrothermal degradation resistance and fracture toughness. *J Eur Ceram Soc.* 2014; 34:2453-63. <https://doi.org/10.1016/j.jeurceramsoc.2014.02.026>
95. Inokoshi M, Vanmeensel K, Zhang F, De Munck J, Eliades G, Minakuchi S, Naert I, Van Meerbeek B, Vleugels J. Aging resistance of surface-treated dental zirconia. *Dent Mater.* 2015; 31(2):182-94. <https://doi.org/10.1016/j.dental.2014.11.018> PMID:25572860
96. Kosmač T, Oblak Č, Jevnikar P, Funduk N, Marion Lj. Strength and reliability of surface treated Y-TZP dental ceramics. *J Biomed Mater Res.* 2000; 53(4):304-13. [https://doi.org/10.1002/1097-4636\(2000\)53:4<304::AID-JBM4>3.0.CO;2-S](https://doi.org/10.1002/1097-4636(2000)53:4<304::AID-JBM4>3.0.CO;2-S)
97. Hjerpe J, Närhi T, Fröberg K, Vallittu PK, Lassila LVJ. Effect of shading the zirconia framework on biaxial strength and surface microhardness. *Acta Odontol Scand.* 2008; 66(5):262-7. <https://doi.org/10.1080/00016350802247123> PMID:18645687
98. Piconi C, Maccauro G, Muratori F. Alumina matrix composites in arthroplasty. *Key Eng Mater.* 2005; 284-286:979-82. <https://doi.org/10.4028/www.scientific.net/KEM.284-286.979>
99. Winchester LJ. Bond strengths of five different ceramic brackets: an in vitro study. *Eur J Orthod.* 1991; 13(4):293-305. <https://doi.org/10.1093/ejo/13.4.293> PMID:1915618
100. Meyenberg KH, Lüthy H, Schärer P. Zirconia posts: a new all-ceramic concept for nonvital abutment teeth. *J Esthet Dent.* 1995; 7(2):73-80. <https://doi.org/10.1111/j.1708-8240.1995.tb00565.x> PMID:8593239
101. Luthardt RG, Sandkuhl O, Reitz B. Zirconia-TZP and alumina - advanced technologies for the manufacturing of single crowns. *Eur J Prosthodont Restor Dent.* 1999; 7(4):113-9. PMID:11314423
102. Komine F, Blatz MB, Matsumura H. Current status of zirconia-based fixed restorations. *J Oral Sci.* 2010; 52(4):531-9. <https://doi.org/10.2334/josnusd.52.531> PMID:21206154
103. Li J, Liao H, Hermansson L. Sintering of partially-stabilized zirconia and partially-stabilized zirconia-hydroxyapatite composites by hot isostatic pressing and pressureless sintering. *Biomaterials.* 1996; 17(18):1787-90. [https://doi.org/10.1016/0142-9612\(95\)00356-8](https://doi.org/10.1016/0142-9612(95)00356-8)
104. Stawarczyk B, Özcan M, Trottmann A, Hammerle CHF, Roos M. Evaluation of flexural strength of hiped and presintered

- zirconia using different estimation methods of Weibull statistics. *J Mech Behav Biomed Mater.* 2012;10:227-34. <https://doi.org/10.1016/j.jmbbm.2012.01.020> PMID:22520434
105. Badwal SPS. Zirconia-based solid electrolytes: microstructure, stability and ionic conductivity. *Solid State Ionics.* 1992; 52(1-3):23-32. [https://doi.org/10.1016/0167-2738\(92\)90088-7](https://doi.org/10.1016/0167-2738(92)90088-7)
106. Fasbinder DJ. Chairside CAD/CAM: An overview of restorative material options. *Compend Contin Educ Dent.* 2012; 33(1):50,52-8. PMID:22432177
107. American Dental Association. CDT: Code on dental procedures and nomenclature. <http://www.ada.org/en/publications/cdt/>.
108. http://www.d-way.cz/data/product/13/23/files/Lava_Ult_TPP.pdf
109. Studart AR. Towards high-performance bio-inspired composites. *Advanced Materials.* 2012; 24(37):5024-44. <https://doi.org/10.1002/adma.201201471> PMID:22791358
110. https://mam.vita-zahnfabrik.com/portal/ecms_mdb_download.php?id=31792&sprache=en&fallback=&cls_session_id=&neuste_version=1
111. <https://www.vitanorthamerica.com/en-US/VITA-ENAMIC-multiColor-276.html>
112. Coldea A, Swain MV, Thiel N. Mechanical properties of polymer-infiltrated-ceramic-network materials. *Dent Mater.* 2013; 29(4):419-26. <https://doi.org/10.1016/j.dental.2013.01.002> PMID:23410552
113. Lauvahutanon S, Takahashi H, Shiozawa M, Iwasaki N, Asakawa Y, Oki M, Finger WJ, Arksornnukit M. Mechanical properties of composite resin blocks for CAD/CAM. *Dent Mater J.* 2014; 33(5):705-10. <https://doi.org/10.4012/dmj.2014-208> PMID:25273052
114. Mörmann W, Stawarczyk B, Ender A, Sener B, Attin T, Mehl A. Wear characteristics of current aesthetic dental restorative CAD/CAM materials: Two-body wear, gloss retention, roughness and Martens hardness. *J Mech Behav Biomed Mater.* 2013; 20(4):113-25. <https://doi.org/10.1016/j.jmbbm.2013.01.003> PMID:23455168
115. Dirxen C, Blunck U, Preissner S. Clinical performance of a new biomimetic double network material. *Open Dent J.* 2013; 6(7):118-22. <https://doi.org/10.2174/1874210620130904003> PMID:24167534 PMID:PMC3807582
116. http://www.gcamerica.com/products/digital/CERASMART_Universal/GCA_CERASMART_Universal_Bro-iPad.pdf
117. Awada A, Nathanson D. Mechanical properties of resin-ceramic CAD/CAM restorative materials. *J Prosthet Dent.* 2015;114(4):587-93. <https://doi.org/10.1016/j.prosdent.2015.04.016> PMID:26141648