

SYNTHESIS AND CHARACTERIZATION OF TITANIUM DIOXIDE BASED TERNARY NANOCOMPOSITES FOR PHOTOCATALYTIC HYDROGEN PRODUCTION

Árpád Turcsányi¹, Emília Tálás², Szijjártó Gábor², Ágnes Veres¹, Imre Dékány¹, András Tompos², Tamás Szabó¹

¹*Department of Physical Chemistry and Materials Science, University of Szeged, H-6720 Szeged, Aradi vértanúk tere 1, Hungary*

²*Institute of Materials and Environmental Chemistry, Research Centre for Natural Sciences, Hungarian Academy of Sciences, H-1117 Budapest, Magyar tudósok körútja 2, Hungary*

Abstract

Titanium dioxide based photocatalysts of different graphene oxide (GO) and silver nanoparticle (AgNP) content were prepared and tested in catalytic methanol reformation reaction. Aqueous suspensions of the composite solids obtained by heterocoagulation of alkaline exfoliated GO suspension and slightly acidic TiO₂ suspension showed enhanced sedimentation rate at pH = 6.5-7, when they contained less than 2 wt% graphene oxide. This enables easier catalyst recovery but the suspension needs to be stirred strongly during the catalytic run in order to achieve homogeneous light distribution within the reaction vessel.

The catalytic runs were performed in 6 V/V% methanol/water mixture using 500 mg/L catalyst under UV-illumination. The activity of pure titanium dioxide (Degussa P25) continuously increases and reaches a saturation plateau after 150 min with an activity of 0.12 mmol H₂/(h×g_{cat}). Incorporation of GO into the titanium dioxide matrix by heterocoagulation method results in aggregated suspensions exhibiting an enhancement of the hydrogen evolution rate to the saturation value of 0.17 mmol H₂/(h×g_{cat}). Deposition of different amounts of AgNPs of different sizes onto the surface of titanium dioxide resulted in an even higher photocatalytic activity, reaching 0.25-0.29 mmol H₂/(h×g_{cat}). The combination of AgNP's and GO platelets to obtain ternary TiO₂ based catalysts has not shown any further increase of hydrogen generation rate.