

# Photocatalytic Decomposition of Nitrous Oxide using TiO<sub>2</sub> and Ag-TiO<sub>2</sub> Nanocomposite Thin Films

*L. Obalová\*, M. Reli, J. Lang, V. Matějka, J. Kukutschová, K. Kočí*

*VŠB - Technical University of Ostrava, 17. listopadu 15, Ostrava, Czech Republic*

*\*Corresponding author. Phone: +420 596991532, e-mail: lucie.obalova@vsb.cz*

## Abstract

TiO<sub>2</sub> and Ag-TiO<sub>2</sub> (0.05, 0.25 and 1 wt% of Ag) thin films were prepared by the sol-gel method. The prepared films were characterized using SEM-EDAX, XRD, Raman spectroscopy, atomic force microscopy and UV-Vis spectrometry. Photocatalytic decomposition of N<sub>2</sub>O was performed in an annular batch reactor illuminated with an 8 W Hg lamp (254 nm wavelength). The photoreactivity of Ag-TiO<sub>2</sub> increases with the Ag amount to 0.25 wt% Ag. Further increase of Ag loading to 1 wt% Ag did not change N<sub>2</sub>O conversion. The Ag particles deposited on the TiO<sub>2</sub> surface can act as electron-hole separation centers. The presence of water vapor and oxygen in the reaction mixture slightly improved N<sub>2</sub>O conversion.

**Key words:** N<sub>2</sub>O, Photocatalytic decomposition, Ag, TiO<sub>2</sub>, Thin film

## 1. Introduction

N<sub>2</sub>O is the third most important of the long-lived greenhouse gases in terms of global warming, accounting for 6.2% of the total global radiative forcing. Although it only comprises 320 parts per billion of the earth's atmosphere, its contribution to global warming is important, as it has a GWP<sub>100</sub> (global warming potential time horizon of 100 years) nearly 300 times greater than that of CO<sub>2</sub> [1].

The largest anthropogenic source of nitrous oxide (N<sub>2</sub>O) is agriculture (use of synthetic nitrogen fertilizers) and cattle breeding. N<sub>2</sub>O is also emitted from the industrial production of nitric acid and of adipic acid, fossil fuel combustion and biomass burning. An important message is that N<sub>2</sub>O emission has been identified for aged three-way catalysts. N<sub>2</sub>O is also formed in soils and oceans throughout the world by a natural biogeochemical nitrogen cycle: the microbial processes of nitrification of ammonium and denitrification of nitrate. As they are predominantly biogenic in origin, N<sub>2</sub>O emissions are difficult to estimate, but the quantity of this gas has virtually doubled since the beginning of the industrial age. The concentration

of N<sub>2</sub>O in the atmosphere continues to increase (0.2–0.3% yearly), and this increase appears to be caused mainly by anthropogenic activities [1]. Photocatalytic decomposition of N<sub>2</sub>O under UV irradiation on semiconductor photocatalysts (Eq. 1) is one of the candidate methods for its removal.



N<sub>2</sub>O can be reduced by the electrons generated by UV irradiation on semiconductor photocatalysts. Since photocatalysts are suitable for treatment of low-concentration gases and are used at room temperature with light as the energy source, photocatalytic decomposition has many advantages: the concentration process is not necessary, the reaction conditions are mild, and furthermore, when sunlight would be utilized, it will lead to energy savings. While thermal catalytic decomposition of N<sub>2</sub>O (without light) is suitable mainly for N<sub>2</sub>O abatement from waste gases from industry and combustion, N<sub>2</sub>O photocatalytic decomposition might help to reduce its concentration in the atmosphere caused by other sources. The first field experiment of decreasing the N<sub>2</sub>O concentration in a pig house by coating the walls with TiO<sub>2</sub>, carried out in 2008 [1], showed that this method is feasible in real conditions.

In comparison with thermal catalytic decomposition of N<sub>2</sub>O, there are only a few papers dealing with this. These researchers focused on Cu and Ag ion-exchanged powder zeolite catalysts [2, 3], and Cu<sup>I</sup> ion anchored on various oxides (SiO<sub>2</sub>.Al<sub>2</sub>O<sub>3</sub>, Al<sub>2</sub>O<sub>3</sub>, SiO<sub>2</sub>) [4-5].

Also, the most famous TiO<sub>2</sub> photocatalyst was tested for N<sub>2</sub>O photocatalytic decomposition [6]. TiO<sub>2</sub> may be doped or combined by non-metallic ions, metallic ions, and other semiconductors. Improved photocatalytic activity was observed after the doping of TiO<sub>2</sub> by Pt [6] and Ag [7, 8]. Noble metals deposited on or doped into the TiO<sub>2</sub> lattice provide high Schottky barriers and act as electron traps which facilitate e<sup>-</sup> - h<sup>+</sup> separation and promote interfacial electron transfer processes. These phenomena enhance the photocatalytic activity of TiO<sub>2</sub> through the decreasing of the carriers' recombination rate.

However, some noble metals such as Pt, Pd, Rh, and Au are too expensive to be used on an industrial scale. Since silver is not as expensive, research on Ag-doped TiO<sub>2</sub> has a significant practical value. Silver is suitable for industrial applications due to its low cost and easy preparation. Moreover, silver has been observed to play an important role in increasing the photocatalytic stability of TiO<sub>2</sub> as well [9].

In our recent work, Ag-enriched TiO<sub>2</sub> powders with various Ag loading (0.7–5.2 wt%) were prepared by a sol-gel process controlled in the reverse micellar environment, and successfully used for N<sub>2</sub>O photocatalytic decomposition to oxygen and nitrogen [8]. The

highest N<sub>2</sub>O conversion after 24 hours was reached in the presence of 3.4 wt% Ag-TiO<sub>2</sub> catalyst.

Recent investigations on TiO<sub>2</sub> photocatalysis are oriented towards the photocatalyst immobilization in the form of a thin film. The immobilization of the photocatalyst in the form of a thin film overcomes the drawbacks encountered with the powder form of catalyst: (1) the difficulty of separating inactive catalysts, (2) the difficulty of applying them to continuous flow systems, and (3) the tendency of the particle catalysts to aggregate [10].

Ag is one of the most promising transition metals for the improvement of photocatalytic activity of TiO<sub>2</sub> thin film [11] and has been investigated extensively in the literature e.g. for the degradation of organic pollutants [11-15] or bacteria degradation [16]. However, any thin films have not yet been tested for N<sub>2</sub>O photocatalytic decomposition. For that reason we decided to prepare TiO<sub>2</sub> and Ag-modified TiO<sub>2</sub> thin films and investigate them for this reaction. To simulate real conditions, the effect of oxygen and water vapor on the N<sub>2</sub>O conversion was also tested as it has been studied only rarely.

## 2. Experimental

### 2.1. TiO<sub>2</sub> and Ag-TiO<sub>2</sub> thin film preparation

Films i) TiO<sub>2</sub> and ii) Ag-TiO<sub>2</sub> were prepared. The synthesis of the TiO<sub>2</sub> film was performed according to the procedure described by Zita et al. [17]. In this procedure, two independent solutions A and B are prepared. Solution A consists of 36 ml titanium tetraisopropoxide (TTIP, Sigma Aldrich) and 50 ml of anhydrous ethylalcohol (EtOH, Lachema), and solution B consists of 50 ml EtOH, 10 ml ethyl acetoacetate (EA, Merck) and 8.5 ml of concentrated HCl (Lachema). Solution A was dropwise added into the stirred solution B.

The sol for preparation of Ag-TiO<sub>2</sub> film was prepared using a previously slightly modified procedure based on the addition of the appropriate amount of the AgNO<sub>3</sub> (to give 0.05, 0.25 and 1 wt.% of Ag in final sol) into solution A under stirring. Both sols for preparation of TiO<sub>2</sub> as well as Ag-TiO<sub>2</sub> films were stirred for 24 hours using an electromagnetic stirrer. The prepared sol was dip-coated using COATER5 (idLAB) on the microscopy slide glass tubes (length of 10 cm, i.d. of 4 cm, Marienfield). The coating parameters were: dipping speed 20 cm/min, a delay of 3 s, and withdrawing speed 6 cm/min. The samples were calcined at 500°C for 1 h. A coated surface of 124.5 cm<sup>2</sup> is expected for each glass tube.

## 2.2. Characterization of $TiO_2$ and Ag- $TiO_2$ thin films

Various techniques were used to characterize the prepared layers. The scanning electron microscope (SEM) Philips XL30 with energy dispersive X-ray microanalysis (EDAX) was utilized for determination of the Ag content in prepared films.

Transmission spectra of the thin films deposited on the microscope slides were recorded using fiber optic spectrometer USB4000 (OceanOptics), and a deuterium tungsten halogen source DT-MINI-2GS (OceanOptics) was used as a light source. The pure microscope slide calcined for 1 h at 500°C was used for setting the background.

Raman spectra of all samples were obtained using a Smart Raman Microscopy System XploRA™ (HORIBA Jobin Yvon, France). Raman spectra were acquired with a 532 nm excitation laser source, 100x objective and grating with 600 gr./mm. Achieved Raman spectra were processed by LabSpec software.

The atomic force microscope (AFM) SOLVER NEXT (NT-MDT) operating in the semicontact mode and PPP-NCHR probes (Nanosensors) were utilized for observation of the topography of the as prepared and calcined thin films. The data were evaluated using software Gwyddion ver. 2.26.

## 2.3. Photocatalytic reactivity experiments

Photocatalytic  $N_2O$  decomposition was carried out in a homemade apparatus at an ambient temperature. The glass tube with a catalyst thin film was inserted in the batch annular reactor (volume of 450 ml). The reactor was filled with 0.1 molar%  $N_2O/He$  mixture and illuminated by an 8 W Hg lamp with a peak light intensity at 254 nm. Water vapor (0.8 molar %) and oxygen (6.5 molar %) were added to the reaction mixture in some experimental runs. During the reaction, pressure and temperature inside the reactor were monitored. Gas chromatograph with thermal conductivity detector (GC/TCD) equipped with the Molsieve and HP Poraplot Q columns was used for the analysis of  $N_2O$  and  $O_2/N_2$  molar ratio. The  $N_2O$  concentration level was measured before switching on a UV lamp, and during the irradiation. The reproducibility of photocatalytic experiments was verified by repeated tests.

The  $N_2O$  conversion was determined according to Eq. 2 provided that the total pressure in the reactor could be considered as constant due to low  $N_2O$  concentration.

$$X_{N_2O} = \frac{x_{N_2O}^o - x_{N_2O}}{x_{N_2O}^o} \quad (2)$$

Where  $x_{N_2O}^o$ ,  $x_{N_2O}$  is the  $N_2O$  concentration at the beginning of reaction ( $t = 0$ ) and at different times during the photocatalytic reaction, respectively.

### 3. Results and discussion

#### 3.1. Characterization of $TiO_2$ and $Ag-TiO_2$ thin films

Chemical analysis of  $Ag-TiO_2$  films using EDAX analysis confirmed the Ag content to be 0.05, 0.25 and 1 wt.%, respectively. SEM images (Fig. 1) show all the samples of the anatase film on the glass microscope slides to have amorphous character with crystalic salts based on various chlorides on the surface of the film. The chlorides come from the synthesis of the film.

Fig. 2 shows the dependency of transmittance of prepared films on wavelength of irradiation. The run of the registered transmittance spectra is typical for thin layers consisting of the  $TiO_2$ . It is evident that the transmittance of the  $TiO_2$  layers doped with silver reaches slightly higher values in comparison to pure  $TiO_2$  layer and  $TiO_2$  layer with the lowest content of Ag. The strong decrease in transmittance of optical spectra for all samples was evident in the the UV region proving the semiconducting properties of the  $TiO_2$  and  $Ag-TiO_2$  films due to the existence of the band gap. The strong absorption of irradiation starts to occur below the wavelength 350 nm ( $\sim 3.5$  eV) for sample 0.05% $Ag-TiO_2$ , below 360 nm ( $\sim 3.4$  eV) for sample  $TiO_2$  and below 370 nm ( $\sim 3.4$  eV) for samples 0.25% $Ag-TiO_2$  and 1% $Ag-TiO_2$ . The estimated band gap energies are slightly higher in comparison with the energy of pure  $TiO_2$  in anatase form  $\sim 3.2$  eV. The higher band gaps observed at our samples could be associated with the nano-crystalline nature of the prepared films.

Fig. 3 shows the Raman spectra in the range of  $100-700\text{ cm}^{-1}$  of  $Ag-TiO_2$  films annealed at  $500^\circ\text{C}$ . An intensive band at  $137\text{ cm}^{-1}$  and low intensity bands around 190, 390, 540, and  $635\text{ cm}^{-1}$  verify the  $TiO_2$  presence in the anatase form [18]. Compared to the literature, the most intense peak of the anatase single crystal at  $144\text{ cm}^{-1}$  [19] was in the Raman spectra of the calcined films shifted towards a lower frequency. This shift may be attributed to the higher roughness of the  $Ag-TiO_2$  thin film in comparison with anatase single crystal as was also observed by Medina-Valtierra et al. [20]. No bands belonging to the rutile form were observed. The main difference evident from the Raman spectra is in the width of the most intense band at  $137\text{ cm}^{-1}$ . Full width half-maximum (FWHM) determined for this band was the highest for the pure  $TiO_2$  sample ( $45.8\text{ cm}^{-1}$ ) while the Ag-modified samples

have much lower values of FWHW (down to 22.8 cm<sup>-1</sup>). This tendency may show the Ag-modified samples to have less amorphous character compared to the pure TiO<sub>2</sub> sample.

The surface topography of the original and calcined thin films reveals the 3D images obtained using semi-contact AFM. Surface topography of the thin film assigned as 0.05% Ag-TiO<sub>2</sub> in non-calcined state and after its 1 hour calcinations at 500°C is shown in Fig. 4 a, b, respectively. Surface topography of the thin films assigned as 0.25% Ag-TiO<sub>2</sub> and 1% Ag-TiO<sub>2</sub> in non-calcined state and after its 1 hour long calcinations at 500°C are shown in Figs. 4 c, d and e, f. The determined values of the root mean square height of the surface (Sq) of the prepared thin films are summarized in Table 1.

The effect of the silver on the properties of the TiO<sub>2</sub> films is evident from the AFM images. All of the non-calcined films show porous structure, when regularly distributed holes appeared mainly in the case of the films containing silver, also apparent porosity is higher in the case of the silver doped films. After the calcination at 500°C, the surface characteristic of all of the films changed. The surface roughness of the pure TiO<sub>2</sub> thin film increases after the calcination, whereas the surface roughness of the thin film with Ag decreases after the calcination. It is also evident, that the higher the content of the silver, the lower the value of the root mean square height (Sq) of the surface (see Table. 1). It can be considered that the presence of the silver has an inhibitory effect on the TiO<sub>2</sub> grains growth.

### 3.2. The photocatalytic decomposition of N<sub>2</sub>O

The effect of irradiation time on the photocatalytic decomposition of N<sub>2</sub>O was studied for TiO<sub>2</sub> and Ag-TiO<sub>2</sub> thin films during 0–24 h (Fig. 5). The gradual increase of N<sub>2</sub>O conversion with increasing Ag content was observed; the highest N<sub>2</sub>O conversions of 45% over samples containing 0.25% and 1% Ag in reaction time of 24 hours were reached. N<sub>2</sub>/O<sub>2</sub> molar ratio close to the expected value of 2 confirmed that N<sub>2</sub>O decomposes only to nitrogen and oxygen. An integral form of material balance of batch reactor with ideal mixing working in isothermal and isobaric regime and 1<sup>st</sup> order kinetic equation  $r = k c_{N_2O}$  were used for data processing:

$$\ln \frac{1}{1-X} = k \frac{S_{cat}}{V} t \quad (1)$$

Where  $c_{N_2O}$  is a concentration of N<sub>2</sub>O (mol cm<sup>-3</sup>),  $k$  is kinetic constant (cm<sup>3</sup> h<sup>-1</sup> cm<sub>cat</sub><sup>-2</sup>),  $r$  is reaction rate (mol cm<sub>cat</sub><sup>-2</sup>h<sup>-1</sup>),  $t$  is reaction time (h),  $V$  is volume of reactor (cm<sup>3</sup>),  $S_{cat}$  surface of catalyst film (cm<sub>cat</sub><sup>2</sup>) and  $X$  is N<sub>2</sub>O conversion (-). Evaluation of the kinetic

confirmed that the reaction kinetics was well described by 1<sup>st</sup> rate order which is in agreement with plausible reaction mechanisms published recently on Ag-TiO<sub>2</sub> photocatalyst powders [8]. The effect of silver doping on the kinetic constants  $k$  of N<sub>2</sub>O photocatalytic decomposition is shown in Table 1. The photoreactivity of Ag-TiO<sub>2</sub> increases with Ag amount to 0.25% Ag. Nevertheless, further increase of Ag loading (1%) enhances the kinetic constant only slightly in accordance with measured N<sub>2</sub>O conversions. Thus, the range 0.25% - 1% Ag loading seems to be the optimal amount with respect to a catalyst's activity (the highest kinetic constant).

The Ag loading content has an important effect on the photocatalytic activity. Too much Ag loading content may result in a photohole trapping effect. Due to the fact that the Ag particles and clusters on the TiO<sub>2</sub> nanoparticles are relatively negative charged due to the formation of the Schottky barriers, the photoholes in the interfacial region of the TiO<sub>2</sub> film may be trapped by the negatively charged Ag particles and clusters before they react with N<sub>2</sub>O. This trapping effect was neglectable when the Ag concentration is below 1wt.%, and the Schottky barrier predominantly promoted the TiO<sub>2</sub> charge separation efficiency. The TiO<sub>2</sub> photocatalytic activities, therefore, increased with the increasing Ag concentration. With the Ag concentration increasing beyond this threshold, however, the trapping effect became prevailing and the decrease of photocatalytic activity is expected. The decline in the photocatalytic activity can also be associated with the change of the reaction site density. As the Ag<sup>+</sup> concentration increased beyond threshold value, the coverage of Ag on TiO<sub>2</sub> surface will increase. In other words, the density of reaction sites (for adsorption of UV light, to produce photohole and photoelectrons) at the surface of the resulting film would decrease. Consequently, the TiO<sub>2</sub> photocatalysis is depressed [21].

The effect of oxygen and water vapour presence on N<sub>2</sub>O photocatalytic decomposition was tested over the most active 1%Ag-TiO<sub>2</sub> photocatalyst. Oxygen and water vapour are always present in atmosphere together with N<sub>2</sub>O and it is known that they often inhibit the rate of N<sub>2</sub>O thermal decomposition, mainly due to the competitive adsorption on active sites [22]. In N<sub>2</sub>O photocatalytic decomposition, a completely opposite effect was observed (Fig. 6): higher N<sub>2</sub>O conversion corresponding to the higher 1<sup>st</sup> order rate constant was obtained in the presence of O<sub>2</sub> and H<sub>2</sub>O in comparison with N<sub>2</sub>O photocatalytic decomposition in inert gas (Table 1). It could be caused by reduction of N<sub>2</sub>O by atomic hydrogen formed by the photoreduction of water on an Ag-TiO<sub>2</sub> photocatalyst [7].

Increase of N<sub>2</sub>O conversion in the presence of water vapour e.g. over TiO<sub>2</sub> modified by Ag, Cu, Ru and Pt [6], as well as a decrease of N<sub>2</sub>O conversion e.g. over Ag-TiO<sub>2</sub> [7] was published for N<sub>2</sub>O photocatalytic decomposition. It depends on the photocatalyst type and on

its properties. If the splitting of water proceeds simultaneously with N<sub>2</sub>O photocatalytic decomposition, an increase of N<sub>2</sub>O conversion can be expected.

Reducing agents such as CO, NH<sub>3</sub> or methanol have been described for N<sub>2</sub>O photocatalytic reduction in literature [6, 7, 23]. The necessity of reductant storage, dosing and undesirable products of its oxidation are among the main disadvantages. From this point of view, water as a reductant seems to be favorable. However, further research needs to be performed for broadening the light spectrum range allowing the adsorption of the solar energy.

#### 4. Conclusions

TiO<sub>2</sub> and Ag-TiO<sub>2</sub> thin films were successfully prepared by dip-coating on glass tubes and showed promising photocatalytic activity for N<sub>2</sub>O decomposition. The gradual increase of N<sub>2</sub>O conversion with increasing Ag content was observed, and samples containing 0.25 wt% and 1 wt% Ag were the most active. Moreover, a slight increase in N<sub>2</sub>O conversion in the presence of water vapor and oxygen was observed. Atomic hydrogen formed by the photoreduction of water on an Ag-TiO<sub>2</sub> photocatalyst acts as a reducing agent. Reaction kinetics was well described by 1<sup>st</sup> rate. The Ag particles deposited on the TiO<sub>2</sub> surface can act as electron-hole separation centers, retarded their recombination and increased N<sub>2</sub>O conversion.

#### Acknowledgements

This paper has been elaborated in the framework of the Nanotechnology – the basis for international cooperation project, reg. no. CZ.1.07/2.3.00/20.0074 supported by Operational Programme 'Education for competitiveness' funded by Structural Funds of the European Union and state budget of the Czech Republic and EU - projects No. CZ.1.05/2.1.00/03.0069 „ENET“ and No. CZ.1.05/2.1.00/03.0100 „Institute of Environmental Technologies“.

#### References

- [1] R. Richter, S. Caillol, *Journal of Photochemistry and Photobiology C: Photochemistry Reviews*, 12 (2011) 1.
- [2] K. Ebitani, Y. Hirano, A. Morikawa, *Journal of Catalysis*, 157 (1995) 262.
- [3] M. Matsuoka, W.-S. Ju, H. Yamashita, M. Anpo, *Journal of Photochemistry and Photobiology A: Chemistry*, 160 (2003) 43.



- [4] M. Matsuoka, K. Takahashi, H. Yamashita, M. Anpo, *Journal de Physique IV France*, 7 (1997) 943.
- [5] M. Matsuoka, W.-S. Ju, K. Takahashi, H. Yamashita, M. Anpo, *Journal of Physical Chemistry*, 104 (2000) 4911.
- [6] A. Kudo, T. Sakata, *Chemistry Letters*, (1992) 2381.
- [7] T. Sano, N. Negishi, D. Mas, K. Takeuchi, *Journal of Catalysis*, 194 (2000) 71.
- [8] K. Kočí, S. Krejčíková, Z. Lacný, O. Šolcová, L. Obalová, *Catalysis Today*, 191 (2012) 134.
- [9] N. Salami, M.R. Bayati, F. Golestani-Fard, H.R. Zargar, *Material Research Bulletin*, 47 (2012) 1080.
- [10] N. Alenzi, W.-S. Liao, P.S. Cremer, V. Sanchez-Torres, T.K. Wood, Ch. Ehlig-Economides, Z. Cheng, *International Journal of Hydrogen Energy*, 35 (2010) 11768.
- [11] C. He, Y. Xiong, J. Chen, C. Zha, X. Zhu, *Journal of Photochemistry and Photobiology A: Chemistry*, 157 (2003) 71.
- [12] Ch.-Ch. Chang, Ch.-K. Lin, Ch.-Ch. Chan, Ch.-S. Hsu, Ch.-Y. Chen, *Thin Solid Films*, 494 (2006) 274.
- [13] A.A. Ismail, *Microporous and Mesoporous Materials*, 149 (2012) 69.
- [14] Jinyu Zheng, Hua Yu, Xinjun Li, Shanqing Zhang, *Applied Surface Science*, 254 (2008) 1630.
- [15] X.-G. Hou, M.-D. Huang, X.-L. Wu, A.-D. Liu, *Chemical Engineering Journal*, 146 (2009) 42.
- [16] O. Akhavan, E. Ghaderi, *Surface and Coatings Technology*, 204 (2010) 3676.
- [17] J. Zita, J. Maixner, J. Krýsa, *Journal of Photochemistry and Photobiology A: Chemistry*, 216 (2010) 194.
- [18] S.K. Gupta, R. Desai, P.K. Jha, S. Sahoo, D. Kirin, *Journal of Raman Spectroscopy*, 41 (2010) 350.
- [19] H.C. Choi, Y.M.Jung, S.B.Kim, *Vibrational Spectroscopy*, 37 (2005) 33.
- [20] J. Medina-Valtierra, C. Frausto-Reyes, J. Ramírez-Ortiz, E. Moctezuma, F. Ruiz, *Applied Catalysis B: Environmental*, 76 (2007) 264.
- [21] J. Zheng, H. Yu, X. Li, S. Zhang, *Applied Surface Science*, 254 (2008) 1630.
- [22] F. Kapteijn, J. Rodriguez-Mirasol, J.A. Moulijn, *Applied Catalysis B: Environmental*, 9 (1996) 25.
- [23] H. Chen, S. Kuranari, M. Matsuoka, J. Zhang, M. Anpo, *Catalysis Letters* 126 (2008) 218.

