

4. Investigation of the interaction of tools and rocks during impact destruction / E.V. Alexandrov, V.B. Sokolinsky, G.M. Zakharikov et al. - Moscow: IGD them. A.A. Skochinskogo, 1967. - 62 p.
5. Slidenko V.M. Mathematicians modulation of shock processes of hydropulse systems of mining machines: monograph / V.M. Slidenko, O. M. Slidenko -NTUU "KPI" , 2017. - 220 p.
6. Eroshenko V.A. A new paradigm of mechanical energy dissipation. Part 1: theoretical aspects and practical solutions // J. Proc. of mechanical Engineers, Vol. 221. Part D: J. of Automobile Engineering. - 2007. - Vol. 221, No. 3. - P. 285-300.
7. Eroshenko V.A Power dissipation of the energy of oscillations of mining machines by heterogeneous leiophobic systems / Eroshenko V.A., V.M. Slidenko, S.P. Shevchuk, V.P. Studenets V.P.: NTUU "KPI", 2016 -180 p.
8. Ivanov A.P. Dynamics of systems with mechanical collisions / A.P. Ivanov .- Moscow: International Program of Education, 1997. – 336 p.

## FEATURES OF THE PROCESSES OF FORMING AND SINTERING OF POWDERED THERMOMAGNETIC MATERIALS ON THE IRON-NICKEL BASE WITH CHROMIUM ADDITIVES

SYTNYK Iaroslav & MASLYUK Vitalii

Frantsevich Institute for Problems of Materials Science, Ukraine

**Purpose.** Investigate the influence of chromium addition on the demagnetization temperature and Curie point of powder metallurgy thermomagnetic materials by determining the breakout force of its sample from a permanent magnet.

**Methodology.** The studies were carried out through the investigations of processes for the formation and sintering of powdered thermomagnetic materials on the iron-nickel base and the determination of the breakout force of its sample from a permanent magnet on a laboratory stand.

**Findings.** With an increase in the concentration of Cr, the difference in breakout force from a permanent magnet increases and at concentrations of Cr 6 - 8 wt. % reaches the maximum value. On this basis, the optimum content of Cr is in the range of 6 - 8 wt. %. The dependence of the density on the temperature of sintering shows that when the temperature rises from 1200 to 1350 °C, the density of the samples also increases, and the porosity decreases significantly. This indicates a greater completeness of the processes of alloying. The highest density of the alloy is 7.01 g/cm<sup>3</sup>, at the temperature of 1350 °C. When the temperature of sintering increases, the amount of the new phase - a triple solid solution decreases. In the temperature range of 1200 - 1300 °C, this phase is distributed evenly throughout the sample volume, and in the temperature range 1300 - 1350 °C

combines into separate plots. The dependence of the breakout force on the sintering temperature and on the concentration of chromium showed that the resulting phase reduces the separation effort and the deviation of the curve on the graph from the linear dependence at a temperature of 1300 °C can be explained by the accumulation of this phase in the microobjective. The analysis of microstructures showed that the most satisfactory temperature of sintering is 1200 °C.

They contain the researches, which were conducted within the project III-6-12, financed by Ministry of Education and Science of Ukraine.

**Key words:** thermomagnetic material, Curie point, relays, electromotor devices, iron-nickel alloy

### References

1. Sytnyk I.A., Masliuk V.A., Kotliar S.B. y dr (2016). Mahnitom'iaki pretsyziyni termomahnitni materialy: otrymannia, vlastyvoli ta zastosuvannia v tekhnitsi (ohliad) [Low-Coercivity Precision Hermomagnetic Materials: Production, Properties, and Application in Engineering (Review)]. Poroshkova metalurhiia – Powder Metallurgy, 11/12, 30-40 [in Ukrainian].

2. Sytnyk I.A., Maslyuk V.A., Bahlyuk G.A. (2016). Vlyyanye lehyruyushchykh dobavok na svoystva spechenykh termomahnitnykh materialov [Effect of alloying additives on the properties of sintered thermomagnetic materials]. Novyye materialy i tekhnologii: poroshkovaya metallurgiya, kompozitsionnyye materialy, zashchitnyye pokrytiya, svarnyye materialy – New materials and technologies: powder metallurgy, composite materials, protective coatings, welded materials, 12. 158-162 [in Russian]

3. Radomysel'skyj Y. D., Serdiuk H. H., Scherban' N. Y. (1985). Konstruktsionnyye poroshkovyye materyaly [Structural powder materials]. Kyiv: Tekhnika [in Russian].

4. Minits'kyj A.V., Masliuk V.A., Panasiuk O.O. (2005) Vplyv lehuiuchykh dobavok na strukturu i mahnitni vlastyvoli poroshkovykh materialiv na osnovi zaliza [Influence of alloying additives on the structure and magnetic properties of iron-based powder materials]. Visnyk Ternopil's'koho Derzhavnoho Tekhnichnoho Universytetu – Bulletin of the Ternopil State Technical University, 2. 17-22 [in Ukrainian].

5. Kekalo Y.B., Samaryn B.A. (1989). Fyzycheskoe metallovedenye pretsyzyonnykh splavov. Splavy s osobymy mahnytnymy svoystvamy [Physical metallurgy of precision alloys. Alloys with special magnetic properties]. Moscow: Metallurhiya [in Russian].

6. Piatin Yu.M. (Eds.) (1982). Materyaly v pryborostroenny y avtomatyke [Materials in instrument making and automation]. Moscow: Mashynostroenye [in Russian].

7. Tykhonovych V.Y., Kovalenko O.Y., Loktyonov V.A. (1980). TMM materyaly, ykh razrabotka y pryomenenye [TMM materials, their development and application]. Kyiv: Znanye [in Russian].