Engineering Conferences International ECI Digital Archives

Nanomechanical Testing in Materials Research and Development V

Proceedings

Fall 10-4-2015

Using in-situ microLaue diffraction to understand plasticity in MgO

Ayan Bhowmik Imperial College London, a.bhowmik@imperial.ac.uk

T. Ben Britton Imperial College London

Finn Giuliani Imperial College London

Follow this and additional works at: http://dc.engconfintl.org/nanomechtest_v Part of the <u>Materials Science and Engineering Commons</u>

Recommended Citation

Ayan Bhowmik, T. Ben Britton, and Finn Giuliani, "Using in-situ microLaue diffraction to understand plasticity in MgO" in "Nanomechanical Testing in Materials Research and Development V", Dr. Marc Legros, CEMES-CNRS, France Eds, ECI Symposium Series, (2015). http://dc.engconfintl.org/nanomechtest_v/69

This Abstract is brought to you for free and open access by the Proceedings at ECI Digital Archives. It has been accepted for inclusion in Nanomechanical Testing in Materials Research and Development V by an authorized administrator of ECI Digital Archives. For more information, please contact franco@bepress.com.

USING IN-SITU MICROLAUE DIFFRACTION TO UNDERSTAND PLASTICITY IN MgO

Ayan Bhowmik, Department of Materials, Imperial College London, South Kensington, London SW72AZ, UK a.bhowmik@imperial.ac.uk

T. Ben Britton, Department of Materials, Imperial College London, South Kensington, London SW72AZ, UK Finn Giuliani, Department of Materials, Imperial College London, South Kensington, London SW72AZ, UK

The present study investigates the micromechanical modes of deformation in MgO prior to cracking at room temperature. A combination of time resolved white beam Laue diffraction technique and *in-situ* nano-indentation of large single crystal micropillars provides a unique method to study the operating mechanisms of deformation in this otherwise brittle oxide ceramic. Upon indenting an [100]-oriented MgO micropillar, rotation and streaking of Laue spots were observed. From the streaking of the Laue spots, differential slip on orthogonal {110} slip planes was inferred to take place in adjacent areas under the indent - this was consistent with the results from the transmission electron microscopy studies. Upon cyclic loading of the pillar, subsequent stretching and relaxation of peaks was hypothesised to happen due to pronounced mechanical hysteresis commonly observed in MgO. Also, time-resolved spatial mapping of the deformation gradients of the area under the indent were obtained from which the strain and rotation components were identified.