

Engineering Conferences International ECI Digital Archives

Nanomechanical Testing in Materials Research and
Development V

Proceedings

Fall 10-4-2015

Deformation behavior of bulk metallic glasses produced via Severe Plastic Deformation and the influence of a second phase

Lisa Kraemer

Austrian Academy of Sciences, lisa.kraemer@stud.unileoben.ac.at

Verena Maier

Austrian Academy of Sciences

Karoline Kormout

Austrian Academy of Sciences

Marlene Kapp

Austrian Academy of Sciences

Yannick Champion

Institut de Chimie et des Matériaux Paris-Est, Université Paris-Est Créteil

See next page for additional authors

Follow this and additional works at: http://dc.engconfintl.org/nanomechtest_v



Part of the [Materials Science and Engineering Commons](#)

Recommended Citation

[1] Krämer, L.; Kormout, K.S.; Setman, D.; Champion, Y.; Pippan, R. Production of Bulk Metallic Glasses by Severe Plastic Deformation. *Metals* 2015, 5, 720-729.

This Abstract is brought to you for free and open access by the Proceedings at ECI Digital Archives. It has been accepted for inclusion in Nanomechanical Testing in Materials Research and Development V by an authorized administrator of ECI Digital Archives. For more information, please contact franco@bepress.com.

Authors

Lisa Kraemer, Verena Maier, Karoline Kormout, Marlene Kapp, Yannick Champion, and Reinhard Pippan

DEFORMATION BEHAVIOR OF BULK METALLIC GLASSES PRODUCED VIA SEVERE PLASTIC DEFORMATION AND THE INFLUENCE OF A SECOND PHASE

Lisa Krämer, Erich-Schmid-Institute for Materials Sciences, Leoben, Austrian Academy of Sciences, Austria
lisa.kraemer@stud.unileoben.ac.at

Verena Maier, Erich-Schmid-Institute for Materials Sciences, Leoben, Austrian Academy of Sciences, Austria
Karoline Kormout, Erich-Schmid-Institute for Materials Sciences, Leoben, Austrian Academy of Sciences, Austria
Marlene Kapp, Erich-Schmid-Institute for Materials Sciences, Leoben, Austrian Academy of Sciences, Austria
Yannick Champion, Institut de Chimie et des Matériaux Paris-Est, Université Paris-Est Créteil, France
Reinhard Pippan, Erich-Schmid-Institute for Materials Sciences, Leoben, Austrian Academy of Sciences, Austria

Over the last years bulk metallic glasses (BMG) have been strongly investigated as their mechanical properties are very promising especially in terms of their high yield strength and high elastic strain. However, a major drawback is their complicated production depending strongly on dimensions and chemistry. A promising technique to overcome these drawbacks is using a severe plastic deformation process, e.g. high pressure torsion (HPT), where the production can be started with metallic glass powders, which are generally much easier to fabricate.

For this route, the powder is consolidated and then the powder particles are welded together by applying a high shear deformation. The produced specimen remain fully amorphous and no porosity is detectable after sufficient deformation [1]. To improve the mechanical properties of the BMG, the used Zr-based metallic glass powder is mixed with a crystalline Cu-powder or a Ni-based metallic glass powder to achieve a metal/metallic glass composite or a metallic glass/ metallic glass composite, respectively.

Due to the small amounts of produced material, conventional macroscopic characterization methods, like compression or tension tests can hardly be used to analyze the overall mechanical properties. Therefore, in this work different micromechanical testing methods, such as nanoindentation, *in-situ* SEM micropillar compression, and finally *in situ* TEM picoindentation were carried out to investigate the deformation behavior under ambient but also non-ambient conditions. Using nanoindentation, the hardness and the Young's Modulus was determined for two HPT-deformed BMGs with different composition. Additionally, high temperature nanoindentation experiments up to 350 °C were conducted to determine not only the temperature dependent hardness and the Young's modulus but also to study the change in thermally activated processes during deformation via nanoindentation strain rate jump tests. It was found, that nanoindentation hardness is in good accordance to the macroscopic Vickers results. Increasing the temperature, hardness decreases slightly, while the modulus increases. The shear band formation is also dependent on the deformation temperature, since the extent of stair case formation in the load-displacement curves changes. Overcoming 300°C, the material becomes extremely ductile showing a strong strain rate sensitivity.

Further, the uniaxial mechanical response of Zr-based BMG was examined *in-situ* in SEM using FIB prepared micropillars. The microcompression experiments revealed a strength of more than 2 GPa. Steps in the stress-strain curve suggest shear band formation, which could also be confirmed by the *in-situ* recorded SEM images. Finally the influence of the second materials phase was investigated via TEM *in-situ* picoindentation, where a wedge shaped indenter was pressed in a TEM lamella. The load-displacement curve show a similar stair case behavior as seen during nanoindentation and microcompression, indicating shear band formation. The shear band formation could be also observed in the TEM micrographs.

[1] Krämer, L.; Kormout, K.S.; Setman, D.; Champion, Y.; Pippan, R. Production of Bulk Metallic Glasses by Severe Plastic Deformation. *Metals* 2015, 5, 720-729.