

## Durham Research Online

---

### Deposited in DRO:

28 February 2018

### Version of attached file:

### Peer-review status of attached file:

Peer-reviewed

### Citation for published item:

Wilson, M. and Kore, R. and Ritchie, A.W. and Fraser, R.C. and Beaumont, S.K. and Srivastava, R. and Badyal, J.P.S. (2018) 'Palladium–poly(ionic liquid) membranes for permselective sonochemical flow catalysis.', *Colloids and surfaces A : physicochemical and engineering aspects.*, 545 . pp. 78-85.

### Further information on publisher's website:

<https://doi.org/10.1016/j.colsurfa.2018.02.044>

### Publisher's copyright statement:

© 2018 The Authors. Published by Elsevier B.V. This is an open access article under the CC BY license (<http://creativecommons.org/licenses/by/4.0/>)

## Use policy


---

The full-text may be used and/or reproduced, and given to third parties in any format or medium, without prior permission or charge, for personal research or study, educational, or not-for-profit purposes provided that:

- a full bibliographic reference is made to the original source
- a [link](#) is made to the metadata record in DRO
- the full-text is not changed in any way

The full-text must not be sold in any format or medium without the formal permission of the copyright holders.

Please consult the [full DRO policy](#) for further details.



## Palladium–poly(ionic liquid) membranes for permselective sonochemical flow catalysis


M. Wilson<sup>a</sup>, R. Kore<sup>b</sup>, A.W. Ritchie<sup>a</sup>, R.C. Fraser<sup>a</sup>, S.K. Beaumont<sup>a,1</sup>, R. Srivastava<sup>b,1</sup>, J.P.S. Badyal<sup>a,\*,1</sup>

<sup>a</sup> Department of Chemistry, Science Laboratories, Durham University, Durham DH1 3LE, England, UK

<sup>b</sup> Department of Chemistry, Indian Institute of Technology Ropar, Punjab 140001, India



### GRAPHICAL ABSTRACT



### ARTICLE INFO

#### Keywords:

Catalyst membrane  
Ionic liquid  
Palladium catalyst  
Plasmachemical functionalization

### ABSTRACT

Anisotropic palladium–poly(ionic liquid) catalyst membranes have been prepared by complexation of palladium (II) chloride to poly(ionic liquid) functionalised flexible porous substrates. The practical viability of these low loading (sub 0.1 mol%) palladium catalyst membranes for continuous flow reactions at ambient temperature is demonstrated for the Suzuki–Miyaura carbon–carbon coupling reaction by contacting the reactant mixture with the catalyst membrane and applying sonication. The Suzuki–Miyaura carbon–carbon coupling reaction proceeds at the palladium–poly(ionic liquid) catalyst membrane surface in conjunction with selective permeation (separation) of the desired product species through the underlying porous support. These palladium–poly(ionic liquid) catalyst membranes display minimal metal leaching enabling them to be reused multiple times.

\* Corresponding author.

E-mail address: [j.p.badyal@durham.ac.uk](mailto:j.p.badyal@durham.ac.uk) (J.P.S. Badyal).

<sup>1</sup> These authors have made equal contributions.

## 1. Introduction


Ionic liquids are used for a wide range of applications including catalysis [1–3]. In the case of the Suzuki–Miyaura carbon–carbon coupling reaction, palladium species immobilised within ionic liquids have been shown to be highly effective catalyst systems [4–16]. For instance, ionic liquid imidazolium cations can coordinate palladium catalyst centres [4–15]. The covalent attachment of ionic liquids to conventional polymer backbones such as poly(vinylbenzyl) [7,12] and poly(divinylbenzene) [13] has also been reported [17]. Whilst such systems can produce high yields and reaction selectivities [4–16], the inherent requirement for elution of the product limits their more widespread application. Other disadvantages include the need for high metal catalyst loadings, metal loss due to leaching, or catalyst breakdown; all of which can lead to additional processing steps and extra costs being incurred (e.g. post-reaction metal recovery in order to comply with public health regulations for pharmaceutical active ingredients [18]).

For the case of heterogeneous catalyst Suzuki–Miyaura carbon–carbon coupling reaction systems, palladium dispersed onto carbon (Pd/C) provides ease of product recovery, a relatively high reaction rate, lower cost, and integration into packed bed reactors or columns [19–22]. However, not only are high temperatures and loadings necessary to achieve adequate yields, significant levels of metal leaching are observed. Lower palladium loadings have been reported for other solid support materials (these include metal phosphates [23], metal oxides [24], and organic polymers [25]). Despite such heterogeneous systems displaying reduced palladium leaching compared to conventional Pd/C systems, elevated temperatures or microwave heating are still needed to achieve high product yields. Microchannel and capillary reactors are alternatives to packed bed reactor systems, benefiting from lower loadings, high turnover frequencies (TOFs), and low levels of catalyst leaching [26,27]. Their drawback is the small active catalytic areas available in such devices limiting the overall reaction product capacity compared to conventional larger-scale packed bed flow reactors.

Hybrid catalyst–membrane systems can potentially address the aforementioned limitations. Poly(ionic liquids) supported onto membranes have been prepared by photo-initiated grafting of imidazolium groups onto polyethersulfone membranes [28]. The resulting membrane supported palladium–poly(ionic liquid) catalysts yield rapid TOFs ( $147 \text{ h}^{-1}$ , moles of product per mole of palladium per hour), but operate at above ambient temperatures (333 K).

In this article, we describe a continuous flow anisotropic palladium–poly(ionic liquid) catalyst membrane system containing the above advantages of low Pd loading, but which operates at low temperatures (293 K) and delivers comparable performance ( $\text{TOF} = 154 \text{ h}^{-1}$ ). Its fabrication comprises pulsed plasma deposition of a poly(vinylbenzyl chloride) layer onto a membrane to generate surface benzyl chloride groups followed by the Menshutkin reaction to form surface tethered quaternised *N*-butylimidazole moieties which are subsequently used to complex palladium chloride catalyst to the imidazolium cations [29], Scheme 1.


The pulsed plasma deposition step entails modulating an electrical discharge in the presence of vinylbenzyl chloride gaseous precursor containing a polymerisable carbon–carbon double bond [30,31]. Mechanistically, there are two distinct reaction regimes corresponding to the plasma duty cycle on- and off- periods (typical timescales are of the order of microseconds and milliseconds respectively) [32]. Namely, monomer activation and reactive site generation occur at the substrate surface during each short burst of plasma (via VUV irradiation, ion, or electron bombardment) followed by conventional carbon–carbon double bond polymerization proceeding in the subsequent extended off-period (in the absence of any VUV-, ion-, or electron-induced damage to the growing film). High levels of precursor functional group structural retention within pulsed plasma deposited nanolayers can be achieved



**Scheme 1.** Preparation of anisotropic palladium–poly(ionic liquid) catalyst membrane by pulsed plasma deposition of poly(vinylbenzyl chloride) layer (diagonally hatched shading) onto PTFE membrane followed by solution phase quaternisation with *N*-butylimidazole and then complexation to palladium(II) catalyst.

(as confirmed by ToF-SIMS [33] and NMR [34]). Furthermore, by programming the pulsed plasma duty cycle, it is possible to control (i.e. tailor) the surface density of desired chemical groups. Strong covalent attachment of the deposited functional layers to the underlying substrate occurs via free radical sites created at the interface during the onset of plasma exposure (this has allowed for the preparation of flexible substrate heterogeneous catalyst systems [35]). Other distinct advantages include the fact that the plasmachemical approach is quick (single-step), solventless, energy-efficient, and the reactive gaseous nature of the electrical discharge provides conformality to the host substrate membrane material [36,37].

The palladium–poly(ionic liquid) catalyst membranes fabricated in



**Scheme 2.** Suzuki–Miyaura carbon–carbon coupling reaction of iodobenzene with phenylboronic acid using palladium–poly(ionic liquid) catalyst membrane.

the present study have been employed for the Suzuki–Miyaura carbon–carbon coupling reaction, [Scheme 2](#).

## 2. Experimental

### 2.1. Preparation of palladium–poly(ionic liquid) catalyst membrane

A cylindrical glass reactor (5.5 cm diameter, 475 cm<sup>3</sup> volume) housed within a Faraday cage was used for plasmachemical deposition. This was connected to a 30 L min<sup>-1</sup> rotary pump (model E2M2, Edwards Vacuum Ltd.) via a liquid nitrogen cold trap (base pressure less than  $2 \times 10^{-3}$  mbar and air leak rate better than  $6 \times 10^{-9}$  mol s<sup>-1</sup>) [38]. A copper coil wound around the reactor (4 mm diameter, 10 turns, located 10 cm downstream from the gas inlet) was connected to a 13.56 MHz radio frequency (RF) power supply via an L–C matching network. A signal generator (model TG503, Thurlby Thandar Instruments Ltd.) was used to trigger the RF power supply. Prior to film deposition, the whole apparatus was thoroughly scrubbed using detergent and hot water, rinsed with propan-2-ol (+99.5 wt.%, Fisher Scientific UK Ltd.), oven dried at 423 K, and further cleaned using a 50 W continuous wave air plasma at 0.2 mbar for 30 min. Silicon substrate preparation comprised successive sonication in propan-2-ol and cyclohexane (+99.7 wt.%, Sigma–Aldrich Co.) for 15 min prior to insertion into the centre of the chamber. Further cleaning entailed running a 50 W continuous wave air plasma at 0.2 mbar for 30 min prior to film deposition. Polytetrafluoroethylene (PTFE) membrane film ( $180 \pm 10 \mu\text{m}$  thickness,  $5 \pm 2 \mu\text{m}$  surface pore size determined by SEM, Mupor Ltd) was used following rinsing in a 1 : 1 vol. ratio mixture of cyclohexane and propan-2-ol. Vinylbenzyl chloride (mixture of 3- and 4- isomers, 97 wt.%, Sigma–Aldrich Co.) precursor was loaded into a sealable glass tube, degassed via several freeze–pump–thaw cycles, and then attached to the reactor. Monomer vapour was then allowed to purge the apparatus at a pressure of 0.15 mbar for 15 min prior to electrical discharge ignition. Pulsed plasma deposition was performed at 293 K using a duty cycle on-period ( $t_{\text{on}}$ ) of 100  $\mu\text{s}$  and a duty cycle off-period ( $t_{\text{off}}$ ) of 4 ms in conjunction with a RF generator power output ( $P_{\text{on}}$ ) of 30 W [39]. Upon plasma extinction, the precursor vapour was allowed to continue to pass through the system for a further 15 min, and then the chamber was evacuated to base pressure followed by venting to atmosphere. Deposited layer thicknesses were approximately  $2.3 \pm 0.2 \mu\text{m}$  (deposition rate  $160 \pm 10 \text{ nm min}^{-1}$ ).

For conversion to a supported poly(ionic liquid) layer, the pulsed plasma poly(vinylbenzyl chloride) coated substrate was immersed for 120 h at 293 K into a 1 : 6 by volume solution of *N*-butylimidazole (98 wt.%, Sigma–Aldrich Co.) in dimethylformamide (DMF, 99.5 wt.%, Fisher Scientific UK Ltd.), followed by rinsing in DMF for 16 h. The quaternised surfaces were then immersed for 16 h at 293 K into an aqueous solution comprising 2 mM palladium(II) chloride (+99.999 wt.%, Alfa Aesar Co. Ltd.), 3.0 M sodium chloride (+99.5 wt.%, Sigma–Aldrich Co.), and 0.5 M sodium citrate dihydrate (+99 wt.%, Sigma–Aldrich Co.) in high purity water (BS 3978 Grade 1) adjusted to pH 4.5 with citric acid monohydrate (+99 wt.%, Sigma–Aldrich Co.) [40]. The surfaces were then rinsed in high purity water for 20 min.

### 2.2. Characterisation

Film thickness values of pulsed plasma poly(vinylbenzyl chloride) deposited onto silicon wafers were measured using a spectrophotometer (model nkd-6000, Aquila Instruments Ltd.). Transmittance–reflectance curves (350–1000 nm wavelength range) were acquired for each sample and fitted to a Cauchy model for dielectric materials [41] using a modified Levenberg–Marquardt algorithm [42].

Reflection-absorption infrared (RAIRS) spectra of pulsed plasma poly(vinylbenzyl chloride) deposited onto silicon wafers were acquired using a FTIR spectrometer (Spectrum One, Perkin–Elmer Inc.) fitted with a liquid nitrogen cooled MCT detector operating at 4 cm<sup>-1</sup> resolution across the 400–4000 cm<sup>-1</sup> range. The instrument included a variable angle reflection-absorption accessory (Specac Ltd.) set to a grazing angle of 66° for silicon wafer substrates and adjusted for p-polarization. Attenuated total reflectance (ATR) infrared spectra of vinylbenzyl chloride precursor were obtained using a Golden Gate accessory (Specac Ltd.).

Surface elemental compositions of pulsed plasma poly(vinylbenzyl chloride) deposited onto silicon wafers and PTFE membrane were measured by X-ray photoelectron spectroscopy (XPS) using a VG ESCALAB II electron spectrometer equipped with a non-monochromated Mg K $\alpha_{1,2}$  X-ray source (1253.6 eV) and a concentric hemispherical analyser. Photoemitted electrons were collected at a take-off angle of 20° from the substrate normal, with electron detection in the constant analyser energy mode (CAE, pass energies of 20 and 50 eV for high resolution and survey spectra respectively). Experimentally determined instrument sensitivity factors were C(1s) : O(1s) : N(1s) : Cl(2p) : Pd(3d) : F(1s) equals 1.00 : 0.35 : 0.70 : 0.37 : 0.06 : 0.25 respectively. The core level binding energy envelopes were fitted using Gaussian peak shapes with fixed full-width-half-maxima (fwhm) and linear backgrounds [43,44]. All binding energies were referenced to the C(1s) –C<sub>x</sub>H<sub>y</sub> hydrocarbon peak at 285.0 eV [45]. Measurements were repeated at least 3 times.

Palladium loading on the catalyst membrane, and amount leached during multiple use studies was measured by ICP-OES (Vista MPX CCD Simultaneous axial ICP-OES, Varian Inc.). Calibration of detected palladium signal intensity to actual palladium content in solution was carried out to an accuracy of 0.01 ppm using reference samples at 1, 2, and 5 ppm, prepared from a 1000 ppm stock solution (26 X 1-Pd(a), MBH Analytical Ltd.) diluted in high purity water (resistance of 18.2 M $\Omega$ ). Analyte solutions were digested in 5 mL of sulphuric and perchloric acids (95 wt.% Normapur<sup>®</sup>, and 65 wt.% Normatom<sup>®</sup> respectively, VWR International Ltd.) using a wet digestion method followed by dilution to 25 mL in high purity water. The detection limit of palladium in these catalysis experiment analyte solutions was 0.1 ppm on a mass basis. Palladium membranes were treated in the same manner to remove the palladium containing poly(ionic liquid)–plasma polymer layer from the PTFE membrane substrate.

### 2.3. Suzuki–Miyaura carbon–carbon coupling reaction

For palladium–poly(ionic liquid) catalyst membrane heated batch reactor studies of catalysis, B10 borosilicate sample flasks were rinsed with ethanol (+99.8 wt.%, Fisher Scientific UK Ltd.), thoroughly scrubbed using detergent and hot water, followed by immersion for 1 h in a solution comprising sodium hydroxide (99.2 wt.%, Fisher Scientific UK Ltd.), propan-2-ol (+99.5 wt.%, Fisher Scientific UK Ltd.), and high purity water (mass ratio 1 : 20 : 5) in order to remove any organic residue. The flasks were then thoroughly scrubbed using detergent and hot water, rinsed in propan-2-ol, and oven dried at 423 K. A final wash step consisted of immersion for 1 h in a 1 wt% nitric acid bath (70 wt.% in water, Fisher Scientific UK Ltd., further diluted in high purity water), followed by thorough rinsing with high purity water and oven drying at 423 K, to ensure that no palladium transfer occurred between solutions. This rigorous cleaning procedure was undertaken before each reaction.

$0.50 \pm 0.05$  mmol of iodobenzene (98 wt%, Sigma–Aldrich Co.),  $0.75 \pm 0.01$  mmol of phenylboronic acid (95 wt%, Sigma–Aldrich Co.), and  $0.99 \pm 0.01$  mmol of potassium carbonate (98 wt%, Sigma–Aldrich Co.) were weighed out into a borosilicate flask. 3 mL of a solution comprising ethanol (+99.8 wt%, Fisher Scientific UK Ltd.) and high purity water in a 2 : 1 vol. ratio was added, the flask was agitated to dissolve the potassium carbonate, and then the catalyst membrane was added ( $47.9 \pm 3.4$  mg catalyst membrane, with  $0.304 \pm 0.022$   $\mu\text{mol}$  of palladium(II) or 0.067 wt.% ( $32.3 \pm 2.3$   $\mu\text{g}$ ) initial palladium loading as measured by ICP-OES analysis). The flask was fitted to a water cooled condenser, and immersed in a water bath at 343 K for 30 min for the reaction to proceed. The reaction solutions were not stirred in order to prevent abrasive damage to the membrane material (it should be noted this means the reported turnover frequencies (TOF, moles of product per mole of palladium per hour) are a lower estimate as diffusion may also limit reaction rates measured). Afterwards, the flask was removed from the water bath and allowed to cool to room temperature, followed by removal of the catalyst membrane and the solution decanted. The flask was then rinsed twice with 1 mL of chloroform (99.8 wt%, Fisher Scientific UK Ltd.) and the washings were added to the decanted solution. Solutions for gas chromatography (GC) analysis were extracted three times with 3 mL of chloroform, spiked with  $4 \text{ mg mL}^{-1}$  decane (0.1 g, +99 wt%, Sigma–Aldrich Co.), and made up to 25 mL with dichloromethane (99.99 wt%, Fisher Scientific UK Ltd.). Solutions for ICP-OES analysis were sealed in screw topped borosilicate glass vials fitted with a PTFE/silicone slit septum. Catalyst membranes were dried in air at 293 K for a minimum of 1 h before reuse with a fresh reactant solution each time. As a control experiment,  $0.50 \pm 0.05$  mmol of 4-methoxyiodobenzene (98 wt%, Sigma–Aldrich Co.) was substituted for iodobenzene to rule out homocoupled by-product formation.

For Suzuki–Miyaura carbon–carbon coupling reactions under sonicated flow conditions at room temperature, a custom gravity-fed flow cell was used with the membrane sealed using a compression fitting, Fig. 1 and Supplementary information Fig. S1.  $1.0 \pm 0.1$  mmol of iodobenzene,  $1.50 \pm 0.01$  mmol of phenylboronic acid, and  $2.00 \pm 0.01$  mmol of  $\text{K}_2\text{CO}_3$  were added to the reactor along with 6 mL of a solution comprising ethanol and high purity water in a 2 : 1 vol. ratio (the area of exposed catalyst was  $3.6 \text{ cm}^2$ , with  $0.61 \mu\text{mol}$  of palladium(II) ( $64.6 \pm 2.3 \mu\text{g}$ ) initial palladium loading as measured by ICP-OES analysis). The reactor was then immersed in an ultrasonic bath (Clifton Ultrasonic Bath, Nickel-Electro Ltd.) at  $20 \pm 2^\circ\text{C}$  for 1 h. Afterwards, the reactor was removed from the ultrasonic bath, the product solutions and residual reaction solutions were decanted and stored separately. As reported in the Results and Discussion sections, the membrane setup preferentially separates biphenyl product (and some remaining iodobenzene reactant) from the phenylboronic acid




Fig. 1. Sonicated catalyst membrane reactor for room temperature Suzuki–Miyaura coupling reaction. See Supplementary information Fig. S1 for further details about union connector.

reactant and reaction solvents. The product solution glassware was rinsed twice with 1 mL of chloroform and the washings were added to the decanted product solution. Residual reaction solutions were extracted for GC analysis three times with 3 mL of chloroform, spiked with  $4 \text{ mg mL}^{-1}$  decane (0.1 g), and made up to 25 mL with dichloromethane. Product solutions (which did not require extraction) were spiked with  $4 \text{ mg mL}^{-1}$  decane (0.1 g), and made up to 25 mL with dichloromethane. As a control experiment,  $1.0 \pm 0.1$  mmol of 4-methoxyiodobenzene (98 wt%, Sigma–Aldrich Co.) was substituted for iodobenzene to rule out homocoupled by-product formation.

GC (Bruker Corp. Scion 456 gas chromatograph with a flame ionization detector (FID) fitted with a siloxane capillary column (5% phenyl / 95% dimethylpolysiloxane BP-5), length of 30 m, internal diameter of 0.25 mm, coating thickness of 0.25  $\mu\text{m}$ ) was conducted using high-performance liquid chromatography (HPLC) autosampler vials with a PTFE/silicone slit septum at a starting temperature of 373 K, a hold time of 4 min, a ramp rate of  $20 \text{ K min}^{-1}$ , and a final temperature of 473 K with a hold time of 9 min. Product yield was calculated from GC traces as the percentage conversion of haloarene to desired coupled product in the recovered reaction solution, all other reagents were used in excess. GC–MS (Shimadzu Europa GmbH, GCMS-QP2010 Ultra fitted with an Rxi<sup>®</sup>-5Sil column, length of 10 m, internal diameter of 0.15 mm, column coating thickness of 0.15  $\mu\text{m}$ ) was conducted using high-performance liquid chromatography (HPLC) autosampler vials with a PTFE/silicone slit septum at a starting temperature of 303 K and a hold time of 1 min, a ramp rate of  $50 \text{ K min}^{-1}$ , and a final temperature of 573 K, with a hold time of 5 min.

### 3. Results

#### 3.1. Pulsed plasma deposited poly(vinylbenzyl chloride)

Infrared spectroscopy of pulsed plasma deposited poly(vinylbenzyl chloride) films confirmed a high level of benzyl chloride functional group structural retention [46–48], Fig. 2. Disappearance of the monoalkyl vinyl  $=\text{CH}_2$  wag vibration mode ( $906 \text{ cm}^{-1}$ ) associated




Fig. 2. Infrared spectra of: (a) vinylbenzyl chloride liquid precursor; (b) pulsed plasma deposited poly(vinylbenzyl chloride); and (c) pulsed plasma deposited poly(vinylbenzyl chloride) quaternised with *N*-butylimidazole. I and II denote characteristic para-substituted benzene ring stretches at  $1603 \text{ cm}^{-1}$  and  $1490 \text{ cm}^{-1}$  respectively. III denotes characteristic  $\text{Cl}-\text{CH}_2-$  wag mode at  $1263 \text{ cm}^{-1}$ . IV denotes precursor monoalkyl vinyl  $=\text{CH}_2$  wag at  $906 \text{ cm}^{-1}$ .

**Table 1**

XPS relative atomic compositions at each stage of palladium–poly(ionic liquid) catalyst membrane preparation, and for a control sample comprising non-quaternised poly(vinylbenzyl chloride) functionalised PTFE membrane exposed to PdCl<sub>2</sub> solution and then rinsed in high purity water.

PTFE Membrane	C/%	N/%	O/%	Cl/%	Pd/%	F/%
Untreated	29.2	–	–	–	–	70.8
Pulsed Plasma Poly(Vinylbenzyl Chloride) Functionalised	90.4 ± 0.5	–	0.4 ± 0.8	9.2 ± 0.3	–	–
Pulsed Plasma Poly(Vinylbenzyl Chloride) Functionalised + Quaternised	83.7 ± 0.7	7.9 ± 0.4	4.1 ± 0.3	4.3 ± 0.3	–	–
Pulsed Plasma Poly(Vinylbenzyl Chloride) Functionalised + Quaternised + PdCl <sub>2(aq)</sub>	78.6 ± 2.2	6.4 ± 0.6	9.8 ± 2.4	4.3 ± 0.6	0.9 ± 0.1	–
Control Pulsed Plasma Poly(Vinylbenzyl Chloride) Functionalised + PdCl <sub>2(aq)</sub>	80.7	–	12.9	6.4	0.0	–

with the precursor molecule confirmed selective vinyl group polymerisation during pulsed plasma deposition [49]. Characteristic para substituted benzene ring absorbances can be found at 1603 cm<sup>-1</sup>, and 1490 cm<sup>-1</sup> [49]. The band at 1263 cm<sup>-1</sup> for both the precursor and plasma deposited polymer corresponds to the Cl–CH<sub>2</sub>– wag mode [49]. This halogen-containing group is a prerequisite for quaternisation leading to the formation of a poly(ionic liquid) layer.

XPS analysis of pulsed plasma deposited poly(vinylbenzyl chloride) onto PTFE membrane detected carbon, chlorine, and low levels of oxygen (attributed to a small amount of atmospheric water absorption [50]), Table 1 and Supplementary information Fig. S2. The absence of fluorine signal confirmed complete coverage of the underlying PTFE membrane (no pinholes).

### 3.2. Palladium–poly(ionic liquid) catalyst membrane

Quaternisation of the pulsed plasma deposited poly(vinylbenzyl chloride) films with *N*-butylimidazole resulted in the appearance of nitrogen XPS signal at the surface, Table 1 and Supplementary information Fig. S3. The N(1s) binding envelope of the quaternised films could be fitted to a main nitrogen environment at 401.9 ± 0.1 eV corresponding to two equivalent nitrogen centres in positively charged imidazolium rings [39,51,52], Fig. 3 and Scheme 1. The slight shoulder towards lower N(1s) binding energy can be attributed to the reaction of *N*-butylimidazole with trapped free radicals contained within the plasma deposited layer [36,53]. The Cl(2p) peak envelope could be fitted to two different chlorine atom environments with Cl(2p<sub>3/2</sub>) binding energy values of 197.3 ± 0.1 eV and 200.6 ± 0.2 eV corresponding to chloride anions and non-quaternised unreacted benzyl chloride groups respectively [54], Fig. 4. Based on these two Cl(2p<sub>3/2</sub>) binding energy environments, the level of surface quaternisation was calculated to be 52 ± 9% (this is most likely to be an underestimate due to the XPS sampling depth (2–5 nm) also probing the sub-surface [55,56]). Infrared spectroscopy of the quaternised membranes did not




Fig. 3. N(1s) XPS spectra: (a) pulsed plasma poly(vinylbenzyl chloride) deposited onto PTFE membrane and quaternised with *N*-butylimidazole; and (b) following palladium(II) chloride complexation to (a). Signal intensity is counts per second.




Fig. 4. Cl(2p) XPS spectra: (a) pulsed plasma poly(vinylbenzyl chloride) deposited onto PTFE membrane; (b) following quaternisation with *N*-butylimidazole; and (c) following palladium(II) chloride complexation to (b). Due to spin–orbit coupling, Cl(2p<sub>1/2</sub>) components are shifted by 1.6 eV to higher binding energy relative to the Cl(2p<sub>3/2</sub>) components, with a Cl(2p<sub>3/2</sub>):Cl(2p<sub>1/2</sub>) peak area ratio equal to 2:1 [54]. Signal intensity is counts per second.

detect any contributions from characteristic positively charged imidazolium ring absorbances at 1350 cm<sup>-1</sup> and 1180 cm<sup>-1</sup> [57], thereby indicating that only near-surface quaternisation had occurred (i.e. very low concentration relative to the bulk underlying pulsed plasma deposited poly(vinylbenzyl chloride) layer), Fig. 2. This is consistent with the shallower sampling depth for XPS.

Immersion of the quaternised films into aqueous palladium(II) chloride solution gave rise to the appearance of palladium XPS signals, signifying surface complexation, Table 1. No significant change in binding energy was observed in the N(1s) XPS signal at 401.9 ± 0.1 eV, which is consistent with previous studies for palladium(II) containing ionic liquids, Fig. 3 [58]. This was accompanied by the relative Cl(2p<sub>3/2</sub>) chloride anion peak component at 197.3 ± 0.1 eV within the overall Cl(2p) envelope increasing (as well as a shift towards higher binding energy) due to the incorporation of additional chloride anions accompanying the palladium(II) catalyst complexation process, Fig. 4.

### 3.3. Suzuki–Miyaura carbon–carbon coupling reaction

#### 3.3.1. Heated batch catalysis

The Suzuki–Miyaura carbon–carbon coupling reaction product yield at 343 K for the palladium–poly(ionic liquid) catalyst membrane was measured to be 77 ± 7% (apart from unreacted iodobenzene and

phenylboronic acid, no other compounds exceeded 1% of the GC biphenyl product peak area), with a catalyst turnover frequency of  $3097 \pm 323 \text{ h}^{-1}$  (TOF, moles of product per mole of palladium per hour). Over 4 cycles, palladium leaching into the reaction solution was measured to be  $83 \pm 33 \text{ ppb h}^{-1} \text{ cm}^{-3}$  (for the initial membrane equivalent reaction solution loading of  $11.1 \pm 8 \text{ ppm}$  on a mass basis (or  $0.061 \pm 0.004 \text{ mol}\%$ ) — this is equivalent to  $\sim 1\%$  of the Pd present leaching from an already sub 0.1 mol% catalyst loading during one reaction cycle at 343 K). This is consistent with the negligible drop in product yield with reaction cycle number, Supplementary information Fig. S4.

As a control, the Suzuki–Miyaura coupling reaction was run using 4-methoxyiodobenzene and phenylboronic acid reactants under similar reaction conditions in order to rule out the possibility of homocoupled by-product formation. GC–MS analysis of the obtained products showed the presence of only 4-methoxybiphenyl, and an absence of homocoupled biphenyl by-product.

### 3.3.2. Room temperature sonicated membrane flow catalysis


The practical viability of these palladium–poly(ionic liquid) catalyst membranes for continuous flow Suzuki–Miyaura carbon–carbon coupling reactions was demonstrated by allowing the reaction solution to permeate into the membrane during sonication at room temperature (sonication speeded up the liquid flow rate). After 1 h of reaction time, 17 mol% (0.17 mmol of 1.0 mmol) of the iodobenzene reactant present in the starting solution had been transported through the catalytic membrane as either product or unreacted iodobenzene. The collected solution contained only aromatic organic compounds (54 mol% biphenyl product, 42 mol% iodobenzene, and 4 mol% phenylboronic acid — no other components exceeded 3% of the GC biphenyl product peak area). This indicates that iodobenzene (either unreacted or as carbon–carbon coupled biphenyl product) preferentially passes through the membrane relative to phenylboronic acid. The TOF (calculated as before) for biphenyl product formation was found to be  $154 \text{ h}^{-1}$ .

For this system also, a control Suzuki–Miyaura coupling reaction run using 4-methoxyiodobenzene and phenylboronic acid reactants under similar experimental conditions showed an absence of homocoupled biphenyl by-product (only 4-methoxybiphenyl detected), thereby ruling out the possibility of homocoupled by-product formation.

## 4. Discussion

Pulsed plasmachemical functionalisation of solid surfaces using polymerisable functional precursors is a well-established, solventless, single-step, conformal, and substrate-independent technique, which offers the advantage of high levels of functional group retention [59], thus making it well-suited for the preparation of membrane supported poly(ionic liquid) catalysts. Infrared spectroscopy and XPS analyses have shown that there is a high level of chloro- group and benzene ring retention during pulsed plasma deposition of vinylbenzyl chloride precursor, thereby facilitating the subsequent step of quaternisation with *N*-butylimidazole to form a poly(ionic liquid) layer, Scheme 1, Figs. 2–4. Complexation of this surface to palladium chloride yields a palladium containing poly(ionic liquid) catalyst membrane.

Although high TOFs are achievable with conventional dispersed homogeneous and heterogeneous palladium catalyst systems [60–63], such materials suffer from the drawback of requiring post reaction recovery of the palladium catalyst or higher palladium loadings. The practical viability of the palladium–poly(ionic liquid) catalyst membranes in the present study has been demonstrated for the Suzuki–Miyaura coupling reaction of iodobenzene. The measured TOF value of  $3097 \pm 323 \text{ h}^{-1}$  for heated (343 K) batch reaction mode is comparable with previously reported homogeneous ionic liquid catalysts (TOFs of  $10^2$ – $10^5 \text{ h}^{-1}$ ) [4,5,7,9,10] and other heterogeneous poly(ionic liquid) catalysts (TOFs of  $10^1$ – $10^3 \text{ h}^{-1}$ ) [12–15].



**Scheme 3.** Selective separation of iodobenzene and Suzuki–Miyaura carbon–carbon coupling reaction biphenyl product from phenylboronic acid and solvent mixture using palladium–poly(ionic liquid) membrane flow reactor.

The palladium membrane loadings used for the Suzuki–Miyaura coupling reaction (a reaction solution equivalent of  $0.061 \pm 0.004 \text{ mol}\%$  or  $11.1 \pm 8 \text{ ppm}$  on a mass basis) are lower than most previously reported ionic liquid catalysts (homogeneous and heterogeneous) which range between 0.1–18 mol% [5,7–12,14–16,22,64]. A palladium leaching value of  $83 \text{ ppb h}^{-1} \text{ cm}^{-3}$  at 343 K compares favourably with previously reported solid support heterogeneous catalysts (where palladium leaching rates exceed  $100 \text{ ppb h}^{-1} \text{ cm}^{-3}$ ) [65,66]. This is equivalent to  $\sim 1\%$  of the Pd present leaching from an already sub 0.1 mol% catalyst during one reaction cycle at 343 K, and even lower leaching rates are to be expected when the membrane is used at room temperature.

In the case of the flow membrane reactor mode of operation, ambient temperature sonicated Suzuki–Miyaura reactions gave a calculated TOF value for biphenyl product formation of  $154 \text{ h}^{-1}$ . This is comparable with previously reported Suzuki–Miyaura flow reactors (TOF  $10^1$  to  $10^4 \text{ h}^{-1}$ ) [24,26–28,67], however such systems require high pressures or elevated temperatures. The beneficial preferential separation of iodobenzene reactant and biphenyl product from the phenylboronic acid and reaction solvents in the present study can be ascribed to the selective solubility of the prepared membrane system, Scheme 3. Ionic liquids tend to solvate a wide range of species including unsubstituted benzene and haloarenes [68,69], therefore iodobenzene can diffuse directly through the poly(ionic liquid) layer, accounting for its high concentration in the product solution. Comparatively, phenylboronic acid is insoluble in some imidazolium ionic liquids and will therefore predominantly remain behind in the reactant ethanol:water solvent phase [70]. The absence of transportation for the water and ethanol reaction mixture constituents through the catalyst membrane is most probably due to the immiscibility of ethanol and water with imidazole containing ionic liquids and the pulsed plasma deposited poly(vinylbenzyl chloride) interfacial layer at ambient temperature [71–73], as well as liquid repellency from the underlying PTFE membrane (surface tension of water =  $72.8 \text{ mN m}^{-1}$  [74], surface tension of ethanol =  $22.3 \text{ mN m}^{-1}$  [74], and surface energy of PTFE =  $20.0 \text{ mN m}^{-1}$  [75]). Therefore, the outlined approach not only allows for the palladium catalysed Suzuki–Miyaura carbon–carbon coupling reaction to proceed at room temperature under flow conditions, but also concurrently separates the solvent mixture from the aromatic product phase, thereby eliminating any need for post reaction separation of product from reaction solvents.

## 5. Conclusion

Plasmachemical surface functionalisation with benzyl chloride groups provides a quick, low cost approach for fabricating anisotropic palladium–poly(ionic liquid) catalyst membrane systems. This





- [43] J.F. Evans, J.H. Gibson, J.F. Moulder, J.S. Hammond, H. Goretzki, Angle resolved ESCA analysis of plasma modified polystyrene, *Fresen. Z. Anal. Chem.* 319 (1984) 841–844.
- [44] R.M. Friedman, J. Hudis, M.L. Perlman, Chemical effects on linewidths observed in photoelectron spectroscopy, *Phys. Rev. Lett.* 29 (1972) 692–695.
- [45] G. Johansson, J. Hedman, A. Berndtsson, M. Klasson, R. Nilsson, Calibration of electron spectra, *J. Electron. Spectrosc. Relat. Phenom.* 2 (1973) 295–317.
- [46] S. Morsch, W.C.E. Schofield, J.P.S. Badyal, Surface actuation of smart nanoshutters, *Langmuir* 26 (2010) 12342–12350.
- [47] S. Morsch, W.C.E. Schofield, J.P.S. Badyal, Tailoring the density of surface-tethered bottlebrushes, *Langmuir* 27 (2011) 14151–14159.
- [48] S. Morsch, T.J. Wood, W.C.E. Schofield, J.P.S. Badyal, A combined plasmachemical and emulsion templating approach for actuated macroporous scaffolds, *Adv. Funct. Mater.* 22 (2012) 313–322.
- [49] D. Lin-Vien, N.B. Colthup, W.G. Fateley, J.G. Grasselli, *The Handbook of Infrared and Raman Characteristic Frequencies of Organic Molecules*, Academic Press, Inc., San Diego, 1991.
- [50] L.M. Han, R.B. Timmons, D. Bogdal, J. Pielichowski, Ring retention via pulsed plasma polymerization of heterocyclic aromatic compounds, *Chem. Mater.* 10 (1998) 1422–1429.
- [51] T. Cremer, C. Kolbeck, K.R.J. Lovelock, N. Paape, R. Wölfel, P.S. Schulz, P. Wasserscheid, H. Weber, J. Thar, B. Kirchner, F. Maier, H.-P. Steinrück, Towards a molecular understanding of cation–anion interactions—probing the electronic structure of imidazolium ionic liquids by NMR spectroscopy, X-ray photoelectron spectroscopy and theoretical calculations, *Chem. Eur. J.* 16 (2010) 9018–9033.
- [52] X.F. Luo, S.H. Goh, S.Y. Lee, C.H.A. Huan, Spectroscopic studies of interactions in complexes of poly(1-vinylimidazole) with poly(styrenesulfonic acid) or the zinc salt of poly(styrenesulfonate), *Macromol. Chem. Phys.* 200 (1999) 874–880.
- [53] D.O.H. Teare, W.C.E. Schofield, R.P. Garrod, J.P.S. Badyal, Rapid polymer brush growth by TEMPO-mediated controlled free-radical polymerization from swollen plasma deposited poly(maleic anhydride) initiator surfaces, *Langmuir* 21 (2005) 10818–10824.
- [54] J.F. Moulder, W.F. Stickle, P.E. Sobol, K.D. Bomden, J. Chastain (Ed.), *Handbook of X-Ray Photoelectron Spectroscopy*, Perkin-Elmer Corporation, Minnesota, 1992.
- [55] D. Briggs, M.P. Seah, *Practical surface analysis, Auger and X-Ray Photoelectron Spectroscopy vol. 1*, John Wiley, Chichester, UK, 1990.
- [56] M. Prutton, *Surface Physics*, Oxford University Press, New York, 1985, p. 23.
- [57] K. Noack, P.S. Schulz, N. Paape, J. Kiefer, P. Wasserscheid, A. Leipertz, The role of the C2 position in interionic interactions of imidazolium based ionic liquids: a vibrational and NMR spectroscopic study, *Phys. Chem. Chem. Phys.* 12 (2010) 14153–14161.
- [58] F. Maier, J.M. Gottfried, J. Rossa, D. Gerhard, P.S. Schulz, W. Schwieger, P. Wasserscheid, H.-P. Steinrück, Surface enrichment and depletion effects of ions dissolved in an ionic liquid: an X-ray photoelectron spectroscopy study, *Angew. Chem., Int. Ed.* 45 (2006) 7778–7780.
- [59] J.P.S. Badyal, Beyond the surface, *Chem. Br.* 37 (2001) 45–46.
- [60] G.M. Scheuermann, L. Rumi, P. Steurer, W. Bannwarth, R. Mülhaupt, Palladium nanoparticles on graphite oxide and its functionalized graphene derivatives as Highly active catalysts for the Suzuki–Miyaura coupling reaction, *J. Am. Chem. Soc.* 131 (2009) 8262–8270.
- [61] K. Okumura, T. Tomiyama, S. Okuda, H. Yoshida, M. Niwa, Origin of the excellent catalytic activity of Pd loaded on ultra-stable Y zeolites in Suzuki–Miyaura reaction, *J. Catal.* 273 (2010) 156–166.
- [62] M. Beller, H. Fischer, W.A. Herrmann, K. Öfele, C. Brossmer, Palladacycles as efficient catalysts for aryl coupling reactions, *Angew. Chem. Int. Ed.* 34 (1995) 1848–1849.
- [63] M. Feuerstein, D. Laurenti, C. Bougeant, H. Doucet, M. Santelli, Palladium–Tetraphosphine catalysed cross coupling of aryl bromides with arylboronic acids: remarkable influence of the nature of the ligand, *Chem. Commun.* 4 (2001) 325–326.
- [64] M. Burguete, E. García-Verdugo, I. García-Villar, F. Gelat, P. Licence, S. Luis, V. Sans, Pd catalysts immobilized onto gel-supported ionic liquid-like phases (g-SILLPs): a remarkable effect of the nature of the support, *J. Catal.* 269 (2010) 150–160.
- [65] B.M. Choudary, S. Madhi, N.S. Chowdari, M.L. Kantam, B. Sreedhar, Layered double hydroxide supported nanopalladium catalyst for Heck-, Suzuki-, Sonogashira-, and Stille-type coupling reactions of chloroarenes, *J. Am. Chem. Soc.* 124 (2002) 14127–14136.
- [66] S. Frindy, A. Primo, M. Lahcini, M. Bousmina, H. Garcia, A. El Kadib, Pd embedded in chitosan microspheres as tunable soft-materials for Sonogashira cross-coupling in water–ethanol mixture, *Green Chem.* 17 (2015) 1893–1898.
- [67] H. Hagiwara, Y. Sugawara, K. Isobe, T. Hoshi, T. Suzuki, Immobilization of Pd(OAc)<sub>2</sub> in ionic liquid on silica: application to sustainable Mizoroki–Heck reaction, *Org. Lett.* 6 (2004) 2325–2328.
- [68] M.B. Shiflett, A.M.S. Niehaus, A. Yokozeki, liquid-liquid equilibria in binary mixtures containing chlorobenzene, bromobenzene, and iodobenzene with ionic liquid 1-Ethyl-3-methylimidazolium Bis(trifluoromethylsulfonyl)imide, *J. Chem. Eng. Data* 54 (2009) 2090–2094.
- [69] J.G. Huddleston, H.D. Willauer, R.P. Swatloski, A.E. Visser, R.D. Rogers, Room temperature ionic liquids as novel media for ‘Clean’ liquid–liquid extraction, *Chem. Commun.* 16 (1998) 1765–1766.
- [70] R. Singh, M. Sharma, R. Mamgain, D.S. Rawat, Ionic liquids: a versatile medium for palladium-catalyzed reactions, *J. Braz. Chem. Soc.* 19 (2008) 357–379.
- [71] V. Najdanovic-Visak, J.M.S.S. Esperanc, L.P.N. Rebelo, M.N. da Ponte, H.J.R. Guedes, K.R. Seddon, H.C. de Sousa, J. Szydowski, Pressure, isotope, and water co-solvent effects in liquid-liquid equilibria of (ionic liquid + alcohol) systems, *J. Phys. Chem. B* 107 (2003) 12797–12807.
- [72] Polymer Source Inc., [www.polymersource.com/Resources/Solubility.pdf](http://www.polymersource.com/Resources/Solubility.pdf) (Accessed May 29, 2017).
- [73] Alfa Aesar, Thermo Fisher Scientific, [www.alfa.com/en/content/msds/english/43067.pdf](http://www.alfa.com/en/content/msds/english/43067.pdf) (Accessed May 29, 2017).
- [74] G. Vázquez, E. Alvarez, J.M. Navaza, Surface tension of alcohol + water from 20 to 50 °C, *J. Chem. Eng. Data* 40 (1995) 611–614.
- [75] J.-R. Chen, T. Wakida, Studies on the surface free energy and surface structure of PTFE film treated with low temperature plasma, *J. Appl. Polym. Sci.* 63 (1997) 1733–1739.