



Open Access

Comparison of mcl-Poly(3-hydroxyalkanoates) synthesis by different *Pseudomonas putida* strains from crude glycerol: citrate accumulates at high titer under PHA-producing conditions

Ignacio Poblete-Castro^{1,2*}, Danielle Binger³, Rene Oehlert² and Manfred Rohde⁴

Abstract

Background: Achieving a sustainable society requires, among other things, the use of renewable feedstocks to replace chemicals obtained from petroleum-derived compounds. Crude glycerol synthesized inexpensively as a byproduct of biodiesel production is currently considered a waste product, which can potentially be converted into value-added compounds by bacterial fermentation. This study aimed at evaluating several characterized *P. putida* strains to produce medium-chain-length poly(3-hydroxyalkanoates) (mcl-PHA) using raw glycerol as the only carbon/energy source.

Results: Among all tested strains, *P. putida* KT2440 most efficiently synthesized mcl-PHA under nitrogen-limiting conditions, amassing more than 34% of its cell dry weight as PHA. Disruption of the PHA depolymerase gene (*phaZ*) in *P. putida* KT2440 enhanced the biopolymer titer up to 47% PHA (%wt/wt). The low biomass and PHA titer found in the mutant strain and the wild-type strain KT2440 seems to be triggered by the high production of the side-product citrate during the fermentation process which shows a high yield of 0.6 g/g.

Conclusions: Overall, this work demonstrates the importance of choosing an appropriate microbe for the synthesis of mcl-PHA from waste materials, and a close inspection of the cell metabolism in order to identify undesired compounds that diminish the availability of precursors in the synthesis of biopolymers such as polyhydroxyalkanoates. Future metabolic engineering works should focus on reducing the production of citrate in order to modulate resource allocation in the cell's metabolism of *P. putida*, and finally increase the biopolymer production.

Keywords: *Pseudomonas putida* strains, mcl-polyhydroxyalkanoates, Raw glycerol, PHA depolymerase, Metabolic engineering, Citrate

Background

The consumption of non-renewable materials for industrial production of chemicals has given rise to environmental and energy concerns within society. Plastic products are considered essential materials to meet the needs of our current lifestyle and modern manufacturing. As an attempt to move towards a sustainable society, research has been undertaken to develop the microbial fermentation of renewable resources for the synthesis of biopolymers [1,2]. An example of the sustainable production of biopolymers is the large-scale production of polyhydroxyalkanoates (PHAs), which exhibit similar physical and mechanical properties to oil-based thermoplastics [1]. Bacteria have the capability to naturally accumulate PHAs as carbon/energy storage materials in their cytoplasmic space, usually when there is a nutrient imbalance in the environment: a high carbon concentration accompanied by the limitation of an inorganic nutrient [3]. Taking advantage of this evolutionary bacterial trait, commercialized PHAs are currently being produced by Metabolix (USA), Meridian Inc. (USA),



© 2014 Poblete-Castro et al.; licensee BioMed Central. This is an Open Access article distributed under the terms of the Creative Commons Attribution License (http://creativecommons.org/licenses/by/4.0), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly credited. The Creative Commons Public Domain Dedication waiver (http://creativecommons.org/publicdomain/zero/1.0/) applies to the data made available in this article, unless otherwise stated.

^{*} Correspondence: ignacio.poblete@unab.cl

¹Facultad de Ciencias Biológicas, Center for Bioinformatic and Integrative Biology, Biosystems Engineering Laboratory, Universidad Andrés Bello, Santiago 8340176, Chile

²Helmholtz Centre for Infection Biology, Microbial Drugs Group, Braunschweig D-38124, Germany

Full list of author information is available at the end of the article

Biocycle (Brazil), and Biomer (Germany), to name a few. They use sugars (cane or beet) and plant-based fatty acids as carbon feedstocks for the fermentation process in stirred-tank bioreactors, and obtain a diverse assortment of biopolymers. Despite the advances, one of the main drawbacks of PHAs for better market positioning is the high costs related to the production process [4,5]. To truly develop the synthesis of these polyesters and make them more cost-competitive against petroleum-based thermoplastics, it is crucial to find novel sustainable alternatives for largescale production. Recently, production of PHAs using waste materials from agriculture residues and waste water treatment streams as a carbon substrate has shown to be a very promising alternative [6-8], since raw materials account for the majority of production costs in the bacterial synthesis of PHAs [4,9]. These processes have mainly focused on the synthesis of Poly(3-hydroxybutyrate) (PHB), the first and best-characterized PHA [1]. Despite the large range of applications possible with PHB and its co-polymer Poly(3hydroxybutyrate-valerate) (PHBV), there is still an urgent demand for other types of biopolymers with unique physical and mechanical properties, with a particular emphasis on medical applications [10]. Medium chain length polyhydroxyalkanoates (mcl-PHAs) are polyesters synthesized mainly by gram-negative bacteria; most studies on their synthesis have focused on the use of Pseudomonas species as microbial cell factories [11-14]. By applying different metabolic engineering strategies [15-17] and fermentation conditions [18,19] the titer of this biopolymer was successfully improved, and it was demonstrated also that the monomer composition of the produced mcl-PHAs can be tuned [20-22]. In addition, given the high metabolic versatility shown by some *Pseudomonas putida* strains [23], waste materials from different streams have been used as carbon substrate to produce mcl-PHAs. Efficient synthesis of mcl-PHAs was obtained from animal wastes [24], PET [25] and raw glycerol [26]. Also, the conversion of biomassderived compounds into mcl-PHA has been recently achieved [27,28]. One of the most promising raw materials for the synthesis of biobased chemicals is glycerol. The commercial price of this polyol has drastically decreased in the last decade due to the large industrial production of biodiesel from fatty acids, where glycerol is produced as a

byproduct of the esterification process. For every 10 tons of biodiesel, 1 ton of glycerol is formed. Because of this, there is currently an oversupply of this commodity worldwide which has resulted in its classification as a waste product instead of a valuable good [29]. P. putida strains have been recently described to be capable of synthesizing mcl-PHAs from raw glycerol [25,26]. In this work, several P. putida strains were challenged to growth in raw glycerol as carbon and energy source and compared for their capability to produce mcl-PHA. The best PHA-producing P. putida strain was further engineered to enhance the synthesis of mcl-PHA in the cell. An exo-metabolome analysis was performed to identify and quantify byproduct formation during the fermentation process in bioreactors, and finally the causes for the low yield of biomass and biopolymers in Pseudomonas putida fed with glycerol were elucidated.

Results and discussion

Raw glycerol is produced as a byproduct of the chemical conversion of fatty acids into biodiesel, a process that results in the following basic products: glycerol (60-80%), water (10%), organic matter (8%), ash (8%), and methanol (0.5-20%). Although methanol concentration seems to be minor, it exerts a high degree of toxicity to this feed stock material, thus limiting its use in industrial biotechnology. Bacteria from the genus Pseudomonas especially Pseudomonas putida- possess a high metabolic versatility which allow them to colonize harsh and toxic environments [30]. In an attempt to test whether this raw material is suitable for the efficient production of medium chain length polyhydroxyalkanoates (mcl-PHAs), we selected three well-known PHA-producing strains: Pseudomonas putida KT2440, KT2442, and F1, and the solvent-tolerant P. putida S12 (Table 1). All of them have been previously reported to be able to grow in pure glycerol [12,31,32]. As shown in Figure 1, each P. putida strain grew well in minimal medium supplemented with 3 (g/L) of raw glycerol as carbon source. It is noteworthy to mention that we have not filtered or in any way modified the industrial byproduct glycerol. As already reported, P. putida KT2440 showed a long lagphase (8 hours, this work) when grown on glycerol [33]. Escapa and co-workers found that by adding a small

Table 1 Features of *Pseudomonas putida* strains used in this study

Strain	Genome size (bp)	GC content (%)	Isolated in	Solvent- tolerant	Biotechnological applications
P. putida KT2440	6.181.863	61.5	Japan	No	Bioremediation Synthesis of biomaterials and chemicals
P. putida KT2442	N. K	N. K	Spontaneous rifampicin resistant	No	Bioremediation Synthesis of biomaterials and chemicals
<i>P. putida</i> F1	5.959.964	61.9	USA	No	Degradation of chloroaromatic compounds
P. putida S12	6.284.656	61.5	The Netherlands	Yes	Synthesis of added-value chemicals

N.K. Not known.



amount of octanoate or glucose, the length of the lagphase can be reduced. In addition, elimination of the lag-phase was also achieved by knocking out the transcriptional regulator glpR (PP_1074). In this work, all tested *P. putida* strains have a similar lag-phase to that shown by KT2440, except for KT2442, which took more than 15 hours to begin the exponential growth phase (Figure 1).

Evaluation of PHA synthesis on different *Pseudomonas putida* strains in shake flask experiments

We next challenged *Pseudomonas putida* KT2440, KT2442, S12, and F1 to grow in minimal medium (M9) supplemented with 30 (g/L) of crude glycerol as the sole carbon source in batch cultures. After 72 hours of cultivation, cells were harvested so as to quantify the biomass and mcl-PHA content. *P. putida* KT2442, S12, and F1 were found to have a similar biomass concentration (Table 2). This was not the case for PHA production, where *P. putida* KT2442 produced twice as much biopolymer in comparison to the other two strains (Table 2). *P. putida* KT2440 was by far the most efficient PHA-producing organism among all tested strains, amassing 35% of its CDW as PHA, and achieving a biomass yield of 0.048 (g/g). This demonstrates the intrinsic

metabolic differences between P. putida KT2440 and KT2442, which highly influence their PHA production capacity in the presence of PHA-unrelated carbon sources (glycerol, gluconate, and glucose). In this regard, a similar response has been found when both strains were compared in batch cultures using gluconate as carbon source; the production of mcl-PHA was 10-fold higher for KT2440 relative to KT2442 [34]. This phenomenon might be attributed to an inefficient transport capacity of 2-ketogluconate in P. putida KT2442, which would diminish the amount of available carbon within the cell, and negatively impact PHA synthesis. As glycerol is metabolized via a different metabolic route compared to the one used for gluconate, no gluconate-related oxidized compounds, e.g. 2-ketogluconate, are formed in the upper catabolic pathways. This may explain the reduced amount of synthesized biomass and mcl-PHA in P. putida KT2442.

Deletion of the *phaZ* gene in *P. putida* KT2440 enhances mcl-PHA synthesis using raw glycerol as a carbon and energy source

One of the first strategies for maintaining the titer of PHA inside of cells during the fermentation process is to remove the gene responsible for the depolymerization process of PHA (PHA depolymerase). However, the role of PhaZ proteins in the synthesis of mcl-PHA in P. putida strains is not well understood. In a previous work, disruption of the PHA depolymerase gene (PP_5004, phaZ) in P. putida KT2442 led to an increase in PHA synthesis using fatty acids as carbon source, but not when growing on glucose or gluconate [15], where the mutant strain produced less PHA in comparison to the wild-type strain. One could argue then, since glycerol is also a non-related PHA carbon source, it should show the same PHA-accumulation pattern as glucose or gluconate, resulting ultimately in no increase of the biopolymer. Nevertheless, in the study done by [15], they generated a phaZmutant strain in KT2442, and as demonstrated in the research presented in this paper, this strain produces less mcl-PHA from no-alkanoate substrates. Therefore we generated a knockout mutant strain in the best PHAproducing strain, P. putida KT2440. The chromosomal

Table 2 Monomer composition of medium chain length PHA produced by different P. putida strains

Strain	CDW (g/L)	PHA (%wt)	PHA (g/L)	Monomer composition (%)					
				C6	C8	C10	C12:1	C12	C14:0
P. putida KT2440	4.23 ± 0.11	34.5	1.46 ± 0.21	0.83	16.2	74.6	2.9	6.0	0.59
P. putida KT2442	3.45 ± 0.07	26.5	0.91 ± 0.13	t.d.	7.8	78.5	3.6	9.2	0.95
P. putida F1	3.50 ± 0.14	10.3	0.36 ± 0.01	t.d.	14.4	71.3	3.9	11.4	t.d
P. putida S12	3.20 ± 0.07	12.6	0.40 ± 0.05	t.d.	4.0	70.9	4.5	20.1	t.d.
∆phaZ	4.20 ± 0.21	46.8	1.94 ± 0.17	1.1	16.3	72.3	3.4	6.9	t.d

The data were determined by GC/MS and are given as relative molar fraction (%) of C6: 3-hydroxyexanoate, C8: 3-hydroxyoctanoate, C10:3-hydroxydecanoate, C12: 3-hydroxydodecanoate, C12:1: 3-hydroxy-5-cis-dodecanoate, and C14: 3-hydroxytetradecanoate.

deletion of phaZ (PP_5004) in P. putida KT2440 was performed as described in Methods. The $\Delta phaZ$ mutant strain was then subjected to PHA-production conditions in flask cultures in the same manner as described above with the wild type strain KT2440. There was no difference in total biomass yield (Table 2) between $\Delta phaZ$ and P. putida KT2440 wild type, however and most importantly, the first improved the PHA titer by 34% (Table 2). PHA depolymerase is believed to be required for the efficient production of the polyester -- under PHA-accumulating conditions in batch culture— in P. putida KT2442 and P. putida U using fatty acids as the carbon substrate [35-37]. However, the opposite result has been reported for the same mutant strain ($\Delta phaZ$) in *P. putida* KT2442 [15], and P. putida U [38]. Because we measured more mcl-PHA in $\Delta phaZ$ than its parent strain KT2440, we conclude that PHA depolymerase does not impose a negative effect on the PHA synthesis machinery. The PHA cluster genes orchestrates a simultaneous process of PHA synthesis and hydrolysis [35], making it impossible for the cell to degrade the PHA granule and further mobilize 3hydroxyalkanoic acids for energy generation; this may be the primary reason for the greater accumulation of mcl-PHA in the $\Delta phaZ$ mutant strain when grown on glycerol.

PHA morphology and monomer composition of PHA in *P. putida* strains grown on pure and raw glycerol

As raw glycerol contains methanol and other toxic compounds, it may impose a stressful environment to cells. To

get insight into the structural changes of cells and the accumulated PHA in both strains while growing in raw and pure glycerol, field emission scanning and transmission electron microscopy was applied. Micrographs were taken of cells at 72 h of cultivation, where maximum accumulation of PHA was obtained. Cells of the mutant and the wild-type strain did not show changes in their morphology when grown on raw or pure glycerol (Figure 2A,B,C,D), instead cells cultivated on crude glycerol stick together, where some of the impurities contained in the growing substrate can be observed (Figure 2B,D). The deletion of phaZ gene in P. putida KT2440 had no effect on PHA granules (Figure 2G,H). A different scenario was observed for PHA granules produced in both strains on raw glycerol, where the number of inclusion bodies was higher and more irregular in comparison to granules synthesized in cells cultivated on pure glycerol (Figure 2I,J,K,L).

The dominant monomer characterized using GC-MS was 3-OH decanoic acid (C10) for all of the tested strains (Table 2). This has been shown to be true for various *P. putida* strains when they synthesize PHA from gluconate, glucose, or glycerol [12,16]. First, glycerol is converted in several steps to yield acetyl-CoA. Next, the glycerol is either used in the TCA cycle or used for the synthesis of *de novo* fatty acids (Figure 3). These *de novo* fatty acids are the precursor for PHA synthesis. Since 3-hydroxyacyl-ACP is restricted to 10 carbon substrates [39], a high content of 3-hydroxydecanoic acid is produced in the PHA polymerization cycle [16].





Influence of aeration on the production of mclpolyhydroxyalkanoates in *P. putida AphaZ* mutant strain

We explored the influence of aeration on the synthesis of biomass and mcl-PHA in shaken-flask cultures of $\Delta phaZ$, the mutant strain with the highest mcl-PHA production rates. $\Delta phaZ$ was grown in 500 mL flasks containing different volumes of minimal medium (50, 100, 200, 300, 400 mL, which correspond to a 0.1, 0.2, 0.4, 0.6, and 0.8 volume ratio, respectively) supplemented with 30 g/L raw glycerol. It was found that volume ratios higher than 0.2 exert a negative influence on biomass formation (Figure 4). In other words, as less oxygen is available with increasing the volume ratio, the oxidation state of the cell is disturbed, which resulted in inefficient energy generation, negatively impacting the production of biomass. PHA synthesis, in turn, also suffers from less oxic conditions, showing a 6-fold decrease of final PHA concentration (Figure 4). From this experiment we can conclude that PHA synthesis benefits from a well-aerated environment when raw glycerol is used as carbon source. This is crucial when developing an efficient PHA production process since biomass formation is critical to the production of biopolymers [19].

Comparison of mcl-PHA synthesis by *P. putida* KT2440 and $\Delta phaZ$ mutant strain on mcl-PHA synthesis in well-controlled batch bioreactor

To fully investigate the PHA production capacity of $\Delta phaZ$ and its parent strain KT2440, each biocatalyst was now cultivated in a more controlled environment using aerobic batch bioreactors. In addition, we did a detailed inspection of the exo-metabolome of the fermentation broth throughout the entire cultivation period via HPLC in order to characterize and quantify possible byproducts (citrate, formate, pyruvate, succinate, malate, acetate, see Methods section) produced by the cell. Both strains had an initial lag-phase of 7 h, after that time they started growing to a maximum specific growth rate of 0.22 h^{-1} . Ammonium was below the detection limit at 18 h and 24 h for $\Delta phaZ$ and *P. putida* KT2440, respectively. As a consequence of nitrogen limitation, both strains began rapidly accumulating PHA until glycerol was completely consumed (Figure 5). Although $\Delta phaZ$ and *P. putida* KT2440 showed a similar total biomass yield when grown on glycerol (Table 2), $\Delta phaZ$ synthesized more PHA (~36% higher) in comparison to KT2440. It can be clearly seen in Figure 5 that $\Delta phaZ$ strain accumulates



the biopolymer while consuming the available carbon source in the culture broth. Thus, the absence of this *loci* (PP_5004, *phaZ*) is not crucial, as previously believed, for the efficient synthesis of mcl-PHA in *Pseudomonas putida*. Another important finding was the detection of citric acid via HPLC, which reached a concentration of more than 20 g/L at the end of the cultivation period (Figure 5). It is important to mention that no other organic acid was detected in the broth culture during the fermentation process. Citrate has a final yield of 0.6 [g/g] for both the mutant and the wild type P. putida strain when grown on glycerol. This seems to be the principal reason for the observed biomass and PHA yield for strains grown on glycerol. Once glycerol is metabolized, the pool of acetyl-CoA replenishes both the TCA cycle and the de novo synthesis of fatty acids (Figure 3). It seems that more carbon was delivered to the TCA cycle since a higher amount of carbon was found in the form of citric acid than mcl-PHA. As methanol concentration in the culture broth is 0.188 g/L (see Methods section), this compound cannot be the principal factor influencing the final titer of citrate obtained at the end of the fermentation period (Figures 3, 5). A possible explanation of the high accumulation of citrate under the tested conditions is that PHAproducing environments (nitrogen limitation) increase the ratio of NAPH/NADP and/or NADH/NAD into the cell [40,41], which eventually results in repression of several enzymes belonging to the TCA cycle. We recently demonstrated that these cofactors play an important role in the synthesis of mcl-PHA in P. putida KT2440, where NADPH is consumed to increase the biopolymer production within the cell, resulting in a high level of NADH/ NAD ratios [17]. One of the most affected proteins under high NADH levels is isocitrate dehydrogenase (PP_4012 and PP_4011), which catalyzes the conversion of isocitrate into oxalosuccinate. This effect limits the proper functioning of the Krebs cycle to further oxidize citrate. We have previously reported that intracellular concentrations of citrate were higher under elevated PHA levels in continuous cultivations using decanoate as carbon source, whereas both enzymes isocitrate dehydrogenase and lyase had low expression levels at the transcriptome and proteome level [13]. It is well documented that citric acid-producing microorganisms like the yeast Yarrowia lipolytica and the industrial mold Aspergillus niger (Table 3) accumulate large amount of citric acids (>150 g/L) and lipids under nitrogen limiting conditions [42-45]. As they do not posses the PHA machinery to naturally produce the polyester, they synthesize lipids instead, mainly in the form of triacylglycerol, reaching up to 50% of its CDW as lipids [46]. In yeast, N-limitation environments have been found to trigger the drop in the concentration of adenosine monophosphate (AMP) [47], thus inhibiting the isocitrate dehydrogenase leading to the accumulation of citrate and isocitrate [42]. As explained above, it seems that a similar mechanism drives the metabolic response of P. putida KT2440 under the PHA-producing conditions tested in this study. In order to fully confirm this hypothesis, further studies should aim at evaluating the intracellular flux distribution as well as the concentration of AMP, NADP/NADPH, and NAD/NADH ratios, in a more appropriate system such as continuous cultures (chemostat), where there are no changes in the specific growth rate or interferences by



carbon catabolic repression [48], which affect the levels of the redox carrier compounds in the cell [49,50].

Conclusions

This study shows that bacteria from the genus *Pseudo-monas* can cope with the adverse conditions imposed by

the chemical mixture of which raw glycerol from biodiesel production is composed. It also demonstrates the use of this cheap material in the efficient synthesis of mcl-PHA. Among all tested strains, *P. putida* KT2440 was the most efficient at mcl-PHA synthesis, amassing more than 34% of its CDW as PHA using raw glycerol

Table 3 Citric acid-producing microorganisms using different carbon sources

Strain	Carbon substrate	Fermentation mode	Ycitrate/S (g/g)	Citrate (g/L)	Ref.
Y. lipolytica mutant	Rapseed Oil	Batch	1.5	175	[51]
Y. lipolytica A-101	Raw Glycerol	Batch	0.6	112	[52]
A. niger mutant	Beet, Cane Molasse	Batch	0.7	113.5	[53]
A. niger	Glucose	-	0.9	200	[54]
P. putida KT2440	Raw Glycerol	Batch	0.6	20	This study
P. putida ∆phaZ	Raw Glycerol	Batch	0.6	20	This study

as its only energy/carbon source. Disruption of the PHA depolymerase gene (*phaZ*) in *P. putida* KT2440 enhanced the biopolymer titer up to 47% (%PHA/wt). The low biomass and PHA titer found in *P. putida* KT2440 and the $\Delta phaZ$ strain on glycerol seems to be caused by the production of high levels of citrate during the fermentation process. Future metabolic engineering works should focus on eliminating or reducing the production of this organic acid in order to modulate resource allocation in the cell's metabolism, and finally increase the specific volumetric productivity of PHA that is crucial for a cost-effective biopolymer production.

Methods

Bacterial strains

P. putida KT2440 (DSM 6125) and F1 (DSM 6899) were obtained from the German Collection of Microorganisms and Cell Culture (DSMZ, Braunschweig, Germany). *P. putida* KT2442 [55] and *P. putida* S12 [56] were obtained from CSIC Madrid (Spain) and RWTH Aachen (Germany), respectively.

Construction of the *phaZ* knock-out mutant strain in *P. putida* KT2440

All PCR fragments generated for vector construction were subcloned into plasmid pCR°2.1 (Invitrogen, CA, USA), transformed into E. coli DH5a (Invitrogen, CA, USA), and validated by sequencing. Plasmid pEMG [57] was used for the construction of pEMG_APP5004. Approximately 600 bp of the upstream and downstream regions of gene PP5004 were amplified using primers PP5004_UP_fw, PP5004_UP_rev, PP5004_DOWN_fw and PP5004_DOWN_rev (Table 4), Taq DNA polymerase (Qiagen, Venlo, The Netherlands) and genomic DNA from strain P. putida KT2440. Both PCR fragments were fused by PCR [58] and the resulting fusion PCR product was integrated into pEMG via XbaI-KpnI restriction sites to generate pEMG_{DP5004. The resulting vector pEMG_ Δ PP5004 was transformed into E. coli CC118\pir to generate donor cells for later triparental mating with P. putida KT2440 [55] and the helper strain E. coli HB101 as described by [59].

To generate a single mutant of gene PP5004, genome editing was applied [57]. Therefore, vector pEMG_ Δ PP5004 was co-integrated by a single crossover into the chromosome of *P. putida* KT2440 using tri-parental mating with E. coli HB101 as helper strain, as well as the donor strain E. coli CC118 λ pir pEMG_ Δ PP5004. Successful homologous integration of the vector DNA and the successful genomic deletions was confirmed by PCR (data not shown).

Cultivation conditions

Flask experiments

P. putida strains, kept as frozen stock in 25% glycerol at -80°C, were streaked on Luria Bertani agar plates and incubated for one day at 30°C. Single colonies were then picked from the plate and inoculated it into a 50 mL shake flask containing 10 ml of the above described medium (M9) and incubated overnight under aerobic conditions at 30°C and 180 rpm (Innova, Enfield, USA) set. By taking a calculated volume of the obtained cell suspension from the pre-culture (to begin the PHAaccumulating process with an initial OD of 0.05), 500 mL baffled shake flasks containing 100 mL of culture medium were inoculated and placed in a rotary shaker under aerobic conditions at 30°C. Each culture was carried out by triplicate. P. putida strains were grown in a defined M9 mineral medium consisting of (per liter) 12.8 g Na₂HPO₄⁷H₂O, 3 g KH₂O₄, 1 g NH₄Cl, and 0.5 g NaCl. This basic solution was autoclaved and subsequently supplemented with 0.12 g of MgSO₄H₂O, trace elements (mg/L): 6.0 FeSO₄⁻⁷H₂O, 2.7 CaCO₃, 2.0 ZnSO₄⁻H2O, 1.16 MnSO₄H₂O, 0.37 CoSO₄7H₂O, 0.33 CuSO₄5H₂O, 0.08 H₃BO₃ (all filter-sterilized). 30 g/L of raw glycerol was then added to the medium which was previously autoclaved. The raw glycerol used in all experiments was obtained from the company Cremer Oleo (Hamburg, Germany). It contained 80% glycerol, 0.5% methanol, 10% ash, 3% organic matter, and 6.5% water.

Bioreactor fermentations

P. putida strains were grown in M9 medium supplemented with 30 g/L raw glycerol. Bioreactor batch fermentations were carried out in a 2 L top-bench BIOSTAT B1 bioreactor (Sartorius B Systems GmbH, Melsungen, Germany) with a working volume of 1.5 L, at 30°C. The aeration rate was set to 500 mL/Lmin using a mass flow controller (PR4000, MKS Instruments, Wilmington, MA,

Table 4 Pr	imers used	in this	study
------------	------------	---------	-------

Tuble 4 Finners used in this study			
Primer	Sequence (5'-3')		
PP5004_UP fw	TCTAGAGACATCCTGTTCTGGAAC		
PP5004_UP_rev	CCCCTGTCAGGCCGCAGCTGGCACGTGACTCTTGGGTGAAGTAAAC		
PP5004_DOWN_fw	CACCCAAGAGTCACGTGCCAGCTGCGGCCTGACAGGGGAAATGGATC		
PP5004_DOWN rev	GGTACCGTTGAACAGCTCCTTGAC		

USA). The dissolved oxygen level was kept above 20% air saturation by control of the agitation speed up to a maximum of 700 rpm. The pH was maintained at 7.0 by automatic pH controlled addition of 0.5 M $\rm H_2SO_4$ or 1 M of KOH.

Analytical procedures

Cell growth was recorded as optical density (OD) at 600_{nm} (Ultraspec 2000, Hitachi, Japan). The cell dry weight was determined gravimetrically after collection of 10 mL culture broth for 10 min at 4°C and 9,000 × *g* (Eppendorf 5810 R, Hamburg, Germany) in pre-weighed tubes, including a washing step with distilled water, and drying of the obtained pellet at 100°C until constant weight. The ammonium concentration in cell-free supernatant was measured by a photometric test (LCK 303 kit, Hach Lange, Danaher, USA).

HPLC analysis

The glycerol and organic acids concentration (citrate, isocitrate, succinate, fumarate, malate, pyruvate, and citrate) in cultivation supernatant was analyzed by HPLC Agilent 1260 (Agilent, Krefeld, Germany) equipped with an 8 mm Rezex ROA-organic acid H column (Phenomenex, USA) at 65°C with 0.013 N H₂SO₄ as the mobile phase (0.5 mL·min⁻¹) followed by detection using a RID detector (Agilent serie1260).

PHA characterization and quantification

PHA compositions of the polymer produced, as well as the cellular PHA content concentration were determined by gas chromatography (GC) and mass spectrometry (MS) of the methanolyzed polyester. First, 10 mL of the culture broth was placed in a falcon tube and centrifuged for 10 min at 4°C and 9,000 \times g (Eppendorf 5810 R, Hamburg, Germany), following by a washing step with distilled water. The supernatant was poured away by pipetting and the cell pellet kept at -20°C for further process. Methanolysis was carried out by suspending 5-10 mg of lyophilized aliquots in 2 mL of chloroform and 2 mL of methanol containing 15% sulfuric acid and 0.5 mg/mL 3-methylbenzoic acid as internal standard, respectively, followed by incubation at 100°C for 4 h. After cooling, 1 mL of demineralized water was added and the organic phase containing the resulting methyl esters of monomers was analyzed by GC-MS. Analysis was performed in Varian GC-MS system 450GC/240MS ion trap mass spectrometer (Varian Inc., Agilent Technologies) and operated by the software MS Workstation 6.9.3 (Varian Inc., Agilent Technologies). An aliquot (1 mL) of the organic phase was injected into the gas chromatograph at a split ratio of 1:10. Separation of compounds of interest (i.e. the methyl esters of 3-hydroxyexanoate,

3-hydroxyoctanoate, 3-hydroxydecanoate, 3-hydroxydodecanoate, 3-hydroxy-5-cis-dodecanoate, 3-hydroxytetradecanoate) was achieved by a FactorFour VF-5 ms capillary column (30 m × 0.25 mm i.d. × 0.25 mm film thickness). Helium was used as carrier gas at a flow rate of 0.9 mL/min. The injector and transfer line temperature were 275°C and 300°C respectively. The oven temperature program was: initial temperature 40°C for 2 min, then from 40°C up 150°C at a rate of 5°C min⁻¹ and finally up to 280°C at a rate of 10°C min⁻¹. Positive ions were obtained using electron ionization at 70 eV and mass spectra were generated by scanning ions of m/z 50 to m/z 650. The PHA content (wt%) was defined as the percentage of the cell dry weight (CDW) represented by the polyhydroxyalkanoate.

Transmission electron microscopy

Bacteria were fixed by chilling the cultures to 4°C and addition of glutaraldehyde (2%) and formaldehyde (5%). They were then washed with cacodylate buffer (0.01 mol l)1 cacodylate, 0.01 mol l)1 CaCl₂, 0.01 mol l)1 MgCl₂ 6H2O, 0.09 mol l)1 sucrose, pH 6/9) and stained with 1% aqueous osmium for 1 h at room temperature. Samples were then dehydrated with a graded series of acetone (10, 30, 50, 70, 90 and 100%) with incubation for 30 min at each concentration, except for the 70% acetone, which contained 2% uranyl acetate and was performed overnight. Samples were infiltrated with an epoxy resin, according to the Spurr formula for hard resin, for several days with pure resin. Ultrathin sections were cut with a diamond knife, counterstained with uranyl acetate and lead citrate and examined in a TEM910 transmission electron micro- scope (Carl Zeiss, Oberkochen, Germany) at an accelera- tion voltage of 80 kV. Images were taken at calibrated magnifications using a line replica. Images were recorded digitally with a Slow-Scan CCD-Camera (ProScan, 1024 × 1024, Scheuring, Germany) with ITEM-Software (Olympus Soft Imaging Solutions, Munster, Germany).

Field emission scanning electron microscopy

Samples were fixed as above, washed with cacodylate buf- fer and then washed with TE-buffer (20 mmol l)1 TRIS, 1 mmol l)1 EDTA, pH 6.9). 50 ll of washed bacteria were applied to poly-l-lysine precoated cover slips (12 mm in diameter), which were left for 5 min, washed in TE-buffer, incubated with 2% glutaraldehyde in TE-buffer for 15 min and washed again with TE-buffer. Dehydration was carried out with a graded series of ace- tone (10, 30, 50, 70, 90, 100%) on ice for 15 min for each step, followed by 100% acetone at room temperature and critical-point drying with liquid CO_2 (CPD 30; Bal-Tec, Balzers, Liechtenstein). Samples were then gold shadowed by sputter coating (SCD 500; Bal-Tec) and examined with

Competing interest

The authors declare that they have no competing interests.

Authors' contributions

IPC designed the study and composed the manuscript. DB, RH, MR, and IPC have made substantial contributions to the acquisition of data. IPC analyzed and interpreted the data. All authors read and approved the final version of the manuscript.

Acknowledgements

We would like to thank Dr. Nick Wierckx for providing the *P. putida* S12 strain used in this study. The authors thank Carie M. Frantz for carefully reading this manuscript. Ignacio Poblete-Castro acknowledges the financial support by the program "Convenio de Desempeño Apoyo a la Innovación en Educación Superior" (PMIUAB 1301).

Author details

¹Facultad de Ciencias Biológicas, Center for Bioinformatic and Integrative Biology, Biosystems Engineering Laboratory, Universidad Andrés Bello, Santiago 8340176, Chile. ²Helmholtz Centre for Infection Biology, Microbial Drugs Group, Braunschweig D-38124, Germany. ³Helmholtz Centre for Infection Biology, Systems and Synthetic Biology, Braunschweig D-38124, Germany. ⁴Helmholtz Centre for Infection Biology, Molecular Mechanism of Streptococci Group, Braunschweig D-38124, Germany.

Received: 8 October 2014 Accepted: 11 December 2014 Published online: 23 December 2014

References

- Madison LL, Huisman GW: Metabolic engineering of poly(3-Hydroxyalkanoates): from DNA to plastic. *Microbiol Mol Biol Rev* 1999, 63(1):21–53.
- Chen G-Q: A microbial polyhydroxyalkanoates (PHA) based bio- and materials industry. Chem Soc Rev 2009, 38:2434–2446.
- Anderson AJ, Dawes EA: Occurrence, metabolism, metabolic role, and industrial uses of bacterial polyhydroxyalkanoates. *Microbiol Rev* 1990, 54(4):450–472.
- Choi J, Lee SY: Factors affecting the economics of polyhydroxyalkanoate production by bacterial fermentation. *Appl Microbiol Biotechnol* 1999, 51:13–21.
- 5. Frazzetto G: White biotechnology. EMBO Rep 2003, 4:835-837.
- Salehizadeh H, Van Loosdrecht MCM: Production of polyhydroxyalkanoates by mixed culture: recent trends and biotechnological importance. *Biotechnol Adv* 2004, 22:261–279.
- Van-Thuoc D, Quillaguamán J, Mamo G, Mattiasson B: Utilization of agricultural residues for poly(3-hydroxybutyrate) production by Halomonas boliviensis LC1. J Appl Microbiol 2008, 104:420–428.
- Koller M, Bona R, Braunegg G, Hermann C, Horvat P, Kroutil M, Martinz J, Neto J, Pereira L, Varila P: Production of polyhydroxyalkanoates from agricultural waste and surplus materials[†]. *Biomacromolecules* 2005, 6:561–565.
- Serafim L, Lemos P, Albuquerque ME, Reis MM: Strategies for PHA production by mixed cultures and renewable waste materials. *Appl Microbiol Biotechnol* 2008, 81:615–628.
- Zinn M, Witholt B, Egli T: Occurrence, synthesis and medical application of bacterial polyhydroxyalkanoate. Adv Drug Deliv Rev 2001, 53:5–21.
- Zinn M, Durner R, Zinn H, Ren Q, Egli T, Witholt B: Growth and accumulation dynamics of poly(3-hydroxyalkanoate) (PHA) in Pseudomonas putida GPo1 cultivated in continuous culture under transient feed conditions. *Biotechnol J* 2011, 6:1240–1252.
- 12. Huijberts GN, Eggink G, de Waard P, Huisman GW, Witholt B: Pseudomonas putida KT2442 cultivated on glucose accumulates poly

(3-hydroxyalkanoates) consisting of saturated and unsaturated monomers. *Appl Environ Microbiol* 1992, **58**(2):536–544.

- Poblete-Castro I, Escapa IF, Jäger C, Puchalka J, Chi Lam C, Schomburg D, Prieto M, Martins dos Santos VA: The metabolic response of P. putida KT2442 producing high levels of polyhydroxyalkanoate under singleand multiple-nutrient-limited growth: highlights from a multi-level omics approach. *Microb Cell Fact* 2012, 11:34.
- O'Leary ND, O'Connor KE, Ward P, Goff M, Dobson ADW: Genetic characterization of accumulation of polyhydroxyalkanoate from styrene in pseudomonas putida CA-3. *Appl Environ Microbiol* 2005, 71(8):4380–4387.
- Cai L, Yuan M-Q, Liu F, Jian J, Chen G-Q: Enhanced production of medium-chain-length polyhydroxyalkanoates (PHA) by PHA depolymerase knockout mutant of Pseudomonas putida KT2442. *Bioresour Technol* 2009, 100:2265–2270.
- Poblete-Castro I, Binger D, Rodrigues A, Becker J, Martins Dos Santos VAP, Wittmann C: In-silico-driven metabolic engineering of Pseudomonas putida for enhanced production of poly-hydroxyalkanoates. *Metab Eng* 2013, 15:113–123.
- Borrero-de Acuña JM, Bielecka A, Häussler S, Schobert M, Jahn M, Wittmann C, Jahn D, Poblete-Castro I: Production of medium chain length polyhydroxyalkanoate in metabolic flux optimized Pseudomonas putida. *Microb Cell Fact* 2014, 13:88.
- Sun Z, Ramsay J, Guay M, Ramsay B: Carbon-limited fed-batch production of medium-chain-length polyhydroxyalkanoates from nonanoic acid by Pseudomonas putida KT2440. Appl Microbiol Biotechnol 2007, 74:69–77.
- Poblete-Castro I, Rodriguez AL, Lam CMC, Kessler W: Improved production of medium-chain-length polyhydroxyalkanoates in glucose-based fed-batch cultivations of metabolically engineered Pseudomonas putida strains. J Microbiol Biotechnol 2014, 24:59–69.
- Liu W, Chen G-Q: Production and characterization of medium-chainlength polyhydroxyalkanoate with high 3-hydroxytetradecanoate monomer content by fadB and fadA knockout mutant of Pseudomonas putida KT2442. Appl Microbiol Biotechnol 2007, 76:1153–1159.
- Sun Z, Ramsay J, Guay M, Ramsay B: Fed-batch production of unsaturated medium-chain-length polyhydroxyalkanoates with controlled composition by Pseudomonas putida KT2440. *Appl Microbiol Biotechnol* 2009, 82:657–662.
- Escapa I, Morales V, Martino V, Pollet E, Avérous L, García J, Prieto M: Disruption of β-oxidation pathway in Pseudomonas putida KT2442 to produce new functionalized PHAs with thioester groups. *Appl Microbiol Biotechnol* 2011, 89:1583–1598.
- Poblete-Castro I, Becker J, Dohnt K, Dos Santos VM, Wittmann C: Industrial biotechnology of *Pseudomonas putida* and related species. *Appl Microbiol Biotechnol* 2012, 93:2279–2290.
- Muhr A, Rechberger EM, Salerno A, Reiterer A, Malli K, Strohmeier K, Schober S, Mittelbach M, Koller M: Novel description of mcl-PHA biosynthesis by pseudomonas chlororaphis from animal-derived waste. J Biotechnol 2013, 165:45–51.
- Kenny S, Runic J, Kaminsky W, Woods T, Babu R, O'Connor K: Development of a bioprocess to convert PET derived terephthalic acid and biodiesel derived glycerol to medium chain length polyhydroxyalkanoate. *Appl Microbiol Biotechnol* 2012, 95:623–633.
- Fu J, Sharma U, Sparling R, Cicek N, Levin DB: Evaluation of medium-chainlength polyhydroxyalkanoate production by Pseudomonas putida LS46 using biodiesel by-product streams. Can J Microbiol 2014, 60:461–468.
- Davis R, Kataria R, Cerrone F, Woods T, Kenny S, O'Donovan A, Guzik M, Shaikh H, Duane G, Gupta VK, Tuohy MG, Padamatti RB, Casey E, O'Connor KE: Conversion of grass biomass into fermentable sugars and its utilization for medium chain length polyhydroxyalkanoate (mcl-PHA) production by Pseudomonas strains. *Bioresour Technol* 2013, 150:202–209.
- Linger JG, Vardon DR, Guarnieri MT, Karp EM, Hunsinger GB, Franden MA, Johnson CW, Chupka G, Strathmann TJ, Pienkos PT, Beckham GT: Lignin valorization through integrated biological funneling and chemical catalysis. Proc Natl Acad Sci 2014, 111(33):12013–12018.
- 29. Almeida JR, Favaro LC, Quirino B: Biodiesel biorefinery: opportunities and challenges for microbial production of fuels and chemicals from glycerol waste. *Biotechnol Biofuels* 2012, 5:48.
- Timmis KN: Pseudomonas putida: a cosmopolitan opportunist par excellence. Environ Microbiol 2002, 4:779–781.

- Wang Q, Tappel RC, Zhu C, Nomura CT: Development of a new strategy for production of medium-chain-length polyhydroxyalkanoates by recombinant escherichia coli via inexpensive non-fatty acid feedstocks. *Appl Environ Microbiol* 2012, 78(2):519–527.
- Meijnen J-P, Verhoef S, Briedjlal A, de Winde J, Ruijssenaars H: Improved p-hydroxybenzoate production by engineered Pseudomonas putida S12 by using a mixed-substrate feeding strategy. *Appl Microbiol Biotechnol* 2011, 90:885–893.
- Escapa IF, del Cerro C, García JL, Prieto MA: The role of GlpR repressor in Pseudomonas putida KT2440 growth and PHA production from glycerol. Environ Microbiol 2013, 15:93–110.
- Follonier S, Panke S, Zinn M: A reduction in growth rate of Pseudomonas putida KT2442 counteracts productivity advances in medium-chainlength polyhydroxyalkanoate production from gluconate. *Microb Cell Fact* 2011, 10:25.
- De Eugenio LI, Escapa IF, Morales V, Dinjaski N, Galán B, García JL, Prieto MA: The turnover of medium-chain-length polyhydroxyalkanoates in Pseudomonas putida KT2442 and the fundamental role of PhaZ depolymerase for the metabolic balance. *Environ Microbiol* 2010, 12:207–221.
- Ren Q, de Roo G, Witholt B, Zinn M, Thony-Meyer L: Influence of growth stage on activities of polyhydroxyalkanoate (PHA) polymerase and PHA depolymerase in Pseudomonas putida U. *BMC Microbiol* 2010, 10:254.
- Solaiman DKY, Ashby RD, Foglia TA: Effect of inactivation of poly (hydroxyalkanoates) depolymerase gene on the properties of poly (hydroxyalkanoates) in Pseudomonas resinovorans. *Appl Microbiol Biotechnol* 2003, 62:536–543.
- Arias S, Bassas-Galia M, Molinari G, Timmis KN: Tight coupling of polymerization and depolymerization of polyhydroxyalkanoates ensures efficient management of carbon resources in Pseudomonas putida. *Microb Biotechnol* 2013, 6:551–563.
- Fujita Y, Matsuoka H, Hirooka K: Regulation of fatty acid metabolism in bacteria. *Mol Microbiol* 2007, 66:829–839.
- 40. Lee IY, Kim MK, Park YH, Lee SY: **Regulatory effects of cellular nicotinamide nucleotides and enzyme activities on poly(3-hydroxybutyrate) synthesis in recombinant Escherichia coli.** *Biotechnol Bioeng* 1996, **52**:707–712.
- Sánchez AM, Andrews J, Hussein I, Bennett GN, San K-Y: Effect of overexpression of a soluble pyridine nucleotide transhydrogenase (UdhA) on the production of poly(3-hydroxybutyrate) in Escherichia coli. *Biotechnol Prog* 2006, 22:420–425.
- Ochoa-Estopier A, Guillouet SE: D-stat culture for studying the metabolic shifts from oxidative metabolism to lipid accumulation and citric acid production in Yarrowia lipolytica. J Biotechnol 2014, 170:35–41.
- Papagianni M: Advances in citric acid fermentation by Aspergillus niger: biochemical aspects, membrane transport and modeling. *Biotechnol Adv* 2007, 25:244–263.
- 44. Kristiansen B, Sinclair CG: Production of citric acid in continuous culture. *Biotechnol Bioeng* 1979, 21:297–315.
- Anastassiadis S, Aivasidis A, Wandrey C: Citric acid production by Candida strains under intracellular nitrogen limitation. *Appl Microbiol Biotechnol* 2002, 60:81–87.
- Papanikolaou S, Aggelis G: Lipid production by Yarrowia lipolytica growing on industrial glycerol in a single-stage continuous culture. *Bioresour Technol* 2002, 82:43–49.
- Ratledge C, Wynn JP: The biochemistry and molecular biology of lipid accumulation in oleaginous microorganisms. In Adv Appl Microbiol. Volume Volume 51. Edited by Allen I. Laskin JWB and GMGBT-A in AM. Academic Press; 2002, 51:1–52.
- Daran-Lapujade P, Jansen MLA, Daran J-M, van Gulik W, de Winde JH, Pronk JT: Role of transcriptional regulation in controlling fluxes in central carbon metabolism of Saccharomyces cerevisiae: A CHEMOSTAT CULTURE STUDY. J Biol Chem 2004, 279(10):9125–9138.
- Canelas AB, van Gulik WM, Heijnen JJ: Determination of the cytosolic free NAD/NADH ratio in Saccharomyces cerevisiae under steady-state and highly dynamic conditions. *Biotechnol Bioeng* 2008, 100:734–743.
- Vemuri GN, Altman E, Sangurdekar DP, Khodursky AB, Eiteman MA: Overflow metabolism in Escherichia coli during steady-state growth: transcriptional regulation and effect of the redox ratio. *Appl Environ Microbiol* 2006, 72(5):3653–3661.

- Kamzolova S, Lunina J, Morgunov I: Biochemistry of citric acid production from rapeseed oil by Yarrowia lipolytica yeast. J Am Oil Chem Soc 2011, 88:1965–1976.
- Rymowicz W, Fatykhova A, Kamzolova S, Rywińska A, Morgunov I: Citric acid production from glycerol-containing waste of biodiesel industry by Yarrowia lipolytica in batch, repeated batch, and cell recycle regimes. *Appl Microbiol Biotechnol* 2010, 87:971–979.
- Lotfy WA, Ghanem KM, El-Helow ER: Citric acid production by a novel Aspergillus niger isolate: I. Mutagenesis and cost reduction studies. *Bioresour Technol* 2007, 98:3464–3469.
- Cullen D: The genome of an industrial workhorse. Nat Biotechnol 2007, 25:189–190.
- Bagdasarian M, Lurz R, Rückert B, Franklin FCH, Bagdasarian MM, Frey J, Timmis KN: Specific-purpose plasmid cloning vectors II. Broad host range, high copy number, RSF 1010-derived vectors, and a host-vector system for gene cloning in Pseudomonas. *Gene* 1981, 16:237–247.
- Hartmans S, Smits JP, van der Werf MJ, Volkering F, de Bont JAM: Metabolism of styrene oxide and 2-phenylethanol in the styrenedegrading xanthobacter strain 124X. *Appl Environ Microbiol* 1989, 55(11):2850–2855.
- 57. Martínez-García E, de Lorenzo V: Engineering multiple genomic deletions in Gram-negative bacteria: analysis of the multi-resistant antibiotic profile of Pseudomonas putida KT2440. *Environ Microbiol* 2011, **13**:2702–2716.
- Shevchuk NA, Bryksin AV, Nusinovich YA, Cabello FC, Sutherland M, Ladisch S: Construction of long DNA molecules using long PCR-based fusion of several fragments simultaneously. Nucleic Acids Res 2004, 32(2):e19–e19.
- De Lorenzo V, Timmis KN: [31] Analysis and construction of stable phenotypes in gram-negative bacteria with Tn5- and Tn10-derived minitransposons. In *Bact Pathog Part A Identif Regul Virulence Factors. Volume Volume 235*. Edited by Virginia L. Clark PMBBT-M in E. Academic Press; 1994:386–405.

Submit your next manuscript to BioMed Central and take full advantage of:

- Convenient online submission
- Thorough peer review
- No space constraints or color figure charges
- Immediate publication on acceptance
- Inclusion in PubMed, CAS, Scopus and Google Scholar
- Research which is freely available for redistribution

) BioMed Central

Submit your manuscript at www.biomedcentral.com/submit