



Liu, Y., Wang, J., Huang, Y., Zhang, R., Zhu, H. and Hou, L. (2019) High-Power AlGaInAs/InP DFB Lasers with Low Divergence Angle. In: CLEO/Europe-EQEC Conference (EQEC 2019), Munich, Germany, 23-27 Jun 2019, ISBN 9781728104706 (doi:[10.1109/CLEOE-EQEC.2019.8872502](https://doi.org/10.1109/CLEOE-EQEC.2019.8872502))

The material cannot be used for any other purpose without further permission of the publisher and is for private use only.

There may be differences between this version and the published version. You are advised to consult the publisher's version if you wish to cite from it.

<http://eprints.gla.ac.uk/182926/>

Deposited on 27 March 2019

Enlighten – Research publications by members of the University of
Glasgow

<http://eprints.gla.ac.uk>

High-Power AlGaInAs/InP DFB Lasers with Low Divergence Angle

Yihui Liu^{1,2}, Jiankun Wang^{1,2}, Yongguang Huang^{1,2*}, Ruikang Zhang^{1,2},
Hongliang Zhu^{1,2}, Lianping Hou^{3*}

1. Key Laboratory of Semiconductor Materials Science, Institute of Semiconductors, Chinese Academy of Sciences, Beijing 100083, China

2. Center of Materials Science and Optoelectronics Engineering, University of Chinese Academy of Sciences, Beijing 100049, China

3. School of Engineering, University of Glasgow, Glasgow, G12 8QQ, U.K

(Corresponding author: *yghuang@semi.ac.cn and *lianping.hou@glasgow.ac.uk.)

High-power semiconductor DFB lasers with low divergence angle fundamental transverse mode operating at wavelengths near 1.31 μm have many applications such as analog and digital fiber communication, WDM pump sources, spectroscopy, remote sensing, free-space communication, laser-based radar, and wavelength conversion in nonlinear materials [1]. These devices can potentially reduce system costs by simplifying optical alignment and package processes [2]. Devices with narrow far-field patterns (FFPs) are highly desirable for simple, high-yield optical alignment, as a low divergence angle improves the coupling efficiency and imposes less stringent tolerances in the alignment between the device and the single-mode fiber (SMF). Until now most of the high-power low divergence angle 1.31 μm DFB laser is based on InGaAsP/InP material system which has lower characteristic temperature value T_0 [3]. Here we first demonstrate the high-power fundamental transverse mode 1.31 μm AlGaInAs/InP DFB laser with low divergence angle, enabling uncooled continuous-wave (CW) operation at high ambient temperatures.

The MQW region contains three compressive strain InGaAlAs quantum wells and four tensile strained InGaAlAs barriers. There is a specially optimized far-field reduction layer (FRL) (1.15Q) located below the MQW active layer to pull the optical mode into the lower n-cladding layer which will increase the near field pattern size, reduce the internal loss of the waveguide and the optical confinement factor, thus to increase the saturation output power and increase the linearity of the output current-power (I-P) curve. The buried InGaAsP grating layer is positioned 160 nm above the MQW layer. The DFB laser is fabricated using a two-channel shallow etching ridge process with the ridge width of 2 μm . The device cavity length is 500 μm long with a $\lambda/4$ phase shift within the cavity. As a final step, the sample was cleaved into individual laser bars with one side facets anti-reflection (AR) coated (1%) and the other facets high-reflection (HR) coated (90%). All the measured results below are from the AR coated facet under cw operation from a single device.

Figure 1 is the I-P curve, optical spectra, horizontal and vertical FFP measured at the temperature of 25°C, 40°C, 75°C respectively. An output power of 110 mw @320 mA at 25°C with a slope efficiency of 0.37 mW/mA and a threshold current of 22 mA, and 60 mW @255mA at 75°C with a slope efficiency is 0.27 mW/mA and a threshold current of 31 mA were achieved (Fig.1(a)). The center wavelength is 1312.02 nm, 1313.26nm, 1316.24 nm at 25°C, 40°C, 75°C temperature respectively with a DFB injection current of 170 mA. The change rate of wavelength with temperature is of 0.08 nm/°C. In all cases, the sidemode suppression ratio (SMSR) is more than 50 dB (Fig.1(b)). At the injection current of 170 mA, the FFP divergence angle is 14°×21°@40°C and 15.5°×23°@75°C (Fig.1(c), (d)). Compared with the conventional DFB lasers, the vertical divergence is reduced more than 10° which is highly desirable when coupling with a single-mode fiber.

In conclusion, a high-power 1.31 μm AlGaInAs/InP DFB laser with a fundamental transverse mode and low divergence angle has been successfully demonstrated. The threshold current is as small as 22 mA. The highest power is more than 110 mW with a slope efficiency of 0.37 mW/mA. The FFP is 14°×21°@40°C and 15.5°×23°@75°C.




Fig. 1 (a) Measured I-P curve, (b) optical spectra, (c) vertical, and (d) horizontal FFP at 25°C, 40°C, 75°C temperature.

This work was supported by the National Natural Science Foundation of China under Grant 61574137 and Grant 61320106013.

References

- [1] S. R. Selmic, G. A. Evans, T. M. Chou, J. B. Kirk, J. N. Walpole, J. P. Donnelly, C. T. Harris, and L. J. Missaggia, "Single frequency 1550-nm AlGaInAs-InP tapered high-power laser with a distributed Bragg reflector," *IEEE Photon. Technol. Lett.* **14**, 890 (2002).
- [2] J. Darja, M. J. Chan, M. Sujiyama, and Y. Nakano, "Four channel DFB laser array with integrated combiner for 1.55 μm CWDM systems by MOVPE selective area growth," *IEICE Electron. Express* **3**, 522 (2006).
- [3] J. Pipek, J. K. White, and A. J. SpringThorpe, "What limits the maximum output power of long-wavelength AlGaInAs/InP laser diodes?," *IEEE Journal Of Quantum Electronics* **38**, 1253-1259 (2002).