



ELSEVIER

Available online at www.sciencedirect.com

Optical Materials 22 (2003) 147–154

www.elsevier.com/locate/optmat

Beneficial effect of Lu^{3+} and Yb^{3+} ions in UV laser materials

M. Laroche ^a, S. Girard ^a, R. Moncorgé ^{a,*}, M. Bettinelli ^b,
R. Abdulsabirov ^c, V. Semashko ^c

^a Centre Interdisciplinaire de Recherche Ions Laser, UMR 6637, CNRS-CEA-ISMRA, Université de Caen,
43 Boulevard Marechal Juin, 14050 Caen Cedex, France

^b Dipartimento Scientifico e Tecnologico, Università di Verona and INSTM, UdR Verona, 37134 Verona, Italy

^c Kazan State University, Kremlevskaya Street, 480008 Kazan, Russia

Abstract

Several Lu^{3+} - and Y^{3+} -based oxide and fluoride single crystals with isomorphic structures and doped with Ce^{3+} (or Pr^{3+}) or codoped with Yb^{3+} ions have been grown and studied to show the beneficial effects of the Lu^{3+} and Yb^{3+} ions on their broad-band UV luminescence properties. Time-resolved color center absorption measurements clearly show the reduction of the usually observed UV laser pump-induced optical losses and thus confirm the previous gain and laser results obtained in these materials. Some preliminary interpretations of the involved mechanisms are advanced.

© 2002 Elsevier Science B.V. All rights reserved.

1. Introduction

Most of the Ce^{3+} or Pr^{3+} doped materials known for their broad-band 5d–4f UV emissions and which have been investigated in the past for their potentials as tunable solid-state laser media suffer from photochromic (solarization) effects, when they are pumped in the near UV spectral domain, which usually limit their laser performance or even hinder any laser action [1,2]. However, several recent works involving materials with Lu^{3+} instead of Y^{3+} or codoped with Yb^{3+} ions showed reduced solarization effects and improved laser performance [3–7].

The present paper thus gives the state of the art in this field of research and some preliminary interpretations of the beneficial effects of these Lu^{3+} and Yb^{3+} ions. Crystal characteristics are gathered in Section 2. Transient absorption measurement conditions are described in Section 3. Section 4 gives a comparison of the results obtained in the Lu^{3+} - and Y^{3+} -based materials. Finally, Section 5 presents the results obtained in Ce^{3+} doped crystals codoped with Yb^{3+} ions.

2. Crystal growth and sample characteristics

In order to verify the beneficial effect of Lu^{3+} , two families of single crystals—namely $\text{LiY}(\text{Lu})\text{F}_4$ and $\text{Y}(\text{Lu})\text{PO}_4$ —were synthesised. These materials were selected for their perfect isomorphisms and because they have already demonstrated interesting and encouraging properties for a laser emission

* Corresponding author. Tel.: +33-2-31-45-25-58; fax: +33-2-31-45-25-57.

E-mail address: moncorgé@spalp255.ismra.fr (R. Moncorgé).