

Applied Magnetic Resonance 1996 vol.11 N3-4, pages 493-498

Electron spin-lattice relaxation of Yb³⁺ and Gd³⁺ ions in glasses

Vergnoux D., Zinsou P., Zaripov M., Ablart G., Pescia J., Misra S., Rakhmatullin R., Orlinskii S.
Kazan Federal University, 420008, Kremlevskaya 18, Kazan, Russia

Abstract

The electron spin-lattice relaxation rate (T_1^{-1}) was measured in two glass samples: (i) a phosphate glass doped with 1 wt% Yb₂O₃ and (ii) a Li₂Si₄O₉ glass sample doped with 0.2 wt% Gd₂O₃. In the Yb³⁺-doped glass sample, T_1 was measured by an electron-spin-echo technique from 4.2 to 6 K, by the modulation method from 10 to 26 K and by the EPR linewidth from 30 to 100 K. It was found that $(T_1^{-1}) \propto T^n$ with $n = 9$ in the range 4.2-6 K. n decreased gradually as the temperature was increased and tended towards 2 above 40 K. Over the entire temperature range 4.2-100 K, (T_1^{-1}) was fitted to $AT + BT^9J_8(\Theta_D/T)$ (where A and B are two temperature-independent constants, J_8 is the well-known Van Vleck integral and Θ_D is the Debye temperature). The value of $\Theta_D (= 46.3 \pm 0.9$ K) so determined is in good agreement with that of Stevens and Stapleton from their T_1 measurements in the range 1.5 to 7 K. In the Gd³⁺-doped glass, it was observed that $(T_1^{-1}) \propto T$ over the range 50-150 K. The data for Yb³⁺-doped glass sample were accounted for by assuming that the phonon modulation of the ligand field is the dominant mechanism, associated with a low Debye temperature in accordance with the published data obtained by using other techniques to study lattice dynamics. On the other hand, the data on the Gd³⁺-doped glass sample were explained to be predominantly due to a mechanism involving Two-Level-Systems (TLS). © Springer-Verlag 1996 Printed in Austria.
