

Available online at www.sciencedirect.com

SCIENCE DIRECT.



Journal of Luminescence 117 (2006) 225-232

www.elsevier.com/locate/jlumin

The nonlinear Zeeman and parastriction effects in luminescence spectra of $\text{LiY}_{1-x}\text{Tm}_x\text{F}_4$ (0.02 $\leq x \leq 1$) crystals

R.Yu. Abdulsabirov, A.A. Kazantsev, S.L. Korableva, B.Z. Malkin*, S.I. Nikitin, A.L. Stolov

Kazan State University, Kremlevskaya Str. 18, Kazan 420008, Russian Federation

Received 19 December 2004 Available online 21 July 2005

Abstract

Splitting of the first excited $\Gamma_{34}^1({}^{3}H_6)$ doublet state of Tm^{3+} ions in the LiY_{1-x}Tm_xF₄ crystals in external magnetic fields up to 5.5 T has been studied using measurements of luminescence spectra at low temperatures. In the magnetic field perpendicular to the S₄-symmetry axis of the crystal lattice, the splitting of the non-Kramers doublet is caused by the joint action of the nonlinear Zeeman effect and the piezospectroscopic effect related to parastriction. Experimental dependences of the doublet splitting on the magnetic field strength and direction are in good correspondence with the theoretical estimations obtained in the framework of the semiphenomenological crystal field model. It is shown that spectroscopic data present direct information on the forced magnetostriction in the basal plane of uniaxial Van Vleck paramagnets that contain non-Kramers rare earth ions. The measured concentration dependence of the doublet splitting into account variations of the elastic constants with the concentration of Tm³⁺ ions. © 2005 Elsevier B.V. All rights reserved.

PACS: 75.80.+q; 78.55.Hx; 63.20.Kr

Keywords: Van Vleck paramagnets; Parastriction; Electron-lattice interaction; Crystal field; LiYF4; LiTmF4

1. Introduction

The magnetoelastic properties of lithiumlanthanide double fluorides LiRF_4 have been systematically studied both experimentally and theoretically from the late 1970s [1–3]. The titled

*Corresponding author. Tel.: +78432315342.

E-mail address: Boris.Malkin@ksu.ru (B.Z. Malkin).

crystals have a scheelite (CaWO₄) structure with the space group C_{4h}^6 ; the unit cell contains two magnetically equivalent lanthanide R³⁺ ions at sites with the S₄ point symmetry. Giant lowtemperature forced magnetostriction (parastriction) in the Van Vleck paramagnet LiTmF₄ was discovered by Altshuler et al. [4]. Lattice strains achieve values of ~10⁻³ in magnetic fields of 2–4 T perpendicular to the crystal symmetry axis. The

^{0022-2313/\$ -} see front matter \odot 2005 Elsevier B.V. All rights reserved. doi:10.1016/j.jlumin.2005.06.002