


Commun Nonlinear Sci Numer Simulat 16 (2011) 4643–4648

Contents lists available at [ScienceDirect](http://www.sciencedirect.com)

## Commun Nonlinear Sci Numer Simulat

journal homepage: [www.elsevier.com/locate/cnsns](http://www.elsevier.com/locate/cnsns)

### New approach for consideration of adsorption/desorption data

Mihaela-Cristina Băleanu<sup>a,b</sup>, Raoul R. Nigmatullin<sup>c,\*</sup>, Salih Okur<sup>d</sup>, Kasim Ocakoglu<sup>e</sup><sup>a</sup> Faculty of Physics, University of Bucharest, P.O. Box MG-7, Măgurele 077125, Romania<sup>b</sup> Mihail Sadoveanu Theoretical High School, District 2, Bucharest 021586, Romania<sup>c</sup> Kazan (Volga Region) Federal University, Kazan 420008, Tatarstan, Russia<sup>d</sup> Izmir Institute of Technology, Faculty of Science, Izmir TR-35430, Turkey<sup>e</sup> Advanced Technologies Research & Application Center, Mersin University, TR-33343 Yenisehir, Mersin, Turkey

#### ARTICLE INFO

##### Article history:

Available online 17 March 2011

##### Keywords:

QCM  
Langmuir model  
Eigen-Coordinates  
Adsorption  
Desorption  
Ruthenium polypridyl complex

#### ABSTRACT

In this paper we proposed a new approach to modify the Langmuir model by considering nonlinear effects such as diffusion of water molecules in/out of an adsorbing film for humidity adsorption and desorption kinetics. The model was tested on the humidity adsorption and desorption data of a spin coated 50 nm thick Ruthenium polypridyl complex (Ru-PC K314) film, measured under relative humidity between 11% and 97% using by Quartz Crystal Microbalance (QCM) technique.

© 2011 Elsevier B.V. All rights reserved.

#### 1. Introduction

Quartz Crystal Microbalance (QCM) has been frequently used to investigate the kinetics of adsorption/desorption of adsorbate molecules [1,2] for monolayer films. It is a powerful technique to determine humidity sensing properties of materials before designing a sensor device during development stages. It is well known that the Langmuir model has been used successfully for monolayer films to analyze adsorption kinetics. A novel ceramic nanowires of TiO<sub>2</sub> and poly (2-acrylamido-2-methylpropane sulfonate) composite material films coated QCM was prepared as a low humidity sensor [3].

In the literature, the swelling behaviour of a series of hydrophilic random copolymer coatings in controlled humidity environments and in water has been investigated using QCM and spectroscopic ellipsometry by Chen et al. [4]. Thin films of polyaniline base, emeraldine base (EB), coating on the quartz crystal microbalance (QCM) electrode have been used as a sensitive layer for the detection of a number of primary aliphatic alcohols such as ethanol, methanol, 2-propanol and 1-propanol vapours [5]. A QCM coated with Nafion<sup>®</sup> film recast from Nafion<sup>®</sup>(Ag) complex solution has been used to investigate the interaction between methanol, water and Nafion<sup>®</sup>(Ag) and to determine simultaneously the concentration of methanol and water (relative humidity) [6].

In this work, we suggest a generalized Langmuir model to include nonlinear effect such as diffusion and condensation during humidity adsorption/desorption process. The suggested model was used to analyze the humidity adsorption and desorption QCM data of spin coated 50 nm Ruthenium polypridyl complex (Ru-PC K314) obtained under relative humidity between 11 % and 97 %.

\* Corresponding author.

E-mail addresses: [cris\\_balance@yahoo.com](mailto:cris_balance@yahoo.com) (M.-C. Băleanu), [nigmat@knet.ru](mailto:nigmat@knet.ru) (R.R. Nigmatullin), [salihokuru@iyte.edu.tr](mailto:salihokuru@iyte.edu.tr) (S. Okur), [kasim.ocakoglu@mersin.edu.tr](mailto:kasim.ocakoglu@mersin.edu.tr) (K. Ocakoglu).