



You have downloaded a document from
RE-BUŚ
repository of the University of Silesia in Katowice

Title: Influence of temperature on critical fields in ZnxSbyCrzSe4

Author: Ewa Malicka, Tadeusz Groń, Henryk Duda, A. W. Pacyna, Józef Krok-Kowalski

Citation style: Malicka Ewa, Groń Tadeusz, Duda Henryk, Pacyna A. W., Krok-Kowalski Józef. (2009). Influence of temperature on critical fields in ZnxSbyCrzSe4 . "Acta Physica Polonica A" (Vol. 116, nr 5 (2009), s. 964-966).



Uznanie autorstwa - Użycie niekomercyjne - Bez utworów zależnych Polska - Licencja ta zezwala na rozpowszechnianie, przedstawianie i wykonywanie utworu jedynie w celach niekomercyjnych oraz pod warunkiem zachowania go w oryginalnej postaci (nie tworzenia utworów zależnych).



Influence of Temperature on Critical Fields in $\text{Zn}_x\text{Sb}_y\text{Cr}_z\text{Se}_4$

E. MALICKA^a, T. GROŃ^b, H. DUDA^b, A.W. PACYNA^c AND J. KROK-KOWALSKI^b

^aInstitute of Chemistry, University of Silesia, Szkolna 9, 40-006 Katowice, Poland

^bInstitute of Physics, University of Silesia, Uniwersytecka 4, 40-007 Katowice, Poland

^cThe Henryk Niewodniczański Institute of Nuclear Physics, Polish Academy of Sciences

E. Radzikowskiego 152, 31-342 Kraków, Poland

The electrical and complex ac dynamic magnetic susceptibility measurements were used to study an influence of temperature on critical fields in single-crystalline $\text{Zn}_x\text{Sb}_y\text{Cr}_z\text{Se}_4$ spinel system with $y = 0.11, 0.16$ and 0.20 . The p -type conduction and a shift both of the Néel temperature T_N to lower temperatures and a susceptibility peak at T_m in the paramagnetic region — to higher temperatures were established. Below T_N the magnetic field dependence of susceptibility, $\chi_{ac}(H)$, shows two peaks. First peak at the critical field H_{c1} slightly decreases with temperature and remains almost constant as Sb content increases. Second peak at the critical field H_{c2} drops rapidly with temperature and remains almost unchanged as Sb content increases. At T_N both critical fields disappear.

PACS numbers: 75.50.Pp, 75.30.Kz, 75.30.Et

1. Introduction

Previous structural and magnetic investigations carried out on the ZnCr_2Se_4 spinel doped with the Sb ions up to 0.2 located in tetrahedral sites of the spinel structure revealed the antiferromagnetic order with the Néel temperature $T_N = 22$ K and the strong short-range ferromagnetic exchange evidenced by the large and positive value of the Curie–Weiss temperature $\theta_{CW} = 106$ K [1]. The magnetic moment taken from experiment is quite close to the spin-only value for Cr^{3+} . Chemical composition of the $\text{Zn}_x\text{Sb}_y\text{Cr}_z\text{Se}_4$ single crystals was determined by the non-destructive energy-dispersive X-ray fluorescence spectrometry showing a slight non-stoichiometry in the octahedral sites [1]. The structure refinement performed by the SHELXL-97 program package revealed that all single crystals under study have cubic structure with the space group $Fd\bar{3}m$ (No. 227). The Cr and ions occupy the octahedral 16e sites, while the Zn and Sb ions are in the tetrahedral 4a positions [1]. The structural and magnetic parameters are displayed in Table I.

2. Experimental details

The ac susceptibility χ_{ac} vs. external magnetic field up to 60 kOe was measured at 4.3, 8, 12, 18, 21.2 and 22.8 K at internal oscillating magnetic field $H_{ac} = 1$ Oe with internal frequency $f = 120$ Hz using a Lake Shore 7225 ac susceptometer. The χ_{ac} vs. temperature was recorded at $H_{ac} = 1$ Oe with $f = 120$ Hz for external magnetic fields $H = 0, 5, 12.5, 25, 40$ and 50 kOe.

TABLE I

Structural and magnetic parameters of $\text{Zn}_x\text{Sb}_y\text{Cr}_z\text{Se}_4$. a and u are the lattice and anion positional parameters, R_1 and wR_2 — criteria of fit, T_N is the Néel temperature, θ_{CW} is the Curie–Weiss temperature, μ_{eff} and μ_s are the effective and saturation magnetic moments, respectively [1].

x	0.89	0.84	0.80
y	0.11	0.16	0.20
z	1.97	1.95	1.92
a [pm]	1049.8(1)	1051.(1)	1052.6(1)
u	0.25913(2)	0.25925(3)	0.25936(3)
R_1	0.019	0.022	0.019
wR_2	0.040	0.043	0.038
T_N [K]	22.0(4)	21.7(2)	21.8(3)
θ_{CW} [K]	108(1)	106(1)	103(1)
μ_s [μ_B/Cr^{3+}]	2.90(2)	2.83(2)	2.64(3)
μ_{eff} [μ_B/Cr^{3+}]	3.81(2)	3.81(3)	3.84(2)

The electrical measurements have been done in the temperature range 270–500 K and in the $\langle 001 \rangle$ direction. The electrical conductivity $\sigma(T)$ has been measured with the aid of the 4-point dc method. The maximal error $\delta\sigma/\sigma$ was less than $\pm 1\%$. The thermopower $S(T)$ was measured with a differential method using the temperature gradient ΔT of about 2 K. The accuracy of $S(T)$ was better than $3 \mu\text{V}/\text{K}$.

3. Results and discussion

The electrical results presented in Figs. 1 and 2 show the thermally activated p -type $\text{Zn}_x\text{Sb}_y\text{Cr}_z\text{Se}_4$ semiconductors of the Arrhenius type. A general decrease of thermopower below 400 K as well as an increase of the p -type electrical conductivity as the Sb content y increases seem to be connected both with a hole transport in the lowest $\text{Cr}^{3+}t_{2g}^2e_g^0$ band and an activation of the holes in the valence band to the acceptor energy levels. The nature of acceptor levels can be related to the Cr vacancies, occupying the octahedral sites, because a slight increase of non-stoichiometry as the Sb content y increases is observed (see Table I).




Fig. 1. The electrical conductivity ($\ln \sigma$) vs. reciprocal temperature T^{-1} for single crystals with $y = 0.11, 0.16,$ and 0.20 of the $\text{Zn}_x\text{Sb}_y\text{Cr}_z\text{Se}_4$ spinel system.




Fig. 2. The thermoelectric power S vs. temperature T for single crystals with $y = 0.11, 0.16,$ and 0.20 of the $\text{Zn}_x\text{Sb}_y\text{Cr}_z\text{Se}_4$ spinel system.

The magnetic results depicted in Figs. 3 and 4 and in Table II show the strong long-range antiferromagnetic and short-range ferromagnetic interactions evidenced by a shift of T_N to lower temperatures and a susceptibility




Fig. 3. In phase χ' and out of phase χ'' components of fundamental susceptibility vs. temperature T for the $\text{Zn}_{0.89}\text{Sb}_{0.11}\text{Cr}_{1.97}\text{Se}_4$ spinel recorded at $H_{ac} = 1$ Oe with $f = 120$ Hz for external magnetic fields $H = 0, 5,$ $12.5, 25, 40$ and 50 kOe. The Néel T_N and T_m temperatures are indicated by arrows.




Fig. 4. Ac mass susceptibility χ_{ac} vs. external magnetic field H for $\text{Zn}_{0.89}\text{Sb}_{0.11}\text{Cr}_{1.97}\text{Se}_4$ recorded at internal oscillating magnetic field $H_{ac} = 1$ Oe with internal frequency $f = 120$ Hz for $T = 4.3, 8, 12, 18, 21.2$ and 22.8 K. The critical fields H_{c1} and H_{c2} are indicated by arrows.

peak at T_m in the paramagnetic region — to higher temperatures as a magnetic field increases, respectively. The $\chi_{ac}(H)$ dependence reveals two peaks below T_N . First at the critical field H_{c1} , connected with a metamagnetic transition and the breakdown of the helical spin structure [2, 3], which slightly decreases with temperature. Second at the critical field H_{c2} , connected with the breakdown of the conical spin structure [3], which drops strongly

TABLE II
Critical fields H_{c1} and H_{c2} at 4.3, 8, 12, 18, 21.2 and 22.8 K of the $Zn_xSb_yCr_zSe_4$ single crystals for $y = 0.11$, 0.16 and 0.20.

Critical fields	Sb content y		
	0.11	0.16	0.20
$T = 4.3$ K			
H_{c1} [kOe]	12	13	12
H_{c2} [kOe]	55	57.5	55
$T = 8$ K			
H_{c1} [kOe]	12	13	11.5
H_{c2} [kOe]	50	50	45
$T = 12$ K			
H_{c1} [kOe]	12	12.5	11
H_{c2} [kOe]	40	40	40
$T = 18$ K			
H_{c1} [kOe]	11.5	12	12
H_{c2} [kOe]	25	30	25
$T = 21.2$ K			
H_{c1} [kOe]	7.5	11	8
H_{c2} [kOe]	0	0	0
$T = 22.8$ K			
H_{c1} [kOe]	0	0	0
H_{c2} [kOe]	0	0	0

with temperature. The H_{c2} is mainly responsible for a spin frustration of the re-entrant type confirmed by the experimentally observed splitting of the zero-field-cooled and field-cooled susceptibilities [1]. Both critical fields do not significantly depend on Sb content in a sample and they disappear at T_N . The non-zero values of out of phase component of susceptibility at T_N visible in Fig. 3 seem to be associated with an energy loss connected only with the spin re-arrangement and strong long-range interactions.

Acknowledgments

This work is funded from science resources for years 2007–2009 as a research project No. N N204 178433.

References

- [1] E. Malicka, A. Wařkowska, J. Heimann, T. Mydlarz, R. Sitko, D. Kaczorowski, *J. Solid State Chem.* **181**, 1970 (2008).
- [2] R. Kleinberger, R. de Kouchkovsky, *C.R. Acad. Sci. Paris Ser. B* **262**, 628 (1966).
- [3] J. Hemberger, H.-A. Krug von Nidda, V. Tsurkan, A. Loidl, *Phys. Rev. Lett.* **98**, 147203 (2007).