

## Durability of thermally modified *Pinus banksiana* (Jack pine) wood against brown and white rot fungi

LEKOUNOUGOU, S., KOCAEFE, D.\*

Department of Applied Sciences, University of Quebec at Chicoutimi,

555 Blvd. de l'Université, Chicoutimi, G7H2B1, QC, Canada.

\* Corresponding author: Kocaefe D: [duygu\\_kocaefe@uqac.ca](mailto:duygu_kocaefe@uqac.ca)

Tel: (+1) 418-545 5011 ext 5215 Fax: (+1) 418- 545 5012

### Abstract

The resistance of thermally modified Canadian *Pinus banksiana* against four wood decaying fungi was evaluated. Wood samples were treated at different temperatures (190°C, 200°C and 210°C) and exposed to three brown rot fungi as well as to a white rot fungus. Results showed that the untreated wood samples lost more weight when exposed to *P. placenta*, *T. versicolor* and *G. trabeum* compared to the weight loss observed in case of *C. puteana*. Thermal modification at 210°C improved the resistance of *Pinus banksiana* against *G. trabeum* and *T. versicolor* fungi as evident from the fact that reduction in weight loss of wood was found to be 98.3% and 96.3%, respectively.

**Keywords:** Decay resistance, *Pinus banksiana*, Brown rot fungi, White rot fungus, Thermal modification, Wood degradation.

## **Introduction**

Biological degradation including attack by fungi, termites and marine borers is the main cause of deterioration of lignocellulosic materials such as *Pinus banksiana lamb.* Among these biodeteriorations, fungi cause the greatest financial losses of wood materials (Bowyer et al., 2003; Goodell 2003). The wood decay fungi can be classified as decay fungi brown rot, white rot and soft rot fungi. Wood decay fungi secrete various enzymes including cellulase, hemicellulase, lignin peroxidases, manganese-dependent peroxidases and laccase, to depolymerise cellulose, hemicelluloses and lignin (Suziki et al., 2006; Yelle et al., 2008).

The environmental awareness in some European and American countries resulted in elimination of some preservatives containing inorganic metals in several areas (Preston 2000). The U.S Environmental Protection Agency (EPA) banned the use of wood treated with copper-chrome-arsenic (CCA) for residential purposes in 2003. Alternative products such as wood-plastic composites (WPC), chemically modified wood, and thermally modified wood grew rapidly (Baysal and Yalinkilic 2005, Kartal et al., 2006, Chang and Chang 2006, Clausen and Yang 2007, Boonstra et al., 2007, Lekounougou et al., 2008). Thermal modification is an eco-friendly technology which can improve the wood durability. This technology is non-toxic and does not require the use of chemicals. The utilization of thermal modification and the production of thermally modified wood have increased considerably during the last decade (Hill 2006, Bächle et al., 2010, Khalid et al., 2010). Thermal modification of wood at temperature from 160 °C to 230 °C leads to the degradation of hemicelluloses and lignin (Kocaeffe et al., 2008a). This process

modifies the chemical composition of the wood and reduces its hygroscopicity. Thus, the thermally modified wood tends to be dimensionally more stable than the untreated wood of the same species (Hill 2006, Shi et al., 2007, Korkut 2012). The thermal modification brings new business opportunities for many species of hardwoods and softwood such as *P. banksiana*. The market value of a species can be increased by treatment with improved dimensional stability, appearance and durability (value-added product).


The decrease in hygroscopicity, improvement of dimensional stability and loss of mechanical properties of wood treated at high temperature have been studied by several authors (Militz 2002; Weiland and Guyonnet 2003; Kocaefe et al. 2008b; Gunduz and Aydemir 2009; Calenego et al. 2010; Tumen et al. 2010; Xianjun et al. 2011; Lekounougou et al. 2011). Numerous investigations have been conducted on the resistance against fungal decay using laboratory tests (Hakkou et al., 2006, Boonstra et al., 2007, Lekounougou et al. 2008). However, the fungal resistance of thermally modified *P. banksiana* has not been studied in detail.

In this study, *P. banksiana* was thermally modified at different temperature using the Perdure technology in the prototype furnace of University of Quebec at Chicoutimi (UQAC). The aim of this study was to assess the efficacy of thermal modification temperature on the biological resistance of this species against the brown and white rot basidiomycete fungi. The molecular reasons behind the improvement of the resistance of thermally modified wood against fungal attack were studied.

## Materials and Methods

### Experimental Design and statistical analysis

Figure 1 shows durability tests performed on *P. banksiana* samples exposed to four decay fungi during 12 weeks incubation.



**Fig. 1** Tests diagram performed in this study

Diagram shows the thermally modified and unmodified wood degradation at different temperatures (190°C, 200°C et 210°C) by decay fungi *T. versicolor*, *P. placenta*, *G. trabeum* et *C. puteana*. The prototype furnace of University of Quebec at Chicoutimi (UQAC) was used for testing thermal modification of wood. 36 wood samples were

removed every two weeks incubation for each fungus and each treatment condition. 216 wood samples were taken and thus involved in the statistical results for each fungus used in this study. The standard deviations data were showed in Table 1

### **Thermal modification of *P. banksiana***

#### **Wood Samples**

*P. banksiana* boards were sawed in a local sawmill at Saguenay-Lac-St-Jean (Quebec, Canada). 35 boards were dried in the air. The final moisture boards were about 15-17% after drying. Then, they were thermally modified. Wood samples required for fungal tests were prepared as described in the diagram (Fig 1). Sapwood boards were used for this test.

#### **Thermal modification process**

The prototype furnace of University of Quebec at Chicoutimi (UQAC) was used for testing thermal modification of *P. banksiana*. Dimensions of boards were 0.015 x 0.045 x 2.44 m in the radial, tangential and longitudinal directions respectively. In this furnace, propane was used as fuel gas and wood was thermally modified in a non-oxidizing environment composed of hot combustion gas (CO<sub>2</sub> and H<sub>2</sub>O). The wood samples were treated at different temperatures (190 °C, 200 °C and 210 °C) at heating rate of 15 °C hr<sup>-1</sup> and humidity of the gas was 100 g of water/m<sup>3</sup> of dry gas. Samples were treated according to the method proposed by Poncsák et al. (2006).

## **Durability tests**

### **Wood Samples preparation**

*Pinus banksiana* specie was subjected to four decay fungi during this study. 216 thermally-modified and untreated wood samples with dimensions of 0.015 x 0.005 x 0.035 m in the radial, tangential and longitudinal, respectively, were cut per fungus. Wood samples were conditioned in a furnace at 103 °C for 48 hours (Mburu et al. 2007; Lekounougou et al. 2009) until they reach a constant weight and this weight was recorded as initial weight (WI) of the wood samples. A modified version of ASTM D-2017 standard was followed during the experiment. This standard is similar to the EN-113 (1986) standard, except the size of the wood samples that has been reduced as described by Lekounougou et al. (2009) and Bami and Mohebby (2011), to accelerate fungal decay and reduce testing time from 16 to 12 weeks.

### **Preparation of biological decay tests, fungi inoculation and incubation**

Three species of brown rot fungi, *Poria placenta* (Frees) Cooke (FTK120E), *Gloeophyllum trabeum* (Pers: Fr) Murrill (FTK45D) and *Coniophora puteana* (Frees) Karten (FTK9B) and a white-rot fungus *Trametes versicolor* (FTK105D) were used in this study. These fungi were obtained from stock culture provided by FPInnovation Forintek, Quebec, Canada. The re-isolation was performed on Petri dishes and they were incubated for two weeks before inoculation.

Malt agar substrate was used as a nutrient medium for the cultivation of fungi in Petri dishes. It was prepared by mixing 30 g agar and 40 g of malt extract dissolved in 1L of

distilled water. The medium was sterilized for 35 minutes at 121 °C (105 KPa). 30 ml of medium was poured into sterile Petri dishes for inoculation.

A disc of 5 mm of fungus was cut from the mother culture with the scalpel and placed in Petri dish for inoculation. It was then incubated at a temperature of 22 °C ± 1 °C and relative humidity (RH) of 70% ± 4% for two weeks or until the samples were completely covered by the mycelium. Every 2 weeks (this time interval was chosen to follow the progressive degradation of wood samples over time), 36 thermally-modified and untreated wood samples were taken out and the mycelium was scraped carefully with the help of scalpel. Finally, the wood samples were conditioned in a furnace at 103 °C until their weight remained constant. This weight was recorded as the final weight (WF). Three sets of both thermally modified and untreated wood samples were placed in different Petri dishes and exposed to fungi as explained above. Each experiment was performed three times to ensure that the reproducibility of results. The percentage of weight loss was calculated as follows:

$$(1) \text{ Weight loss (\%)} = (WI - WF / WI) \times 100$$

Where:

WI = initial weigh

WF = final weigh

The percentage of weight loss of wood sample was used to measure the relative susceptibility to decay, or to contrast, resistance to decay of thermally-modified wood.

The moisture content (MC, %) wood samples was determined after fungal decay using the following formula:

$$(2) \text{ MC (\%)} = (W_C - W_D / W_D) \times 100$$

Where:

$W_C$  = wet weight after fungal attack (g)

$W_D$  = dry weight after fungal attack (g).

## Results

The weight loss due to fungal degradation at different times of incubation is shown in Figure 2. This figure shows that the weight loss caused by *G. trabeum*, *T. versicolor* and *P. placenta* fungi increased gradually every two weeks up to 12 weeks of incubation. At the beginning of the colonization process, the weight loss was relatively low (2, 4, and 6 weeks), however, it increased noticeably starting from 8 weeks of colonization. In the case of *C. puteana* fungus, the evolution of degradation was different at the beginning of the colonization (Figure 2). The weight loss trend was the same as that observed with other fungi used in this test between 2 and 4 weeks. Thereafter, the weight loss remained constant (4 and 8 weeks), followed by a slight increase towards the end of the colonization process (weeks 10 and 12). *P. placenta*, *T. versicolor* and *G. trabeum* fungi were the most virulent with weight losses of 52.3%, 43.5% and 41.5%, respectively, after 12 weeks of incubation (Table 1). *C. puteana* fungus was less effective resulting in lower weight loss of 14.9% compared to other fungi. By contrast, tests conducted by Rowell et al. (2009) showed the virulence of *C. puteana* against the attack of *P. sylvestris* with a weight loss of 47.5% and *Douglas fir* with a weight loss of 27.4%.



According to durability criteria proposed by Van Acker et al. (2003), if the weight loss is between 15% and 30%, the species are defined as slightly durable (class 4), and if the weight loss is more than 30% , the species are defined as non durable (class 5). Thus, weight loss data in Table 1 and Figure 2 showed that the Canadian wood *P. banksiana* can be considered as non-durable against *P. placenta*, *T. versicolor* and *G. trabeum* fungi, but durable against the attack of *C. puteana* for the same period of incubation (12 weeks).

Figure 3 shows the effect of the maximum thermal modification temperature on the resistance of *P. banksiana* against fungal decay attack after 12 weeks of incubation. The results indicated an improvement in the resistance of thermally-modified *P. banksiana* wood against fungal attack. In the case of *T. versicolor* and *G. trabeum* fungi, the results showed that the weight loss decreases with increasing thermal modification temperature (Figure 3 and Table 1), consequently, the resistance against these two decay fungi improves. Weight losses of thermally-modified wood obtained at 210 °C were 1.5% and 0.7% for *T. versicolor* and *G. trabeum* fungi, respectively (Table 1), which were lower than that of untreated wood. Weight losses of control (untreated wood) were 43.5% and 41.53% for the above fungi indicating a percentage reduction of 96.5% and 98.3 %, respectively, in the weight loss due to thermal modification (Table 1). With this weight loss percentage, thermally-modified *P. banksiana* becomes resistant to *T. versicolor* and *G. trabeum* according to the classification of Van Acker (2003). Untreated *P. banksiana* was already resistant to *C. puteana* fungus. As seen with a slight weight loss (14.9%) observed when it was exposed to the fungus before thermal modification. However, with the thermal modification, the weight loss was completely eliminated.

In the case of *P. placenta* fungus, the thermal modification temperature had a limited effect. Indeed, there was a slight decrease in the weight loss of wood treated at different temperatures compared to control (52.3%), however, this decrease was not sufficient. Because the weight loss obtained at the highest temperature (210 °C) was 39.1%, with a smaller percentage reduction of 25.2% (Table 1) compared to the other fungi studied.

## **Discussion**

The data of this study indicated that thermal modification improved resistance of wood against decay fungi (Figure 3 and Table 1). These results are in agreement with previous studies on a number of other decay fungi and wood systems (Boonstra et al. 2006; Calenego et al. 2010; Juanito et al. 2011; Lekounougou and Kocaefe 2012). The reduction of weight loss observed during the thermal modification can be attributed to the degradation of amorphous carbohydrates, mainly hemicelluloses, which are thermally sensitive polymers which are major components of wood (Bourgois and Guyonnet 1988; De Groot et al. 1988; Zaman et al. 2000; Juanito et al. 2011). Brown rot fungi preferentially degrade polysaccharides and partially lignin oxide, whereas, white rot fungi degrade lignin and polysaccharides simultaneously or successively (Zabel and Morrell 1992; Jensen et al. 2001; Koyani et al. 2011; Monrroy et al. 2011). Among the carbohydrates, it is assumed that the hemicelluloses are degraded easier than cellulose, with the increasing temperature, probably due to the shorter chain length and an exhibition of cellulose microfibrils in the wood cell walls (Zabel and Morrell 1992). Hemicelluloses degradation during thermal modification may reduce the availability of

substrate for fungi. In addition, the degradation of hemicelluloses, which is the most hydrophilic compounds in the cell wall, could reduce the hygroscopicity of wood (Kamdem et al. 2002). The presence of moisture is essential for the development of fungal growth. Therefore, decreasing hygroscopicity and the lack of nutrient availability improve the decay resistance of thermally-modified *P. banksiana* as evidenced by the results shown in Table 1. Furthermore, chemical changes of wood cell walls take place during the thermal modification (Tjeerdsma et al. 1998; Tumen et al. 2010). Changes in the structure of the wood cell wall make the degradation difficult and eliminate substrate recognition by the oxidative enzymes of fungus (Perez et al. 2002, Hakkou et al. 2006). This could be the reason for the observed increase in durability of thermally-modified *P. banksiana* compared to that untreated wood.

This study showed that the beginning of the colonization process was characterized by a slow degradation of untreated *P. banksiana* samples by four decay fungi, *P. placenta*, *T. versicolor*, *G. trabeum* and *C. puteana* (Figure 2). This could be explained by the fact that during the initial stage of the colonization, the fungi use a readily available carbon source present in the malt-agar medium for growth (Aro et al. 2005; Lekounougou et al. 2009). After 6 to 8 weeks of inoculation, nutrients become scarce in the culture medium and, fungi begin to degrade the compounds present in the wood, which causes an increase in the weight loss, as observed for *T. versicolor*, *G. trabeum* and *P. placenta*. In addition, during the initial stage of wood degradation, enzymes are known not to be involved because of their larger size than the pores of the cell wall (Garote et al. 2001, Bami and Mohebbi 2011). Brown and white rot fungi use of low molecular weight mediators such as  $\text{Fe}^{2+}$  ions and hydrogen peroxide that are responsible for generating highly reactive

free radicals that undergo a complex of spontaneous cleavage (Cullen and Kersten 2004, Machuca and Ferraz 2001). The depolymerisation of cellulose takes place which makes it accessible to further degradation (Wang and Gao 2003; Bami and Mohebbi 20011). However, the degradation of *P. banksiana* by *C. puteana* is different compared to its decay by other decay fungi. The works carried out by Tremblay and Lihra (2005) showed the use of perjure process on the thermal modification of *Pinus banksiana* (Jack pine) treated at 210 °C. These data showed an improvement in the thermally modified of *Pinus banksiana* (Jack pine) against *G. trabeum* and *P. placenta* fungi. While unmodified jack pine (*Pinus banksiana*) was resistant to the *T. versicolor* fungus. In the case of *G. trabeum* fungus, the thermally modified wood data confirmed the results of this study. But, *P. placenta* and *T. versicolor* fungi results were not the same. This can be explain by the type of furnace used in the perjure technology. The tests performed in this study used a prototype furnace inspired from perjure technology. At this point, a patent has been filed on this process. While the study carried out by Tremblay and Lihra (2005) used the perjure technology at great scale in an industrial furnace. On the other hand, the origin and dimensions of the wood samples can explain the differences obtained. Changes in biological resistance of *P. banksiana* against the four basidiomycete decay fungi observed in this study were also observed by Jesus et al. (1998), Paes al. (2004) and Calenego et al. (2010). They have all shown that different wood species frequently exhibited differences in their resistance to various decay fungi, and ASTM D-2017 (1994) cited that the same kind of wood does not have necessarily the same class of resistance against all types of decay fungi.

This investigation provides some information for a better understanding of the degradation of thermally-modified Canadian wood by brown and white rot fungi. The other complementary tests are planned to study the different enzymes involved in degradation of the compounds of the wood cell wall and the mechanism of degradation of thermally-modified *P. banksiana* by decay fungi.

## **Conclusion**

This study showed that the increasing thermal modification temperature between 190 °C and 210 °C improves the biological resistance of *P. banksiana* against decay fungi, *T. versicolor*, *G. trabeum* and *C. puteana*. The reduction in the weight losses of 96.5%, 98.3% and 100% respectively were obtained compared to that of the untreated wood. However, the thermal modification was not found to prevent effectively the degradation of wood when exposed to *P. placenta* fungus shown by 25.2% reduction in weight loss of wood thermally-modified at 210 °C.

## **Acknowledgements**

The authors thank Dr. Yasar Kocaefe, Dr. Noura Oumarou, Dr. Dipankar Bhattacharyay and Claire Fournier for their collaboration during the thermal modification trials and fungal tests. The financial support of NSERC, UQAC (University of Quebec at Chicoutimi) and FUQAC (Foundation of University of Quebec at Chicoutimi) is greatly appreciated.

## References

American Society for Testing and Materials-ASTMD-2017. 1994. Standard Method of Accelerated Laboratory test of Natural decay resistance of Wood. Philadelphia: Annual Book of ASTM Standard 0410, pp. 324-328.

Aro, N., Pakula, T., Penttila, M. 2005. Transcriptional regulation of plant cell degradation by filamentous fungi. *FEMS Microbiol. Rev.* 32: 59-65.

Bami, L. K, Mohebbi, B. 2011. Bioresistance of poplar wood compressed by combined hydro-thermo-mechanical wood modification (CHTM): soft rot and brown-rot. *Int. Biodetr. Biodegrad.* 65: 866-870.

Bächle, H., Zimmer, B., Windeisen, E., Wegener, G. 2010. Evaluation of thermally modified beech and spruce wood and their properties by FT-NIR spectroscopy. *Wood Sci. Technol.* 44 (3): 421-433.

Baysal, E., Yalinkilic, M. K. 2005. A comparative study on stability and decay resistance of some environmentally friendly fire-retardant boron compounds. *Wood Sci. Technol.* 39: 169-186

Boonstra, M. J., Acker, J. V., and Kegel, E. 2006. The effect of two-stage heat treatment process on the mechanical properties of full construction timber. *Wood. Mater. Sci. Engen.* 2: 138-146.

Boonstra, M. J., Van Acker, J., Kegel, E., and Stevens, M. 2007. Optimisation of two-stage heat treatment process: durability aspects. *Wood Sci. Technol.* 41: 31-57.

Bowyer, J. L., Shmulsky, R., Haygreen, J. G. 2003. Wood durability and protection. In: Bowyer JL, Shmulsky R, Haygreen JG (eds) *Forest products and wood science*, 4<sup>th</sup> edn. Iowa State Press, Iowa, pp 261-286.

Bourgois, J., and Guyonnet, R. 1988. Characterization and analysis of torrefied wood. *Wood Sci. Technol* 22 (2): 143-155.

Calonego, F., Severo, E. T. D., and Furtado, E. L. 2010. Decay resistance of thermally-modified *Eucalyptus grandis* wood at 140°C, 160°C, 180°C, 200°C and 220°C. *Biores. Technol.* 101: 9391-9394.

Chang, H. T., and Chang, S. T. 2006. Modification of wood with isopropyl glycidyl ether and its effects on decay resistance and light stability. *Bioresour. Technol.* 97:1265-1271.

Clausen, C., and Yang, V. 2007. Protecting wood from mould, decay, and termites with multi-component biocide systems. *Int. Biodeterior. Biodegrad.* 59: 20-24.

Cullen, D., and Kersten, P. J. 2004. Enzymology and molecular biology of lignin degradation. *Bioch. Mol. Biol.* 2: 249-263.

De Groot, W.F., Pan, W.P, Rahman, M. D. and Richards, G. N. 1988. First chemical events in pyrolysis of wood. *J. Analt. Appl. Pyr.* 13: 221-231.

EN 113. 1986. Wood preservatives. Determination of toxic values of wood preservatives against wood destroying basidiomycetes cultured on AN agar medium (Norme Francaise NF EN 113 produits de préservation des bois-Détermination du seuil d`efficacité contre les champignons basidiomycetes lignivores cultivés sur milieu gélosé).

Garote, G., Domínguez, H., and Parajó, J. C. 2001. Study on the deacetylation of hemicelluloses during the hydrothermal processing of Eucalyptus wood. *Holz als Roh Werkst* 59 (1-2): 53-59.

Goodell, B. 2003. Brown-rot fungal degradation of wood: our evolving view. In: Goodell B, Nicholas DD, Schultz TP (eds) *Wood deterioration and preservation: advances in our changing world*. American Chemistry Society, Washington, pp 97-118.

Gunduz, G., and Aydemir, D. 2009. Some physical properties of heat-treated hornbeam (*Carpinus betulus L.*) wood. *Drying. Technol.* 27 (5): 714-720.

Jensen, Jr. K. A., Houtman, C. J., Ryan, Zc., and Hammel, K. E. 2001. Pathways for extracellular fenton chemistry in the brown rot basidiomycete *Gloeophyllum Trabeum*. *Appl. Environ. Microbiol.* 67: 2705-2711.

Jesus, M., A., de Morais, J., W., de Abreu R., L., S., and Cardias M., de Fat., C. 1998. Natural durability of 46 amazonian woods species in an in-ground essay in a forest environment. *Scientia Forestalis* 54: 81-92.



Juanito, P., Jimenez, Jr., Menandro, N. A., Ramon, A. R., and Ponciano, S.M. 2011. Physico-Mechanical Properties and durability of thermally modified Malapapaya [*Polysciasnodosa* (Blume) seem] wood. Philip. J. Sci.140 (1): 13-23.

Hakkou, M., Petrissans, M., Gérardin, P., and Zoulalian, A. 2006. Investigations of the reasons for fungal durability of heat-treated beech wood. Polym. Degrad. Stab. 91: 393-397.

Hill, A. S. 2006. Wood modification: chemical, thermal and other processes. Wiley series in renewable resources, Wiley, Chichester.

Kamdem, D. P., Pizzi, A., and Jermannaud, A. 2002. Durability of heat-treated wood. Holz Roh Werkst 60:1-6.

Kartal, S. N., Brischke, C., Rapp, A. O., and Imamura, Y. 2006. Biological effectiveness of didecyl dimethyl ammonium tetrafluoroborate (DBF) against basidiomycetes following preconditioning in soil bed tests. Wood Sci. Technol.40: 63-71.

Khalid, I., Wahab, R., Sudin, M., Sulaiman, O., Hassan, A., and Alamjuri, R. H. 2010. Chemical changes in 15 year-old cultivated acacia hybrid oil-heat treated at 180, 220 and 220 °C. Int. J. Chem. 2 (1): 97-107.

Kocaeffe, D., Poncsák, S., Dore, G., and Younsi, R. 2008a. Effect of heat treatment on the wettability of white ash and soft maple by water. Holz Roh-Wekst 66 (5): 355-361

Kocafe, D., Shi, J. L., Yang, D. Q, and Bouazara, M. 2008b. Mechanical properties, dimensional stability, and mold resistance of heat-treatment jack pine and aspen. For Prod J 58 (6): 88-93.

Korkut, S. 2012. Performance of three thermally treated tropical wood species commonly used in Turkey. Indust. Crops Prod. 36: 355-362.

Koyani, R. D., Sanghvi, G. V., and Rajput, K. S. 2011. Comparative study on the delignification of azadirachta India (L) Del., wood by *Chrysosporium asperatum* and *Trichoderma harzianum*. Inter. Biodeter. Biodegrad. 65 (1):179-184.

Lekounougou, S., Jacquot, J. P., Gerardin, P., and Gelhayé, E. 2008. Effects of propiconazole on extra-cellular enzymes involved in nutrient mobilization during *Trametes versicolor* wood colonization. Wood. Sci. Technol. 42: 169-177.

Lekounougou, S., Pétrissans, M., Jacquot, J. P., Gelhayé, E., and Gérardin, P. 2009. Effect of heat treatment on extracellular enzymatic activities involved in beech wood degradation by *Trametes versicolor*. Wood. Sci. Technol. 43: 331-341.

Lekounougou, S., Kocafe, D., Oumarou, N., Kocafe, Y., and Poncsák, S. 2011. Effect of thermal modification on mechanical properties of Canadian white birch (*Betula papyfera*). Intern. Wood. Product. J. 2 (2): 101-107.

Lekounougou, S., and Kocaefe, D. 2012. Comparative study on the durability of heat-treated White birch (*Betula papyrifera*) subjected to the attack of brown rot and white rot fungi. *Wood. Mater. Sci. Engin.* 7 (2): 101-106.

Machuca, A., and Ferraz, A. 2001. Hydrolytic and oxidative enzymes produced by white and brown-rot fungi during *Eucalyptus grandis* decay in solid medium. *Enzym. Microb. Technol.* 29: 386-391.

Mburu, F., Dumarcay, S., Huber, F., Petrissans, M., and Gérardin, P. 2007. Evaluation of thermally modified wood *Grevillea robusta* heartwood as an alternative to shortage of wood resource in Kenya: Characterisation of physicochemical properties and improvement of bio-resistance. *Bioresour. Technol.* 98: 3478-3486.

Militz, H. (edited). 2002. Heat treatment technologies in Europe: Scientific background and technological state of art. Madison, USA.

Monrroy, M., Ortega, I., Ramírez, M., Baeza, J., and Freer, J. 2011. Structural change in wood by brown rot fungi and effect on enzymatic hydrolysis. *Enz. Microbiol Technol.* 49: 472-477.

Paes, J. B., Morais, V. deM., And de Lima, C., R. 2004. Natural resistance of nine woods of Brazilian semi-arid region to wood-destroying fungi under laboratory conditions. *Revista Avore* 28: 275-282.

Perez, J., Munoz-Dorado, J., de la Rubia, T., and Martinez, J. 2002. Biodegradation and biological treatments of cellulose, hemicelluloses and lignin: An overview. Intern. Microbiol. 5: 53-63.

Preston 2000. Wood preservation: trends of today that will influence the industry tomorrow. For. Prod. J. 50: 13-19

Poncsák, S., Kocaefe, D., Bouazara, M., and Pichette, A. 2006. Effect of high temperature treatment on the mechanical properties of birch (*Betula papyrifera*). Wood. Sci. Technol 40: 647-663.

Rowell, R. M., Ibach, R. E., Mcsweeny, J., and Nilsson, T. 2009. Understanding decay resistance, dimensional stability and strength changes in heat-treated and acetylated wood. Wood Mater. Sci. Engin. 1-2: 14-22.

Shi, J. L., Kocaefe, D., Amburgey, T., and Zhang, J. 2007. A comparative study on brown rot fungus decay and subterranean termite resistance of thermally-modified and ACQ-C-treated wood. Eur. J. Wood Prod. 65 (5): 353-358

Suzuki, M. R., Hunt, C. G., Houtman, C. J., Dalebroux, Z. D., and Hammel, K. E. 2006. Fungal hydroquinones contribute to brown rot of wood. Environ. Microbiol. 8: 2214-2223.

Tremblay C and Lihra T. 2005. Physical properties of thermally modified Basalm Fir and Jack pine. Proc. 2<sup>nd</sup> European conf. of wood modification. Göttingen, Germany, October 2005. Holger Militz and Callum Hill. Paper 11.

Tjeerdsma, B. F., Boonstra, M., Pizzi, A., Tekey, P., and Militz, H. 1998. Characterisation of thermally modified wood: molecular reasons for wood performance improvement. Holz Roh Wekst 56: 149-153

Tumen, I., Aydemir, D., Gunduz, G., Uner, B., and Cetin, H. 2010. Changes in the chemical structure of thermally treated wood. Bioresourc. 5 (3): 1936-1944.

Van Acker, J., Stevens, M., Carey, J., Sierra-Alvarez, R., Militz, H., Le Bayon, I., Kleist, G., and Peek, R. D. 2003. Biological durability of wood in relation to end-use. Part 1. Towards a European standard for laboratory testing of the biological durability of wood. HolzRoh-Werkst 61:35-45.

Wang, W., and Gao, P. J. 2003. Function and mechanism of low-molecular-weight peptide produced by *Gloeophyllum trabeum* in biodegradation of cellulose. J. Biotechnol. 101:119-130.


Weiland, J. J., and Guyonnet, R. 2003. Study of chemical modifications and fungi degradation of thermally modified wood using DRIFT spectroscopy. Holz Roh-Werkst 61 (3): 216-220.

Xianjun, L., Zhiyong, C., Tuning, M., Yiqiang, W., and Yuan, L. 2011. Effects of heat treatment on some physical properties of Douglas Fir (*Pseudotsuga menziesii*) wood. *Adv. Mater. Resear.* (197-198): 90-95.


Yelle, D. J, Ralph, J., Lu, F., and Hammel, K. E. 2008. Evidence for cleavage of lignin by a brown rot basidiomycete. *Environ. Microbiol.* 10: 1844-1849

Zabel, R. A., and Morrell, J. 1992. Wood microbiology. In: decay and its prevention Academic Press, New York, USA. P-476.

Zaman, A., Alén, R., and Kotilainen, R. 2000. Thermal behaviour of scot pine (*Pinus sylvestris*) and silver Birch (*Betula pendula*) at 200-230°C. *Wood. Fiber. Sci.* 32: 138-143.




**Fig. 1** Tests diagram performed in this study



**Fig. 2** Weight loss of untreated *Pinus banksiana* wood due to fungal decay after 12 weeks incubation.

■: *P. placenta*, □: *G. trabeum*, ▲: *T. versicolor*, ■: *C. puteana*





**Fig. 3** Effect of thermal modification temperature on the decay resistance of *Pinus banksiana* after 12 weeks incubation

□: Untreated wood, ▨: 190 °C, ▩: 200 °C, ■: 210 °C

**Table 1.** Effect of thermal modification temperature on the decay resistance of *Pinus banksiana* to the decay fungi after 12 weeks of incubation

Fungal species	Thermal Modification Temperature of <i>Pinus Banksiana</i>	MC (%)	SD* (%)	Weight loss (%)	SD* (%)	Reduction in weight loss due to thermal modification
<i>G. trabeum</i>	Untreated	255.4 ± 2.6		41.53 ± 2.6		-
	190°C	136.1 ± 0.8		2.2 ± 0.8		94.7
	200°C	171.5 ± 0.5		0.9 ± 0.5		97.3
	210°C	37.4 ± 0.5		0.7 ± 0.5		98.3
<i>C. puteana</i>	Untreated	0.4 ± 0.5		14.9 ± 0.5		-
	190°C	0.7 ± 0.5		1.5 ± 0.5		89.9
	200°C	0.4 ± 0.4		3.9 ± 0.4		97.4
	210°C	-	-	-	-	100
<i>P. placenta</i>	Untreated	117.5 ± 2.2		52.3 ± 2.2		-
	190°C	66.08 ± 1.6		48.8 ± 1.6		6.7
	200°C	47.6 ± 1.6		47.6 ± 1.6		8.9
	210°C	16.7 ± 1.9		39.1 ± 1.9		25.2
<i>T. versicolor</i>	Untreated	5.3 ± 1.9		43.5 ± 1.9		-
	190°C	4.1 ± 1.5		18.5 ± 1.5		57.4
	200°C	1.6 ± 1.0		9.1 ± 1.0		79.1
	210°C	0.5 ± 0.5		1.5 ± 0.5		96.5

\* SD: Standard Deviations; MC: Moisture Content