

Rhizomucor miehei LIPASE SUPPORTED ON CHITOSAN-GRAPHENE OXIDE
BEADS FOR THE PRODUCTION OF GERANIOL PROPIONATE

ISAH ABDURRAHMAN ADAMU

UNIVERSITI TEKNOLOGI MALAYSIA

Rhizomucor miehei LIPASE SUPPORTED ON CHITOSAN-GRAPHENE OXIDE
BEADS FOR THE PRODUCTION OF GERANIOL PROPIONATE

ISAH ABDURRAHMAN ADAMU

A dissertation submitted in partial fulfillment of the
requirements for the award of the degree of
Master of Science (Chemistry)

Faculty of Science
Universiti Teknologi Malaysia

DECEMBER 2015

To my beloved wife, Fatima Lawan

ACKNOWLEDGEMENT

Alhamdulillah, thanks be to Allah (S.W.T) for giving me the strength and privilege throughout my work.

I would like to express my sincere appreciation to my supervisor, Dr. Roswanira Abdul Wahab, for her guidance, patience, encouragement and support. It was a great learning experience. To a practical student, Siti Rohaiza binti Ab Rahman, I am very thankful to her assistance and advice. I am also grateful to Faculty of Biosciences and Medical Engineering (FBME), Universiti Teknologi Malaysia (UTM) and Dr. Zainoha's laboratory for allowing me to use their equipments'.

I thank all my laboratory mates, in particular Ida Rahman, Fatin Myra and Nur Haziqa and for their assistance in one way or the other. Special thanks go to Kano State Government for awarding me with full scholarship and Universiti Teknologi Malaysia (UTM) for funding my research.

Finally, I would like to acknowledge my wife, Fatima Lawan, with her encouraging kind words and moral supports in my hard times during the work, I really appreciate all that she has done for me.

ABSTRACT

The biotechnological route to manufacturing geraniol propionate may present a feasible solution to drawbacks associated with the production of such ester by the chemical synthesis or extraction from plants. The use of such technique can be advantageous considering the ever increasing demands for such products while reducing waste production and simplifying the manufacturing process. The properties and morphology of the developed *Rhizomucor miehei* lipase (RML) immobilized onto activated chitosan-graphene oxide (CS/GO) support were characterized using field emission scanning electron microscopy (FESEM), transmission electron microscopy (TEM), Fourier transform infrared spectroscopy (FTIR) and thermogravimetric analysis (TGA). The morphological evaluations strongly indicated successful covalent attachment of the RML on the support. It was evident from the thermogram of TGA that 13.5% of RML was successfully immobilized onto the CS/GO matrix. The approach of response surface methodology (RSM) employing the Box-Behnken design (BBD) based on four parameters (incubation time, temperature, substrate molar ratio, and enzyme loading) were used to seek the optimized experimental conditions for the RML-CS/GO catalyzed synthesis of geraniol propionate. The study illustrated that the predicted and actual responses were well correlated, suggesting adequacy of the generated model for predicting the yield of the ester, as well as the factor of reaction time being most impacting in the RML-CS/GO catalyzed synthesis of geraniol propionate. Under optimized conditions, the highest yield of geraniol propionate (49.46%) was obtained at 17.98 h, 37.67 °C, 100.70 rpm, and molar ratio of acid:alcohol of 1:3.28 in the solvent free esterification of propionic acid and geraniol. The investigation demonstrated that the developed RML-CS/GO was a promising alternative to overcome drawbacks associated with solvent assisted enzymatic reactions. Therefore, the RML-CS/GO biocatalysts developed here appear to be a promising substitute and yet environmentally practical biocatalyst for the production of geraniol propionate.

ABSTRAK

Laluan bioteknologi untuk penghasilan geraniol propionat mungkin merupakan penyelesaian kepada kelemahan yang dikaitkan dengan penghasilan ester tersebut dengan menggunakan sintesis kimia atau pengekstrakan daripada tumbuh-tumbuhan. Penggunaan teknik sedemikian adalah berfaedah memandangkan peningkatan permintaan yang berterusan terhadap produk tersebut di samping mengurangkan penghasilan bahan buangan dan memudahkan proses pembuatan. Sifat dan morfologi *Rhizomucor miehei* lipase (RML) terpegun pada penyokong kitosan teraktif-grafin oksida (RML-CS/GO) yang dibangunkan telah dicirikan menggunakan mikroskopi pengimbasan elektron pancaran medan (FESEM), spektroskopi inframerah transformasi Fourier (FTIR) dan analisis termogravimetri (TGA). Penilaian morfologi menunjukkan secara jelas kejayaan pengikatan RML secara kovalen dengan penyokong. Ini terbukti daripada termogram TGA bahawa 13.5% daripada RML telah berjaya dipegunkan ke atas matriks CS/GO. Pendekatan kaedah permukaan respons (RSM) menggunakan reka bentuk Box-Behnken (BBD) berasaskan empat pembolehubah (masa pengeraman, suhu, kadar pengacauan, dan nisbah molar substrat) telah digunakan untuk mendapatkan keadaan eksperimen yang optimum dalam sintesis geraniol propionat bermangkinkan RML-CS/GO. Kajian ini menjelaskan bahawa respons yang diramal dan sebenar berhubungkait dengan baik, mencadangkan model yang dihasilkan adalah memuaskan untuk meramalkan penghasilan ester, di samping juga faktor masa tindak balas yang paling memberi impak kepada sintesis geraniol propionat bermangkinkan RML/CS/GO. Pada keadaan optimum, penghasilan tertinggi geraniol propionat (49.46 %) telah diperoleh pada 17.98 h, 37.67 °C, 100.70 rpm, dan nisbah molar asid:alkohol 1:3.28 dalam pengesteran bebas pelarut bagi asid propionik dan geraniol. Kajian ini menunjukkan bahawa biomangkinkan RML-CS/GO yang dibangunkan adalah alternatif yang berpotensi untuk mengatasi kelemahan yang dikaitkan dengan tindak balas enzim berbantuan pelarut. Oleh itu, biomangkinkan RML-CS/GO yang dibangunkan ini merupakan pengganti dan biopemangkinkan yang praktikal alam sekitar untuk penghasilan geraniol propionat.

TABLE OF CONTENTS

CHAPTER	TITLE	PAGE
	DECLARATION	ii
	DEDICATION	iii
	ACKNOWLEDGEMENT	iv
	ABSTRACT	v
	ABSTRAK	vi
	TABLE OF CONTENTS	vii
	LIST OF TABLES	xi
	LIST OF FIGURES	xii
	LIST OF SCHEMES	xiv
	LIST OF SYMBOLS	xv
	LIST OF ABBREVIATIONS	xvi
	LIST OF EQUATIONS	xvii
	LIST OF APPENDICES	xviii
1	INTRODUCTION	
	1.1 Background of Study	1
	1.2 Problem Statement	4
	1.3 Objectives	4
	1.4 Scope of Study	4
	1.5 Hypothesis	5
	1.6 Significance of Study	5
2	LITERATURE REVIEW	
	2.1 Esterification	7
	2.2 Geraniol and its Esters	9
	2.3 Geraniol propionate	10

2.4	Sustainable Methods to Produce Geraniol propionate	11
2.5	Lipases	12
2.6	Sources of Lipases	13
2.7	<i>Rhizomucor miehei</i> Lipase	15
2.8	Three-dimensional structure of RML	15
2.9	Mechanism of Lipase Activation During Catalysis	17
2.10	Kinetics and mechanism of esterification catalyzed by lipases	17
2.11	Immobilization of Enzymes	19
2.12	Methods for Enzyme Immobilization	20
	2.12.1 Adsorption	22
	2.12.2 Cross linking	22
	2.12.3 Entrapment	23
	2.12.4 Covalent binding	23
2.13	Types of Supports for Enzyme Immobilization	24
2.14	Chitosan	26
2.15	Properties and Application of Chitosan	27
2.16	Chitosan Beads	28
2.17	Chitosan Flakes	29
2.18	Nano-chitosan	29
2.19	Graphene oxide	30
2.20	Response Surface Methodology (RSM)	32
2.21	Box-Behnken Designs	33
2.22	Applications of Box-Behnken Design (BBD)	35
	2.22.1 Application of BBD for the optimizing synthetic processes	35
2.23	Rationale of Study	36
3	METHODOLOGY	
3.1	Experimental Design	40
3.2	Materials and Reagents	40
3.3	Preparation of CS/GO Beads	41
3.4	Functionalization of CS/GO Beads	41

3.5	Immobilization of RML onto CS/GO Beads	42
3.6	Characterizations of CS, CS/GO and RML/CS/GO Beads	42
3.6.1	Fourier Transform Infra-Red Spectroscopy (FT-IR)	42
3.6.2	Thermal Gravimetric Analysis (TGA)	43
3.6.3	Field Emission Scanning Electron Microscopy (FESEM) and Transmission Electron Microscopy (TEM).	43
3.7	RML-CS/GO Catalyzed Synthesis of Geraniol propionate	43
3.8	Determination of Percentage Conversion	44
3.9	Experimental design, Statistical Analysis and Optimization	45
4	RESULTS AND DISCUSSION	
4.1	Structure and Textural Characterization	48
4.1.1	Fourier Transform Infrared (FT-IR)	48
4.1.2	Electron Microscopy of Raw Chitossan (CS), Chitosan Reinforced with Graphene Oxide (CS/GO) and Covalently Immobilized RML onto CS/GO (RML-CS/GO) Beads	52
4.1.3	Thermal Gravimetric Analysis (TGA)	54
4.2	Optimization of the Esterification for the Synthesis of Geraniol propionate using Response Surface Methodology (RSM)	55
4.2.1	RSM Experiments, Model Fitting and Statistical Analysis	56
4.3	Effects of Process Variables on the Percentage Yield of Geraniol propionate	62
4.4	Mutual Effects of Factors on the RML-CS/GO catalyzed Synthesis of Geraniol propionate	64
4.4.1	Effect of Time and Temperature	64

4.4.2	Effect of Time and Molar ratio	67
4.4.3	Effect of Molar ratio and Stirring rate	70
4.5	Attaining Optimum Condition and Verification of the Model	72
5	CONCLUSION AND RECOMMENDATIONS	
5.1	Conclusion	74
5.2	Recommendations for Future Research	74
	REFERENCES	75-94
	APPENDICES	95-98

LIST OF TABLES

TABLE NO	TITLE	PAGE
2.1	Summary of advantages and disadvantages of different enzyme immobilization methods.	25
3.1	Coded and actual levels of variables for the Box-Behnken design.	44
4.1	FT-IR Frequency Table for (a) CS, (b) CS/GO, (c) RML-CS/GO	50
4.2	Composition of the various runs of the Box-Behnken design, actual and predicted responses.	57
4.3	Analysis of Variance (ANOVA) and Coefficients of the Model.	59
4.4	Optimum conditions for the RML-CS/GO catalyzed synthesis of geraniol propionate	73

LIST OF FIGURES

FIGURE NO	TITLE	PAGE
2.1	General equations for the formation of esters	8
2.2	Synthesis of geraniol esters	10
2.3	Structure of geraniol propionate	11
2.4	Secondary structure of the <i>Rhizomucor miehei</i> lipase. The positions of glycines and prolines are indicated and colored red and purple, respectively	16
2.5	Schematic representation of physical adsorption, entrapment and covalent attachment/cross-linking.	21
2.6	Chemical structure of chitosan	28
2.7	Structure of graphene oxide	31
2.8	BBD for three factors. Each point represents the factor values for one experiment	34
4.1	FT-IR spectra of (a) raw CS, (b) CS/GO and (c) RML-CS/GO.	51
4.2	(a) FESEM and (b) TEM images of CS. (c) FESEM and (d) TEM images of CS/GO. (e) FESEM and (f) TEM images of RML-CS/GO.	53
4.3	Themogravimetric analysis results of (a) CS, (b) CS/GO (c) RML-CS/GO.	55
4.4	Diagnostic plots of the quadratic model for GP catalyzed synthesis. (a) Normal percent probability versus residual error; (b) the actual versus predicted response.	61
4.5	The deviation of the reference point for the percentage conversion of geraniol propionate for the effect of Time (A), Temperature (B), Molar ratio (C) and	63

	Stirring rate (D).	
4.6	Graph showing the response surface plot (a) and contour plot (b) and the mutual interactions between reaction time (A) and temperature (B) in the RML-CS/GO catalyzed synthesis of geraniol propionate.	65
4.7	Graph showing the response surface plot (a) and contour plot (b) and the mutual interactions between reaction time (A) and molar ratio (C) in the RML-CS/GO catalyzed synthesis of geraniol propionate.	68
4.8	Graph showing the response surface plot (a) and contour plot (b) and the mutual interactions between molar ratio (C) and stirring rate (D) in the RML-CS/GO catalyzed synthesis of geraniol propionate.	71

LIST OF SCHEMES

SCHEME NO.	TITLE	PAGE
2.1	Different reactions catalyzed by lipases. Reactions (b), (c) and (d) are often grouped as a single reaction (transesterification).	13
2.2	Reaction sequence of a lipase-catalyzed esterification reaction.	19
2.3	Schematic diagram showing (a) Possible microstructure present in CS/GO nanocomposites, and (b) formation of hydrogen bonds between CS chains and GO sheets.	38
2.4	Cross linking reaction mechanism of GO and CS with EDAC.	39
3.1	Flow chart for the experimental design.	47
4.1	Enzymatic synthesis of geraniol propionate using immobilized <i>Rhizomucor miehei</i> as the biocatalyst.	55

LIST OF SYMBOLS

$^{\circ}\text{C}$	-	Degree Celsius
g	-	Gram
h	-	Hour
L	-	Liter
mg	-	Milligram
mL	-	Milliliter
mg/mL	-	Milligram per milliliter
M	-	Molar
rpm	-	Rotation per minutes
v/v	-	Volume per volume
w/v	-	Weight per volume
w/w	-	Weight per weight
%	-	Percentage

LIST OF ABBREVIATIONS

CS	-	Chitosan
GO	-	Graphene Oxide
BBD	-	Box-Behnken Design
FT-IR	-	Fourier Transform Infrared
FESEM	-	Field Emission Scanning Electron Microscope
TEM	-	Transmission Electron Microscope
TGA	-	Thermal Gravimetric Analysis
RSM	-	Response Surface Methodology
EDAC	-	1-(3-dimethylaminopropyl)-3-ethylcarbodiimide hydrochloride
NHS	-	<i>N</i> -hydroxysuccinimide

LIST OF EQUATIONS

NO	EQUATIONS	PAGE
3.1	% Conversion = $\left(\frac{V_0 - V_t}{V_0}\right) \times 100$	44
3.2	$y = b_o + \sum_{i=1}^4 b_i x_i + \sum_{i=1}^4 b_{ii} x_i + \sum_{i=j}^3 \sum_{j=i+1}^4 b_{ij} x_{ij} + e$	45
4.1	Conversion (%) = +45.65 + 4.11A - 1.11B + 1.09C - 1.61D + 2.43 AB - 1.70AC - 1.02AD + 0.58BC + 1.25BD - 2.14CD - 0.96A ² - 0.46 B ² - 4.70C ² - 1.31D ² .	58

LIST OF APPENDICES

APPENDIX	TITLE	PAGE
A	Details of ANOVA from RSM software DX7 Design Expert 7.1.6	95
B	TGA curve for the determination of the amount of RML immobilized onto CS/GO beads	98

CHAPTER 1

INTRODUCTION

1.1 Background of Study

Terpene esters of alcohol are economically important fragrance and flavor compounds used in food, pharmaceutical, beverage and cosmetic industries; geraniol, citronellol and linalool being the principal components in essential oils. These esters are traditionally obtained by chemical synthesis, physical extraction from plants and by fermentation of natural precursors (You *et al.*, 2011). However, natural flavor esters extracted from plant sources are too expensive or scarce for commercial purposes, while the production of terpene esters using chemical synthesis incurs undesirable use of strong acids. The drawbacks of such method are formation of by-products which have an effect on the odor of terpene esters. Also, the products produced by the method are considered as not natural, therefore, are marketed with less value than esters obtained from natural sources (Stamatis *et al.*, 1998; You *et al.*, 2011). Hence, the biotechnological route to producing fragrances and flavors using natural raw materials may prove useful for industrial processes in view of the ever increasing demands for such products (Paroul *et al.*, 2010).

Biotechnology as an emerging science promotes the development of better industrial processes such as manufacturing of new aromas and production of high purity compounds for use in food industries. Presently, biocatalysis is a feasible alternative to chemical synthesis method, especially when regioselectivity or stereoselectivity of the resulting end product is pertinent. Among the important widely used industrial enzymes are carbohydrases, proteases and lipases. The major benefits of using these biocatalysts in synthetic reactions such as esterification and

transesterification reactions refers to their high activity of enzymes in organic solvents and water and also, their ability to convert large amounts of substrate with high stereospecificity (Ferraz *et al.*, 2015). In this context, lipases (triacylglycerol hydrolase E.C 3.1.1.3) can catalyze esterification reactions under ambient conditions with good activity and selectivity. The mesophilic *Rhizomucor miehei* lipase (RML) is the frequent biocatalyst of choice due to its specificity, versatility, and its suitability for ester synthesis under different conditions of temperature, pressure, water content, and substrates (Skoronsi *et al.*, 2014). The lipase is commercially obtainable both in soluble and immobilized form (Rodrigues and Fernandez-Lafuente, 2010).

Utilization of RML to catalyze esterification reactions in anhydrous media is advantageous as compared to other lipases that preferred transesterification reactions (Rodrigues and Fernandez-Lafuente, 2010). However, use of the free form RML has drawbacks of being unstable and prematurely denatured under extensive reaction time, susceptible to high temperature, extreme pH and organic solvents. In addition, the homogeneity of RML with the reaction mixture results in difficult recovery of the enzyme in reactive mixtures. Considering the numerous shortcomings associated with the free RML, immobilization of the lipase onto appropriate solid support may prove feasible to improve the catalytic characteristics of RML, facilitate enzyme recovery (Zou *et al.*, 2010) and allow reusability of the enzyme (Mohamad *et al.*, 2015a). According to review of literature (Palla and Carrin, 2014), the *R. miehei* lipase immobilized onto modified chitosan microspheres can stabilize the open conformation of the lipase and promote their hyperactivation after immobilization.

To date, many techniques such as biological, physical and chemical methods have been used by biochemists to improve the performance of the lipase in order to meet the target goal (Zhang *et al.*, 2008). Enzyme immobilization offers a multitude of benefits in terms of improved structural stability and enzyme activity, ease of recovery of the biocatalyst (Masakapalli *et al.*, 2014; Palla *et al.*, 2011; Park *et al.*, 2015; Sharma *et al.*, 2001), longer life of enzymes, specificity and selectivity as well as minimizing product contamination (Palla *et al.*, 2011; Tang *et al.*, 2014;

Worzakowska, 2014). Among the challenges in this field is the well known slight loss in catalytic activity of the enzyme upon immobilization (Palla *et al.*, 2011).

The structure (shape and size) of the support material has an influence on the immobilized enzyme (Palla *et al.*, 2011). Among the various supports available for enzyme immobilization, chitosan (CS), graphene oxide (GO) and multi-walled carbon nanotubes (MWCNTs) are gaining considerable popularity as the support of choice. CS is chosen due to its ability to exhibit many properties such as availability of reactive functional groups for chemical modification, biocompatibility, regenerability, mechanical stability, and easy to prepare in different geometrical configurations suitable for a particular biotransformation. Furthermore, chitosan is a cheap material making it possible to prepare cheap carriers for large scale applications (Popiskova *et al.*, 2013). Chitosan beads embedded with graphene oxide has an open cell foam structure, ultrafine pores and a cell size that results to a large surface area. Graphene oxide can enhance the physical strength of chitosan due to its low thermal conductivity and superior mechanical integrity. In addition, the epoxy and hydroxyl functional groups of GO can provide additional active sites for the immobilization of lipase (Lau *et al.*, 2014).

Apart from enhancing the robustness of enzymes for use in synthetic reactions, the conditions employed in the reactions may also affect the yield of the product. This is due to the fact that enzymes are biological entities whose catalytic activity is sensitive to conditions of the surroundings (Mohamad *et al.*, 2015a) such as temperature, duration of catalysis, stirring rate, molar ratio of reaction substrates and etc. Considering the multiple complexities associated with enzyme assisted reaction, predictions of the optimum conditions to improve efficiency of its bioprocesses is almost infeasible. This is attributable to the nonlinearity and complicated structure of many biotechnological practices. To expedite prediction of best reaction conditions of processes or products, utilization of response surface methodology may prove valuable (Wahab *et al.*, 2014). The method facilitates rapid and less expensive empirical investigation to establish the optimum conditions of

reactions as compared to that of the conventional one-variable-at-a-time or full factorial experiment (Wahab *et al.*, 2014; Mohamad *et al.*, 2015b).

1.2 Problem Statement

Considering that geraniol propionate obtained from plants or by chemical synthesis faces drawbacks such as production in low yield and produced at high cost which may not meet the high commercial demand for the ester. Therefore, development of an alternative green method to produce high yield of the ester, preferably at a low cost would be of considerable advantage. Furthermore, the use of green nanobioconjugates of RML-CS-GO for the preparation of geraniol propionate is yet to be explored and the the feasibility of such biocatalysts for such purpose remains unknown.

1.3 Objectives

The objectives of the research are as follows:

1. To prepare the chitosan beads reinforced with graphene oxide (CS-GO) and immobilize the *R. miehei* lipase onto the CS-GO (RML-CS/GO) beads.
2. To characterize the CS, CS/GO and RML-CS/GO beads.
3. To optimize the RML-CS/GO catalyzed solventless synthesis of geraniol propionate from geraniol and propionic acid.

1.4 Scope of Study

1. To covalently immobilize the prepared CS-GO beads with free RML in order to obtain the RML-CS/GO beads.

2. To characterize the CS, CS/GO and RML-CS/GO beads by using Fourier transform infrared spectroscopy (FT-IR), Field emission scanning electron microscope (FESEM), Transmission electron spectroscopy (TEM), and thermal gravimetric analysis (TGA).
3. To perform RML-CS/GO assisted esterification of geraniol and propionic acid to afford geraniol propionate by response surface methodology (RSM) according to the proposed conditions of the Design Expert 7.1.6 software utilizing the Box- Behnken design (BBD) method.

1.5 Hypothesis

Covalent immobilization of RML onto CS-GO beads may increase rigidity of the RML protein structure through additional covalent bonds between the matrix and RML, and subsequently improve stability of RML to catalyze prolong esterification reactions. To improve the yield of enzyme assisted esterification of geraniol propionate, the statistical multivariate guided experiments can be used to establish the optimal parameters i.e temperature, time, molar ratio and stirring rate to attain high yield of the ester.

1.6 Significance of Study

Herein, immobilizing the free RML onto a modified matrix promotes solventless bioproduction of geraniol propionate which adheres to the philosophy of green chemistry, hence a step towards green and sustainable means of producing important commercial esters. The employment of green chemistry in synthetic reactions may bring long term benefits as such include being environmentally friendly, production of less wastes as well as economically desirable. In this context, covalently immobilizing RML onto CS-GO beads may possibly bring about three benefits: i) improve activity of RML, ii) potentially cost saving due to utilization of small amount of the enzyme, and iii) increase the yield of geraniol propionate due to

the well-known enzyme enhancing properties of CS and GO. In addition, immobilizing RML onto the CS-GO matrix effectively insolubilizes the RML and supports cost saving practices as it permits easy recovery, reusability of the enzyme and prolong the reaction life of RML for use in subsequent reactions.

REFERENCES

- Abdelbary, A.A., AbouGhaly, M.H. (2015). Design and optimization of topical methotrexate loaded niosomes for enhanced management of psoriasis: Application of Box–Behnken design, in-vitro evaluation and in-vivo skin deposition study. *International Journal of Pharmaceutics*. **485**; 235-243.
- Abdul Manan, F.M., Abd Rahman, I.N., Che Marzuki, N.H., Mahat, N.A., Huyop, F., Wahab, R.A. (2015). Statistical modelling of eugenol benzoate synthesis using *Rhizomucor miehei* lipase reinforced nanobioconjugates. *Process Biochemistry*. ISSN 1359-5113– accepted in press.
- Abdul Rahman, M.B., Jumbri, K., Hanafiah, N.A., Abdulmalek, E., et al. (2012). Enzymatic esterification of fatty acid esters by tetraethylammonium amino acid ionic liquids-coated *Candida rugosa* lipase. *Journal of Molecular Catalysis B: Enzymatic*. **79**; 61-65.
- Abdul Rahman, M.B., Chaibaksh, N., Basri, M., Abdul Rahman, R.N., Salleh, A.B., Radzi, S.M. (2008). Modeling and optimization of lipase-catalyzed synthesis of dilauryl adipate ester by response surface methodology. *Journal of Chemical Technology and Biotechnology*. **83**; 1534-1540.
- Ahmad, A., Alkharfy, K.M., Wani, T.A., Raish, M. (2015). Application of Box–Behnken design for ultrasonic-assisted extraction of polysaccharides from *Paeonia emodi*. *International Journal of Biological Macromolecules*. **72**; 990-997.
- Akar, T., Turkyilmaz, S., Celik, S., Akar, S.T. (2015). Treatment design and characteristics of a biosorptive decolourization process by a green type sorbent. *Journal of Cleaner Production*. **xxx**; 1-10.
- Aloulou, A., Frikha, F., Noiriél, A., Ali, M.B., Abousalham, A. (2014). Kinetic and structural characterization of triacylglycerol lipases possessing phospholipase A₁ activity. *Biochimica et Biophysica Acta*. **1841**; 581-587.

- Amieva, E.J., Fuentes-Ramirez, R., Martinez-Hernandez, A.I., Millan-Chiu, B., et al. (2015). Graphene oxide and reduced graphene oxide modification with polypeptide chains from chicken feather keratin. *Journal of Alloys and Compounds*. **643**; S137-S143.
- Aslan, A. (2008). Application of response surface methodology and central composite rotatable design for modeling and optimization of a multi-gravity separator for chromite concentration. *Powder Technology*. **185**; 80-86.
- Aslan, N., Cebeci, Y. (2007). Application of Box–Behnken design and response surface methodology for modeling of some Turkish coals. *Fuel*. **86**; 90-97.
- Babaki, M., Yousefi, M., Habibi, Z., Brask, J., Mohammadi, M. (2015). Preparation of highly reusable biocatalysts by immobilization of lipase on epoxy-functionalized silica for production of biodiesel from canola oil. *Biochemical Engineering Journal*. **101**; 23-31.
- Badgujar, K.C., Dhake, K.P., Bhanage, B.M. (2013). Immobilization of *Candida cylindracea* lipase on poly lactic acid, polyvinyl alcohol and chitosan based ternary blend film: Characterization, activity, stability and its application for *N*-acylation. *Process Biochemistry*. **48**; 1335-1347.
- Badgujar, K.C., Bhanage, B.M. (2015). Immobilization of lipase on biocompatible co-polymer of polyvinyl alcohol and chitosan for synthesis of laurate compounds in supercritical carbon dioxide using response surface methodology. *Process Biochemistry*. **50**; 1224-1236.
- Bas, D., Boyaci, I.H. (2005). Modelling and optimization I: Usability of response surface methodology. *Journal of Food Engineering*. **78**; 836-845.
- Bezerra, M.A., Santelli, R.E., Oliveira, E.P., Villar, L.S., Escaleira, L.A. (2008). Response surface methodology (RSM) as a tool for optimization in analytical chemistry. *Talanta*. **76**; 965-977.
- Bouaziz, A., Horchani, H., Salem, N.B., Chaari, A., et al. (2010). Enzymatic propyl gallate synthesis in solvent-free system: Optimization by response surface methodology. *Journal of Molecular Catalysis B: Enzymatic*. **67**; 242-250.

- Bradley Nuran (2007). *The response surface methodology*. MSc Thesis, Indiana University of South Bend.
- Brena, B., González-Pombo, P., Batista-Viera, F. (2013). Immobilization of enzyme. A literature survey. *Immobilization of Enzymes and Cells*. **1051**; 15-31.
- Brígida, A.I., Amaral, P.F., Coelho, M.A., Goncalves, L.R. (2014). Lipase from *Yarrowia Lipolytica*: Production, characterization and application as an industrial biocatalyst. *Journal of Molecular Catalysis B: Enzymatic*. **101**; 148-158.
- Bukhari, A., Idris, A., Atta, M., Loong, T.C. (2014). Covalent immobilization of *Candida antarctica* lipase B on nanopolystyrene and its application to microwave-assisted esterification. *Chinese Journal of Catalysis*. **35**; 1555-1564.
- Carrasco-Lopez, C. Godoy, C., de las Rivas, B., Fernandez-Lafuente, G., Palomo, J.M., Guisan, J.M., Fernandez-Lafuente, R., Martinez-Ripoll, M. and Hermoso, J.A. (2009). Activation of bacterial thermoalkalophilic lipases is spurred by dramatic structural rearrangements. *The Journal of Biological Chemistry*. **284**; 4365-4372.
- Ceni, G., Lerin, L.A., de Conto, J.F., Brancher, C.V., et al. (2010). Optimization of 1-glyceryl benzoate production by enzymatic transesterification in organic solvents. *Enzyme and Microbial Technology*. **46**; 107-112.
- Çetinus, S.A., Öztop, H.N. (2003). Immobilization of catalase into chemically crosslinked chitosan beads. *Enzyme and Microbial Technology*. **32**; 889-894.
- Chaibakhsh, N., Abdul Rahman, M.B., Abd-Aziz, S., Basri, M., Salleh, A.B., Abdul Rahman, R.N.Z. (2009). Optimized lipase-catalysed synthesis of adipate ester in a solvent free system. *J Ind Microbiol Biotechnol*. **36**; 1149-1155.
- Chaibakhsh, N., Basri, M., Anuar, S.H., Abdul Rahman, M.B., Rezayee, M. (2012). Optimization of enzymatic synthesis of eugenol ester using statistical approaches. *Biocatalysis and Agricultural Biotechnology*. **1**; 226-231.

- Chang, C., Chen, J., Chang, C.J., Wu, T., Shieh, C. (2009). Optimization of lipase-catalyzed biodiesel by isopropanolysis in a continuous packed-bed reactor using response surface methodology. *New Biotechnology*. **26**; 3/4.
- Charpe T.W., Rathod, V.K. (2011). Biodiesel production using waste frying oil. *Waste Management*. **31**; 85–90.
- Che Marzuki, N.H., Mahat, N.A., Huyop, F., Buang, N.A., Wahab, R.A. (2015a). Modeling and optimization of *Candida rugosa* nanobioconjugates catalyzed synthesis of methyl oleate by response surface methodology. *Biotechnology and Biotechnology Equipment*. **29**; 1113-1127.
- Che Marzuki, N.H., Huyop, F., Aboul-Enein, H.A., Mahat, N.A., Wahab, R.A. (2015b). *Candida rugosa* Lipase Immobilized onto Acid-Functionalized Multi-walled Carbon Nanotubes for Sustainable Production of Methyl Oleate. *Appl Biochem Biotechnol*. **177**; 967-984.
- Chen, W., Viljoen, A.M. (2010). Geraniol – A review of a commercially important fragrance material. *South African Journal of Botany*. **76**; 643-651.
- Converti, A., Borghi, A.D., Gandolfi, R., Molinari, F., et al. (2002). Simplified kinetics and thermodynamics of geraniol acetylation by lyophilized cells of *Aspergillus oryzae*. *Enzyme and Microbial Technology*. **30**; 219-223.
- Claon, P.A., Akoh, C.C. (1993). Enzymatic synthesis of geraniol and citronellol esters by direct esterification in n-hexane. *Biotechnology letters*. **15**; 1211-1216.
- Dalmau, E., Montesinos, J.L., Lotti, M., Casas, C. (2000). Effect of different carbon sources on lipase production by *candida rugosa*. *Enzyme and Microbial Technology*. **26**; 657-663.
- Datta, S., Christena, L.R., Rajaram, Y.R. (2013). Enzyme immobilization: an overview on techniques and support materials. *Biotech* 3(1): 1-9
- Depan, D., Shah, J.S., Misra, R.D. (2013). Degradation mechanism and increased stability of chitosan-based hybrid scaffolds cross-linked with nanostructured

- carbon: Process-structure-functional property relationship. *Polymer Degradation and Stability*. **98**; 2331-2339.
- Depan, D., Pesacreta, T.C., Misra, R.D.K. (2014). The synergistic defect of a hybrid graphene oxide-chitosan system and biomimetic mineralization of osteoblast functions. *Biomaterials Science*. **2**; 264–274.
- Dong, L., Miettinen, K., Goedbloed, M., Verstappen, F.W., et al. (2013). Characterization of two geraniol synthases from *Valeriana officinalis* and *Lippia dulcis*: Similar activity but difference in subcellular localization. *Metabolic Engineering*. **20**; 198-211.
- Dwivedi, G., Sharma, M.P. (2015). Application of Box–Behnken design in optimization of biodiesel yield from Pongamia oil and its stability analysis. *Fuel*. **145**; 256-262.
- Elagli, A., Belhacene, K., Vivien, C., Dhulster, P., Froidevaux, R., Supiot, P. (2014). Facile immobilization of enzyme by entrapment using a plasma-deposited organosilicon thin film. *Journal of Molecular Catalysis B: Enzymatic*. **110**; 77-86.
- El-Boulifi, N., Araci, J., Martinez, M. (2014). Optimization of lipase-catalyzed synthesis of glycerol monooleate by response surface methodology. *Biomass Bioenerg* **61**; 179–186.
- Fan, L., Luo, C., Sun, M., Li, X., Lu, F., Qiu, H. (2012). Preparation of novel magnetic chitosan/graphene oxide composite as effective adsorbents toward methylene blue. *Bioresour Technol*. **114**; 703-706.
- Ferraz, L.I., Possebom, G., Alvez, E.V., Cansian, R.L., et al. (2015). Application of home-made lipase in the production of geranyl propionate by esterification of geraniol and propionic acid in solvent-free system. *Biocatalysis and Agricultural Biotechnology*. **4**; 44-48.
- Ferreira, S.L., Bruns, R.E., Paranhos da Silva, E.G., et al. (2007a). Statistical designs and response surface techniques for the optimization of chromatographic systems. *Journal of Chromatography A*. **1158**; 2-14.

- Ferreira, S.L., Bruns, R.E., Ferreira, H.S., Matos, G.D., David, J.M. (2007b). Box- Behnken design: An alternative for the optimization of analytical methods. *Analytica Chimica Acta*. **597**; 179-186.
- Gandhi, M.R., Kosalya, G.N., Viswanathan, N., Meenakshi, S. (2011). Sorption behaviour of copper on chemically modified chitosan beads from aqueous solution. *Carbohydrate Polymers*. **83**; 1082-1087.
- Garcia, T., Sanchez, N., Martinez, M., Aracil, J. (1999). Enzymatic synthesis of fatty esters Part I. Kinetic approach. *Enzyme and Microbial Technology*. **25**; 584-590.
- Ge, H., Ma, Z. (2015). Microwave preparation of triethylenetetramine modified grapheneoxide/chitosan composite for adsorption of Cr(VI). *Carbohydrate Polymers*. **131**; 280-287.
- Gunawan, E.R., Basri, M., Abd Rahman, M.B., Salleh, A.B., Abd Rahman, R.N.Z. (2005). Study on response surface methodology (RSM) of lipase-catalyzed synthesis of palm-based wax ester. *Enzyme and Microbiology Technology*. **37**; 739-744.
- Guncheva, M., Zhiryakova, D. (2011). Catalytic properties and potential applications of *Bacillus* lipases. *Journal of Molecular Catalysis B: Enzymatic*. **68**; 1-21.
- Habulin, M., Sabeder, S., Paljevac, M., Primožic, M., Knez, Z. (2007). Lipase-catalyzed esterification of citronellol with lauric acid in supercritical carbon dioxide/co-solvent media. *J. of Supercritical Fluids*. **43**; 199-203.
- Habulin, M., Sabeder, S., Sampedro, M.A., Knez, Z. (2008). Enzymatic synthesis of citronellol laurate in organic media and in supercritical carbon dioxide. *Biochemical Engineering Journal*. **42**; 6-12.
- Hamze, H., Akia, M., Yazdani, F. (2015). Optimization of biodiesel production from the waste cooking oil using response surface methodology. *Process Safety and Environmental Protection*. **94**; 1-10.

- Han, D., Yan, L., Chen, W., Li, W. (2011). Preparation of chitosan/graphene oxide composite film with enhanced mechanical strength in the wet state. *Carbohydrate Polymers*. **83**; 653-658.
- Hasan, F., Shah, A.A., Hameed, A. (2006). Industrial applications of microbial lipases. *Enzyme and Microbial Technology*. **39**; 235-251.
- Hasan, F., Shah, A.A., Hameed, A. (2009). Methods for detection and characterization of lipases: A comprehensive review. *Biotechnology Advances*. **27**; 782-798.
- Hazime, R., Nguyen, Q.H., Ferronato, C., Huynh, T.K.X., Jaber, F., Chovelon, J.M. (2013). Optimization of imazalil removal in the system UV/TiO₂/K₂S₂O₈ using a response surface methodology (RSM). *Applied Catalysis B: Environmental*. **132-133**; 519-526.
- He, L., Wang, H., Xia, G., Sun, J., Song, R. (2014). Chitosan/graphene oxide nanocomposite films with enhanced interfacial interaction and their electrochemical applications. *Applied Surface Science*. **314**; 510-515.
- Hermanson, G.T. (1996). Zero-length cross-linkers. *Bioconjugate Techniques*. 169-186.
- Hibbert, D.B. (2012). Experimental design in chromatography: A tutorial review. *Journal of Chromatography B*. **910**; 2-13.
- Horchani, H., Chaïboune, M., Gargouri, Y., Sayari, A. (2010). Solvent-free lipase-catalyzed synthesis of long-chain starch esters using microwave heating: Optimization by response surface methodology. *Carbohydrate Polymers*. **79**; 466-474.
- Huang, D., Han, S., HAN, Z., Lin, Y. (2012). Biodiesel production catalyzed by *Rhizomucor miehei* lipase-displaying *Pichia pastoris* whole cells in an isooctane system. *Biochemical Engineering Journal*. **63**; 10-14.
- Iqbal, J., Wattoo, F.H., Wattoo, M.H., Malik, R., et al. (2011). Adsorption of acid yellow dye on flakes of chitosan prepared from fishery wastes. *Arabian Journal of Chemistry*. **4**; 389-395.

- Jaeger, K.E., Dijkstra, B.W. and Reetz, M.T. Bacterial biocatalysts: Molecular biology three-dimensional structures and biotechnological applications of lipases. (1996) *Annual Review Microbiology*. **53**; 315-351.
- Jayakumar, R., Prabakaran, M., Kumar, P.T., Nair, S.V., Tamura, H. (2011). Biomaterials based on chitin and chitosan in wound dressing application. *Biotechnology Advances*. **29**; 322-337.
- Ju, I.B., Lim, H., Jeon, W., Suh, D.J., Park, M., Suh, Y. (2011). Kinetic study of catalytic esterification of butyric acid and n-butanol over Dowex 50W x 8-400. *Chem. Eng.* **168**; 293–302.
- Juang, R.S., Wu, F.C., Tseng, R.L. (2001). Solute adsorption and enzyme immobilization on chitosan beads prepared from shrimp shell wastes. *Bioresource Technology*. **80**; 187-193.
- Kapoor, M., Gupta M.N. (2012). Obtaining monoglycerides by esterification of glycerol with palmitic acid using some high activity preparations of *Candida antarctica* lipase B. *Process Biochemistry*. **47**; 503-508.
- Khan, N.R. and Rathod, V.K. (2015). Enzyme catalyzed synthesis of cosmetic esters and its intensification: a review. *Process Biochemistry*. <http://dx.doi.org/10.1016/j.procbio.2015.07.014>.
- Khan, N.R., Jadhav, S.V., Rathod, V.K. (2015). Lipase catalysed synthesis of cetyl oleate using ultrasound: Optimisation and kinetic studies. *Ultrasonics Sonochemistry*. **27**; 522-529.
- Khemekhem, B., Fendri, I., Dahech, I., Belghuith, K., Kammoun, R., Mejdoub, H. (2013). Purification and characterization of a maltogenic amylase from Fenugreek (*Trigonella foenum graecum*) seeds using the Box Benken Design (BBD). *Industrial Crops and Products*. **43**; 334-339.
- Khodadoust, S., Ghedi, M. (2014). Application of response surface methodology for determination of methyl red in water samples by spectrophotometry method. *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy*. **133**; 87-92.

- Khuri, A.I., Mukhopadhyay, S. (2010). Response surface methodology. *WIREs Computational Statistics*. DOI: 10.1002/wics.73.
- Kocak, N., Sahin, M., Kucukkolbasi, S., Erdogan, Z.O. (2012). Synthesis and characterization of novel nano-chitosan Schiff base and use of lead (II) sensor. *International Journal of Biological Macromolecules*. **51**; 1159-1166.
- Krishna, S.H., Manohar, B., Divakar, S., Prapulla, S.G., Karanth, N.G. (2000). Optimization of isoamyl acetate production by using immobilized lipase from *Mucor miehei* by response surface methodology. *Enzyme and Microbial Technology*. **26**; 131-136.
- Kumar, D., Nagar, S., Bhushan, I., Kumar, L., Parshad, R., Gupta, V.K. (2013). Covalent immobilization of organic solvent tolerant lipase on aluminium oxide pellets and its potential application in esterification reaction. *Journal of Molecular Catalysis B: Enzymatic*. **87**; 51-61.
- Kumar, S., Koh, J. (2014). Physiochemical and optical properties of chitosan based graphene oxide bionanocomposite. *International Journal of Biological Macromolecules*. **70**; 559-564.
- Kumar, R., Singh, R., Kaur, J. (2014). Combinatorial reshaping of a lipase structure for thermostability: Additive role of surface stabilizing single point mutations. *Biochemical and Biophysical Research Communications*. **447**; 626-632.
- Kuo, C., Chen, G., Chen, C., Liu, Y., Shieh, C. (2014). Kinetics and optimization of lipase-catalyzed synthesis of rosefragrance 2-phenylethyl acetate through transesterification. *Process Biochemistry*. **49**; 437-444.
- Kuperkar, V.V., Lade, V.G., Prakash, A., Rathod, V.K. (2014). Synthesis of isobutyl propionate using immobilized lipase in a solvent free system: Optimization and kinetic studies. *Journal of Molecular Catalysis B: Enzymatic* **99**; 143-149.
- Kurtovic, I., Marshall, S.N., Miller, M.R., Zhao, X. (2011). Flavour development in dairy cream using fish digestive lipases from Chinook salmon (*Oncorhynchus tshawytscha*) and New Zealand hoki (*Macruronus novaezealandiae*). *Food Chemistry*. **127**; 1562-1568.

- Lau, S.C., Lim, H.N., Basri, M., Masoumi, H.R., Tajudin, A.A., et al. (2014). Enhanced biocatalytic esterification with lipase-immobilized chitosan/graphene oxide beads. *PLoS ONE* **9**(8): e104695. doi: 10.1371/journal.pone.0104695.
- Lee, D.G., Ponvel, K.M., Kim, M., Hwang, S., Ahn, I.S., Lee, C.H. (2009). Immobilization of lipase on hydrophobic nano-sized magnetite particles. *Journal of Molecular Catalysis B: Enzymatic*. **57**; 62-66.
- Li, C., Sun, J., Fu, C., Yu, B., Liu, S.Q., Li, T., Huang, D. (2014a). Synthesis and evaluation of odour-active methionyl esters of fatty acids via esterification and transesterification of butter oil. *Food Chemistry* **1**. **45**; 796-801.
- Li, X., Zheng, R., Ma, H., Huang, J., Zheng, Y. (2014b). Key residues responsible for enhancement of catalytic efficiency of *Thermomyces lanuginosus* lipase Lip revealed by complementary protein engineering strategy. *Journal of Biotechnology*. **188**; 29-35.
- Lim, H.N., Huang, N.M., Loo, C.H. (2012). Facile preparation of graphene-based chitosan films: Enhanced thermal, mechanical and antibacterial properties. *Journal of Non-crystalline Solids*. **358**; 525-530.
- Lin, J., Zhan, Y. (2012). Adsorption of humic acid from aqueous solution onto unmodified and surfactant-modified chitosan/zeolite composites. *Chemical Engineering Journal*. **200-202**; 202-213.
- Lin, R., Li, H., Long, H., Su, J., Huang, W., Wang, S. (2014). Optimization of lipase-catalyzed rosin acid starch synthesis by response surface methodology. *Journal of Molecular Catalysis B: Enzymatic*. **105**; 104-110.
- Liu, L., Li, C., Bao, C., Jia, Q., Xiao, P., Liu, X., Zhang, Q. (2012). Preparation and characterization of chitosan/graphene oxide composites for the adsorption of Au(III) and Pd(II). *Talanta*. **93**; 350-357.
- Liu, W., Yin, P., Zhang, J., Tang, Q., Qu, R. (2014). Biodiesel production from esterification of free fatty acid over PA/NaY solid catalyst. *Energy Conversion and Management*. **82**; 83-91.

- Liu, S., Kang, M., Yan, F., Peng, D., Yang, Y., et al. (2015). Electrochemical DNA biosensor based on microspheres of cuprous oxide and nano-chitosan for Hg(II) detection. *Electrochimica Acta*. **160**, 64-73.
- Lopresto, C.G., Calabro, V., Woodley, J.M., Tufvesson, P. (2014). Kinetic study of enzymatic esterification of octanoic acid and hexanol by immobilized *Candida antarctica* lipase B. *Journal of Molecular Catalysis B: Enzymatic*. **110**; 64-71
- Low, C.T., Mohamad, R., Tan, C.P., Long, K., Ismail, R., Lo, S.K., Lai, O.M. (2007). Lipase-catalyzed production of medium-chain triacylglycerols from palm kernel oil distillate: Optimization using response surface methodology. *Euro. J. Lipid Sci. Technol.* **109**; 107–119.
- Man, L., Yixin, G., Shanjing, Y. (2013). Optimization of DsbA Purification from Recombinant *Escherichia coli* Broth Using Box-Behnken Design Methodology. *Chinese Journal of Chemical Engineering*. **21**; 185-191.
- Masakapalli, K.S., Ritala, A., Dong, L., Krol, A.R., et al (2014). Metabolic flux phenotype of tobacco hairy roots engineered for increased geranoil production. *Phytochemistry*. **99**; 73-85.
- Mati-Baouche, N., Elchinger, P., Baynast, H.D., Pierre, G., Delattre, C., Michaud, P. (2014). Chitosan as an adhesive. *European Polymer Journal*. **60**; 198-213.
- Mendes, A.A., Castro, H.F., Andrade, G., Tardioli, P.W., Giordano, R. (2013). Preparation and application of epoxy-chitosan/alginate support in the immobilization of microbial lipases by covalent attachment. *Reactive & Functional Polymers*. **73**; 160-167.
- Mohamad, N.R., Marzuki, N.H., Buang, N.R., Huyop, F., Wahab, R.A. (2015a). An overview of technologies for immobilization of enzymes and surface analysis techniques for immobilized enzymes. *Biotechnology & Biotechnological Equipment*, DOI: 10.1080/13102818.2015.1008192.
- Mohamad, N.R., Buang, N.A., Mahat, N.A., Lok, Y.Y., et al. (2015b). A facile enzymatic synthesis of geranyl propionate by physically adsorbed *Candida rugosa* lipase onto multi-walled carbon nanotubes. *Enzyme and Microbial Technology*. **72**; 49-55.

- Mohamad, N.R., Buang, N.A., Mahat, N.A., Huyop, F., Jamalis, J., Aboul-Enein, H.Y., Abdul Wahab, R. (2015c). Simple adsorption of *Candida rugosa* lipase onto multi-walled carbon nanotubes for an economical and sustainable production of the flavor ester geranyl propionate. *Journal of Industrial and Engineering Chemistry*. DOI:10.1016/j.jiec.2015.08.001.
- Mohammadi, M., Habibi, Z., Dezvarei, S., Yousefi, M., Samadi, S., Ashjari, M. (2014). Improvement of the stability and selectivity of *Rhizomucor miehei* lipase immobilized on silica nanoparticles: Selective hydrolysis of fish oil using immobilized preparations. *Process Biochemistry*. **49**; 1314-1323.
- Motevalizadeh, S.F., Khoobi, M., Sadighi, A., Sedagheh, M.K., et al. (2015). Lipase immobilization onto polyethyleneimine coated magnetic nanoparticles assisted by divalent metal chelated ions. *Journal of Molecular Catalysis B: Enzymatic*. **120**; 75-83.
- Mounguengui, R.W., Brunshwig, C., Bar á, B., Villeneuve, P., Blin, J. (2013). Are plant lipases a promising alternative to catalyze transesterification for biodiesel production?. *Progress in Energy and Combustion Science*. **39**; 441-456.
- Nardini, M., Dijkstra, B.W. (1999). α/β hydrolase fold enzymes: the family keeps growing. *Current Opinion in Structural Biology*. **9**; 732-737.
- Ngah, W.S., Endud, C.S., Mayanar, R. (2002). Removal of copper (II) from aqueous solution onto chitosan and cross-linked chitosan beads. *Reactive & Functional Polymers*. **50**; 181-190.
- Ngah, W.S., Fathinathan, S. (2006). Chitosan flakes and chitosan-GLA beads for adsorption of *p*-nitrophenol in aqueous solution. *Colloids and Surfaces A: Physicochem Eng. Aspects*. **277**; 214-222.
- Nisha, S., Arun, K.S., Gobi, N. (2012). A review of methods, applications and properties of immobilized enzymes. *Chemical Science Reviews and Letters*. **1**; 148-155.

- Palla, C.A., Carrin, M.E. (2014). Kinetics modeling of the acidolysis with immobilized *Rhizomucor miehei* lipases for production of structured lipids from sunflower oil. *Biochemical Engineering Journal*. **90**; 184-194.
- Palla, C.A., Pacheco, C., Carrin, M.E. (2011). Preparation and modification of chitosan particles for *Rhizomucor miehei* lipase immobilization. *Biochemical Engineering Journal*. **55**; 199-207.
- Pan, Y., Wu, T., Bao, H., Li., L. (2011). Green fabrication of chitosan films reinforced with parallel aligned graphene oxide. *Carbohydrate Polymers*. **83**; 1908-1915.
- Park, S., Kim, S.H., Won, K., Choi, J.W., Kim, Y.W., et al. (2015). Wood mimetic hydrogel beads for enzyme immobilization. *Carbohydrate Polymers*. **115**; 223-229.
- Paroul, N., Grzegozeski, L.P., Chiaradia, V., Treichel, H., et al. (2010). Production of geranyl propionate by enzymatic esterification of geraniol and propionic acid in solvent-free system. *J Chem Technol Biotechnol*. **85**; 1636-1641.
- Patel, V., Gajera, H., Gupta, A., Manocha, L., Madamwar, D. (2015). Synthesis of ethyl caprylate in organic media using *Candida rugosa* lipase immobilized on exfoliated graphene oxide: Process parameters and reusability studies. **95**; 62-70.
- Paud ila-Rodriguez, A., Hernández-Viezcás, J.A., Peralta-Videa, J.R., et al. (2015). Synthesis of protonated chitosan flakes for the removal of vanadium(III, IV and V) oxyanions from aqueous solutions. *Microchemical Journal*. **118**; 1-11
- Pleiss, J., Fischer, M., Schmid, R.D. (1998). Analysis of lipase binding sites: the scissile fatty acid binding site. *Chemistry and Physics of Lipids*. **93**; 67-80.
- Pleiss, J., Fischer, M., Peiker, M., Thiele, C., Schmid, R.D. (2000). Lipase engineering data base understanding and exploiting sequence-structure-function relationships. *Journal of Molecular Catalysis B: Enzymatic*. **10**; 491-508.

- Poppe, J.K., Costa, A.P., Brasil, M.C., Rodrigues, R.C., Ayub, M.A. (2013). Multi point covalent immobilization of lipases on aldehyde-activated support: Characterization and application in transesterification reaction. *Journal of Molecular Catalysis B: Enzymatic*. **94**; 57-62.
- Qin, R., Li, R., Chen, M., Jiang, W. (2009). Preparation of chitosan–ethylenediaminetetraacetate-enwrapped magnetic CoFe₂O₄ nanoparticles via zero-length emulsion crosslinking method. *Applied Surface Science*. **256**; 27-32.
- Quiroga, A.D., Lehner, R. (2012). Liver triacylglycerol lipases. *Biochimica et Biophysica Acta*. **1821**; 762-769.
- Raghavendra, T., Basak, A., Manocha, L.M., Shah, A.R., Madamwar, D. (2013). Robust nanobioconjugates of *Candida antarctica* lipase B – Multiwalled carbon nanotubes: Characterization and application for multiple usages in non-aqueous biocatalysis. *Bioresource Technology*. **140**; 103-110.
- Raghavendra, T., Panchal, N., Divecha, J., Shah, A.D., Madamwar. (2014). Biocatalytic synthesis of flavor ester “pentyl valerate” using *Candida rugosa* lipase immobilized in microemulsion based organogels: Effect of parameters and reusability. *BioMed Research International*.
- Rahimi, M., Aghel, B., Alitabar, M., Sepahvand, A., Ghasempour, H.R. (2014). Optimization of biodiesel production from soybean oil in a microreactor. *Energy Conversion and Management*. **79**; 599-605.
- Ramani, K., Boopathy, R., Vidya, C., Kennedy, L.J., Velan, M., Sekaran, G. (2010). Immobilisation of *Pseudomonas gessardii* acidic lipase derived from beef tallow onto mesoporous activated carbon and its application on hydrolysis of olive oil. *Process Biochemistry*. **45**; 986-992.
- Ramezani, Z., Zarei, M., Raminnejad, N. (2015). Comparing the effectiveness of chitosan and nanochitosan coatings on the quality of refrigerated silver cap fillets. *Food Control*. **51**; 43-48.
- Ray, A. (2012). Application of lipase in industry. *Asian Journal of Pharmaceutical Technology* **2**; 33-37.

- Reis, P., Holmberg, K., Watzke, H., Leser, M.E., Miller, R. (2009). Lipases at interfaces: a review. *Advances in Colloid and Interface Science*. **147-148**; 237-250.
- Rodrigues, R.C., Fernandez-Lafuente, R. (2010). Lipase from *Rhizomucor miehei* as an industrial biocatalyst in chemical process. *Journal of Molecular Catalysis B: Enzymatic*. **64**; 1-22.
- Romdhane, I.B., Romdhane, Z.B., Gargouri, A., Belghith, H. (2011). Esterification activity and stability of *Talaromyces thermophilus* lipase immobilized onto chitosan. *Journal of Molecular Catalysis B: Enzymatic*. **68**; 230-239.
- Sakkas, V.A., Islam, M.A., Stalikas, C., Albanis, T.A. (2010). Photocatalytic degradation using design of experiments: A review and example of the Congo red degradation. *Journal of Hazardous Materials*. **175**; 33-44.
- Salihu, A., Alam, M.Z., Abdulkarim, M.I., Salleh, H.M. (2014). Esterification of butyl butyrate formation using *Candida cylindracea* lipase produced from palm oil mill effluent supplemented medium. *Arabian Journal of Chemistry*. **7**; 1159-1165.
- Santos, K.C., Cassimero, D.M., Avelar, M.H., Hirata, D.B., et al (2013). Characterization of the catalytic properties of lipases from plant seeds for the production of concentrated fatty acids from different vegetable oils. *Industrial Crops and Products*. **49**; 462-470.
- Sarkar, M., Majumdar, P. (2011). Application of response surface methodology for optimization of heavy metal biosorption using surfactant modified chitosan bead. *Chemical Engineering Journal*. **175**; 376-387.
- Shao, L., Chang, X., Zhang, Y., Huang, Y., Yao, Y., Zhanhu, G. (2013). Graphene oxide cross-linked chitosan nanocomposite membrane. *Applied Surface Science*. **280**; 989-992.
- Sharma, R., Chisti, Y., Banerjee, U.C. (2001). Production, purification, characterization and applications of lipases. *Biotechnology Advances*. **19**; 627-662.

- Singh, V., Joung, D., Zhai, L., Das, S., Khondaker, SI., Seal, S. (2011). Graphene based materials: Past, present and future. *Progress in Materials Science*. **56**; 1178-1271.
- Skoronski, E., Padoin N., Soares, C., Furigo, J.A. (2014). Stability of immobilized *Rhizomucor miehei* lipase for the synthesis of pentyl octanoate in a continuous packed bed bioreactor. *Brazilian Journal of Chemical Engineering*. **31(3)**; 633–641.
- Spahn, C., Minter, D. (2008). Enzyme immobilization in biotechnology. *Recent Patents on Engineering*. **2**; 195-200.
- Stamatis, H., Christakopoulos, P., Kekos, D., Macris, B.J., Kolisis, F.N. (1998). Studies on the synthesis of short-chain geranyl esters catalyzed by *Fussarium oxysporum* esterase in organic solvents. *Journal of Molecular Catalysis B: Enzymatic*. **4**; 229-236.
- Stergiou, P.Y., Foukis, A., Filippou, M., Koukouritaki, M., Parapouli, M., et al. (2013). Advances in lipase-catalyzed esterification reactions. *Biotechnology Advances*. **31**; 1846-1859 .
- Stobiecka, A. (2005). Acrylamide-quenching of *Rhizomucor miehei* lipase. *Journal of Photochemistry and Photobiology B: Biology*. **80**; 9-18.
- Suibramaniam, A., Kennel, S.J., Oden, P.I., Jacobson, K.B., Woodward, J., Doktycz, M.J. (1998). Comparison of techniques for enzyme immobilization on silicon supports.
- Sultania, M., Rai, J.S., Srivastava, D. (2011). Process modelling, optimization and analysis of esterification reaction of cashew nut shell liquid (CNSL)-derived epoxy resin using response surface methodology. *J Hazard Mater*. **185**; 1198-1204.
- Sun, J., Yu, B., Curran, P., Liu, S.Q. (2013). Lipase-catalysed ester synthesis in solvent-free oil system: Is it esterification or transesterification?. *Food Chemistry*. **141**; 2828-2832.

- Sundramoorthy, A.K., Gunasekaran, S. (2014). Applications of graphene in quality assurance and safety of food. *Trends in Analytical Chemistry*. **60**; 36-53.
- Svendsen, A. (2000). Lipase protein engineering. *Biochimica et Biophysica Acta*. **1543**; 223-238.
- Sureshkumar, R.S., Dhivya, C., Dhamodaran, S., Narasimhan, S. (2012). Design, synthesis, and evaluation of geraniol esters against the inflammation drug target protein TNF- α . *International Journal of Current Research*. **4**; 40-44.
- Tan, T., Lu, J., Nie, K., Deng, L., Wang, F. (2010). Biodiesel production with immobilized lipase: A review. *Biotechnology Advances*. **28**; 628-634.
- Tang, C., Saquing, C.D., Sarin, P.K., Kelly, R.M., Khan, S.A. (2014). Nanofibrous membranes for single-step immobilization of hyperthermophilic enzymes. *Journal of Membrane Science*. **472**; 251-260.
- Trani, M., Ergan, F., Andre, G. (1991). Lipase-catalyzed production of wax esters. *Journal of the American Oil chemists Society*. **68**; 20-22.
- Tripathy, P., Srivastava, V.C., Kumar, A. (2009). Optimization of an azo dye batch adsorption parameters using Box–Behnken design. *Desalination*. **249**; 1273-1279.
- Tural, B., Tarhan, T., Tural, S. (2014). Covalent immobilization of benzoylformate decarboxylase from *pseudomonas putida* on magnetic epoxy support and its carboligation reactivity. *Journal of Molecular Catalysis B: Enzymatic*. **102**; 188-194.
- Vakili, M., Rafatullah, M., Salamatinia, B., Abdullah, A.Z., et al. (2014). Application of chitosan and its derivatives as adsorbent for dye removal from water and waste water: A review. *Carbohydrate Polymers*. **113**; 115-130.
- Vakili, M., Rafatullah, M., Salamatinia, B., Ibrahim, M.H., Abdullah, A.Z. (2015). Elimination of reactive blue 4 from aqueous solutions using 3-aminopropyl triethoxysilane modified chitosan beads. *Carbohydrate Polymers*. **132**; 89-96.

- Vashist, S.K., Zheng, D., Al-Rubeaan, K., Luong, J.H.T., Sheu, F.S. (2011). Advances in carbon nanotube based electrochemical sensors for bioanalytical applications. *Biotechnology Advances*. **29**; 169-188.
- Villeneuve, P., Muderhwa, J.M., Graille, J., Haas, M.J. (2000). Customizing lipases for biocatalysis: a survey of chemical, physical and molecular biological approaches. *Journal of Molecular Catalysis B: Enzymatic*. **9**; 113-148.
- Wahab, R.A., Basri, M., Rahman, R.N., Salleh, A.B., et al. (2014). Enzymatic production of a solvent-free menthyl butyrate via response surface methodology catalyzed by a novel thermostable lipase from *Geobacillus Zalihae*. *Biotechnology & Biotechnological Equipment*, DOI: 10.1080/13102818.2014.978220.
- Wang, J., Zhao, G., Jing, L., Peng, X., Li, Y. (2015). Facile self-assembly of magnetite nanoparticles on three-dimensional graphene oxide–chitosan composite for lipase immobilization. *Biochemical Engineering Journal*. **98**; 75-83.
- Watthanaphanit, A., Supaphol, P., Tamura, H., Tokura, S., Rujiravanit, R. (2010). Wet-spun alginate/chitosan whiskers nanocomposite fibers: Preparation, characterization and release characteristic of the whiskers. *Carbohydrate Polymers*. **79**; 738-746.
- Wei, F., Jiang, X., Lu, Y., Hou, M., Lin, S., Geng, Z. (2015). Effects of surfactants on graphene oxide nanoparticles transport in saturated porous media Effects of surfactants on graphene oxide nanoparticles transport in saturated porous media. *Journal of Environmental Sciences*. **35**; 12-19.
- Worzakowska, M. (2014). TG/FTIR/QMS studies of long chain esters of geraniol. *Journal of Analytical and Applied Pyrolysis*. **110**; 181-193.
- Yadav, G.D. and Devi, K.M. (2004). Immobilized lipase-catalysed esterification and transesterification reactions in non-aqueous media for the synthesis of tetrahydrofurfuryl butyrate: comparison and kinetic modeling. *Chemical Engineering Science*. **59**; 373-383.

- Yadav, G.D. and Lathi, P.S. (2004). Synthesis of citronellol laurate in organic media catalyzed by immobilized lipases: kinetic studies. *Journal of Molecular Catalysis B: Enzymatic*. **27**; 113–119.
- Yadav, M. and Ahmad, S. (2015). Montmorillonite/graphene oxide/chitosan composite: Synthesis, characterization and properties. *International Journal of Biological Macromolecules*. **70**; 923-933.
- Yahya, A.R., Anderson, W.A., Moo-Young, M. (1998). Esther synthesis in lipase catalyzed reactions. *Enzyme and Microbial Technology*. **23**; 438-450.
- Yang, H.C., Wang, W.H., Huang, K.S., Hon, M.H. (2010). Preparation and application of nanochitosan of finishing treatment with anti-microbial and anti-shrinking properties. *Carbohydrate Polymers*. **79**; 176-179.
- Ye, N., Xie, Y., Shi, P., Gao, T., Ma, J. (2014). Synthesis of magnetite/graphene oxide/chitosan composite and its application for protein adsorption. *Materials Science and Engineering C*. **45**; 8-14.
- Yildirim, D., Tükel, S.S., Alptekin, Ö., Alagöz, D. (2014). Optimization of immobilization conditions of *Mucor miehei* lipase onto Florisil via polysuccinimide spacer arm using response surface methodology and application of immobilized lipase in asymmetric acylation of 2-amino-1-phenylethanols. *Journal of molecular catalysis B: Enzymatic*. **100**; 91-103.
- Yilmaz, E., Can, K., Sezgin, M., Yilmaz, M. (2011). Immobilization of *Candida rugosa* lipase on glass beads for enantioselective hydrolysis of racemic Naproxen methyl ester. *Bioresource Technology*. **102**; 499-506.
- Yin, P., Chen, L., Wang, Z., Qu, R., Liu, X., Ren, S. (2012a). Production of biodiesel by esterification of oleic acid with ethanol over organophosphonic acid-functionalized silica. *Bioresource Technology*. **110**; 258-263.
- Yin, P., Chen, L., Wang, Z., Qu, R., Liu, X., Xu, Q., Ren, S. (2012b). Biodiesel production from esterification of oleic acid over aminophosphonic acid resin D418. *Fuel*. **102**; 499-505.

- Yin, P., Chen, W., Liu, W., Chen, H., et al. (2013). Efficient bifunctional catalyst lipase/organophosphonic acid-functionalized silica for biodiesel synthesis by esterification of oleic acid with ethanol. *Bioresource Technology*. **140**; 146-151.
- You, P., Su, E., Yang, X., Mao, D., Wei, D. (2011). *Carica papaya* lipase-catalyzed synthesis of terpene esters. *Journal of molecular catalysis B: Enzymatic*. **71**; 152-158.
- Zhang, D.H., Bai, S., Ren, M.Y., Sun, Y. (2008). Optimization of lipase-catalyzed esterification of (\pm) – menthol in ionic liquid. *Food Chemistry*. **109**; 72-80.
- Zhao, H., Liu, J., Lv, F., Ye, R., Bie, X., Zhang, C., Lu, Z. (2014). Enzymatic synthesis of lard-based ascorbyl esters in a packed-bed reactor: Optimization by response surface methodology and evaluation of antioxidant properties. *LWT – Food Science and Technology*. **57**; 393-399.
- Zhao, X., Qi, F., Yuan, C.L., Du, W., Liu, D. (2015). Lipase-catalyzed process for biodiesel production: Enzyme immobilization, process simulation and optimization. *Renewable and Sustainable Energy Reviews*. **44**; 182-197.
- Zhou, J., Wang, C., Yoon, S.H., Jang, H.J., et al. (2014). Engineering *Escherichia coli* for selective geraniol production with minimized endogenous dehydrogenation. *Journal of Biotechnology*. **169**; 42-50.
- Zivkovic, L.T., Zivkovic, L.S., Babic, M.B., Kokunesoski, M.J., et al. (2015). Immobilization of *Candida rugosa* lipase by adsorption onto biosafe meso/macroporous silica and zirconia. *Biochemical Engineering Journal*. **93**; 73-83.
- Zoupanionti, M., Stamatis, H., Xenakis, A. (2010). Microemulsion-based organogels as matrices for lipase immobilization. *Biotechnology Advances*. **28**; 395-406.
- Zysk, M., Zadlo, A., Brodza, A., Wisniewska, C., Ostaszewski, R. (2014). The unexpected kinetic effect of enzyme mixture: The case of enzymatic esterification. *Journal of Molecular Catalysis B: Enzymatic*. **102**; 225-229