FIFTEENTH ANNUAL CONFERENCE

# **YUCOMAT 2013**

Hunguest Hotel Sun Resort Herceg Novi, Montenegro, September 2-6, 2013 http://www.mrs-serbia.org.rs

## Programme and The Book of Abstracts

Organised by: Materials Research Society of Serbia

under the auspices of Federation of European Material Societies and Materials Research Society

Title:	THE FIFTEENTH ANNUAL CONFERENCE YUCOMAT 2013 Programme and The Book of Abstracts
Publisher:	Materials Research Society of Serbia Knez Mihailova 35/IV, 11000 Belgrade, Serbia Phone: +381 11 2185-437; Fax: + 381 11 2185-263 http://www.mrs-serbia.org.rs
Editors:	Prof. Dr. Dragan P. Uskoković and Prof. Dr. Velimir Radmilović
Technical editor:	Aleksandra Stojičić

Cover page: Aleksandra Stojičić and Milica Ševkušić

Copyright © 2013 Materials Research Society of Serbia

#### Acknowledgments:



Printed in:Biro Konto<br/>Sutorina bb, Igalo – Herceg Novi, Montenegro<br/>Phones: +382-31-670123, 670025, E-mail: bkonto@t-com.me<br/>Circulation: 220 copies. The end of printing: August 2013

P.S.B.18.

### INFLUENCE OF M0O3 ON CORDIERITE CERAMICS SINTERING AND CRYSTALLIZATION

N. Djordjević<sup>1</sup>, A. Mihajlović<sup>2</sup>, <u>A. Peleš</u><sup>3</sup>, N. Obradović<sup>3</sup>, V. Pavlović<sup>3</sup>

<sup>1</sup>Institute for Technology of Nuclear and Other Mineral Raw Materials, Belgrade, Serbia, <sup>2</sup>Institute of Nuclear Sciences Vinča, University of Belgrade, Belgrade, Serbia, <sup>3</sup>Institute of Technical Sciences of SASA, Belgrade, Serbia

The influence of MoO<sub>3</sub> on the process of cordierite ceramics preparation,  $2MgO-2Al_2O_3-5SiO_2$  (MAS) was researched by sintering followed binary systems:  $MgO/MoO_3$  (sintered at 850 °C and 1000 °C),  $Al_2O_3/Bi_2O_3$  and  $SiO_2/Bi_2O_3$  (sintered at 850 °C and 1000 °C). Composition of these systems was 80 % of oxide and 20 % MoO<sub>3</sub>. The effects of sintering, the composition and morphology were followed by x-ray diffraction, scanning electron microscopy and EDS analysis. It has been found that MoO<sub>3</sub>, beside liquid phase, forms intermediary unstable compounds with MgO and  $Al_2O_3$ . The following research is planned to investigate the effect of 5 % mass of MoO<sub>3</sub> on the electrical properties of cordierite ceramics.

#### P.S.B.19. INFLUENCE OF ONE ACTIVATED COMPONENT ON THE SINTERING PROCESS OF THREE PHASE SYSTEM

<u>N. Obradović</u><sup>1</sup>, A. Peleš<sup>1</sup>, N. Djordjević<sup>2</sup>, S. Marković<sup>1</sup>, M. Mitrić<sup>3</sup>, V. Pavlović<sup>1</sup> <sup>1</sup>Institute of Technical Sciences of SASA, Belgrade, Serbia, <sup>2</sup>Institute for Technology of Nuclear and Other Raw Mineral Materials, Belgrade, Serbia, <sup>3</sup>Institute of Nuclear Sciences Vinča, University of Belgrade, Belgrade, Serbia

According to its low temperature thermal expansion coefficient, low dielectric constant, also good mechanical properties, cordierite,  $2MgO \cdot 2Al_2O_3 \cdot 5SiO_2$ , represents a very attractive high-temperature ceramic material. In this study, cordierite was prepared by solid state reaction of the MgO,  $Al_2O_3$  and  $SiO_2$  mixture. One of the components from the mixture,  $SiO_2$ , was mechanically activated in a high energy ball mill during 5 and 10 minutes. The applied pressure before the sintering process was 2 t/cm<sup>2</sup>. Sintering process of mixtures containing non-activated and activated  $SiO_2$  powder was performed at 1350 °C for 4h in the air atmosphere. The phase composition of starting oxides and sintered samples was analyzed by the X-ray diffraction method. Particle size analysis was performed to investigate the differences between starting components and sintered samples. This paper investigates the influence of one mechanically activated  $SiO_2$  component on the densities of green bodies as well as on the sintered samples, along with electrical properties of cordierite ceramics.