

ELEVENTH ANNUAL CONFERENCE

, citation and similar papers at core.ac.uk

brought to y

provided by Serbian Academy of Science and Arts Dig

YUCOMAT 2009

Hotel "Plaža", Herceg Novi, Montenegro, August 31 - September 4, 2009
<http://www.mrs-serbia.org.rs>

Programme and The Book of Abstracts

Organised by:
Materials Research Society of Serbia,
and
**Institute of Technical Sciences of the
Serbian Academy of Sciences and Arts, Belgrade**

under the auspices of
Federation of European Material Societies
and
Materials Research Society

Title: THE ELEVENTH ANNUAL CONFERENCE
“YUCOMAT 2009”
Programme and The Book of Abstracts

Publisher: Institute of Technical Sciences of the Serbian Academy of Sciences & Arts
Knez Mihailova 35/IV; P.O. Box 377, 11000 Belgrade, Serbia
Phone: +381 11 2185-437; Fax: + 381 11 2185-263
<http://www.itn.sanu.ac.rs>

Editor: Prof. Dr. Dragan P. Uskoković

Technical editor: Aleksandra Stojičić

Cover page: Aleksandra Stojičić and Milica Ševkušić

Copyright © 2009 Institute of Technical Sciences of the Serbian Academy of Sciences & Arts

Acknowledgment:

The logo for 'nanopaprika.eu' features the text 'nanopaprika.eu' in a stylized, white, outlined font on a black rectangular background.

Printed in: Printing office “Čigoja”
Studentski trg 15, 11000 Belgrade
Phones: + 381 11 2186-725; + 381 11 625-954
Circulation: 300 copies. The end of printing: July 2009.

ISBN 978-86-80321-18-9



CIP – Каталогizacija u publikaciji
Nародна библиотека Србије, Београд

66.017/.018(048)

MATERIALS Research Society (Beograd).
Conference (11 ; 2009 ; Herceg Novi)
Programme ; and The Book of Abstracts /
Eleventh Annual Conference YUCOMAT 2009,
organized by Materials Research Society of
Serbia and Institute of Technical Sciences of
the Serbian Academy of Sciences and Arts,
Belgrade ; [editor Dragan P. Uskoković]. –
Belgrade : Institute of Technical Sciences of
SASA, 2009 (Belgrade : Čigoja).– L, 219 str.
; 24 cm

Tiraž 300. – Registar.

ISBN 978–86–80321–18–9

1. Materials Research Society (Beograd) 2.
Institute of Technical Sciences of SASA
(Beograd)

a) Наука о материјалима – Апстракти b)
Технички материјали – Апстракти
COBISS.SR-ID 168339724

P.S.A.14.

**KINETICS OF THE HYDROGEN OXIDATION ON Pt MODIFIED MoO_x
NANO-SIZED CATALYST IN THE PRESENCE OF CARBON MONOXIDE**

N.V. Krstajić¹, N. Elezović², Lj.M. Vračar¹, Lj. Gajić-Krstajić³, V.R. Radmilović⁴

¹Faculty of Technology and Metallurgy, University of Belgrade, Belgrade, Serbia, ²Institute for Multidisciplinary Research, Belgrade, ³Institute of Technical Science, SASA, Belgrade, Serbia,

⁴National Center for Electronic Microscopy, LBLN, Berkeley, USA

Due to the importance of the HOR in fuel-cells technology, various Pt-based catalysts have been examined from the viewpoint of immunity of the electrocatalysis of the HOR from CO-poisoning of the anode catalysts. An appreciable improvement of the CO tolerance has been found at Pt with adatoms such as Ru, Sn [1,2], Pt-M (M=Ru, Rh, Os, W Sn) [3-5] based alloys, and Pt with oxides (RuO_xH_y) [6].

In the present work, the electrocatalytic of home made highly dispersed nano-sized MoO_x-Pt/C catalysts prepared by the polyole method combined by MoO_x post-deposition was investigated in the presence of CO, in 0.5 moldm⁻³ HClO₄ solution. The partial pressure of CO in CO/H₂ gas mixture was 100 ppm.

Carbon monoxide was adsorbed on the RDE for various time interval with keeping the potential at 0.05 V (RHE). The coverage of CO was determined by applying the first potential sweep (from 0.04 to 1.20 V), in N₂ saturated solution at potential scan rate of 0.1 Vs⁻¹ and compared it with the sweep on the clean electrode, by measuring the decrease in the hydrogen desorption charge, ΔQ_H .

MoO_x(20%)Pt/C catalyst exhibits an excellent CO tolerance, as it was found that the reduction in kinetic current, I_k , is negligible even at $\theta_{CO} = 0.46$. It was found for this catalyst too, that the CO adsorption rate was much slower than that of Pt and the Pt sites for HOR were not so rigidly blocked by adsorbed CO partially due to its enhanced mobility, resulting from their modified electronic structure of surface Pt sites. Voltammetric studies suggest that an excellent CO tolerance of this catalyst could be also result of the oxidation of adsorbed CO to CO₂ by oxophilic MoO_x species at low overpotentials by a redox-mediated mechanism.

References:

- [1] S.J.Lee, D.Mukerjee, E.A.Ticianelli, J.McBreen, *Electrochim.Acta*, 44 (1999) 3283.
- [2] H.Gasteiger, N.Marković, P.Ross, *J.Phys.Chem.*, 99 (1995) 8945.
- [3] H.Uchida, K.Izumi, M.Watanabe, *J.Phys.Chem. B* 110 (2006) 21924.
- [4] E.Leiva, T.Iwasita, E.Herrero, J.M.Feliu, *Langmuir* 13 (1997) 6287.
- [5] V.Clement, E.Herrero, J.M.Feliu, *Electrochim.Acta* 44 (1998) 1403.
- [6] W.Sugimoto, T.Saida, Y.Takasu, *Electrochem.Comm.*,