



UNIVERSITI PUTRA MALAYSIA

**SYNTHESIS, CHARACTERIZATION AND ANTIBACTERIAL
PROPERTIES OF SILVER NANOPARTICLES IN CLAY AND
ORGANIC POLYMERS AS NANOCOMPOSITES**

KAMYAR SHAMELI

FS 2011 11

**SYNTHESIS, CHARACTERIZATION AND ANTIBACTERIAL
PROPERTIES OF SILVER NANOPARTICLES IN CLAY AND ORGANIC
POLYMERS AS NANOCOMPOSITES**

By

KAMYAR SHAMELI

**Thesis Submitted to the School Of Graduate Studies, Universiti Putra Malaysia,
in Fulfilment of the Requirements for the Degree of
Doctor of Philosophy**

April 2011



Abstract of thesis presented to the senate of University Putra Malaysia in fulfilment of the requirement for the degree of Doctor of Philosophy.

**SYNTHESIS, CHARACTERIZATION AND ANTIBACTERIAL
PROPERTIES OF SILVER NANOPARTICLES IN CLAY AND ORGANIC
POLYMERS AS NANOCOMPOSITES**

By

KAMYAR SHAMELI

April 2011

Chairman : Associate Professor Mansor bin Hj Ahmad @ Ayob, PhD

Faculty : Science

In this study, silver nanoparticles (Ag NPs) with the small size (2.12–30.63 nm) were successfully synthesized in the lamellar space of montmorillonite (MMT), montmorillonite/chitosan (MMT/Cts), porous zeolite framework and external surface layer of talc by chemical reducing agent in the absence of heat treatment. The most favourable experimental condition for the synthesis of Ag NPs in the MMT, talc, zeolite nanocomposites (NCs) and silver/montmorillonite/chitosan bionanocomposites (Ag/MMT/Cts BNCs) are described in terms of the initial concentrations of AgNO₃. The mean diameters and standard deviation of Ag NPs in all of solid supports increased gradually with the increase of silver ions concentration. The external morphologies indicate that there are no noteworthy morphological distinctions between solid substrates and Ag NPs incorporated to them. The Ag NPs by the physical synthetic route were synthesized in the lamellar space of MMT/Cts utilising the UV-irradiation reduction method in the absence of



reducing agent or heat treatment. The properties of Ag/MMT/Cts BNCs were studied as the function of UV-irradiation times. UV-irradiation disintegrated the Ag NPs into smaller size until a relatively stable size and size distribution were achieved. The silver nanocrystals were also synthesized by another physical method into the interlamellar space of MMT by using γ -irradiation in the absence of reducing agent or heat treatment. The properties of Ag/MMT NCs and the diameters of Ag NPs were studied as a function of γ -irradiation doses. The results from the UV-visible spectroscopy and TEM demonstrated that increasing the γ -irradiation doses enhanced the concentration of Ag NPs. In addition, the particle size of Ag NPs gradually increased from 1 until 20 kGy. When the γ -irradiation doses increased from 20 to 40 kGy, the particle diameters decreased suddenly as a result of the induced fragmentation for Ag NPs. Moreover silver/poly(lactic acid) nanocomposites (Ag/PLA NCs) films were investigated, while Ag NPs were synthesized into the biodegradable PLA as a polymeric matrix and stabilizer in the presence of sodium borohydride as a chemical reduction agent in diphasic solvent. In all preparation, MMT, talc and zeolite were used as the inorganic solid supports and poly(lactic acid) was used as organic polymeric matrix. The silver nitrate, chitosan, and sodium borohydride were used as the silver precursor, natural and biodegradable polymeric stabilizer, and the reduction agent respectively. The crystalline structure of Ag NPs for all of samples, average size and size distributions, surface plasmon resonance, surface morphology, and functional groups were studied using X-ray diffraction (XRD), transmission electron microscopy (TEM), UV-visible spectroscopy (UV-vis), scanning electron microscopy (SEM) and Fourier transform infrared (FT-IR) respectively. The XRD analysis confirmed that the crystallographic planes of the silver crystals were the face-centred cubic (fcc) types. The UV-visible absorption

spectra showed the peaks characteristic of the surface plasmon resonance (SPR) bands of Ag NPs. The antibacterial activities of Ag NPs were investigated against Gram-negative and Gram-positive bacteria by the disk diffusion method using Mueller-Hinton Agar (MHA) at different sizes and amounts of Ag NPs. Results show that the antibacterial activity of Ag NPs can be modified with the particle size of Ag NPs.

Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia sebagai memenuhi keperluan untuk ijazah Doktor Falsafah

**SINTESIS, PENCIRIAN DAN ANTIBAKTERI SIFAT-SIFAT
NANOKOMPOSIT NANOZARAH PERAK DI DALAM POLIMER
ORGANIK DAN TAK ORGANIK**

Oleh

KAMYAR SHAMELI

April 2011

Pengerusi : Profesor Madya Mansor bin Hj Ahmad @ Ayob, PhD

Fakulti : Sains

Dalam kajian ini, nanozarah perak (Ag NPs) bersaiz kecil berjaya disintesis dalam ruangan pipih montmorilonit (MMT), montmorillonit/kitosan (MMT/Cts), rangka zeolit berliang dan lapisan permukaan luar talk dengan agen penurun kimia tanpa rawatan pemanasan. Keadaan percubaan yang paling sesuai untuk sintesis Ag NP dalam MMT, talk, nanokomposit zeolit (NCs) dan bionanokomposit perak/montmorilonit/kitosan (Ag/MMT/Cts BNCs) dijelas berdasarkan kepekatan awal AgNO₃. Purata diameter dan sisihan piawai Ag NPs di semua sokongan pepejal meningkat secara berperingkat dengan peningkatan kepekatan ion perak. Morfologi luaran menunjukkan bahawa tidak ada perbezaan morfologi penting antara substrat pepejal dan Ag NPs yang dimasukkan ke dalam mereka. Hablur perak dengan laluan sintetik hijau fizikal disintesis dalam ruangan pipih MMT/Cts dengan menggunakan kaedah penurunan UV-penyinaran tanpa agen penurun atau rawatan pemanasan. Sifat Ag/MMT/Cts BNCs dikaji sebagai fungsi tempoh masa UV- penyinaran. UV-

penyinaran menghancurkan Ag NPs ke saiz yang lebih kecil sehingga ke paras yang relatif stabil dan pengedaran saiz telah dicapai. Nanokristal perak juga disintesis dengan kaedah fizikal yang lain dalam ruangan antara pipih MMT dengan menggunakan γ - penyinaran tanpa agen penurun atau rawatan pemanasan. Sifat Ag/MMT NCs dan diameter Ag NPs dikaji sebagai fungsi dos γ - penyinaran. Keputusan spektroskopi UV-tampak dan TEM menunjukkan bahawa peningkatan dos γ -iradiasi meningkatkan kepekatan Ag NPs. Selain itu, saiz zarah Ag NPs meningkat secara perlahan-lahan dari 1 hingga 20 kGy. Apabila dos γ -iradiasi meningkat dari 20 hingga 40 kGy, diameter zarah menurun secara mendadak akibat fragmentasi Ag NPs. Tambahan pula, kepingan nanokomposit perak/poli(asid laktat) (Ag/PLA NCs) juga dikaji, sementara Ag NPs disintesis dalam PLA terbiodegradasi sebagai matriks polimer dan penstabil dengan kehadiran borohidrida natrium sebagai agen penurun kimia di dalam pelarut dwifasa. Dalam kesemua penyediaan, MMT, talk dan zeolit digunakan sebagai sokongan pepejal tak organik dan poli(asid laktat) digunakan sebagai matrik polimer organik. Perak nitrat, kitosan dan borohidrida natrium digunakan sebagai prekursor perak, semula jadi dan penstabil polimer terbiodegradasi, dan agen penurunan masing-masing. Struktur hablur Ag NPs untuk kesemua sampel, purata saiz dan saiz edaran, resonans permukaan plasmon, morfologi permukaan, dan kumpulan-kumpulan berfungsi dikaji dengan menggunakan belauan sinar-X (XRD), mikroskopi penghantaran elektron (TEM), spektroskopi UV-tampak (UV-vis), mikroskopi imbasan elektron (SEM) dan infra-merah jelmaan fourier (FT-IR). Analisis XRD menegaskan bahawa bidang kristalografi dari kristal perak adalah jenis kubus berpusat muka (fcc). Spektrum serapan UV-tampak menunjukkan puncak ciri-ciri permukaan plasmon resonan (SPR) Ag NPs. Aktiviti antibakteria Ag NPs diselidik terhadap bakteria Gram-

negatif dan Gram-positif dengan kaedah pembauran cakera dengan menggunakan Mueller-Hinton Agar (MHA) pada pelbagai saiz dan kuantiti Ag NPs. Keputusan kajian menunjukkan bahawa aktiviti antibakteria Ag NPs boleh diubahsuai dengan saiz zarah Ag NPs.

ACKNOWLEDGEMENTS

At first I want to thank Allah for all of things that he has given in my life and then I offer my sincerest gratitude to my chairman, Associate Professor Dr. Mansor Bin Ahmad who has supported me throughout my thesis from the initial to the final level with his patience and knowledge whilst allowing me the room to work in my own way. I would like to express my deep and sincere gratitude to my co-supervisor, Professor Dr. Wan Md Zin Wan Yunus. His wide knowledge and his logical way of thinking have been of great value for me. His encouraging, detailed and constructive comments have enabled me to develop an understanding of the subject. I am also grateful to Dr. Nor Azowa Ibrahim for serving in the supervisory committee.

I owe great thanks to my precious parents, my dearest mother Ruhangiz Sifolahzadeh and my darling father Iraj Shameli, for all things that they gave me or taught me. Without their encouragements, understandings and also for financial and spiritual supporting I would never have made any success and also it would have been impossible for me to finish this work. I owe special thanks to my dear's wife Dr. Parvaneh Shabanzade and my sweetheart daughter and son Armita and Artin for all their helping in during my study and writing thesis, without them I would never able to finish my PhD.

I owe my loving thanks to my dear sisters and darling brother, for their loving supports and personal guidance.



I certify that Examination Committee has met on date of viva voce to conduct the final examination of Kamyar Shameli on her Degree of Doctor of Philosophy thesis entitled “Synthesis, characterization and properties of silver nanoparticles in inorganic and organic polymer nanocomposites” in accordance with Universiti Pertanian Malaysia (Higher Degree) Act 1980 and Universiti Pertanian Malaysia (Higher Degree) Regulations 1981. The Committee recommends that the student be awarded the Degree of Doctor of Philosophy.

Member of the Examination committee were as follows

MOHD ASPOLLAH HJ. MD. SUKARI, PhD

Professor
Faculty of Science
Universiti Putra Malaysia
(Chairman)

ANUAR KASSIM, PhD

Professor
Faculty of Science
Universiti Putra Malaysia
(Internal Examiner)

MOHAMAD ZAKI AB. RAHMAN, PhD

Associate Professor
Faculty of Science
Universiti Putra Malaysia
(Internal Examiner)

BETTAHAR, PhD

Professor
Faculty Des Science
University Hendri Poincare
(External Examiner)

HASANAH MOHD GHAZALI , PhD

Professor and Dean
School of Graduate Studies
Universiti Putra Malaysia

Date:



This thesis was submitted to the Senate of Universiti Putra Malaysia and has been accepted as fulfilment of the requirement for the degree of Doctor of Philosophy. The members of Supervisory committee were as follows:

Mansor Bin Ahmad, PhD

Associate Professor
Faculty of Science
Universiti Putra Malaysia
(Chairman)

Wan Md Zin Wan Yunus, PhD

Professor
Faculty of Science
Universiti Putra Malaysia
(Member)

Nor Azowa Ibrahim, PhD

Senior lecturer
Faculty of Science
Universiti Putra Malaysia
(Member)

HASANAH MOHD GHAZALI, PhD

Professor and Dean
School of Graduate Studies
Universiti Putra Malaysia

Date:



DECLARATION

I hereby declare that the thesis is my original work except for quotations and citations which have been duly acknowledged. I also declare that it has not been previously, and it is not concurrently, submitted for any other degree at University Putra Malaysia or at any institutions.

KAMYAR SHAMELI

Date: 8 April 2011



TABLE OF CONTENTS

	Page
ABSTRACT	ii
ABSTRAK	v
ACNOWLEDGEMENTS	viii
APPROVAL	ix
DECLARATION	xi
LIST OF TABLES	xvii
LIST OF FIGUERS	xviii
LIST OF ABBREVIATIONS	xxiv
CHAPTER	
1 INTRODUCTION	1
1.1 Background of the Study	1
1.2 Research Approach	4
1.3 Objectives	5
1.4 Format of the Thesis	6
2 LITERATURE REVIEWS	7
2.1 Silver Nanoparticles	7
2.2 Synthesis of Silver Nanoparticles	8
2.2.1 Chemical Methods	8
2.2.2 Physical Methods	11
2.3 Silver Nanoparticles Incorporated in the Clays and Zeolite Nanocomposites	15
2.3.1 Montmorillonite Structure	17
2.3.2 Talc Structure	19
2.3.3 Zeolite Structure	20
2.4 Silver Nanoparticles Incorporated in the Polymer Nanocomposites	22
2.4.1 Poly (lactic acid)/Silver Nanoparticles	24
2.4.2 Chitosan/Silver Nanoparticles	26
2.5 Characterization of Silver Nanoparticles	27
2.6 Application of Silver Nanoparticles	28
2.7 Antibacterial Activity of Silver Nanoparticles	29
2.8 Effect of Size and Shape on the Antibacterial Activity of Nanoparticles	30



3	SILVER/MONTMORILLONITE NANOCOMPOSITES: SYNTHESIS AND CHARACTERIZATION AND THEIR ANTIBACTERIAL ACTIVITY	32
3.1	Introduction	32
3.2	Materials and Methods	34
3.2.1	Materials	34
3.2.2	Methods	34
3.3	Results and Discussion	37
3.3.1	UV-visible Spectroscopy	39
3.3.2	Powder X-ray Diffraction	40
3.3.3	Morphology	42
3.3.4	FT-IR Chemical Analysis	44
3.3.5	Inductively Coupled Plasma-Optical Emission Spectroscopy	46
3.3.6	Antibacterial Activity	47
3.4	Conclusion	49
4	SYNTHESIS AND CHARACTERIZATION OF SILVER/TALC NANOCOMPOSITES USING CHEMICAL REDUCTION METHOD	51
4.1	Introduction	51
4.2	Materials and Methods	52
4.2.1	Materials	52
4.2.2	Methods	53
4.3	Results and Discussion	54
4.3.1	UV-visible Spectroscopy	56
4.3.2	Morphology	57
4.3.3	Powder X-Ray Diffraction	61
4.3.4	FT-IR Chemical Analysis	63
4.3.5	Inductively Coupled Plasma-Optical Emission Spectroscopy	64
4.4	Conclusion	66
5	FABRICATION OF SILVER NANOPARTICLE DOPED IN ZEOLITE FRAMEWORK AND ANTIBACTERIAL ACTIVITY	67



5.1	Introduction	67
5.2	Materials and Methods	68
	5.2.1 Materials	68
	5.2.2 Methods	69
5.3	Results and Discussion	71
	5.3.1 UV-visible Spectroscopy	73
	5.3.2 Powder X-ray Diffraction	75
	5.3.3 Morphology	76
	5.3.4 FT-IR Chemical Analysis	80
	5.3.5 Inductively Coupled Plasma-Optical Emission Spectroscopy	81
	5.3.6 Antibacterial Activity	82
5.4	Conclusion	84
6	SYNTHESIS AND CHARACTERIZATION OF SILVER/MONTMORILLONITE/CHITOSAN BIONANOCOMPOSITES BY CHEMICAL REDUCTION METHOD AND THEIR ANTIBACTERIAL ACTIVITY	86
6.1	Introduction	86
6.2	Materials and Methods	88
	6.2.1 Materials	88
	6.2.2 Methods	89
6.3	Results and Discussion	91
	6.3.1 UV-visible Spectroscopy	94
	6.3.2 Powder X-ray Diffraction	95
	6.3.3 Morphology	98
	6.3.4 FT-IR Chemical Analysis	101
	6.3.5 Inductively Coupled Plasma-Optical Emission Spectroscopy	103
	6.3.6 Antibacterial Activity	104
6.4	Conclusion	106
7	GREEN SYNTHESIS OF SILVER/MONTMORILLONITE/CHITOSAN BIONANOCOMPOSITES USING THE UV-IRRADIATION METHOD AND EVALUATION OF ANTIBACTERIAL ACTIVITIES	108



7.1	Introduction	108
7.2	Materials and Methods	110
	7.2.1 Materials	110
	7.2.2 Methods	111
7.3	Results and Discussion	113
	7.3.1 UV-visible Spectroscopy	116
	7.3.2 Powder X-ray Diffraction	118
	7.3.3 Morphology	120
	7.3.4 FT-IR Chemical Analysis	123
	7.3.5 Antibacterial Study	125
7.4	Conclusion	126
8	SYNTHESIS OF SILVER/MONTMORILLONITE NANOCOMPOSITES USING GAMMA-IRRADIATION	128
8.1	Introduction	128
8.2	Materials and Methods	130
	8.2.1 Materials	130
	8.2.2 Methods	130
8.3	Results and Discussion	132
	8.3.1 Powder X-ray Diffraction	136
	8.3.2 Morphology	138
	8.3.3 UV-visible Spectroscopy	143
	8.3.4 Inductively Coupled Plasma-Optical Emission Spectroscopy	145
	8.3.5 FT-IR Chemical Analysis	146
8.4	Conclusion	147
9	SILVER/POLY (LACTIC ACID) NANOCOMPOSITE: PREPARATION, CHARACTERIZATION AND ANTIBACTERIAL ACTIVITY	149
9.1	Introduction	149
9.2	Materials and Methods	150
	9.2.1 Materials	150
	9.2.2 Methods	151
9.3	Results and Discussion	154



9.3.1	X-Ray Diffraction	154
9.3.2	UV-visible Spectroscopy	155
9.3.3	Morphology	157
9.3.4	FT-IR Chemical Analysis	160
9.3.5	Silver Ions Release	161
9.3.6	Antibacterial Results	162
9.4	Conclusion	165
10	SUMMARY, GENERAL CONCLUSION AND RECOMMENDATION FOR FUTURE RESEARCH	166
10.1	Summary and General Conclusions	166
10.2	Recommendation for Further Studies	170
	REFERENCES	172
	BIODATA OF STUDENT	196
	LIST OF PUBLICATIONS FROM THIS WORK	195
	OTHER PUBLICATIONS (AS CO-AUTHOR)	196

