



University of Groningen

Synthesis of α -amino- ω -carboxypolytetrahydrofuran

Vanrenterghem, T.; Dubreuil, M.F.; Goethals, E.J.; Loontjens, T.J.

Published in:
Polymer International

DOI:
[10.1002/\(SICI\)1097-0126\(199905\)48:5<343::AID-PI184>3.0.CO;2-T](https://doi.org/10.1002/(SICI)1097-0126(199905)48:5<343::AID-PI184>3.0.CO;2-T)

IMPORTANT NOTE: You are advised to consult the publisher's version (publisher's PDF) if you wish to cite from it. Please check the document version below.

Document Version
Publisher's PDF, also known as Version of record

Publication date:
1999

[Link to publication in University of Groningen/UMCG research database](#)

Citation for published version (APA):

Vanrenterghem, T., Dubreuil, M. F., Goethals, E. J., & Loontjens, T. J. (1999). Synthesis of α -amino- ω -carboxypolytetrahydrofuran. *Polymer International*, 48(5), 343-345. [https://doi.org/10.1002/\(SICI\)1097-0126\(199905\)48:5<343::AID-PI184>3.0.CO;2-T](https://doi.org/10.1002/(SICI)1097-0126(199905)48:5<343::AID-PI184>3.0.CO;2-T)

Copyright

Other than for strictly personal use, it is not permitted to download or to forward/distribute the text or part of it without the consent of the author(s) and/or copyright holder(s), unless the work is under an open content license (like Creative Commons).

Take-down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Downloaded from the University of Groningen/UMCG research database (Pure): <http://www.rug.nl/research/portal>. For technical reasons the number of authors shown on this cover page is limited to 10 maximum.

Rapid Report

Synthesis of α -amino- ω -carboxy-polytetrahydrofuran

T Vanreenterghem,¹ MF Dubreuil,¹ EJ Goethals^{1*} and TJ Loontjens²

¹Department of Organic Chemistry, Polymer Division, University of Ghent, Krijgslaan 281, 9000 Ghent, Belgium


²DSM Research, P.O. Box 18, 6160 MD Geleen, The Netherlands

INTRODUCTION

Telechelic polymers are important building blocks for the design of new macromolecular architectures.¹ In some cases hetero-telechelic polymers, linear polymers containing two different functional end-groups on each polymer chain, may be of interest. In this paper we report a convenient method for the synthesis of α -amino- ω -carboxy-polytetrahydrofuran based on a combination of functional initiation and end-capping.

RESULTS AND DISCUSSION

In a previous paper we reported that a combination of a functionalized alcohol and trifluoromethanesulfonic acid anhydride (triflic anhydride, Tf₂O) can be used as a functional initiator system for the polymerization of tetrahydrofuran (THF).² This method was now applied with ethyl-6-hydroxyhexanoate (EHH) as functional alcohol leading to polyTHF carrying an ester end-group which can be hydrolyzed to the corresponding carboxylate-terminated polymer.



Scheme 1

* Correspondence to: EJ Goethals, Department of Organic Chemistry, Polymer Division, University of Ghent, Krijgslaan 281, 9000 Ghent, Belgium

(Received 22 February 1999; accepted 24 February 1999)




Figure 1. 360 MHz ^1H NMR spectrum of α -amino- ω -carboxy-polyTHF (\overline{M}_n 3500 g mol $^{-1}$, solvent CDCl_3).

To introduce the amino function at the other chain end it is, in principle, possible to end-cap the living polymer with ammonia. However, it was observed that this reaction leads to a substantial fraction of coupling product resulting from reaction of the first formed primary amine with the oxonium end-group of another living polymer. A convenient method leading to the pure primary amino end-group was found to be end-capping of the living polymer with hexamethylene tetramine followed by acid hydrolysis.³ The ester function, introduced by the initiator system, was hydrolyzed to the carboxylic function by treatment with anhydrous potassium hydroxide, as reported.⁴

The complete reaction sequence for the synthesis of the heterotelechelic polymer is given in Scheme 1. Figure 1 shows the ^1H NMR spectrum of a polymer with number average molecular weight 3500. The presence of multiplets of equal intensities at 2.35 and 3.1 ppm are in agreement with the presence of carboxylate and ammonium end-groups in stoichiometric amounts. As reported earlier,² the molecular weight of the polymers can be varied by changing the initiator concentration and/or the polymerization time. Molecular weight distributions ($\overline{M}_w/\overline{M}_n$) are typically below 1.2 (Table 1).

Table 1. Molecular weight and molecular weight distributions of α -amino- ω -carboxy-polytetrahydrofuran as a function of polymerization time. $[\text{THF}] = 11.26 \text{ mol L}^{-1}$, $[\text{EHHOTf}] = 0.0525 \text{ mol L}^{-1}$, solvent CH_2Cl_2 . Values obtained by gel permeation chromatography

| Polymerization time (min) | \overline{M}_n | $\overline{M}_w/\overline{M}_n$ |
|---------------------------|------------------|---------------------------------|
| 7 | 2000 | 1.19 |
| 15 | 3600 | 1.17 |

EXPERIMENTAL PART

Materials

Tf_2O and EHH were purified by distillation. CH_2Cl_2 was purified by general methods and used after distillation over calcium hydride. Trichloromethane was used after distillation over calcium hydride. THF was purified by general methods and used after distillation over sodium in the presence of benzophenone. 2,2-Di-*tert*-butylpyridine (DTBP) was used as received.

Synthesis

A typical synthesis of the polymer is as follows. In a dried two necked-flask of 50 mL, 7 mL of CH_2Cl_2 , 500 μL of DTBP ($2.23 \cdot 10^{-3}$ mol) and 250 μL of Tf_2O ($1.49 \cdot 10^{-3}$ mol) were thermostatted at 20 $^\circ\text{C}$. 239 μL of EHH ($1.47 \cdot 10^{-3}$ mol) was added dropwise under stirring. After one hour, the polymerization was started by introducing 20 mL of THF (0.247 mol). After 15 minutes, the polymerization was terminated with a solution of 0.522 g of HMTA ($3.73 \cdot 10^{-3}$ mol) in 25 mL of trichloromethane. After 10 minutes stirring at room temperature the solvents and unreacted THF were evaporated. The residue was dissolved in 10 mL of toluene, 15 mL of methanol and 1.2 g of concentrated sulfuric acid and the solution was refluxed for 2 hours. The mixture was neutralized by adding a 50% NaOH/water solution, the salts were filtered off and the filtrate was stripped to dryness on a rotary evaporator leaving 4.1 g of α -amino- ω -ester-terminated polyTHF.

4.1 g ($1.18 \cdot 10^{-3}$ mol) of the residue was added to a stirred cooled suspension (0 $^\circ\text{C}$) of 2.73 g ($11.75 \cdot 10^{-3}$ mol) of potassium *tert*-butoxide in 40 mL of dry THF and 55 μL ($3 \cdot 10^{-3}$ mol) of water. The ice-bath was removed and after three hours at room temperature the mixture was acidified with concentrated hydrochloric acid. The salts were filtered off and the polymer

was precipitated in cold water, filtered off, and dried under vacuum (yield 100%).

ACKNOWLEDGEMENTS

T Vanrenterghem thanks the I.W.T. (Vlaams Instituut voor de Bevordering van het Wetenschappelijk-Technologisch onderzoek in de industrie) for a scholarship.

REFERENCES

- 1 Goethals EJ, *Telechelic Polymers: Synthesis and Applications*, CRC Press, Boca Raton (1989)
- 2 Dubreuil MF and Goethals EJ, *Macromol. Chem. Phys.* **198**:3077–3087 (1997)
- 3 Leir CM, Hoffmann JJ and Stark JE, EP 0 296 852 A2, 3M (1988)
- 4 Gassman PG and Schenk WN, *J. Org. Chem.* **42**:918–920 (1977)