

*Technical Report No. 04/06, August 2006*

VARIATIONAL BOUNDS FOR MULTIPHASE TRANSVERSELY  
ISOTROPIC COMPOSITES

H. Brito-Santana, R. Rodríguez-Ramos, R. Guinovart-Díaz, J.  
Bravo-Castillero and F. J. Sabina

# Variational bounds for multiphase transversely isotropic elastic composites

H. Brito–Santana<sup>a</sup>, R. Rodríguez–Ramos<sup>b</sup>,  
R. Guinovart–Díaz<sup>b</sup>, J. Bravo–Castillero<sup>b</sup>, F. J. Sabina<sup>c</sup>

<sup>a</sup>Departamento de Matemática, Universidad de las Ciencias Informáticas, Reparto Lourdes, Boyeros, Habana 36, CP 13600. Cuba.

<sup>b</sup>Facultad de Matemática y Computación, Universidad de la Habana, San Lazaro y L, Vedado, Habana 4, CP 10400. Cuba.

<sup>c</sup>Instituto de Investigaciones en Matemáticas Aplicadas y en Sistemas, Universidad Nacional Autónoma de México, Apartado Postal 20-726, Delegación de Alvaro Obregón, 01000 México D.F., México.

## Abstract

A general algorithm for the calculation of variational bounds for any type of anisotropic linear elastic composite is presented. Analytical expressions for the bounds are derived using this general approach. Bounds for multiphase, linear, transversely isotropic, elastic composites are reported. Bounds for the two-dimensional case are calculated. Some comparisons with other models are shown.

## 1. Introduction

Due to the anisotropic character of a composite, its geometric and physical nonlinear behavior, the geometric shape of the reinforcements and their distributions in the composite, among other factors, exact analytic expressions of overall properties can not be provided. Sometimes, however, the range of validity of the overall properties of a composite using variational principle can be estimated.

The study of the variational bounds for linear and non-linear composite materials has been considered by many authors (see, for instance, Pobodrya (1984), Ponte Castañeda (1992) and Willis (1991)). In Rodríguez-Ramos et al. (2004) a generalization of the Hashin-Shtrikman variational principles is reported.

In this work, starting from the general expression of the energy derived in Rodríguez-Ramos et al. (2004) for non-linear composites, an application to a particular case of linear, elastic, transversely isotropic composites is studied and the analytical expressions of the variational bounds for each material constant are derived. In particular, the bounds for two and three phase transversely isotropic composites are reported.

## 2. Statement of the problem

The solution of the non homogeneous problem follows from:

$$\text{Div } \tilde{\sigma}(\tilde{u}, \tilde{X}) = 0, \text{ or } \sigma_{ij,j} = 0, \quad \sigma_{ij} = F(\tilde{\varepsilon}, \tilde{X}) = \frac{\partial W(\tilde{\varepsilon})}{\partial \tilde{\varepsilon}} = C_{ijkl} \varepsilon_{kl}, \quad (2.1)$$

$$\tilde{u}|_{\Sigma} = \tilde{u}_o = \tilde{\varepsilon}^0, \quad (2.2)$$

where  $\tilde{\sigma}$ ,  $\tilde{\varepsilon}$  denote the second order stress and strain tensors, respectively.  $\varepsilon_{ij} = \frac{1}{2}(u_{i,j} + u_{j,i})$

where  $u_i$  denotes the component of mechanical displacement and the comma denotes partial

differentiation.  $\tilde{C}$  is the stiffness tensor, and it is a fourth range tensor.  $\tilde{\varepsilon}^0$  and  $\vec{u}^0$  are respectively the prescribed second order constant tensor and the mechanical displacement vector.

The solution of the above problem (heterogeneous problem) can be written as the sum of the solution of the comparison problem (homogeneous medium), denoted by Problem A, and the solution of the auxiliar problem related to the second order stress polarization tensor  $\tilde{p}$ , denoted by Problem B.

Therefore,

$$\vec{u} = \vec{u}^c + \vec{u}^p, \quad \tilde{\varepsilon} = \tilde{\varepsilon}^c + \tilde{\varepsilon}^p, \quad \tilde{\sigma} = \tilde{\sigma}^c + \tilde{p}, \quad (2.3)$$

where  $\tilde{\sigma}^c$ ,  $\tilde{\varepsilon}^c$  and  $\vec{u}^c$  are the stress, strain tensors and mechanic displacement of the comparison body, respectively. The magnitudes  $\tilde{\varepsilon}^p$ ,  $\tilde{p}$  and  $\vec{u}^p$  denote the strain, stress polarization tensors and the mechanical displacement of the polarization contribution, respectively.

The solution of the Problem A is the vector  $\vec{u}^c$  and it satisfies the following boundary value problem

$$Div \tilde{\sigma}^c(\vec{u}^c) = 0, \quad \tilde{\sigma}^c = \frac{\partial W^c(\tilde{\varepsilon}^c)}{\partial \tilde{\varepsilon}^c} = \tilde{C}^c : \tilde{\varepsilon}^c, \quad (2.4)$$

$$\vec{u}^c|_{\Sigma} = \vec{u}_0, \quad (2.5)$$

where the quadratic potential energy of the comparison body  $W^c$  can be introduced as

$$W^c(\tilde{\varepsilon}^c) = \frac{1}{2} C_{ijkl}^c \varepsilon_{ij}^c \varepsilon_{kl}^c \text{ and the stiffness constant } C_{ijkl}^c \text{ does not depend on the spatial coordinate } \vec{x}.$$

The solution  $\vec{u}^p$  of the auxiliary problem related to the stress polarization tensor  $\tilde{p}$  (Problem B) can be found from

$$Div(\tilde{p} + \tilde{C}^c \tilde{\varepsilon}^p) = 0, \text{ or } p_{ij,j} + C_{ijkl}^c \varepsilon_{kl,j}^p = 0, \quad (2.6)$$

$$\vec{u}^p|_{\Sigma} = 0, \quad (2.7)$$

where the potential energy of the polarized contribution is denoted by  $W^p(\tilde{\varepsilon})$ , and it is defined by  $W^p(\tilde{\varepsilon}) = W(\tilde{\varepsilon}) - W^c(\tilde{\varepsilon})$ . Then we can obtain the expression for the stress polarization tensor in components as

$$p_{ij} = F^p(\varepsilon_{ij}) = \frac{\partial W^p(\varepsilon_{ij})}{\partial \varepsilon_{ij}} = \sigma_{ij} - C_{ijkl}^c \varepsilon_{kl} = C_{ijkl} \varepsilon_{kl} - C_{ijkl}^c \varepsilon_{kl} = (C_{ijkl} - C_{ijkl}^c) \varepsilon_{kl}. \quad (2.8)$$

The associate constitutive relation (strain as a function of the polarization tensor) from (2.8) can be written in the form,

$$\varepsilon_{ij} = \frac{\partial \omega^p(p_{ij})}{\partial p_{ij}} = H_{ijkl} p_{kl}, \quad H_{ijkl} = (C_{ijkl} - C_{ijkl}^c)^{-1}, \quad (2.9)$$

where

$$\omega^p(\tilde{p}) = \frac{1}{2} H_{ijkl} p_{ij} p_{kl}, \quad (2.10)$$

is the inverse potential energy related to the potential energy  $W^P(\tilde{\varepsilon})$  of the polarization contribution defined in (2.8).

The boundary value problem for the composite can be summarized as follows:

<i>Composite</i>	<i>Comparison body</i>	<i>Polarization contribution</i>
$\sigma_{ij,j} = 0$	$\sigma_{ij,j}^c = 0$	$\sigma_{ij,j}^p = 0$
$\sigma_{ij} = C_{ijkl} \varepsilon_{kl}$	$\sigma_{ij} = C_{ijkl}^c \varepsilon_{kl}^c$	$\sigma_{ij}^p = p_{ij} + C_{ijkl}^c \varepsilon_{kl}^p = 0$
$u_i _{\Sigma} = \varepsilon_{ij}^o x_j$	$u_i _{\Sigma} = \varepsilon_{ij}^o x_j$	$u_i^p _{\Sigma} = 0$

### 3. Some considerations related to elastic energy. General expression of the energy

The analytical expressions for the variational bounds of a linear transversely isotropic elastic composite are obtained using the energy functional given by the formula (53) reported in Rodriguez-Ramos et al. (2003):

$$\Phi = \frac{1}{2} \int (\sigma_{ij}^c \varepsilon_{ij}^c + 2p_{ij} \varepsilon_{ij}^c + p_{ij} \varepsilon_{ij}' - 2\omega^p(\tilde{p})) dV . \quad (3.1)$$

Averaging the functional (3.1) and using the average operator  $\langle \bullet \rangle$  on the volume  $V$ , the expression (3.1) can be written in the following form:

$$A = \frac{2\Phi}{V} = \langle \sigma_{ij}^c \varepsilon_{ij}^c \rangle + 2 \langle p_{ij} \varepsilon_{ij}^c \rangle - 2 \langle \omega^p(\tilde{p}) \rangle + \langle p_{ij} \varepsilon_{ij}^p \rangle . \quad (3.2)$$

Each term of (3.2) can be denoted, for simplicity, in the following form:

$$A_1 = \langle \sigma_{ij}^c \varepsilon_{ij}^c \rangle, \quad A_2 = 2 \langle p_{ij} \varepsilon_{ij}^c \rangle, \quad A_3 = -2 \langle \omega^p(\tilde{p}) \rangle \quad \text{and} \quad A_4 = \langle p_{ij} \varepsilon_{ij}^p \rangle . \quad (3.3)$$

Therefore, the equation (3.2) can be given in an equivalent form as  $A = A_1 + A_2 + A_3 + A_4$ .

Now, consider a composite made of  $q$  components ( $q$ -phases). The stress polarization tensor  $\tilde{p}$  depends on the space variable  $\vec{x}$ , and the stress polarization tensor for each phase  $\alpha$  of the composite is denoted by  $\tilde{p}_\alpha$ . Therefore, we have:

$$\langle \tilde{p} \rangle = \sum_{\alpha=1}^q v_\alpha \tilde{p}_\alpha , \quad (3.4)$$

where  $v_\alpha$  is the volume fraction of the component  $\alpha$  in the composite, and

$$\sum_{\alpha=1}^q v_\alpha = 1 . \quad (3.5)$$

The magnitudes  $A_1$ ,  $A_2$  and  $A_3$  can be written as functions of the spherical and deviator contributions of tensors  $\tilde{\varepsilon}^0$  and  $\tilde{p}$ . The decomposition is  $p_{ij} = \frac{1}{d} p \delta_{ij} + \bar{p}_{ij}$  and

$\varepsilon_{ij}^o = \frac{1}{d} e \cdot \delta_{ij} + \bar{e}_{ij}$ , where  $p$ ,  $e$  are the spherical and  $\bar{p}_{ij}$ ,  $\bar{e}_{ij}$  are the deviator parts of the two tensors  $\tilde{\varepsilon}^o$  and  $\tilde{p}$ , respectively, and  $d$  is the dimension of the Euclidean space, i.e.  $d = 2$  (two-dimensional space) or  $d = 3$  (three-dimensional space).

After some algebraic manipulations, the magnitudes  $A_1$ ,  $A_2$  and  $A_3$  have the following compact and general form in terms of spherical and deviator parts,

$$\begin{aligned} A_1 &= \frac{1}{d^2} e^2 C_{ijij}^c + \frac{2}{d} e \cdot \bar{e}_{ij} C_{ijkk}^c + \bar{e}_{ij} C_{ijkl}^c \bar{e}_{kl}, \\ A_2 &= \sum_{\alpha=1}^q \nu_{\alpha} \left( \frac{2}{d} p_{\alpha} e + 2 \tilde{p}_{\alpha} : \tilde{\varepsilon} \right), \\ A_3 &= - \sum_{\alpha=1}^q \nu_{\alpha} \tilde{p}_{\alpha} : \tilde{H}_{\alpha} : \tilde{p}_{\alpha} = - \sum_{\alpha=1}^q \nu_{\alpha} \left[ \frac{1}{d^2} p_{\alpha}^2 H_{ijij_{\alpha}} + \frac{2}{d} p_{\alpha} \bar{p}_{ij_{\alpha}} H_{ijkk_{\alpha}} + \bar{p}_{ij_{\alpha}} H_{ijkl_{\alpha}} \bar{p}_{kl_{\alpha}} \right], \end{aligned} \quad (3.6)$$

with  $\omega^p(\tilde{p}_{\alpha}) = \frac{1}{2} \tilde{p}_{\alpha} : \tilde{H}_{\alpha} : \tilde{p}_{\alpha}$  and  $\tilde{H} = (\tilde{C} - \tilde{C}^c)^{-1}$ . For the sake of brevity, the proof of the expression (3.6) is omitted.

The expression  $A_4$  is related to polarization contribution (Problem B) and it depends on the unknown polarization displacement  $\bar{u}^p$ . Therefore, we need to solve the auxiliary problem (2.6)-(2.7) related to stress polarization tensor  $\tilde{p}$  where the vector  $\bar{u}^p$  is the solution of the problem. The problem is solved using the Fourier transform.

Applying the Fourier transform to the equation (2.6), we obtain

$$C_{ijkl}^c \omega_j \omega_l U_k = i \omega_j P_{ij}, \quad (3.7)$$

where  $U_k$  and  $P_{ij}$  denote the Fourier transforms of the functions  $u_k^p$  and  $p_{ij}$ , respectively. The magnitude  $A_4$  can be written in the Parsevall form,

$$A_4 = \frac{1}{V} \int_V p_{ij} \varepsilon_{ij}^p dV_x = \frac{1}{8\pi^3 V} \int P_{ij}(\bar{\omega}) E_{ij}(\bar{\omega}) dV_{\omega} = \frac{1}{8\pi^3 V} \int P_{ij}(\bar{\omega}) G_{ij}(\bar{\omega}) dV_{\omega}, \quad (3.8)$$

where  $\tilde{P}(\bar{\omega})$  and  $\tilde{E}(\bar{\omega})$  are the Fourier images of the stress polarization tensor  $\tilde{p}$  and strain tensor  $\tilde{\varepsilon}$ , respectively, and  $E_{ij} = \frac{1}{2}(G_{ij} + G_{ji})$  with  $G_{ij} = i U_i \omega_j$ .

Now, our aim is to derive the integrand function given in (3.8) as a function only of the polarization tensor  $\tilde{p}$ . From the vector  $\bar{\omega}$  we can introduce a unit vector, i.e.  $k_i = \frac{\omega_i}{\|\bar{\omega}\|}$  and then equation (3.7)

is written in the following form,  $C_{ijkl}^c k_j k_l U_k = i \frac{k_j}{\|\bar{\omega}\|} P_{ij}$ . We therefore have,

$$U_k = i (C_{ijkl}^c k_j k_l)^{-1} \frac{k_j}{\|\bar{\omega}\|} P_{ij}. \quad (3.9)$$

We can derive from formula (3.9) the expression,

$$C_{ijkl}^c k_j k_l G_{km} = -k_j k_m P_{ij}^*, \quad (3.10)$$

where  $P_{ij}^*$  is the Fourier image of the component  $p_{ij}^* = p_{ij} - \langle p_{ij} \rangle$ .

The tensor  $\tilde{C}^c$  can be decomposed as sum of two tensors; one isotropic tensor denoted by  $\tilde{C}_{iso}^c$  (the components are denoted as  $c_{ijkl_{iso}}^c$ ) and the other tensor, the so called remainder tensor, denoted by  $\tilde{C}_{res}^c$  (the components are denoted by  $c_{ijkl_{res}}^c$ ). Thus,  $c_{ijkl}^c = c_{ijkl_{iso}}^c + c_{ijkl_{res}}^c$ . Therefore, the equation (310) can be rewritten in the form:

$$(c_{ijkl_{iso}}^c k_j k_l + c_{ijkl_{res}}^c k_j k_l) G_{km} = -k_j k_m P_{ij}^*. \quad (3.11)$$

The tensor  $\tilde{T} = t_{ik} \bar{e}_i \otimes \bar{e}_k$ , with components  $t_{ik} = c_{ijkl_{iso}}^c k_j k_l = \frac{c_{11}^c - c_{12}^c}{2} \delta_{ik} + \frac{c_{11}^c + c_{12}^c}{2} k_i k_k$  has an inverse tensor of the form  $\tilde{Z} = z_{ik} \bar{e}_i \otimes \bar{e}_k$ , with  $z_{ik} = \frac{2}{c_{11}^c - c_{12}^c} \delta_{ik} - \frac{c_{11}^c + c_{12}^c}{c_{11}^c (c_{11}^c - c_{12}^c)} k_i k_k$ . The equation (3.11) is multiplied by the inverse tensor  $\tilde{Z}$  and we have

$$\left(1 + \frac{2}{c_{11}^c - c_{12}^c} c_{ijil_{res}}^c k_j k_l - \frac{c_{11}^c + c_{12}^c}{c_{11}^c (c_{11}^c - c_{12}^c)} c_{ijkl_{res}}^c k_i k_j k_k k_l\right) G_{km} = -k_j k_m P_{ij}^* z_{ik}. \quad (3.12)$$

Let us introduce a unit vector  $\vec{N} = n_i \bar{e}_i$  with the following properties,

$$\langle n_i n_j \rangle = \frac{1}{V} \int_V n_i n_j dV = \begin{cases} \frac{1}{2} \delta_{ij} & \text{if } d = 2 \\ \frac{1}{3} \delta_{ij} & \text{if } d = 3 \end{cases},$$

$$\langle n_i n_j n_k n_l \rangle = \frac{1}{V} \int_V n_i n_j n_k n_l dV = \begin{cases} \frac{1}{8} (\delta_{ij} \delta_{kl} + \delta_{ik} \delta_{jl} + \delta_{il} \delta_{jk}) & \text{if } d = 2 \\ \frac{1}{15} (\delta_{ij} \delta_{kl} + \delta_{ik} \delta_{jl} + \delta_{il} \delta_{jk}) & \text{if } d = 3 \end{cases}.$$

The equation (3.12) is multiplied by the tensor  $\tilde{P}^* = P_{ij}^* \bar{e}_i \otimes \bar{e}_j$ , and using the above properties, the following expression can be derived for two dimensional case ( $d = 2$ )

$$\tau_2 \langle G_{km} P_{km} \rangle = \frac{c_{11}^c + c_{12}^c}{8 c_{11}^c (c_{11}^c - c_{12}^c)} \langle P_{ii}^* P_{jj} \rangle + \frac{c_{12}^c - 3c_{11}^c}{4 c_{11}^c (c_{11}^c - c_{12}^c)} \langle P_{ij}^* P_{ij} \rangle, \quad (3.13)$$

where  $\tau_2 = 1 + \frac{c_{ijij_{res}}^c}{c_{11}^c - c_{12}^c} - \frac{(c_{11}^c + c_{12}^c)}{8 c_{11}^c (c_{11}^c - c_{12}^c)} (c_{iijj_{res}}^c + 2c_{ijij_{res}}^c)$ . Notice that for the isotropic case

$$\tau_2 = 1, \text{ since the reminder tensor is the null tensor, i.e. } c_{ijkl_{res}}^c = 0.$$

The expression  $A_4$  in (3.8) using (3.13) can be written in the following form,

$$A_4 = \langle p_{ij} \varepsilon_{ij} \rangle = \frac{c_{11}^c + c_{12}^c}{8\tau c_{11}^c (c_{11}^c - c_{12}^c)} \langle P_{ii}^* P_{jj} \rangle + \frac{c_{12}^c - 3c_{11}^c}{4\tau c_{11}^c (c_{11}^c - c_{12}^c)} \langle P_{ij}^* P_{ij} \rangle. \quad (3.14)$$

Finally, the components  $p_{ij}^*$  and  $p_{ij}$  of the expression  $p_{ij}^* = p_{ij} - \langle p_{ij} \rangle$  can be split into deviators and spherical parts, and therefore we obtain

$$A_4 = a_c \sum_{\alpha=1}^q v_{\alpha} (p_{\alpha}^2 - \langle p \rangle^2) + b_c \sum_{\alpha=1}^q v_{\alpha} (\bar{p}_{ij\alpha}^2 - \langle \bar{p}_{ij} \rangle^2), \quad (3.15)$$

$$\text{where } a_c = -\frac{1}{4\tau_2 c_{11}^c} \text{ and } b_c = -\frac{3c_{11}^c - c_{12}^c}{4\tau_2 c_{11}^c (c_{11}^c - c_{12}^c)}.$$

Now, we can derive the general expression of  $A_4$  for the three-dimensional case ( $d = 3$ ). The equation (3.12) can be written in the form,

$$\tau_3 \langle G_{km} P_{km} \rangle = \frac{c_{11}^c + c_{12}^c}{15c_{11}^c (c_{11}^c - c_{12}^c)} \langle P_{ii}^* P_{jj} \rangle + \frac{2c_{12}^c - 8c_{11}^c}{15c_{11}^c (c_{11}^c - c_{12}^c)} \langle P_{ij}^* P_{ij} \rangle, \quad (3.16)$$

$$\text{where } \tau_3 = 1 + \frac{2c_{ijj_{res}}^c}{3(c_{11}^c - c_{12}^c)} - \frac{(c_{11}^c + c_{12}^c)}{15c_{11}^c (c_{11}^c - c_{12}^c)} (c_{ijj_{res}}^c + 2c_{ijj_{res}}^c).$$

Analogous to the above procedure for  $d = 2$ , we obtain the general expression  $A_4$  for three-dimensional case ( $d = 3$ ) in the form,

$$A_4 = a_{c_3} \sum_{\alpha=1}^q v_{\alpha} (p_{\alpha}^2 - \langle p \rangle^2) + b_{c_3} \sum_{\alpha=1}^q v_{\alpha} (\bar{p}_{ij\alpha}^2 - \langle \bar{p}_{ij} \rangle^2), \quad (3.17)$$

$$\text{where } a_c = -\frac{1}{9\tau_3 c_{11}^c} \text{ and } b_c = -\frac{8c_{11}^c - 2c_{12}^c}{15\tau_3 c_{11}^c (c_{11}^c - c_{12}^c)}.$$

Finally, the expression for the energy can be calculated for two dimensional problems ( $d = 2$ ) from the equations (3.6) and (3.15) and for three-dimensional problem ( $d = 3$ ) using the expressions (3.6) and (3.17).

#### 4. General approach for variational bounds of multiphase anisotropic elastic composite

It is well known that the solution of the auxiliary problem (2.6)-(2.7) (Problem B) is a stationary point of the functional (see, Rodríguez-Ramos et. at. (2004))

$$\Phi = \frac{1}{2} \int_V (\sigma_{ij}^c \varepsilon_{ij}^c + 2p_{ij} \varepsilon_{ij}^c + p_{ij} \varepsilon_{ij}^p - 2\omega^p(\tilde{p})) dV \quad \text{i.e. } \delta \Phi(\tilde{p}, \delta \tilde{p}) = 0. \quad (4.1)$$

From the variational principle of Hashin-Shtrikman we can state that the stationary point is maximum or minimum according to the following statements:

The functional (4.1) has maximum if the tangential modulus  $\frac{\partial F^P}{\partial \varepsilon_{ij}}$  is positive, i.e. from (2.8), we can see that  $C_{ijkl} > C_{ijkl}^c$ .

The functional (4.1) has minimum if the tangential modulus  $\frac{\partial F^P}{\partial \varepsilon_{ij}}$  is negative, i.e. from (2.8), we can see that  $C_{ijkl} < C_{ijkl}^c$ .

The maximum or minimum of the magnitude  $A$  can be obtained with respect to the stress polarization tensor  $\bar{p}$  from the condition of the existence of extrema applied to the spherical ( $p$ ) and deviator ( $\bar{p}_{ij}$ ) components of the stress polarization tensor. In that case, a system of equations is written in the following form,

$$\left[ \frac{1}{d^2} H_{iijj\alpha} - a_c \right] p_\alpha + \frac{1}{d} \bar{p}_{ij\alpha} H_{ijkk\alpha} = \frac{1}{d} e - 2a_c \langle p \rangle, \quad (4.2)$$

$$\frac{1}{d} p_\alpha H_{ijkk\alpha} + \bar{p}_{kl\alpha} H_{ijkl\alpha} - b_c \bar{p}_{ij\alpha} = \bar{e}_{ij} - b_c \langle \bar{p}_{ij} \rangle. \quad (4.3)$$

The two unknown magnitudes  $\langle p \rangle$  and  $\langle \bar{p}_{ij} \rangle$  are derived from equations (4.2) and (4.3). Then, the unknown functions  $\langle p \rangle$  and  $\langle \bar{p}_{ij} \rangle$  are substituted into the expression for the energy (3.2), but they are now written in a compact form for any anisotropic media as

$$A = \frac{1}{d^2} e^2 C_{iijj}^c + \frac{2}{d} e \cdot \bar{e}_{ij} C_{ijkk}^c + \bar{e}_{ij} C_{ijkl}^c \bar{e}_{kl} + \frac{1}{d} \langle p \rangle + \langle \bar{p}_{ij} \rangle \bar{e}_{ij}, \quad (4.4)$$

and applying the sufficient condition of extrema  $C_{ijkl\alpha} > C_{ijkl}^c$  (maximum) and  $C_{ijkl\alpha} < C_{ijkl}^c$  (minimum) an analytical expression of the bounds can be derived. The analysis of the bounds is done for the composite with well ordered q-phases, i.e.  $C_{ijkl_1} > C_{ijkl_2} > \dots > C_{ijkl_q}$ . The condition  $C_{ijkl\alpha} > C_{ijkl}^c$  is satisfied if we take the properties of the comparison body as the properties of the q-phase elastic moduli, i.e.,  $C_{ijkl_q}$ ; on the other hand, the condition  $C_{ijkl\alpha} < C_{ijkl}^c$  is satisfied if the comparison body is chosen to be one of highest phase elastic moduli  $C_{ijkl_1}$ , i.e. the phase with properties  $C_{ijkl_1}$ .

## 5. Example of bounds for transversely isotropic elastic composite

In this section, an example of bounds using the above procedure is presented. For a better explanation, bounds for two dimensional case ( $d = 2$ ) are studied. In particular, we consider a composite with transversely isotropic properties of their constituents. The Hooke law for the transversely isotropic elastic materials is given in the following matrix form,



$$\begin{bmatrix} \sigma_{11} \\ \sigma_{22} \\ \sigma_{33} \\ \sqrt{2} \sigma_{23} \\ \sqrt{2} \sigma_{13} \\ \sqrt{2} \sigma_{12} \end{bmatrix} = \begin{bmatrix} c_{11} & c_{12} & c_{13} & 0 & 0 & 0 \\ c_{12} & c_{11} & c_{13} & 0 & 0 & 0 \\ c_{13} & c_{13} & c_{33} & 0 & 0 & 0 \\ 0 & 0 & 0 & 2c_{44} & 0 & 0 \\ 0 & 0 & 0 & 0 & 2c_{44} & 0 \\ 0 & 0 & 0 & 0 & 0 & 2c_{66} \end{bmatrix} \begin{bmatrix} \varepsilon_{11} \\ \varepsilon_{22} \\ \varepsilon_{33} \\ \sqrt{2} \varepsilon_{23} \\ \sqrt{2} \varepsilon_{13} \\ \sqrt{2} \varepsilon_{12} \end{bmatrix}. \quad (5.1)$$

The reduced Hooke law for the plane deformation in the plane  $x_1x_2$  where  $\varepsilon_{13} = \varepsilon_{23} = \varepsilon_{33} = 0$  can be written as,

$$\begin{bmatrix} \sigma_{11} \\ \sigma_{22} \\ \sqrt{2} \sigma_{12} \end{bmatrix} = \begin{bmatrix} c_{11} & c_{12} & 0 \\ c_{12} & c_{11} & 0 \\ 0 & 0 & c_{11} - c_{12} \end{bmatrix} \begin{bmatrix} \varepsilon_{11} \\ \varepsilon_{22} \\ \sqrt{2} \varepsilon_{12} \end{bmatrix}. \quad (5.2)$$

In this case, the expressions given in (3.6) and (3.14) can be reduced for transversely isotropic case to

$$A_1 = \frac{1}{4}(2c_{11}^c + 2c_{12}^c)e^2 + (c_{11}^c - c_{12}^c)\bar{e}_{ij}^2, \quad \bar{e}_{ij}^2 = \bar{e}_{11}^2 + \bar{e}_{22}^2 + 2\bar{e}_{12}^2, \quad (5.3)$$

$$A_2 = \sum_{\alpha=1}^q v_{\alpha} (p_{\alpha} e + 2\bar{p}_{ij\alpha} \bar{e}_{ij}), \quad (5.4)$$

$$A_3 = -\sum_{\alpha=1}^q v_{\alpha} \left[ \frac{1}{4} p_{\alpha}^2 \xi_1 + \xi_2 \bar{p}_{ij\alpha}^2 \right], \quad \bar{p}_{ij}^2 = \bar{p}_{11}^2 + \bar{p}_{22}^2 + 2\bar{p}_{12}^2, \quad (5.5)$$

where the constants  $\xi_1$  and  $\xi_2$  are listed as follows,

$$\xi_1 = H_{ijj\alpha} = \frac{2}{c_{11\alpha} - c_{11}^c + c_{12\alpha} - c_{12}^c}, \quad \xi_2 = H_{1111\alpha} - H_{1122\alpha} = \frac{1}{c_{11\alpha} - c_{11}^c - c_{12\alpha} + c_{12}^c}.$$

The magnitude  $A_4$  is given by the formula,

$$A_4 = a_c \sum_{\alpha=1}^q v_{\alpha} (p_{\alpha}^2 - \langle p \rangle^2) + b_c \sum_{\alpha=1}^q v_{\alpha} (\bar{p}_{ij\alpha}^2 - \langle \bar{p}_{ij} \rangle^2), \quad (5.6)$$

where the constants  $a_c, b_c$  are written in the form,

$$a_c = -\frac{1}{4(m^c + k^c)}, \quad b_c = -\frac{k^c + m^c}{4m^c(k^c + m^c)}, \quad \text{where } k^c = \frac{c_{11}^c + c_{12}^c}{2} \quad \text{and} \quad m^c = \frac{c_{11}^c - c_{12}^c}{2}.$$

From the condition of extremum with respect to spherical and deviator parts, i.e.  $\frac{\partial A}{\partial p_{\alpha}} = 0$  and

$\frac{\partial A}{\partial \bar{p}_{ij\alpha}}$ , we obtain the following system of equations,

$$\frac{\partial A}{\partial p_{\alpha}} = v_{\alpha} e - \frac{1}{2} v_{\alpha} p_{\alpha} \xi_1 + 2a_c v_{\alpha} (p_{\alpha} - \langle p \rangle) = 0, \quad (5.7)$$

$$\frac{\partial A}{\partial \bar{p}_{ij\alpha}} = 2v_\alpha \bar{e}_{ij} - 2v_\alpha \bar{p}_{ij\alpha} \xi_2 + 2b_c v_\alpha (\bar{p}_{ij\alpha} - \langle \bar{p}_{ij} \rangle) = 0. \quad (5.8)$$

The unknown functions  $\langle p \rangle$  and  $\langle \bar{p}_{ij} \rangle$  are calculated directly from (5.7) and (5.8). Therefore, we can write,

$$\langle p \rangle = \frac{1}{2} \frac{\gamma_1}{(1+a_c \gamma_1)} e, \quad \text{with} \quad \gamma_1 = \sum_{\alpha=1}^q v_\alpha \left( \frac{1}{4} \xi_{s_1} - a_c \right)^{-1}, \quad (5.9)$$

$$\langle \bar{p}_{ij} \rangle = \frac{\gamma_2}{(1+b_c \gamma_2)} \bar{e}_{ij}, \quad \text{with} \quad \gamma_2 = \sum_{\alpha=1}^q v_\alpha \left( \frac{1}{4} \xi_{s_2} - b_c \right)^{-1}. \quad (5.10)$$

The functional  $A$  given in the formula (4.4) can be written in the compact form  $A = A_1 + \frac{A_2}{2}$ . Thus replacing (5.9) and (5.10) in the compact form, we obtain,

$$A = \frac{1}{2} (c_{11}^c + c_{12}^c) e^2 + (c_{11}^c - c_{12}^c) \bar{e}_{ij}^2 + \frac{1}{2} \langle p \rangle e + \langle \bar{p}_{ij} \rangle \bar{e}_{ij},$$

$$A = k^c e^2 + m^c \bar{e}_{ij}^2 + \frac{1}{4} \frac{\gamma_1}{(1+a_c \gamma_1)} e^2 + \frac{\gamma_2}{1+b_c \gamma_2} \bar{e}_{ij}^2 = \left( k^c + \frac{1}{4} \frac{\gamma_1}{(1+a_c \gamma_1)} \right) e^2 + \left( 2m^c + \frac{\gamma_2}{1+b_c \gamma_2} \right) \bar{e}_{ij}^2.$$

Let us introduce the following notation in the above quadratic form,

$$k = k^c + \frac{\gamma_1}{4(1+a_c \gamma_2)} \quad \text{and} \quad m = m^c + \frac{\gamma_2}{2(1+b_c \gamma_2)}.$$

The expressions of the lower and upper bounds related to multiphase composites can be obtained from the above formula, taking into consideration the relevant statement from the variational principle of Hashin-Shtrikman. They are applied in the following way,

$$k_L = k_1 + \frac{\gamma_1^{(1)}}{4[1+a_c^{(1)} \gamma_1^{(1)}]} \quad \text{and} \quad k_U = k_q + \frac{\gamma_1^{(q)}}{4[1+a_c^{(q)} \gamma_1^{(q)}]}, \quad (k_1 < k_2 < \dots < k_{q-1} < k_q), \quad (5.11)$$

$$m_L = m_1 + \frac{\gamma_2^{(1)}}{2[1+b_c^{(1)} \gamma_2^{(1)}]} \quad \text{and} \quad m_U = m_q + \frac{\gamma_2^{(q)}}{2[1+b_c^{(q)} \gamma_2^{(q)}]}, \quad (m_1 < m_2 < \dots < m_{q-1} < m_q). \quad (5.12)$$

The superscripts 1 and q between brackets mean the replacement of the comparison body by the inclusion or matrix respectively.

The bounds (5.11)-(5.12) for two phases composite can be written in the form,

$$k_L = k_1 + \frac{v_2}{\frac{1}{k_2 - k_1} + \frac{v_1}{m_1 + k_1}} \quad \text{and} \quad k_U = k_2 + \frac{v_1}{\frac{1}{k_1 - k_2} + \frac{v_1}{m_2 + k_2}}, \quad (5.13)$$

$$m_L = m_1 + \frac{v_2}{\frac{1}{m_2 - m_1} + \frac{(k_1 + 2m_1)v_1}{2m_1(m_1 + k_1)}} \quad \text{and} \quad m_U = m_2 + \frac{v_1}{\frac{1}{m_1 - m_2} + \frac{(k_2 + 2m_2)v_2}{2m_2(m_2 + k_2)}}. \quad (5.14)$$

The expressions (5.13)-(5.14) are the same bounds to (4.25)-(4.28) reported by Hashin (1965).

Now, the bounds for the shear module  $\mu (G)$  are studied. We consider the antiplane deformation problem, where the Hooke law in that case has the form  $\sigma_{12} = \mu \varepsilon_{12}$  ,  $\sigma_{13} = \mu \varepsilon_{13}$ . In matrix form we have,

$$\begin{bmatrix} \sqrt{2} \sigma_{12} \\ \sqrt{2} \sigma_{13} \end{bmatrix} = \begin{bmatrix} 2\mu & 0 \\ 0 & 2\mu \end{bmatrix} \begin{bmatrix} \sqrt{2} \varepsilon_{12} \\ \sqrt{2} \varepsilon_{13} \end{bmatrix}.$$

Therefore, the only deviator contributions different from zero are  $\bar{e}_{12}$  and  $\bar{e}_{13}$ . The magnitudes  $A_1, A_2, A_3$  and  $A_4$  are obtained as follows,

$$\begin{aligned} A_1 &= \mu^c \bar{e}_{ij}^2, \quad \bar{e}_{ij}^2 = 2\bar{e}_{12}^2 + 2\bar{e}_{13}^2, \\ A_2 &= 2 \sum_{\alpha=1}^q v_\alpha \bar{p}_{ij\alpha} \bar{e}_{ij}, \quad A_3 = - \sum_{\alpha=1}^q \frac{v_\alpha}{\mu_\alpha - \mu^c} \bar{p}_{ij\alpha}^2, \quad \bar{p}_{ij}^2 = 2\bar{p}_{12}^2 + 2\bar{p}_{13}^2, \\ A_4 &= b_c \sum_{\alpha=1}^q v_\alpha (\bar{p}_{ij\alpha}^2 - \langle \bar{p}_{ij} \rangle^2), \quad \text{with } b_c = -\frac{1}{2\mu^c}. \end{aligned}$$

The necessary condition  $\frac{\partial A}{\partial \bar{p}_{ij\alpha}} = 0$  for the extrema of the functional  $A$  is given in the following form:

$$\frac{\partial A}{\partial \bar{p}_{ij\alpha}} = 2v_\alpha \bar{e}_{ij} - 2 \frac{v_\alpha}{\mu_\alpha - \mu^c} \bar{p}_{ij\alpha} + 2b_c v_\alpha (\bar{p}_{ij\alpha} - \langle \bar{p}_{ij} \rangle) = 0. \quad (5.15)$$

From the equation (5.15) we can get  $\langle \bar{p}_{ij} \rangle = \frac{\gamma}{1+b_c \gamma} \bar{e}_{ij}$ , with  $\gamma = \sum_{\alpha=1}^q v_\alpha \left( \frac{1}{\mu_\alpha - \mu^c} - b_c \right)^{-1}$ .

Thus, the functional  $A = A_1 + \frac{1}{2} A_2$  has the particular form,

$$A = \mu^c \bar{e}_{ij}^2 + \frac{\gamma}{1+b_c \gamma} \bar{e}_{ij}^2 = (\mu^c + \frac{\gamma}{1+b_c \gamma}) \bar{e}_{ij}^2.$$

Let us introduce the notation  $\mu = \mu^c + \frac{\gamma}{1+b_c \gamma}$ . Therefore the bounds for the shear module in the composite with q-phase has the form

$$\mu_L = \mu_1 + \frac{\gamma^{(1)}}{1+b_c^{(1)} \gamma^{(1)}} \quad \text{and} \quad \mu_U = \mu_q + \frac{\gamma^{(q)}}{1+b_c^{(q)} \gamma^{(q)}}, \quad (\mu_1 < \mu_2 < \dots < \mu_{q-1} < \mu_q).$$

In particular, for a two-phase composite we obtain

$$\mu_L = \mu_1 + \frac{v_2}{\frac{1}{\mu_2 - \mu_1} + \frac{v_1}{2\mu_1}} \quad \text{and} \quad \mu_U = \mu_2 + \frac{v_1}{\frac{1}{\mu_1 - \mu_2} + \frac{v_2}{2\mu_2}}. \quad (5.16)$$

The bounds (5.16) are the same bounds to (5.12) – (5.13) given by Hashin (1965).

Finally, the bounds for the parameters  $c_{13}$ ,  $c_{33}$  and  $c_{44}$  are derived. Our analysis is reduced to the plane  $x_1x_3$ . The Hook law for the deformation plane  $x_1x_3$  where  $\varepsilon_{12} = \varepsilon_{22} = \varepsilon_{23} = 0$  can be written in the matrix form

$$\begin{bmatrix} \sigma_{11} \\ \sigma_{33} \\ \sqrt{2} \sigma_{13} \end{bmatrix} = \begin{bmatrix} c_{11} & c_{13} & 0 \\ c_{13} & c_{33} & 0 \\ 0 & 0 & 2c_{44} \end{bmatrix} \begin{bmatrix} \varepsilon_{11} \\ \varepsilon_{33} \\ \sqrt{2} \varepsilon_{13} \end{bmatrix}.$$

Analogous to the above procedure for the other bounds we can calculate the magnitudes  $A_1, A_2, A_3$  and  $A_4$  in the following way,

$$A_1 = \frac{c_{11}^c + 2c_{13}^c + c_{33}^c}{4} e^2 + (c_{33}^c - c_{11}^c) e \bar{e}_{33} + (c_{33}^c + c_{11}^c - 2c_{13}^c) \bar{e}_{33}^2 + 4c_{44}^c \bar{e}_{13}^2,$$

$$A_2 = \sum_{\alpha=1}^q v_{\alpha} (p_{\alpha} e + 4 \bar{p}_{33\alpha}^2 \bar{e}_{33} + 4 \bar{p}_{13\alpha}^2 \bar{e}_{13})$$

$$A_3 = - \sum_{\alpha=1}^q v_{\alpha} \left[ \frac{1}{4} \xi_1 p_{\alpha}^2 - \xi_2 p_{\alpha} \bar{p}_{33\alpha} + \xi_3 \bar{p}_{33\alpha}^2 + 2 \xi_4 \bar{p}_{13\alpha}^2 \right],$$

$$A_4 = a_c \sum_{\alpha=1}^q v_{\alpha} (p_{\alpha}^2 - \langle p \rangle^2) + b_c \sum_{\alpha=1}^q v_{\alpha} (2 \bar{p}_{33\alpha}^2 - 2 \langle \bar{p}_{33} \rangle^2 + 2 \bar{p}_{13\alpha}^2 - 2 \langle \bar{p}_{13} \rangle^2),$$

where

$$\xi_1 = \frac{c_{11\alpha} - c_{11}^c + c_{33\alpha} - c_{33}^c - 2(c_{13\alpha} - c_{13}^c)}{(c_{11\alpha} - c_{11}^c)(c_{33\alpha} - c_{33}^c) - (c_{13\alpha} - c_{13}^c)^2}, \quad \xi_2 = \frac{c_{11\alpha} - c_{11}^c - c_{33\alpha} + c_{33}^c}{(c_{11\alpha} - c_{11}^c)(c_{33\alpha} - c_{33}^c) - (c_{13\alpha} - c_{13}^c)^2},$$

$$\xi_3 = \frac{c_{11\alpha} - c_{11}^c + c_{33\alpha} - c_{33}^c + 2(c_{13\alpha} - c_{13}^c)}{(c_{11\alpha} - c_{11}^c)(c_{33\alpha} - c_{33}^c) - (c_{13\alpha} - c_{13}^c)^2}, \quad \xi_4 = \frac{1}{2(c_{44\alpha} - c_{44}^c)}, \quad \text{with } a_c = -\frac{1}{4\tau c_{11}^c},$$

$$b_c = -\frac{3c_{11}^c - c_{12}^c}{4\tau c_{11}^c (c_{11}^c - c_{12}^c)}, \text{ and}$$

$$\tau = \frac{(c_{11}^c - c_{12}^c)(4c_{11}^c - 4c_{12}^c + 16c_{13}^c + 24c_{44}^c) + (11c_{11}^c - 3c_{12}^c)(2c_{44}^c - c_{11}^c + c_{12}^c)}{16c_{11}^c (c_{11}^c - c_{12}^c)}.$$

From the necessary condition  $\frac{\partial A}{\partial p_{\alpha}} = 0$  and  $\frac{\partial A}{\partial \bar{p}_{ij\alpha}} = 0$  of the extrema of the functional  $A$  we

can write,

$$\left(\frac{1}{4} \xi_1 - a_c\right) p_{\alpha} - \frac{1}{2} \xi_2 \bar{p}_{33\alpha} = \frac{e}{2} - a_c \langle p \rangle, \quad (5.17)$$

$$\frac{\xi_2}{4} p_\alpha + (\xi_3 - b_c) \bar{p}_{33_\alpha} = \bar{e}_{33} - b_c < \bar{p}_{33} >, \quad (5.18)$$

$$(\xi_4 - b_c) \bar{p}_{13_\alpha} + b_c < \bar{p}_{13} > = \bar{e}_{13}. \quad (5.19)$$

An expression for  $< \bar{p}_{13} >$  can be calculated directly from the equation (5.19), i.e.,

$$< \bar{p}_{13} > = \frac{n_{13}}{1 + b_c n_{13}} \bar{e}_{13}, \quad \text{where} \quad n_{13} = \sum_{\alpha=1}^q \frac{v_\alpha}{\xi_4 - b_c}.$$

The system (5.17) – (5.18) can be solved with respect to  $p_\alpha$  and  $\bar{p}_{33_\alpha}$  and a new system is obtained,

$$(1 + a_c \mathcal{G}_1) < p > + \frac{\mathcal{G}_2 b_c}{2} < \bar{p}_{33} > = \frac{\mathcal{G}_1}{2} e + \frac{\mathcal{G}_2}{2} \bar{e}_{33}, \quad (5.20)$$

$$-\frac{\mathcal{G}_2 a_c}{4} < p > + (1 + b_c \mathcal{G}_3) < \bar{p}_{33} > = \mathcal{G}_3 \bar{e}_{33} - \frac{\mathcal{G}_2}{8} e, \quad (5.21)$$

where

$$\mathcal{G}_1 = \sum_{\alpha=1}^q \frac{v_\alpha (\xi_3 - b_c)}{\left(\frac{1}{4} \xi_1 - a_c\right)(\xi_3 - b_c) + \frac{\xi_2^2}{8}}, \quad \mathcal{G}_2 = \sum_{\alpha=1}^q \frac{v_\alpha \xi_2}{\left(\frac{1}{4} \xi_1 - a_c\right)(\xi_3 - b_c) + \frac{\xi_2^2}{8}} \quad \text{and}$$

$$\mathcal{G}_3 = \sum_{\alpha=1}^q \frac{v_\alpha \left(\frac{1}{4} \xi_1 - a_c\right)}{\left(\frac{1}{4} \xi_1 - a_c\right)(\xi_3 - b_c) + \frac{\xi_2^2}{8}}.$$

The system (5.20) – (5.21) is solved with respect to unknown functions  $< p >$  and  $< \bar{p}_{33} >$  and we get,  $< p > = \varphi_1 e + \varphi_2 \bar{e}_{33}$  and  $< \bar{p}_{33} > = \varphi_3 \bar{e}_{33} - 4\varphi_2 e$ , with

$$\varphi_1 = \frac{8\mathcal{G}_1(1 + b_c \mathcal{G}_3) + \mathcal{G}_2^2 b_c}{2[8(1 + a_c \mathcal{G}_1)(1 + b_c \mathcal{G}_3) + \mathcal{G}_2^2 a_c b_c]}, \quad \varphi_2 = \frac{4\mathcal{G}_2}{8(1 + a_c \mathcal{G}_1)(1 + b_c \mathcal{G}_3) + \mathcal{G}_2^2 a_c b_c}$$

$$\text{and} \quad \varphi_3 = \frac{8\mathcal{G}_3(1 + a_c \mathcal{G}_1) + \mathcal{G}_2^2 a_c}{8(1 + a_c \mathcal{G}_1)(1 + b_c \mathcal{G}_3) + \mathcal{G}_2^2 a_c b_c}.$$

Thus, the functional  $A = A_1 + \frac{1}{2} A_2$  can be written in the form,

$$A = \frac{1}{4} [2c_{11}^c + 2c_{13}^c + 2\varphi_1 + \frac{15}{2}\varphi_2] e^2 + [c_{33}^c - c_{11}^c - \frac{15}{2}\varphi_2] \left(\frac{1}{2} e + \bar{e}_{33}\right)^2 + \\ + [2c_{11}^c - 2c_{13}^c + 2\varphi_3 + \frac{15}{2}\varphi_2] \bar{e}_{33}^2 + 2\left[2c_{44}^c + \frac{n_{13}}{1 + b_c n_{13}}\right] \bar{e}_{13}^2.$$

The following notation can be introduced,

$$2c_{11} + 2c_{13} = 2c_{11}^c + 2c_{13}^c + 2\varphi_1 + \frac{15}{2}\varphi_2, \quad (5.22)$$

$$c_{33} - c_{11} = c_{33}^c - c_{11}^c - \frac{15}{2} \varphi_2, \quad (5.23)$$

$$2c_{11} - 2c_{13} = 2c_{11}^c - 2c_{13}^c + 2\varphi_3 + \frac{15}{2} \varphi_2, \quad (5.24)$$

$$2c_{44} = 2c_{44}^c + \frac{n_{13}}{1 + b_c n_{13}}. \quad (5.25)$$

The system (5.22)–(5.25) is solved with respect to the unknown functions  $c_{11}$ ,  $c_{13}$ ,  $c_{33}$  and  $c_{44}$  and we obtain,

$$\begin{aligned} c_{11} &= c_{11}^c + \frac{\varphi_1}{2} + \frac{15\varphi_2}{2} + \frac{\varphi_3}{2}, & c_{13} &= c_{13}^c + \frac{\varphi_1}{2} - \frac{\varphi_3}{2}, \\ c_{33} &= c_{33}^c + \frac{\varphi_1}{2} - \frac{15\varphi_2}{2} + \frac{\varphi_3}{2} & \text{and} & \quad c_{44} = c_{44}^c + \frac{n_{13}}{2(1 + b_c n_{13})}. \end{aligned}$$

The expressions for the bounds of the materials constants  $c_{11}$ ,  $c_{13}$ ,  $c_{33}$  and  $c_{44}$  can be listed as,

$$\begin{aligned} c_{11L} &= c_{11}^{(1)} + \frac{\varphi_1^{(1)}}{2} + \frac{15\varphi_2^{(1)}}{2} + \frac{\varphi_3^{(1)}}{2}, & c_{11U} &= c_{11}^{(q)} + \frac{\varphi_1^{(q)}}{2} + \frac{15\varphi_2^{(q)}}{2} + \frac{\varphi_3^{(q)}}{2}, \\ c_{13L} &= c_{13}^{(1)} + \frac{\varphi_1^{(1)}}{2} - \frac{\varphi_3^{(1)}}{2}, & c_{13U} &= c_{13}^{(q)} + \frac{\varphi_1^{(q)}}{2} - \frac{\varphi_3^{(q)}}{2}, \\ c_{33L} &= c_{33}^{(1)} + \frac{\varphi_1^{(1)}}{2} - \frac{15\varphi_2^{(1)}}{2} + \frac{\varphi_3^{(1)}}{2}, & c_{33U} &= c_{33}^{(q)} + \frac{\varphi_1^{(q)}}{2} - \frac{15\varphi_2^{(q)}}{2} + \frac{\varphi_3^{(q)}}{2}, \\ c_{44L} &= c_{44}^{(1)} + \frac{n_{13}^{(1)}}{2(1 + b_c^{(1)} n_{13}^{(1)})}, & c_{44U} &= c_{44}^{(q)} + \frac{n_{13}^{(q)}}{2(1 + b_c^{(q)} n_{13}^{(q)})}. \end{aligned}$$

## 6. Conclusions

A general procedure for deriving the variational bounds for any type of anisotropic linear elastic composite is studied. Analytical expressions for the bounds of linear, transversely isotropic elastic composite are given. In particular, bounds for two-dimensional case are then calculated. Non limitation about the quantities of inclusions and the geometrical shape of the inclusions are considered for the estimation of the bounds. The method allows us the calculation of all bounds for the material parameters involved in different type of anisotropies and good estimation of the effective properties are obtained.

## Acknowledgments

This work was sponsored by FENOMECA and PAPIIT, DGAPA, UNAM-México, under grant IN101705. Thanks to the project CITMA, Ciencias Básicas IBMFQC 09-2004, Cuba.

#### References

- Pobedrya, B. E. 1984. *Mechanics of Composite Materials*. Moscow State University Press, Moscow, (in Russian).
- Ponte-Castañeda, P. 1992. New variational principles in plasticity and their application to composite materials. *J. Mech. Phys. Solids* 40, 1757–1788.
- Rodriguez-Ramos, R. Pobedria, B.E., Padilla, P., Bravo-Castillero, J., Guinovart-Diaz, R., Maugin, G.A., 2004. Variational principles for nonlinear piezoelectric materials. *Arch. Appl. Mech.* 74, 191-200.
- Willis, J.R., 1991. On methods to bound the overall properties of nonlinear composites. *J. Mech Phys. Solids* 39, 73–86.
- Hashin, Z. 1965. On elastic behaviour of fibre reinforced materials of arbitrary transverse phase geometry. *J. Mech. Phys. Solids*, Vol.13, 119 – 134.

*List of Recent Technical Reports*

46. I. Urrutia-Romaní, R. Rodríguez-Ramos, J. Bravo-Castillero and R. Guinovart-Díaz, *Asymptotic Homogenization Method Applied to Linear Viscoelastic Composites. Examples*, August 2004.
47. Yi Lu and José Garrido, *Double Periodic Non-Homogeneous Poisson Models for Hurricanes Data*, September 2004.
48. M.I. Beg and M. Ahsanullah, *On Characterizing Distributions by Conditional Expectations of Functions of Generalized Order Statistics*, September, 2004.
49. M.I. Beg and M. Ahsanullah, *Concomitants of Generalized Order Statistics from Farlie-Gumbel-Morgenstern Distributions*, September, 2004.
50. Yogendra P. Chaubey and Debaraj Sen, *An investigation into properties of an estimator of mean of an inverse Gaussian population*, September, 2004.
51. Steven N. Evans and Xiaowen Zhou, *Balls-in-boxes duality for coalescing random walks and coalescing Brownian motions*, September, 2004.
52. Qihe Tang, *Asymptotic ruin probabilities of the renewal model with constant interest force and regular variation*, November, 2004.
53. Xiaowen Zhou, *On a classical risk model with a constant dividend barrier*, November, 2004.
54. K. Balasubramanian and M.I. Beg, *Three isomorphic vector spaces-II*, December, 2004.
55. Michael A. Kouritzin and Wei Sun, *Rates for branching particle approximations of continuous-discrete filters*, December, 2004.
56. Rob Kaas and Qihe Tang, *Introducing a dependence structure to the occurrences in studying precise large deviations for the total claim amount*, December, 2004.
57. Qihe Tang and Gurami Tsitsiashvili, *Finite and infinite time ruin probabilities in the presence of stochastic returns on investments*, December, 2004.



58. Alexander Melnikov and Victoria Skorniyakova, *Efficient hedging methodology applied to equity-linked life insurance*, February, 2005.
59. Qihe Tang, *The finite time ruin probability of the compound Poisson model with constant interest force*, June, 2005.
60. Marc J. Goovaerts, Rob Kaas, Roger J.A. Laeven, Qihe Tang and Raluca Vernic, *The tail probability of discounted sums of Pareto-like losses in insurance*, August, 2005.
61. Yogendra P. Chaubey and Haipeng Xu, *Smooth estimation of survival functions under mean residual life ordering*, August, 2005.
62. Xiaowen Zhou, *Stepping-stone model with circular Brownian migration*, August, 2005.
63. José Garrido and Manuel Morales, *On the expected discounted penalty function for Lévy risk processes*, November, 2005.
64. Z. Hu, Z. Ma and W. Sun, *Extensions of Lévy-Khintchine formula and Beurling-Deny formula in semi-dirichlet forms setting*, February, 2006.
65. Z. Hu, Z. Ma and W. Sun, *Formulae of Beurling-Deny and LeJan for non-symmetric dirichlet forms*, February, 2006.
66. Z. Hu and W. Sun, *A note on exponential stability of the nonlinear filter for denumerable Markov chains*, February, 2006.
67. H. Brito-Santana, R. Rodríguez-Ramos, R. Guinovart-Díaz, J. Bravo-Castillero and F. J. Sabina, *Variational bounds for multiphase transversely isotropic composites*, August, 2006.

*Copies of technical reports can be requested from:*

Prof. Xiaowen Zhou  
Department of Mathematics and Statistics  
Concordia University  
1455 de Maisonneuve Blvd West  
Montréal (QC) H3G 1M8 CANADA