

# MULTISCALE DISPERSION CHARACTERIZATION AND BREAKDOWN OF NANOCLAY CLUSTERS DURING MOLDING

L. Aktas\*, S. Dharmavaram\*, Y. K. Hamidi\*, and M. C. Altan\*  
Composites Research Group  
School of Aerospace and Mechanical Engineering University of Oklahoma  
Norman, Oklahoma 73019  
altan@ou.edu

## ABSTRACT

Thermo-mechanical properties of polymers can be significantly altered by the addition of nano-scale particulates such as carbon nanotubes and nanofibers. Among the nano-scale particulates, inclusion of nanoclay is proven to improve thermal and mechanical properties of polymers significantly even at small volume fraction levels. In addition, nanoclay is a viable commercial alternative to conventional fillers owing to its low-cost and accessibility. However, akin to various particulates, extensive agglomeration of nanoclay in polymer matrices presents difficulties in its utilization.

In this study, we implement a multi-scale approach to characterize the dispersion of three different types of nanoclays. Cloisite<sup>®</sup> 15A, 25A and 30B are individually mixed with Epon 815C epoxy resin, by the aid of a sonicator. The resin/nanoclay compound is then mixed with Epi-cure 3282 curing agent and injected into center-gated disk shaped molds. The dispersion state of nanoclay is characterized by using samples cut along the radius of the molded composite disks. Nanoclay clusters larger than 1.5 $\mu\text{m}$  are characterized by performing digital image analysis on the scanning electron micrographs, whereas smaller clusters are identified by wavelength dispersive spectrometry. In addition, intra-cluster structure is studied by transmission electron microscopy.

It is found that the effectiveness of dispersion increases in the order of Cloisite<sup>®</sup> 15A, 25A and 30B. For instance the average content of clusters larger than 1.5 $\mu\text{m}$  is determined as 4.6vol.% for Cloisite<sup>®</sup> 15A, whereas the same value for 25A and 30B are 3.39vol.% and 3.45vol.%, respectively. The nanoclay clusters are observed to break down into smaller pieces in the flow direction, regardless of the nanoclay type. For example, small Cloisite<sup>®</sup> 30B clusters ( $Area < 3\mu\text{m}^2$ ) make up 37.8% of the nanoclay content at the inlet, whereas the same value is calculated to be 46% at the outer edge of the disk. Several nano-voids are detected in the intra-cluster regions from the TEM images. These nano-voids are suspected to result from insufficient dispersion of nanoclay in epoxy matrix.

---

\*Member, ASME

## References

1. Ahmadi S. J.; Huang Y. D. and Li W. *J. Mater. Sci.* 2004, 39, 1919-1925
2. Aktas L., Dharmavaram. S., Hamidi. Y. K. and Altan. M. C. Quantitative Analyses of Nanoclay Dispersion in Molded Epoxy Disks: Effects of Mixing Temperature. In: *Nanomaterials: New Research*. Nova Science Publishers. New York. pp. 197-218. 2005
3. Usuki, A.; Kawasumi, M.; Kojima, Y.; Okada, A.; Kurauchi, T.; Kamigaito, O. *J. Mater. Res.* 1993, 8, 1174-1178.
4. Aktas L., Hamidi Y. K. and Altan M. C. *Plastics. Rubber and Composites: Macromolecular Engineering.* 33(6): 267-272. 2004
5. Usuki, A.; Kojima, Y.; Kawasumi, M.; Okada, A.; Fukushima, Y.; Kurauchi, T.; Kamigaito, O. *J. Mater. Res.* 1993, 8, 1179-1184.
6. Kojima, Y.; Usuki, A.; Kawasumi, M.; Okada, A.; Fukushima, Y.; Kurauchi, T.; Kamigaito, O. *J. Mater. Res.* 1993, 8, 1185-1189.
7. Pinnavaia, T. J.; Lan, T.; Kaviratna, P. D.; Wang, Z.; Shi H. *Polym. Mater. Sci. Eng.* 1995, 73, 117-118.
8. Wang, H.; Zeng, C.; Elkovitch, M.; Lee, L. J.; Koelling, K. W. *Polym. Eng. Sci.* 2001, 41, 2036-2046.
9. Abot, J. L.; Yasmin, A.; and Daniel, I. M.; *Mater. Res. Soc. Symp. Proc.* 2003, 740, 162-177.