



The Structure of Na_xPt₃O₄

Jürg Waser and Edwin D. McClanahan Jr.

Citation: *The Journal of Chemical Physics* **20**, 199 (1952); doi: 10.1063/1.1700180

View online: <http://dx.doi.org/10.1063/1.1700180>

View Table of Contents: <http://scitation.aip.org/content/aip/journal/jcp/20/1?ver=pdfcov>

Published by the AIP Publishing

Articles you may be interested in

[Structure-property correlations in La_{1-x}Na_xMnO₃ manganites](#)

AIP Conf. Proc. **1447**, 1137 (2012); 10.1063/1.4710409

[Structural, electrical, and magnetic properties of polycrystalline Fe_{3-x}Pt_xO₄ \(0 ≤ x ≤ 0.10\) films](#)

J. Appl. Phys. **109**, 073905 (2011); 10.1063/1.3563080

[Structural and thermal properties of \(YBa₂Cu₃\)_{1-x}Na_xO_{7-δ} materials](#)

Appl. Phys. Lett. **63**, 3072 (1993); 10.1063/1.110236

[The Crystal Structure of NaPt₃O₄](#)

J. Chem. Phys. **19**, 413 (1951); 10.1063/1.1748239

[The Crystalline Structure of Pt₃O₄](#)

J. Chem. Phys. **9**, 875 (1941); 10.1063/1.1750860



NEW Special Topic Sections

NOW ONLINE
Lithium Niobate Properties and Applications:
Reviews of Emerging Trends

AIP | Applied Physics Reviews

properties and the x-ray pattern of PtO_2 are both dependent on the heat treatment.

(2) *The substance studied by Moore and Pauling⁶ was probably not PtO.* They write: "PdO was prepared by the method of Shriner and Adams¹¹ involving fusing palladous chloride and potassium nitrate; and PtO by a similar method." . . . "The data are not sufficient to permit a rigorous structure determination to be made for PtO, but the similarity to the PdO photographs makes it highly probable that platinumous oxide has the PdO structure . . ."

The existence of PtO is questioned in Gmelin's handbook.¹² Wöhler and Frey¹³ discuss the preparation of this compound and its easy oxidability. We think the method of Shriner and Adams¹¹ applied to H_2PtCl_4 (because PtCl_2 is insoluble) would give PtO_2 , because of the oxidizing properties of fused KNO_3 . Moore and Pauling have not analyzed the compound obtained, so it is difficult to find out what they have actually studied.

In conclusion, the structure given for PtO is not supported by sufficient experimental evidence. It is doubtful if the authors prepared PtO or not.

(3) *It is possible to prepare the hydrate of PtO by the method of Wöhler and Frey.¹³* The dehydration of this compound gives an oxide whose composition fits well the formula PtO. The x-ray pattern is platinum-like. The only difference is that the parameters of PtO are slightly enlarged with respect to Pt. Chemically, the oxide cannot be confused with platinum because it is insoluble in aqua regia, and its density is very much lower (lying between 11.5 and 14 g/cm³). In the course of a great number of preparations of this substance, we have never found the lines reported by Moore and Pauling.

(4) *On some occasions, we have prepared the platinum oxide studied by Galloni and Roffo and have found the formula Pt_3O_4 together with the x-ray pattern reported by them.* It has been obtained by thermal decomposition of hydrated PtO_2 , but it has not been possible to find a reproducible method of preparation, in spite of very numerous experiments. In two instances the right oxide has appeared, but the conditions upon which its preparation depend are not clear to us.

In conclusion, for the reasons given, we think that the compound studied by Waser and McClanahan is not $\text{Pt}_3\text{O}_4\text{Na}$, that the hexagonal pattern reported by Busch is caused by PtO_2 , that the pattern reported by Galloni and Roffo is caused by Pt_3O_4 , and finally, that the structure given to PtO by Moore and Pauling is open to discussion. Even the existence of anhydrous PtO is open to discussion.

We are indebted to Dr. J. Winkel for obtaining the spectrograms.

¹ J. Waser and E. McClanahan, *J. Chem. Phys.* **19**, 413 (1951).

² S. M. Jørgensen, *J. prakt. Ch.* **16**, 344 (1877).

³ E. E. Galloni and A. E. Roffo, *J. Chem. Phys.* **9**, 875 (1941).

⁴ R. H. Busch, *Z. Naturforschung* **5a**, 130 (1950).

⁵ W. J. Moore and L. Pauling, *J. Am. Chem. Soc.* **63**, 1392 (1941).

⁶ R. Vorhees and R. Adams, *J. Am. Chem. Soc.* **44**, 1397 (1922).

⁷ Busch, Cairo, Galloni, and Raskovan, 14a. Reunión de la Asociación Física Argentina, La Plata (1949).

⁸ Finch, Murison, Stuart, and Thomson, *Proc. Roy. Soc. (London)* **A 141**, 414 (1933).

⁹ S. Altmann and R. H. Busch, *Trans. Faraday Soc.* **45**, 720 (1949).

¹⁰ L. Pigeon, *Ann. chim. et phys.* (7), **2**, 480 (1894).

¹¹ Shriner and R. Adams, *J. Am. Chem. Soc.* **46**, 1684 (1924).

¹² Gmelin, *Handbuch der anorganischen Chemie*, eighth edition (1938), Vol. 68, part C.

¹³ L. Wöhler and W. Frey, *Z. Elektrochem.* **15**, 133 (1909).

The presence of sodium in our compound was inferred from the following facts. An electron density projection showed the presence of a concentration of scattering matter of approximately the correct magnitude for one Na-atom per each four O-atoms. This peak could not have been caused by breaking-off errors since the Pt-contributions had been subtracted from the observed F 's. Thus our projection contained neither Pt peaks nor the subsidiary features which ordinarily accompany large peaks and are caused by termination of the Fourier series. The analogous breaking-off features of the oxygen peaks are correspondingly smaller and have a negligible effect on the sodium peak. The inclusion of a scattering contribution from Na at the positions $2a$ of O_h^3 significantly improved the agreement between calculated and observed intensities. The presence of Na further explains the ionic conductivity observed by us and the sodium content Wöhler reported for his preparations.³

However, as indicated in our paper, the compound NaPt_3O_4 need not be of stoichiometric nature as far as sodium is concerned. The Na-atoms (or ions) are situated in holes formed by cubes of O-atoms, and the number of holes filled in various preparations may vary. The further possibility of filling the holes with other suitable cations exists.

Our findings may thus be reconciled with those of Galloni and Busch¹ by assuming the existence of a whole series of compounds of the formula $\text{Na}_x\text{Pt}_3\text{O}_4$, $0 \leq x \leq 1$, all having the same framework of Pt and O-atoms described in our paper.³ A more detailed investigation is, however, required to clear up completely this question of solubility of Na and possibly other cations in Pt_3O_4 .

We have now had the opportunity to analyze for sodium our original very small sample of $\text{Na}_x\text{Pt}_3\text{O}_4$ which had been used in the x-ray experiments. The sample was treated with strong HCl containing KI followed by boiling with aqua regia. Only a portion of the sample went into solution, the exact amount dissolved being unknown. Analysis with a Beckman flame spectrophotometer showed that the original sample contained 1.3 percent Na or more. As reported previously our preparation had been extracted several times with hot aqua regia to remove traces of Pt. The Na is therefore presumed to be part of the compound.

We wish to thank Dr. R. V. Talmage for the use of the flame spectrophotometer.

¹ E. E. Galloni and R. H. Busch, *J. Chem. Phys.* **19**, 198 (1951).

² J. Waser and E. D. McClanahan, Jr., *J. Chem. Phys.* **19**, 413 (1951).

³ L. Wöhler, *Z. anorg. u. allgem. Chem.* **40**, 450 (1904).

Carrier-Free Radioisotopes from Cyclotron Targets. XXIV. Preparation and Isolation of $\text{Ir}^{188, 190, 192}$ from Osmium*

HERMAN R. HAYMOND, WARREN M. GARRISON, AND JOSEPH G. HAMILTON
*Crocker Laboratory, Radiation Laboratory, Divisions of Medical Physics,
Experimental Medicine and Radiology, University of California,
Berkeley and San Francisco, California*
(Received October 26, 1951)

BOMBARDMENT of osmium with 19-Mev deuterons produces, by ($d, 2n$) and (d, n) reactions, several relatively long-lived, known, radioactive isotopes of iridium:^{1,2} Ir^{187} , Ir^{188} , two isomers of Ir^{190} , and Ir^{192} . Radioisotopes of rhenium and osmium are also produced concurrently in relatively low yield by (n, p) and (d, p) reactions. This paper reports a method for isolation of iridium activities from irradiated osmium without the addition of stable iridium carrier.

The target was osmium metal powder (ca. 0.5g) in which no iridium (less than 0.01 percent) was detected by spectrographic analysis. The osmium powder was held on a grooved, water-cooled target plate by a 0.25-mil platinum foil during bombardment in the 60-inch Crocker Laboratory cyclotron.

After bombardment the osmium powder was dissolved, with heating, in a minimal amount of aqua regia. Excess nitric acid was added and the solution was heated to dryness to distill off the osmium tetroxide. Two milliliters of nitric acid were added and

The Structure of $\text{Na}_2\text{Pt}_3\text{O}_4$

JÜRIG WASER AND EDWIN D. McCLANAHAN, JR.
Department of Chemistry, The Rice Institute, Houston, Texas
(Received August 10, 1951)

IN the preceding note Galloni and Busch¹ report the results of a spectroscopic analysis of a platinum oxide similar to the compound recently investigated by us.² While their compound apparently did not contain significant amounts of sodium, we had assigned the formula NaPt_3O_4 to our preparation.