

## Supporting Information

Precise Synthesis of Bottlebrush Block Copolymers from  $\omega$ -End-Norbornyl Polystyrene and Poly(4-*tert*-butoxystyrene) via Living Anionic Polymerization and Ring-Opening Metathesis Polymerization

Yong-Guen Yu,<sup>†,‡</sup> Chang-Geun Chae,<sup>†,‡</sup> Myung-Jin Kim,<sup>†,‡</sup> Ho-Bin Seo,<sup>†,‡</sup> Robert H. Grubbs,<sup>†,§</sup> and Jae-Suk Lee<sup>\*,†,‡</sup>

<sup>†</sup>School of Materials Science and Engineering and <sup>‡</sup>Grubbs Center for Polymers and Catalysis, Gwangju Institute of Science and Technology (GIST), 123 Cheomdangwagi-ro, Buk-gu, Gwangju 61005, Republic of Korea.


<sup>§</sup>Division of Chemistry and Chemical Engineering, California Institute of Technology (Caltech), Pasadena, California 91125, United States.

E-mail: [jslee@gist.ac.kr](mailto:jslee@gist.ac.kr); Tel: (+82)-62-715-2306.


### Contents

- 1. <sup>1</sup>H and <sup>13</sup>C NMR spectra of chemical compounds**
- 2. Physical data of macromonomer**
- 3. Additional SEM images and photographs of films**
- 3. Additional kinetic profile on ROMP of NPSt in THF at room temperature ([NPSt]<sub>0</sub> = 0.05 M)**


## 1. $^1\text{H}$ and $^{13}\text{C}$ NMR spectra of chemical compounds




**Figure S1.**  $^1\text{H}$  NMR spectrum of 2,2,5,5-tetramethyl-1-(3-chloropropyl)-1-aza-2,5-disilacyclopentane (T1) in  $\text{CDCl}_3$  (400 MHz).




**Figure S2.**  $^{13}\text{C}$  NMR spectrum of 2,2,5,5-tetramethyl-1-(3-chloropropyl)-1-aza-2,5-disilacyclopentane (T1) in  $\text{CDCl}_3$  (100 MHz).




**Figure S3.** <sup>1</sup>H NMR spectrum of *N*-(carboxylhexanoyl)-*cis*-norbornene-*exo*-2,3-dicarboxiimide in CDCl<sub>3</sub> (400 MHz).




**Figure S4.** <sup>13</sup>C NMR spectrum of *N*-(carboxylhexanoyl)-*cis*-norbornene-*exo*-2,3-dicarboxiimide in CDCl<sub>3</sub> (100 MHz).




**Figure S5.** <sup>1</sup>H NMR spectrum of *N*-(perfluorophenyl hexanoate)-*cis*-norbornene-*exo*-2,3-dicarboxiimide (T2) in CDCl<sub>3</sub> (400 MHz).




**Figure S6.** <sup>13</sup>C NMR spectrum of *N*-(perfluorophenyl hexanoate)-*cis*-norbornene-*exo*-2,3-dicarboxiimide (T2) in CDCl<sub>3</sub> (100 MHz).




**Figure S7.**  $^9\text{F}$  NMR spectrum of *N*-(perfluorophenyl hexanoate)-*cis*-norbornene-*exo*-2,3-dicarboxiimide (T2) in  $\text{CDCl}_3$  (376 MHz).




**Figure S8.**  $^1\text{H}$  NMR spectrum of  $\text{PSt-NH}_2$  in  $\text{CDCl}_3$  (400 MHz).




**Figure S9.** <sup>1</sup>H NMR spectrum of PtBOS-NH<sub>2</sub> in CDCl<sub>3</sub> (400 MHz).




**Figure S10.** <sup>1</sup>H NMR spectrum of NPSt in CDCl<sub>3</sub> (400 MHz).




**Figure S11.**  $^1\text{H}$  NMR spectrum of NPtBOS in  $\text{CDCl}_3$  (400 MHz).



**Figure S12.**  $^1\text{H}$  NMR spectrum of  $\text{P}(\text{NB-g-St})_{630}$  in  $\text{CDCl}_3$  (400 MHz).



**Figure S13.**  $^1\text{H}$  NMR spectrum of  $\text{P}(\text{NB-g-tBOS})_{154}$  in  $\text{CDCl}_3$  (400 MHz).



**Figure S14.**  $^1\text{H}$  NMR spectrum of  $\text{P}(\text{NB-g-St})_{151}\text{-b-}\text{P}(\text{NB-g-tBOS})_{140}$  in  $\text{CDCl}_3$  (400 MHz).




## 2. Physical data of macromonomers

**Table S1. Characteristics of  $\omega$ -norbornyl macromonomers**


entry	MM	$M_{n,NMR}$ (kDa)	$M_{n,obsd}^a$ (kDa)	$\bar{D}^a$	$DP_n$
1	NPSt	2.76	2.69	1.14	24
2	NPSt	3.23	3.37	1.07	28
3	NP <i>t</i> BOS	2.79	2.43	1.06	14
4	NP <i>t</i> BOS	3.13	3.01	1.06	16

<sup>a</sup> $M_{n,obsd}$  and  $\bar{D}$  were obtained by SEC calibration using polystyrene standard in THF containing 2% trimethylamine as the eluents at 40 °C.




**Figure S15.** GPC curves of the macromonomers of (a) NPSt and (b) NP*t*BOS

### 3. Additional SEM images and photographs of films of Bottlebrush block copolymers




**Figure S15.** Cross-sectional SEM image of P(NB-*g*-St)-*b*-P(NB-*g*-*t*BOS) with  $M_w = 148$  kDa and  $DP_w = 52$  (Table 2, entry 1).



**Figure S16.** Cross-sectional SEM images and photographs of photonic films of P(NB-*g*-St)-*b*-P(NB-*g*-*t*BOS) with (a,b)  $M_w = 296$  kDa (Table 2, entry 2), (c,d)  $M_w = 830$  kDa (Table 2, entry 3), and (e,f)  $M_w = 1331$  kDa (Table 2, entry 4).

**4. Additional kinetic profile on ROMP of NPSt in THF at room temperature  
([NPSt]<sub>0</sub> = 0.05 M)**



**Figure S17.** SEC traces of P(NB-g-St) aliquots with  $[\text{NPSt}]_0/[\text{G3}]_0 = 650$  withdrawn from mixture during ROMP at time intervals (Table1, entry 3).