

2019

# Phase Separation: Bridging Polymer Physics and Biology

Sarah L. Perry

*University of Massachusetts Amherst*

Follow this and additional works at: [https://scholarworks.umass.edu/che\\_faculty\\_pubs](https://scholarworks.umass.edu/che_faculty_pubs)

---

## Recommended Citation

Perry, Sarah L., "Phase Separation: Bridging Polymer Physics and Biology" (2019). *Current Opinion in Colloid and Interface Science*. 866.

<https://doi.org/10.1016/j.cocis.2019.01.007>

This Article is brought to you for free and open access by the Chemical Engineering at ScholarWorks@UMass Amherst. It has been accepted for inclusion in Chemical Engineering Faculty Publication Series by an authorized administrator of ScholarWorks@UMass Amherst. For more information, please contact [scholarworks@library.umass.edu](mailto:scholarworks@library.umass.edu).

# Phase Separation: Bridging Polymer Physics and Biology

Sarah L. Perry<sup>1,2\*</sup>


<sup>1</sup>Department of Chemical Engineering, University of Massachusetts Amherst, Amherst, MA 01003, USA

<sup>2</sup>Institute for Applied Life Sciences, University of Massachusetts Amherst, Amherst, MA 01003, USA

\*Corresponding email: [perrys@engin.umass.edu](mailto:perrys@engin.umass.edu)

## Abstract:

Significant parallels exist between the phase separation behavior of polymers in solution and the types of biomolecular condensates, or 'membraneless organelles,' that are of increasing interest in living systems. Liquid-liquid phase separation allows for compartmentalization and the sequestration of materials, and can be harnessed as a sensitive strategy for responding to small changes in the environment. Here, I review many of the parallels and synergies between ongoing efforts to study and take advantage of phase separation in living vs. synthetic materials.



## 1. Introduction

The scientific community has long looked to nature for inspiration. This is particularly true in the case of self-assembling materials, where living cells have developed extremely complex systems that achieve exquisite levels of control over chemical reactions, signaling, and data transfer based purely on the complex interactions between molecules. In looking to understand and learn from these systems there is a natural tension between more reductionist, physics-based approaches that look to distill the inherent complexity of a living system down to an elegant set of fundamentals, and biochemical approaches that work to explore the network from within.

Over the last decade there has been an explosion of research demonstrating the importance of self-assembling, liquid phase separated domains in both eukaryotic cells [1-8] and bacteria [9,10]. These droplets of RNA and protein, commonly referred to as 'membraneless organelles,' take advantage of liquid-liquid phase separation to achieve intracellular compartmentalization while enabling rapid exchange of their contents with the surroundings. Tremendous work has been done to identify the biological components that drive the formation of these biomolecular condensates,[11] and ongoing efforts are exploring their functional role in the cell.

At the same time, there have been large-scale efforts in the materials science community focused on studying liquid-liquid phase separation of polymers in water. This work includes investigations of various aqueous two-phase systems, such as the segregative phase separation observed for systems of poly(ethylene glycol)/dextran [12], polymers that undergo either a lower critical solution temperature (LCST) transition or an upper critical solution temperature (UCST) transition based on interactions with water [8], such as elastin-like polypeptides (ELPs) [13,14], and complex coacervation as a form of associative phase separation involving multiple species [15-20] or via self-coacervation of polyampholytes [21-24]. Various aspects of these phase separating systems have relevance to the formation and properties of membraneless organelles. In particular, the formation of these condensates is most closely associated with the types of molecular interactions implicated in complex coacervation and LCST/UCST behavior [5,6,8,25,26]. Here, I will discuss parallels, challenges, and potential synergies associated with extending the results of elegant, reductionist studies of simplified materials systems to the levels of molecular, chemical, and conformational diversity present in living systems.

## 2. The Benefits of Phase Separation

In the context of a complex network of reactions, compartmentalization allows for the segregation of incompatible processes as well as providing a means for imposing spatiotemporal control over the system. The critical feature of any compartment is the defining interface. While cells achieve some of this organization through the use of more traditional membrane-bound organelles, the benefits of such a robust and relatively impermeable boundary can also be a weakness, as the flow of material across a lipid bilayer can require energy-consuming transport mechanisms and specialized machinery.


In contrast, liquid-liquid phase separation allows for the creation of an interface that does not inhibit the easy transport of materials into and out of the compartment. Diffusion occurs along the direction of a gradient in chemical potential. Typically, this means that diffusion in solution occurs from areas of high to low concentration. However, at an interface between two equilibrium phases, such as those present in a liquid-liquid phase separated system, the difference in the chemical potential is zero. Simultaneously, the materials that define the two phases might have different affinities for the solute molecules. As a consequence, liquid-liquid phase separated materials can facilitate and maintain a step-jump in the concentration of a given species without limiting transport across the interface. This natural partitioning of materials can then be used to locally generate high concentrations of reactants or spatially co-localize a cascade of reactions for efficient chemistry. A detailed discussion of diffusive behavior across interfaces in the context of liquid-liquid phase separation in biology is given in a recent review by Hyman *et al.* [3].

## 3. Life Exists Near Tipping Points

In addition to the benefits of an existing compartment, the formation and dissolution of liquid-liquid phase separated, or otherwise reversibly aggregated, materials can be triggered by small variations in concentration and/or solution conditions [26]. Living systems have harnessed this kind of tunability, using liquid-liquid phase separation to respond to environmental and/or metabolic stresses and sequester

enzymes and potentially RNA components related to the affected pathway [3,25,27-29]. In one example, all six enzymes related to purine biosynthesis in HeLa cells were shown to cluster into punctate 'purinosomes' when cells were grown in purine-depleted media, but were spread diffusely through the cytoplasm in the absence of the metabolic stress [30-33]. It has been hypothesized that this ability of the cell to cluster closely related metabolic enzymes could provide an efficient means for regulating the flux of product species in response to variations in environmental conditions. Thus when clustered, more efficient biosynthesis can take place along the multi-enzyme cascade with the low levels of material that are present in the cell, while the dissolution of the clusters slows production when levels are higher. However, the exact mechanisms whereby the cell triggers purinosome formation remain under investigation.

In a more dynamic example, recent work by Brangwynne and coworkers demonstrated how weak gradients in the concentration of a protein Mex-5 are used to regulate position-dependent formation of P granules to achieve asymmetric cell division (**Figure 1**) [34]. Furthermore, experimental evidence indicates that this phase separation takes advantage of many weak, multivalent interactions to facilitate the formation of P granules while maintaining a low overall concentration of protein within the droplet [35]. These results are particularly exciting because they highlight how the cell is able to achieve dramatic structural rearrangements in a near-passive way, with minimal energy and material requirements.



**Figure 1.** (a) Schematic representation of the polarized, one-cell stage *C. elegans* embryo prior to asymmetric cell division. Cell polarity is established by asymmetric localization of proteins in the anterior (red) and posterior (black) cell membranes. This asymmetry is required to generate a cytoplasmic gradient of Mex-5 protein (gray). P granules (green) segregate to the posterior side where they grow, while they disappear in the anterior side. (b) False color representation of fluorescence intensity indicating the gradient of Mex-5 in the cell. (c) Composite micrograph highlighting the presence of fluorescently-labeled P granules localized to the posterior of the *C. elegans* embryo. Reprinted figure with permission from Ref. [34] [Lee, Brangwynne, Gharakhani, Hyman, Julicher. *Phys Rev Lett.* 2013, **111**:088101] Copyright 2013 by the American Physical Society.

In contrast to the ways in which cells are able to respond to very subtle environmental cues, the majority of synthetic phase separating systems require a more dramatic response. This is not to say that biopolymers somehow possess different types of interactions than those synthesized in the laboratory. However, the inherent polydispersity in length and/or the lack of control over the sequential presentation of chemistry means that the phase behavior and material properties of synthetic polymers are the averaged result of a more diverse population of molecules than in many living tissues.


Interestingly, while there are an increasing number of examples where cells use liquid-liquid phase separation in response to a specific stimulus, compartmentalization also provides a way for the cell to passively filter noise, and avoid responding to small variations in a particular signal [36]. Thus, compartmentalization is key in both identifying the important stimuli, and then acting upon them. However, the ability of either living or biomimetic synthetic systems to distinguish between and then take advantage of varying low-level signals represents a challenge for future experiments.

#### 4. Crowding and Entropy vs. 'Soft Interactions' and Enthalpy

The intracellular environment, regardless of compartmentalization, is extremely crowded. (~20-40% protein by mass) [37-39]. While the concentration of an individual species might not be high, the total concentration of biomacromolecules is enough to decrease entropy due to crowding and volume

exclusion. The study of entropic effects has focused mainly on reactions, or equilibria, where conformational changes occur, as crowding favors smaller, more compact states [37,39-65]. For instance, crowding increases the renaturation rate of DNA by 1-2 orders of magnitude, drives the association of 70S ribosomes from 30S and 50S particles, favors actin filament growth, and has been used to explain the function of molecular chaperones [40,49,64,66]. Additionally, Pielak and coworkers recently performed elegant experiments demonstrating that the shape of a protein can determine whether a crowded environment is stabilizing or destabilizing using two different dimeric variants of the B1 domain of protein G [67].

While the potential importance of crowding is very intuitive, there are also many cases where crowding has not produced the expected result. For instance, despite favoring the more compact, folded conformation of a protein, high levels of crowding were insufficient to drive folding of a variant of protein L [68]. Data from in-cell NMR experiments demonstrated that enthalpic, protein-protein interactions helped to stabilize the unfolded form of protein L against the entropic effects of crowding. In a landmark paper, McGuffee and Elcock utilized Brownian dynamics simulations of a molecular model of the *E. coli* cytoplasm to demonstrate that macromolecular crowding alone cannot account for the observed diffusive behavior of proteins *in vivo*, and the subtle electrostatic and hydrophobic interactions between protein molecules must be taken into account [69].



**Figure 2.** Impact of different crowding agents on the stability of chymotrypsin inhibitor 2 (CI2). The backbone of CI2 colored based on the relative change in free energy ( $\Delta\Delta G_{op}'$ ) in the presence of (a) 100.0 g/L and (b) 130.0 g/L dry weight reconstituted cytosol. (c) Changes in the average global stability of CI2 in the presence of a range of different crowding materials. The color scales in (a) and (b) correspond to that shown in (c). Figure adapted with permission from Ref. [70] Sarkar, Smith, and Pielak, *Proc. Natl. Acad. Sci. U.S.A.* 2013, **110**:19342–19347.

While a number of excellent studies have taken advantage of *in situ* measurements such as in-cell NMR to study aspects of biomolecules in their native environment [33,71], one of the most significant limitations associated with efforts to study the effect of the material environment on the stability, activity, and/or structure of a given protein or other biomolecule is the challenge of reconstituting the complexity of the cellular microenvironment in solution. Commonly used crowding agents, such as polyethylene glycol (PEG), dextran, and Ficoll, as well as related aqueous two-phase system (ATPS) strategies [12,72], are accessible, but do not recapitulate either the chemical composition of the cell interior or the specific interactions that are at play, and can potentially give misleading results [73,74]. In a dramatic example, Pielak and coworkers used proton-exchange NMR experiments to quantify changes in the stability of chymotrypsin inhibitor 2 in the presence of crowding agents ranging from polymers to purified proteins to

reconstituted cytosol. Stability, quantified as a relative change in the free energy required to expose amide protons to solvent ( $\Delta\Delta G_{op}^{\circ}$ ), varied dramatically over a range of +0.5 kcal/mol to -0.8 kcal/mol (it should be noted that the overall stability of the protein is greater than 6.0 kcal/mol) [75], with minimally-interacting crowding agents like Ficoll providing stabilization, while the reconstituted cytosolic environment proved to be destabilizing (**Figure 2**) [70,71,75].

## 5. Liquid-Liquid Phase Separation: Segregation, Purification and Stabilization

While the use of in-cell studies and reconstituted cytosol have utility in the context of biophysical experimentation, proteins are involved in an increasing number of real-world applications that could benefit from bioinspired stabilization strategies. For instance, NMR-based studies have shown that charge-charge interactions between a protein and a crowding molecule can be stabilizing if they are repulsive (*i.e.*, effectively increasing the excluded volume). In contrast, attractive charge-based or hydrogen bonding interactions tend to be destabilizing because unfolding of the protein tends to expose more surface to interact with [71,76]. These results raise the question of whether tailored materials that undergo liquid-liquid phase separation could be used as a purification strategy, and/or to create formulations with enhanced stability and/or activity.


In terms of purification, elastin-like polypeptides (ELPs) have been used as a purification tag on recombinantly expressed proteins using a protocol termed the inverse transition cycle (ITC) [13,77,78]. ELPs are artificial polypeptides, derived from the pentapeptide repeats, (VPGXG), found in human tropoelastin, where X can be any amino acid other than proline [13]. ELPs typically undergo a reversible phase transition when heated above a critical temperature (*i.e.*, LCST behavior), which can be tuned through judicious choice of the variable amino acid X, the length of the peptide, and the ionic strength of the solution. In this way, cycles of salt concentration and/or temperature have been shown to produce equivalent protein purity as immobilized metal ion affinity chromatographic methods, but in less time and with fewer equipment requirements [78].

Dubin and coworkers have also demonstrated the utility of direct coacervation for protein purification [79-82]. In fact, the charge-charge interactions that drive coacervation were sufficient to enable separation of two isoforms of  $\beta$ -lactoglobulin that differ only by two amino acids [81]. Recent work by our lab has highlighted the potential for using polymers with patterns of charge to enhance the uptake of specific proteins into the coacervate phase [83]. While the use of complex coacervation requires the addition of additional polymers to facilitate phase separation, judicious polymer selection should facilitate straightforward downstream purification, if needed. However, for applications such as drug delivery, sensing, or biocatalysis, the associating polymer could potentially be utilized in the subsequent formulation or device fabrication.

While most of the reports on the complex coacervation of proteins take advantage of the charge nature of the protein itself, Obermeyer and coworkers recently reported a strategy that takes advantage of recombinantly expressed short ionic peptide tags (6 – 18 amino acids) to facilitate the phase separation of tagged proteins via complex coacervation [84]. Of particular note was the result that proteins with the same total amount of charge distributed isotropically on the protein surface showed lower stability against dissolution by salt than proteins where coacervation with a strong polyelectrolyte was driven by the presence of an ionic tag. These results suggest a range of interesting potential applications, from protein purification to the colocalization of enzymes, and more.

Complex coacervation has also been used to enhance the stability, and potentially the activity, of an incorporated protein. In fact, many examples have taken advantage of block copolymer architecture to facilitate the uptake of proteins into nanometer-scale coacervate-core micelles. Examples include the stabilization of the fluorescent protein mCherry [85], improvements in the activity of encapsulated lipase [86], and stabilization of an organophosphate hydrolase for use in the enzymatic decomposition of nerve agents [87]. The strategy associated with incorporating organophosphate hydrolase into a micellar coacervate structure is particularly noteworthy because of the need to perform the reaction in the presence of both water and an organic solvent. The phase-separated nature of the coacervate core protected the protein against denaturation, while simultaneously maintaining sufficient water in the coacervate matrix to facilitate the decontamination reaction.

While it is easy to draw parallels between the use of liquid-liquid phase separation in the above examples and the types of biomolecular condensates observed in cells, one important difference is the sequence specificity of the ‘polymers’ present in living systems. Given the sheer diversity of folded protein structure and surface chemistry, the idea of designing a specific interaction can be daunting. However, in a very exciting report, Xu and coworkers demonstrated that control over the statistical monomer distribution in a random heteropolymers allowed for creation of a chaperone-like polymer shell that improved protein stability in both water and organic solvents [88]. The statistical design of the heteropolymers was informed by analysis of the size and spacing between clusters of residues with the same properties (*i.e.*, positive charge, negative charge, hydrophobic, and neutral hydrophilic) (**Figure 3**). In fact, the ability of these random heteropolymers to flexibly adapt to stabilize the folded state of a protein enabled the cell-free synthesis and proper folding of the membrane protein aquaporin at levels an order of magnitude higher than with traditional liposome-based technologies. The elegance of this approach comes from the way in which it took inspiration from biology, while taking advantage of the flexibility and scalability of traditional polymer synthesis.



**Figure 3.** Design of random heteropolymers based on protein surface pattern for protein solubilization and stabilization in organic solvents. **(a)** Space-filling protein structures for horseradish peroxidase (HRP), glucose oxidase (GOx), green fluorescent protein (GFP), and  $\alpha$ -chymotrypsin ( $\alpha$ -CT) showing the chemical heterogeneity of the surface. Colors indicate different chemistries: neutral hydrophilic, blue; hydrophobic, red; positively charged, green; negatively charged, purple. **(b)** The histograms of the diameter and the inter-patch distance for hydrophobic groups. **(c)** Designed random heteropolymer with statistical distribution of monomers with varied hydrophobicity matching that of the protein. **(d)** The random heteropolymer can co-assemble with protein (schematically shown as a patchy particle) in organic media and adjust its local conformation to maximize protein-heteropolymer interactions without denaturing the protein’s local structure. Figure adapted from Ref. [88] Panganiban, Qiao, Jiang, DelRe, Obadia, Nguyen, Smith, Hall, Sit, Crosby, Dennis, Drockenmuller, de la Cruz, and Xu, *Science* 2018, **359**:1239–1243. Reprinted with permission from AAAS.

## 6. Liquid-Liquid vs. Liquid-Solid Phase Separation

In addition to a wide variety of liquid-liquid phase separated materials in cells, there is also evidence that self-assembling biomolecular condensates can form solids [6,29,89-91]. This range of behaviors allows for the presentation of a spectrum of properties. For instance, one current hypothesis is that liquid-

like condensates serve to facilitate reactions by concentrating enzymes and substrates, while solid-like granules can more significantly sequester enzymes away from their targets [6,29] and/or potentially serve as a filter to prevent the passage of certain molecules, as in the case of the nuclear pore complex [92,93]. However, some condensed liquid states have shown metastability, and will age over time to form an aggregated, amyloid-like, or even crystalline state [90,94-97]. Thus, while the formation of more solid-like structures can drive cell function, it has been proposed that misregulation of the pathways associated with these materials may be relevant to neurodegenerative and other protein aggregation-related diseases [4,29,35,89,90,97-99].


The formation of liquid vs. solid condensates is typically linked to the strength of the interactions that drive the phase change. For instance, in simple peptide systems that undergo complex coacervation, such as mixtures of poly(lysine) and poly(glutamate), electrostatic interactions alone drive liquid-liquid phase separation. However, if hydrogen bonding interactions between the peptide backbones are also allowed to occur, the resulting increase in interaction between the peptides leads to the exclusion of solvent and the formation of solid precipitates with a  $\beta$ -sheet structure [100-105]. By the same token, the synthetic polymers poly(styrene sulfonate) and poly(diallyldimethylammonium chloride) form solid precipitates at low ionic strength. However, increasing the salt concentration helps to weaken the inter-polymer interactions and allows for the formation of a liquid coacervate phase [106,107]. In both of these systems, the transition from liquid to solid is a gradual continuum that can be effectively described as physical gelation [107]. For synthetic systems, this tunability of properties has been harnessed in a range of applications to facilitate processing of materials in the liquid state, followed by solidification [108-113].

## 7. The Challenge of Understanding a Diversity of Interactions Amongst a Diversity of Components

The growing number of examples where phase separation drives biological function or could inspire an analogous materials system, strongly advocates for the need to better understand the underlying molecular interactions to either elucidate phenomena or allow for their tailored design. However, one of the most significant challenges in looking to Nature for inspiration is the sheer diversity of molecular level interactions and the number of components that are in play. The intrinsically disordered proteins associated with phase separating domains in cells are typically low-complexity sequences, characterized by long stretches with a low overall diversity of amino acids. These proteins often involve repetitive sequences that are enriched in polar amino acids like glycine (G), glutamine (Q), asparagine (N) and serine (S), positively charged amino acids arginine (R) and lysine (K), negatively charged aspartic acid (D) and glutamic acid (E), or aromatic phenylalanine (F) and tyrosine (Y) [5,114]. Still, even in the limit if only this subset of amino acids was present, there exists an incredibly diverse array of interactions and combinatorial arrangements of chemistry that can drive the behavior of these materials.

The types of interactions that have been implicated in the self-assembly and phase separation of membraneless organelles in cells range from long-range electrostatic effects to shorter-range dipolar contacts to short-range and directional cation- $\pi$  and  $\pi$ - $\pi$  interactions (**Figure 4**) [5,8,27,29,97,115-117]. From a modeling perspective, short-range interactions can often be treated at the phenomenological level through the use of an 'effective  $\chi$ ', as is common in polymer physics [118]. However, difficulties still exist in linking the details of a specific chemistry to the value of  $\chi$  because of the complicated interplay between molecular packing and quantum effects. In contrast, electrostatic interactions are long-range and often compete with molecular interactions at shorter length scales [18,119]. Furthermore, intuition regarding electrostatics is typically based on theories that are not valid at relevant salt concentrations and may not be valid for polymers. The result is that the competition between steric, electrostatic, short-range, and entropic considerations are challenging to describe both theoretically and conceptually [18].





**Figure 4.** Molecular interactions underlying intracellular phase transitions.

One recent example that has achieved a level of success in combining theory and experiment utilized extensive mutagenesis on the FUS family of proteins to demonstrate that phase separation for these proteins is primarily governed by multivalent cation- $\pi$  interactions, specifically between tyrosine and arginine residues [97]. The authors then use the theory of associative polymers to interpret their results [120,121]. This theory predicts that phase behavior is dictated through the interaction of associative “stickers” that are separated from one another along a polymer chain by “spacers.” As shown in both experiments and theory, the number of stickers present in the system scales inversely with the saturation concentration of phase separation, but is not impacted by the flexibility of the spacer groups. Instead, the authors demonstrated that switching out highly flexible glycine residues in the spacer regions for alanine, glutamine, or serine decreased the fluidity of the resulting condensates. Despite the elegance of this explanation, the authors acknowledge that they cannot rule out effects, such as increases in hydrophobicity, also affecting the properties of their materials.

This difficulty in describing the competition between the various modes and length-scales of interactions is further exacerbated by the need to validate theoretical and computational approaches via comparison with experimental data, which can be similarly difficult to obtain and/or interpret because of the diversity of interactions, conformational states, and species present. Fortunately, a combination of experimental efforts using model systems, as well as the development of new analytical techniques, is helping to address this issue. For instance, a combination of experimental and computational approaches were recently used to highlight the importance of entropic effects in driving the complex coacervation of polypeptides with different patterns of charge [122]. In particular, this insight into the entropic nature of complex coacervation highlights the importance of sequence effects, rather than overall composition, and provides intuition regarding the design of such systems. In contrast, mutagenesis studies of the nephrin intracellular domain (NICD) highlighted a hierarchy of interactions that drive phase separation [117]. Complex coacervation with a positively-charged partner was necessary to weaken electrostatic repulsion, and the dense phase was further stabilized by shorter-range interactions involving aromatic and hydrophobic residues. Additionally, the authors demonstrated that this hierarchy of interactions meant that the exact sequence of amino acids was not as critical in affecting phase separation as the overall composition.

The overall architecture of the molecules can also have important consequences on phase behavior. A series of reports have investigated how the differences in the flexibility and charge density of single- vs. double-stranded DNA affect its ability to undergo liquid-liquid phase separation (*i.e.*, complex coacervation) vs. liquid-solid precipitation [123,124]. Similarly, the secondary structure of mRNA has been shown to dramatically affect recruitment into a phase separated domain [125]. Branching, or a comb-polymer architecture has also been shown to have effects similar to those of charge patterning [105].

One of the biggest challenges associated with the characterization of both model synthetic and biological systems is the quantity of material required. In a very exciting development, the Brangwynne lab recently reported the use of a novel method based on fluorescence correlation spectroscopy and confocal microscopy to infer information on species concentration (*i.e.*, phase behavior) and the material properties (*e.g.*, diffusivity and second virial coefficients) [35]. This development has the potential to enable the collection of phase diagram information on a much wider range of materials than had been previously accessible.

## 8. Conclusion/Outlook

There is a growing wealth of knowledge associated with how unstructured proteins and/or polymers can take advantage of many weak, multivalent interactions to drive complexation, phase separation, and/or other functional behaviors. Fundamental efforts focused on understanding the full pallet of molecular interactions available are ongoing, as are biochemical and biophysical studies focused on illuminating specific biological phenomena. In particular, the ways in which cells take advantage of the complexity of intracellular phase behavior to affect the flow of information and chemicals represent a tremendous opportunity for collaborative efforts between fundamental and applied scientists to develop biomimetic 'smart' materials.

## 9. Acknowledgements

I would like to thank Prof. Charles E. Sing from the Department of Chemical & Biomolecular Engineering at the University of Illinois at Urbana-Champaign as well as Dr. Matthew Langer and Whitney C. Blocher McTigue for helpful discussions. This work was supported by the National Science Foundation (NSF CMMI-1727660 and CBET-1804177) and the Armstrong Fund for Science (Amherst, MA).

## 10. References and Recommended Readings

Papers of particular interest, published within the period of review, have been highlighted as:

- of special interest
  - of outstanding interest
- [1] Brangwynne CP, Mitchison TJ, Hyman AA. Active liquid-like behavior of nucleoli determines their size and shape in *Xenopus laevis* oocytes. *Proc Natl Acad Sci U S A* 2011;108:4334–9. doi:10.1073/pnas.1017150108.
  - [2] Hyman AA, Simons K. Beyond Oil and Water—Phase Transitions in Cells. *Science* 2012;337:1047–9. doi:10.1126/science.1223728.
  - [3] Hyman AA, Weber CA, Julicher F. Liquid-Liquid Phase Separation in Biology. *Annu Rev Cell Dev Biol* 2014;30:39–58. doi:10.1146/annurev-cellbio-100913-013325.
  - [4] Weber SC, Brangwynne CP. Getting RNA and protein in phase. *Cell* 2012;149:1188–91. doi:10.1016/j.cell.2012.05.022.
  - [5] Brangwynne CP, Tompa P, Pappu RV. Polymer physics of intracellular phase transitions. *Nat Phys* 2015;11:899–904. doi:10.1038/nphys3532.
  - [6]• Weber SC. Sequence-encoded material properties dictate the structure and function of nuclear bodies. *Current Opinion in Cell Biology* 2017;46:62–71. doi:10.1016/j.ceb.2017.03.003.  
This work highlights recent progress made in understanding the relationship between the material properties of phase separated nuclear bodies and their structural and functional consequences.
  - [7] Zhu L, Brangwynne CP. Nuclear bodies: the emerging biophysics of nucleoplasmic phases. *Current Opinion in Cell Biology* 2015;34:23–30. doi:10.1016/j.ceb.2015.04.003.
  - [8]•• Martin EW, Mittag T. Relationship of Sequence and Phase Separation in Protein Low-Complexity Regions. *Biochemistry* 2018;57:2478–87. doi:10.1021/acs.biochem.8b00008.  
This paper uses a polymer physics-based framework to describe how phase behavior and material properties are encoded in the primary sequence of intrinsically disordered proteins.
  - [9] Werner JN, Chen EY, Guberman JM, Zippilli AR, Irgon JJ, Gitai Z. Quantitative genome-scale analysis of protein localization in an asymmetric bacterium. *Proc Natl Acad Sci U S A* 2009;106:7858–63. doi:10.1073/pnas.0901781106.
  - [10] Bayas CA, Wang J, Lee MK, Schrader JM, Shapiro L, Moerner WE. Spatial organization and dynamics of RNase E and ribosomes in *Caulobacter crescentus*. *Proc Natl Acad Sci U S A* 2018;115:E3712–21. doi:10.1073/pnas.1721648115.

- [11] Banani SF, Lee HO, Hyman AA, Rosen MK. Biomolecular condensates: organizers of cellular biochemistry. *Nat Rev Mol Cell Biol* 2017;18:285–98. doi:10.1038/nrm.2017.7.
- [12] Keating CD. Aqueous Phase Separation as a Possible Route to Compartmentalization of Biological Molecules. *Acc Chem Res* 2012;45:2114–24. doi:10.1021/ar200294y.
- [13] Chilkoti A, Christensen T, MacKay J. Stimulus responsive elastin biopolymers: applications in medicine and biotechnology. *Curr Opin Chem Biol* 2006;10:652–7. doi:10.1016/j.cbpa.2006.10.010.
- [14] Roberts S, Dzuricky M, Chilkoti A. Elastin-like polypeptides as models of intrinsically disordered proteins. *FEBS Lett* 2015;589:2477–86. doi:10.1016/j.febslet.2015.08.029.
- [15] van der Gucht J, Spruijt E, Lemmers M, Cohen Stuart MA. Polyelectrolyte complexes: bulk phases and colloidal systems. *J Colloid Interface Sci* 2011;361:407–22. doi:10.1016/j.jcis.2011.05.080.
- [16] Blocher WC, Perry SL. Biomimetic Complex Coacervate-Based Materials for Biomedicine. *WIREs Nanomedicine and Nanobiotechnology* 2017;9:e1442. doi:10.1021/bm900373c.
- [17] Liu Y, Winter HH, Perry SL. Linear Viscoelasticity of Complex Coacervates. *Adv Colloid Interface Sci* 2017;239:46–60. doi:10.1016/j.cis.2016.08.010.
- [18]•• Sing CE. Development of the Modern Theory of Polymeric Complex Coacervation. *Adv Colloid Interface Sci* 2017;239:2–16. doi:10.1016/j.cis.2016.04.004.
- This review article provides a broad overview of the theoretical tools used to understand complex coacervation. In particular, it begins with an historical perspective on the traditional Voorn-Overbeek theory, discusses more recent developments, provides context and comparison for the various methods, and highlights remaining challenges.
- [19] Srivastava S, Tirrell MV. Polyelectrolyte Complexation. In: Rice SA, Dinner AR, editors. *Advances in Chemical Physics*, Hoboken, NJ, USA: John Wiley & Sons, Inc; 2016. doi:10.1002/9781119290971.ch7.
- [20] Voets IK, de Keizer A, Cohen Stuart MA. Complex coacervate core micelles. *Adv Colloid Interface Sci* 2009;147-148:300–18. doi:10.1016/j.cis.2008.09.012.
- [21] Dobrynin AV, Colby RH, Rubinstein M. Polyampholytes. *J Polym Sci, Part B: Polym Phys* 2004;42:3513–38. doi:10.1002/polb.20207.
- [22] Das RK, Pappu RV. Conformations of intrinsically disordered proteins are influenced by linear sequence distributions of oppositely charged residues. *Proc Natl Acad Sci U S A* 2013;110:13392–7. doi:10.1073/pnas.1304749110/-/DCSupplemental.
- [23] Lin Y-H, Chan HS. Phase Separation and Single-Chain Compactness of Charged Disordered Proteins Are Strongly Correlated. *Biophys J* 2017;112:2043–6. doi:10.1016/j.bpj.2017.04.021.
- [24] Lin Y-H, Forman-Kay JD, Chan HS. Sequence-Specific Polyampholyte Phase Separation in Membraneless Organelles. *Phys Rev Lett* 2016;117:178101. doi:10.1103/PhysRevLett.117.178101.
- [25]•• Berry J, Brangwynne CP, Haataja M. Physical principles of intracellular organization via active and passive phase transitions. *Rep Prog Phys* 2018;81:046601. doi:10.1088/1361-6633/aaa61e.
- This paper discusses the application of theoretical approaches to understand liquid-liquid phase separation in cells. This includes theories of nucleation and growth, coarsening, passive and modulated phase separation, as well as systems where reactions occur.
- [26] Malinowska L, Kroschwald S, Alberti S. Protein disorder, prion propensities, and self-organizing macromolecular collectives. *Biochim Biophys Acta, Proteins Proteomics* 2013;1834:918–31. doi:10.1016/j.bbapap.2013.01.003.
- [27] Uversky VN. Protein intrinsic disorder-based liquid–liquid phase transitions in biological systems: Complex coacervates and membrane-less organelles. *Adv Colloid Interface Sci* 2017;239:97–114. doi:10.1016/j.cis.2016.05.012.

- [28] Wippich F, Bodenmiller B, Trajkovska MG, Wanka S, Aebersold R, Pelkmans L. Dual Specificity Kinase DYRK3 Couples Stress Granule Condensation/Dissolution to mTORC1 Signaling. *Cell* 2013;152:791–805. doi:10.1016/j.cell.2013.01.033.
- [29] Mollieix A, Temirov J, Lee J, Coughlin M, Kanagaraj AP, Kim HJ, et al. Phase Separation by Low Complexity Domains Promotes Stress Granule Assembly and Drives Pathological Fibrillization. *Cell* 2015;163:123–33. doi:10.1016/j.cell.2015.09.015.
- [30] An S, Kumar R, Sheets ED, Benkovic SJ. Reversible compartmentalization of de novo purine biosynthetic complexes in living cells. *Science* 2008;320:103–6. doi:10.1126/science.1152241.
- [31] Zhao H, French JB, Fang Y, Benkovic SJ. The purinosome, a multi-protein complex involved in the de novo biosynthesis of purines in humans. *Chem Commun* 2013;49:4444–52. doi:10.1039/c3cc41437j.
- [32] Pedley AM, Benkovic SJ. A New View into the Regulation of Purine Metabolism: The Purinosome. *Trends Biochem Sci* 2017;42:141–54. doi:10.1016/j.tibs.2016.09.009.
- [33]• Cohen RD, Pielak GJ. A cell is more than the sum of its (dilute) parts: A brief history of quinary structure. *Protein Sci* 2017;26:403–13. doi:10.1002/pro.3092.
- This article reviews the idea of quinary structure, or how transient interactions between macromolecules, affects their organization, compartmentalization, an activity.
- [34] Lee CF, Brangwynne CP, Gharakhani J, Hyman AA, Julicher F. Spatial Organization of the Cell Cytoplasm by Position-Dependent Phase Separation. *Phys Rev Lett* 2013;111:088101. doi:10.1103/PhysRevLett.111.088101.
- [35]•• Wei M-T, Elbaum-Garfinkle S, Holehouse AS, Chen CC-H, Feric M, Arnold CB, et al. Phase behaviour of disordered proteins underlying low density and high permeability of liquid organelles. *Nat Chem* 2017;9:1118–25. doi:10.1038/nchem.2803.
- This article introduces a novel experimental technique based on fluorescence correlation spectroscopy that allows for the measurement of second virial coefficients, diffusivity, and concentration using confocal microscopy.
- [36]• Stoeger T, Battich N, Pelkmans L. Passive Noise Filtering by Cellular Compartmentalization. *Cell* 2016;164:1151–61. doi:10.1016/j.cell.2016.02.005.
- This article highlights the ways in which compartmentalization allows for passive noise filtration such that cells can avoid responding to small environmental fluctuations while maintaining the ability to perceive and react to meaningful signals.
- [37] Minton AP. Excluded volume as a determinant of macromolecular structure and reactivity. *Biopolymers* 1981;20:2093–120. doi:10.1002/bip.1981.360201006.
- [38] Fulton AB. How crowded is the cytoplasm? *Cell* 1982;30:345–7.
- [39] Zimmerman SB, Trach SO. Estimation of macromolecule concentrations and excluded volume effects for the cytoplasm of *Escherichia coli*. *J Mol Biol* 1991;222:599–620. doi:10.1016/0022-2836(91)90499-V.
- [40] Zimmerman SB, Minton AP. Macromolecular crowding: biochemical, biophysical, and physiological consequences. *Annu Rev Bioph Biomol Struct* 1993;22:27–65.
- [41] Ralston GB. Effects of “crowding” in protein solutions. *J Chem Educ* 1990;67:857–60. doi:10.1021/ed067p857.
- [42] Minton AP. The effect of volume occupancy upon the thermodynamic activity of proteins: some biochemical consequences. *Mol Cell Biochem* 1983;55:119–40.
- [43] Minton AP, Colclasure GC, Parker JC. Model for the role of macromolecular crowding in regulation of cellular volume. *Proc Natl Acad Sci U S A* 1992;89:10504–6.
- [44] Benton LA, Smith AE, Young GB, Pielak GJ. Unexpected Effects of Macromolecular Crowding on Protein Stability. *Biochemistry* 2012;51:9773–5. doi:10.1021/bi300909q.
- [45] van den Berg B, Wain R, Dobson CM, Ellis RJ. Macromolecular crowding perturbs protein refolding kinetics: implications for folding inside the cell. *Embo J* 2000;19:3870–5. doi:10.1093/emboj/19.15.3870.

- [46] Dhar A, Girdhar K, Singh D, Gelman H, Ebbinghaus S, Gruebele M. Protein Stability and Folding Kinetics in the Nucleus and Endoplasmic Reticulum of Eucaryotic Cells. *Biophys J* 2011;101:421–30. doi:10.1016/j.bpj.2011.05.071.
- [47] Eggers DK, Valentine JS. Molecular confinement influences protein structure and enhances thermal protein stability. *Protein Sci* 2001;10:250–61. doi:10.1110/ps.36201.
- [48] Ellis RJ. Macromolecular crowding: obvious but underappreciated. *Trends Biochem Sci* 2001;26:597–604.
- [49] Ellis RJ. Macromolecular crowding: an important but neglected aspect of the intracellular environment. *Curr Opin Struct Biol* 2001;11:114–9. doi:10.1016/S0959-440X(00)00172-X.
- [50] Flaugh SL, Lumb KJ. Effects of Macromolecular Crowding on the Intrinsically Disordered Proteins c-Fos and p27 Kip1. *Biomacromolecules* 2001;2:538–40. doi:10.1021/bm015502z.
- [51] Garner MM, Burg MB. Macromolecular crowding and confinement in cells exposed to hypertonicity. *Am J Physiol: Cell Physiol* 1994;266:C877–92.
- [52] Laurent TC. The interaction between polysaccharides and other macromolecules. 5. The solubility of proteins in the presence of dextran. *Biochem J* 1963;89:253–7.
- [53] Lee CF, Bird S, Shaw M, Jean L, Vaux DJ. Combined effects of agitation, macromolecular crowding and interfaces on amyloidogenesis. *J Biol Chem* 2012;287:38006–19. doi:10.1074/jbc.M112.400580.
- [54] Malik A, Kundu J, Mukherjee SK, Chowdhury PK. Myoglobin Unfolding in Crowding and Confinement. *J Phys Chem B* 2012;116:12895–904. doi:10.1021/jp306873v.
- [55] McNulty BC, Young GB, Pielak GJ. Macromolecular Crowding in the Escherichia coli Periplasm Maintains  $\alpha$ -Synuclein Disorder. *J Mol Biol* 2006;355:893–7. doi:10.1016/j.jmb.2005.11.033.
- [56] Minton AP. The Influence of Macromolecular Crowding and Macromolecular Confinement on Biochemical Reactions in Physiological Media. *J Biol Chem* 2001;276:10577–80. doi:10.1074/jbc.R100005200.
- [57] Minton AP. Influence of excluded volume upon macromolecular structure and associations in 'crowded' media. *Curr Opin Biotechnol* 1997;8:65–9. doi:10.1016/S0958-1669(97)80159-0.
- [58] Ping G, Yuan J-M, Sun Z, Wei Y. Studies of effects of macromolecular crowding and confinement on protein folding and protein stability. *J Mol Recognit* 2004;17:433–40. doi:10.1002/jmr.710.
- [59] Pioselli B, Bettati S, Mozzarelli A. Confinement and crowding effects on tryptophan synthase  $\alpha 2\beta 2$  complex. *FEBS Lett* 2005;579:2197–202. doi:10.1016/j.febslet.2005.03.011.
- [60] Rivas G, Fernandez JA, Minton AP. Direct Observation of the Self-Association of Dilute Proteins in the Presence of Inert Macromolecules at High Concentration via Tracer Sedimentation Equilibrium: Theory, Experiment, and Biological Significance. *Biochemistry* 1999;38:9379–88. doi:10.1021/bi990355z.
- [61] Walter H, Brooks DE. Phase separation in cytoplasm, due to macromolecular crowding, is the basis for microcompartmentation. *FEBS Lett* 1995;361:135–9.
- [62] Wang Y, Sarkar M, Smith AE, Krois AS, Pielak GJ. Macromolecular Crowding and Protein Stability. *J Am Chem Soc* 2012;134:16614–8. doi:10.1021/ja305300m.
- [63] Zhou H-X, Rivas G, Minton AP. Macromolecular Crowding and Confinement: Biochemical, Biophysical, and Potential Physiological Consequences. *Annu Rev Biophys* 2008;37:375–97. doi:10.1146/annurev.biophys.37.032807.125817.
- [64] Zimmerman SB. Macromolecular crowding effects on macromolecular interactions: some implications for genome structure and function. *Biochim Biophys Acta, Gene Struct Expression* 1993;1216:175–85.
- [65] Eggers DK, Valentine JS. Crowding and hydration effects on protein conformation: a study with sol-gel encapsulated proteins. *J Mol Biol* 2001;314:911–22. doi:10.1006/jmbi.2001.5166.

- [66] McCall PM, Srivastava S, Perry SL, Kovar DR, Gardel ML, Tirrell MV. Partitioning and Enhanced Self-Assembly of Actin in Polypeptide Coacervates. *Biophys J* 2018;114:1636–45. doi:10.1016/j.bpj.2018.02.020.
- [67]•• Guseman AJ, Perez Goncalves GM, Speer SL, Young GB, Pielak GJ. Protein shape modulates crowding effects. *Proc Natl Acad Sci U S a* 2018;115:10965–70. doi:10.1073/pnas.1810054115.
- This article describes an elegant experiment using two variants of a dimeric protein to test how molecular shape affects how it responds to a crowded environment.
- [68] Schlesinger AP, Wang Y, Tadeo X, Millet O, Pielak GJ. Macromolecular Crowding Fails To Fold a Globular Protein in Cells. *J Am Chem Soc* 2011;133:8082–5. doi:10.1021/ja201206t.
- [69] McGuffee SR, Elcock AH. Diffusion, Crowding & Protein Stability in a Dynamic Molecular Model of the Bacterial Cytoplasm. *PLoS Comput Biol* 2010;6:e1000694. doi:10.1371/journal.pcbi.1000694.
- [70] Sarkar M, Smith AE, Pielak GJ. Impact of reconstituted cytosol on protein stability. *Proc Natl Acad Sci U S a* 2013;110:19342–7. doi:10.1073/pnas.1312678110/-/DCSupplemental.
- [71] Smith AE, Zhang Z, Pielak GJ, Li C. NMR studies of protein folding and binding in cells and cell-like environments. *Curr Opin Struct Biol* 2015;30:7–16. doi:10.1016/j.sbi.2014.10.004.
- [72] Strulson CA, Molden RC, Keating CD, Bevilacqua PC. RNA catalysis through compartmentalization. *Nat Chem* 2012;4:941–6. doi:10.1038/nchem.1466.
- [73] Sarkar M, Li C, Pielak GJ. Soft interactions and crowding. *Biophys Rev* 2013;5:187–94. doi:10.1007/s12551-013-0104-4.
- [74] Wang Y, Li C, Pielak GJ. Effects of Proteins on Protein Diffusion. *J Am Chem Soc* 2010;132:9392–7. doi:10.1021/ja102296k.
- [75] Miklos AC, Sarkar M, Wang Y, Pielak GJ. Protein crowding tunes protein stability. *J Am Chem Soc* 2011;133:7116–20. doi:10.1021/ja200067p.
- [76] Smith AE, Zhou LZ, Gorenssek AH, Senske M, Pielak GJ. In-cell thermodynamics and a new role for protein surfaces. *Proc Natl Acad Sci U S a* 2016;113:1725–30. doi:10.1073/pnas.1518620113.
- [77] Fletcher EE, Yan D, Kosiba AA, Zhou Y, Shi H. Biotechnological applications of elastin-like polypeptides and the inverse transition cycle in the pharmaceutical industry. *Protein Expression and Purification* 2019;153:114–20. doi:10.1016/j.pep.2018.09.006.
- [78] Hassouneh W, Christensen T, Chilkoti A. *Elastin-Like Polypeptides as a Purification Tag for Recombinant Proteins*. vol. 2. Hoboken, NJ, USA: John Wiley & Sons, Inc; 2001. doi:10.1002/0471140864.ps0611s61.
- [79] Du X, Dubin PL, Hoagland DA, Sun L. Protein-Selective Coacervation with Hyaluronic Acid. *Biomacromolecules* 2014;15:726–34. doi:10.1021/bm500041a.
- [80] Dubin PL, Gao J, Mattison K. Protein purification by selective phase separation with polyelectrolytes. *Sep Purif Methods* 1994;23:1–16. doi:10.1080/03602549408001288.
- [81] Xu Y, Mazzawi M, Chen K, Sun L, Dubin PL. Protein Purification by Polyelectrolyte Coacervation: Influence of Protein Charge Anisotropy on Selectivity. *Biomacromolecules* 2011;12:1512–22. doi:10.1021/bm101465y.
- [82] Wang Y-F, Gao JY, Dubin PL. Protein Separation via Polyelectrolyte Coacervation: Selectivity and Efficiency. *Biotechnol Prog* 1996;12:356–62. doi:10.1021/bp960013.
- [83]• Blocher McTigue WC, Perry SL. *Design Rules for Encapsulating Proteins into Complex Coacervates* 2019:(in revision).
- This article explores the ways in which protein uptake into complex coacervates is modulated by solution conditions and the properties of the coacervating polymers. In particular, the presence of clusters of charge on the protein and the charge density of the polymer have a dramatic effect.
- [84]• Kapelner RA, Obermeyer A. Ionic polypeptide tags for protein phase separation. *Chem Sci* 2019:(in press).

This article highlights the use of ionic tags for the purification of proteins via complex coacervation.

- [85] Kim B, Lam CN, Olsen BD. Nanopatterned Protein Films Directed by Ionic Complexation with Water-Soluble Diblock Copolymers. *Macromolecules* 2012;45:4572–80.
- [86] Lindhoud S, Norde W, Cohen Stuart MA. Effects of Polyelectrolyte Complex Micelles and Their Components on the Enzymatic Activity of Lipase. *Langmuir* 2010;26:9802–8. doi:10.1021/la1000705.
- [87] Mills CE, Obermeyer A, Dong X, Walker J, Olsen BD. Complex Coacervate Core Micelles for the Dispersion and Stabilization of Organophosphate Hydrolase in Organic Solvents. *Langmuir* 2016;32:13367–76. doi:10.1021/acs.langmuir.6b02350.
- [88]\*\* Panganiban B, Qiao B, Jiang T, DelRe C, Obadia MM, Nguyen TD, et al. Random heteropolymers preserve protein function in foreign environments. *Science* 2018;359:1239–43. doi:10.1126/science.aao0335.

This article uses the average distribution of different chemistries on the surface of proteins to inform the design of a statistical heteropolymer that can form a chaperone-like shell around the outside of the protein to enhance stability in solution and in organic solvents. This approach also allows for cell-free expression and folding of a membrane protein with higher yield than traditional liposomal techniques.

- [89] Patel A, Lee HO, Jawerth L, Maharana S, Jahnel M, Hein MY, et al. A Liquid-to-Solid Phase Transition of the ALS Protein FUS Accelerated by Disease Mutation. *Cell* 2015;162:1066–77. doi:10.1016/j.cell.2015.07.047.
- [90] Shin Y, Brangwynne CP. Liquid phase condensation in cell physiology and disease. *Science* 2017;357:eaaf4382. doi:10.1126/science.aaf4382.
- [91]\*\* Shin Y, Berry J, Pannucci N, Haataja MP, Toettcher JE, Brangwynne CP. Spatiotemporal Control of Intracellular Phase Transitions Using Light-Activated optoDroplets. *Cell* 2017;168:159–71. doi:10.1016/j.cell.2016.11.054.

This article details the use of an exciting new experimental technique inspired by optogenetics. Expression of a fusion protein construct allows for the light-triggered phase separation of proteins in cells.

- [92] Frey S, Richter RP, Görlich D. FG-Rich Repeats of Nuclear Pore Proteins Form a Three-Dimensional Meshwork with Hydrogel-Like Properties. *Science* 2006;314:815–7. doi:10.1126/science.1132516.
- [93] Schmidt HB, Görlich D. Nup98 FG domains from diverse species spontaneously phase-separate into particles with nuclear pore-like permselectivity. *eLife* 2015;4:e04251. doi:10.7554/eLife.04251.
- [94] Galkin O, Chen K, Nagel RL, Hirsch RE, Vekilov PG. Liquid–liquid separation in solutions of normal and sickle cell hemoglobin. *Proc Natl Acad Sci U S A* 2002;99:8479–83. doi:10.1073/pnas.122055299.
- [95] Giegé R. A historical perspective on protein crystallization from 1840 to the present day. *Febs J* 2013;280:6456–97. doi:10.1111/febs.12580.
- [96] Maes D, Vorontsova MA, Potenza MAC, Sanvito T, Sleutel M, Giglio M, et al. Do protein crystals nucleate within dense liquid clusters? *Acta Crystallogr, Sect F: Struct Biol Commun* 2015;71:815–22. doi:10.1107/S2053230X15008997.
- [97]\*\* Wang J, Choi J-M, Holehouse AS, Lee HO, Zhang X, Jahnel M, et al. A Molecular Grammar Governing the Driving Forces for Phase Separation of Prion-like RNA Binding Proteins. *Cell* 2018;174:688–99. doi:10.1016/j.cell.2018.06.006.

This article uses extensive mutagenesis studies to identify the role of cation- $\pi$  interactions in driving the phase separation of the FUS family of proteins, and uses the theory of associative polymers to interpret their results.

- [98] Zhang H, Elbaum-Garfinkle S, Langdon EM, Taylor N, Occhipinti P, Bridges AA, et al. RNA Controls PolyQ Protein Phase Transitions. *Molecular Cell* 2015;60:220–30. doi:10.1016/j.molcel.2015.09.017.
- [99] Lin Y, Protter DSW, Rosen MK, Parker R. Formation and Maturation of Phase-Separated Liquid Droplets by RNA-Binding Proteins. *Molecular Cell* 2015;60:208–19. doi:10.1016/j.molcel.2015.08.018.
- [100] Priftis D, Tirrell M. Phase behaviour and complex coacervation of aqueous polypeptide solutions. *Soft Matter* 2012;8:9396–405. doi:10.1039/c2sm25604e.
- [101] Perry SL, Leon L, Hoffmann KQ, Kade MJ, Priftis D, Black KA, et al. Chirality-selected phase behaviour in ionic polypeptide complexes. *Nat Commun* 2015;6:6052. doi:10.1038/ncomms7052.
- [102] Hoffmann KQ, Perry SL, Leon L, Priftis D, Tirrell M, de Pablo JJ. A molecular view of the role of chirality in charge-driven polypeptide complexation. *Soft Matter* 2015;11:1525–38. doi:10.1039/C4SM02336F.
- [103] Pacalin NM, Leon L, Tirrell M. Directing the phase behavior of polyelectrolyte complexes using chiral patterned peptides. *Eur Phys J Spec Top* 2016;225:1805–15. doi:10.1140/epjst/e2016-60149-6.
- [104] Priftis D, Leon L, Song Z, Perry SL, Margossian KO, Tropnikova A, et al. *Self-Assembly of  $\alpha$ -Helical Polypeptides Driven by Complex Coacervation*. *Angew Chem Int Ed* 2015;54:11128–32. doi:10.1002/anie.201504861R1.
- [105] Johnston BM, Johnston CW, Letteri RA, Lytle TK, Sing CE, Emrick T, et al. The effect of comb architecture on complex coacervation. *Org Biomol Chem* 2017;15:7630–42. doi:10.1021/bm201113y.
- [106] Wang Q, Schlenoff JB. The Polyelectrolyte Complex/Coacervate Continuum. *Macromolecules* 2014;47:3108–16. doi:10.1021/ma500500q.
- [107]• Liu Y, Monami B, Winter HH, Perry SL. Rheological Characterization of Liquid-to-Solid Transitions in Bulk Polyelectrolyte Complexes. *Soft Matter* 2017;13:7332–40. doi:10.1039/C7SM01285C.
- This article uses small amplitude oscillatory shear measurements to characterize the salt-driven solid-to-liquid transition observed in bulk polyelectrolyte complexes as physical gelation. The authors highlight analysis strategies to clearly identify the critical gel point and unambiguously determine the solid or liquid nature of a sample.
- [108] Meng X, Perry SL, Schiffman JD. Complex Coacervation: Chemically Stable Fibers Electrospun from Aqueous Polyelectrolyte Solutions. *ACS Macro Lett* 2017;6:505–11. doi:10.1021/acsmacrolett.7b00173.
- [109] Meng X, Schiffman JD, Perry SL. Electrospinning Cargo-Containing Polyelectrolyte Complex Fibers: Correlating Molecular Interactions to Complex Coacervate Phase Behavior and Fiber Formation. *Macromolecules* 2018;51:8821–32. doi:10.1021/acs.macromol.8b01709.
- [110] Shamoun RF, Reisch A, Schlenoff JB. Extruded Saloplastic Polyelectrolyte Complexes. *Adv Funct Mater* 2012;22:1923–31. doi:10.1002/adfm.201102787.
- [111] Zhu F, Cheng L, Yin J, Wu ZL, Qian J, Fu J, et al. 3D Printing of Ultratough Polyion Complex Hydrogels. *ACS Appl Mater Interfaces* 2016;8:31304–10. doi:10.1021/acsami.6b09881.
- [112] Schaaf P, Schlenoff JB. Saloplastics: Processing Compact Polyelectrolyte Complexes. *Adv Mater* 2015;27:2420–32. doi:10.1002/adma.201500176.
- [113] Porcel CH, Schlenoff JB. Compact Polyelectrolyte Complexes: “Saloplastic” Candidates for Biomaterials. *Biomacromolecules* 2009;10:2968–75. doi:10.1021/bm900373c.
- [114] Uversky VN, Kuznetsova IM, Turoverov KK, Zaslavsky B. Intrinsically disordered proteins as crucial constituents of cellular aqueous two phase systems and coacervates. *FEBS Lett* 2015;589:15–22. doi:10.1016/j.febslet.2014.11.028.
- [115]• Nott TJ, Craggs TD, Baldwin AJ. Membraneless organelles can melt nucleic acid duplexes and act as biomolecular filters. *Nat Chem* 2016;8:569–75. doi:10.1038/nchem.2519.



This article demonstrates that the material environment of cellular bodies can serve to melt double stranded DNA while simultaneously stabilizing the structures of single stranded nucleic acids.

[116] Nott TJ, Petsalaki E, Farber P, Jervis D, Fussner E, Plochowietz A, et al. Phase Transition of a Disordered Nuage Protein Generates Environmentally Responsive Membraneless Organelles. *Molecular Cell* 2015;57:936–47. doi:10.1016/j.molcel.2015.01.013.

[117]•• Pak CW, Kosno M, Holehouse AS, Padrick SB, Mittal A, Ali R, et al. Sequence Determinants of Intracellular Phase Separation by Complex Coacervation of a Disordered Protein. *Molecular Cell* 2016;63:72–85. doi:10.1016/j.molcel.2016.05.042.

This article demonstrates that phase separation of the Nephrin intracellular domain (NICD) occurs via complex coacervation. Furthermore, mutagenesis studies reveal that phase separation depends on the overall composition, rather than the specific sequence of amino acids.

[118] Flory PJ. *Principles of Polymer Chemistry* 1953.

[119] Radhakrishna M, Sing CE. Charge Correlations for Precise, Coulombically Driven Self Assembly. *Macromol Chem Phys* 2016;217:126–36. doi:10.1002/macp.201500278.

[120] Rubinstein M, Dobrynin AV. Solutions of Associative Polymers. *Trends in Polymer Science* 1997;5:181–6.

[121] Semenov AN, Rubinstein M. Thermoreversible Gelation in Solutions of Associative Polymers. 1. Statics. *Macromolecules* 1998;31:1373–85. doi:10.1021/ma970616h.

[122]•• Chang L-W, Lytle TK, Radhakrishna M, Madinya JJ, Vélez J, Sing CE, et al. *Sequence and Entropy-Based Control of Complex Coacervates*. *Nat Commun* 2017;8:1273. doi:10.1038/s41467-017-01249-1.

This article combines experimental and computational efforts, demonstrating how variations in the patterning of charges along model polymers affect the resulting complex coacervate phase behavior. These differences are attributed to the ways in which the sequence of charges affects the localization of counterions along the polymers before complex formation, thus changing the entropy of complexation

[123]• Shakya A, King JT. DNA Local-Flexibility-Dependent Assembly of Phase-Separated Liquid Droplets. *Biophys J* 2018;115:1840–7. doi:10.1016/j.bpj.2018.09.022.

Similar to Ref. [124], this article explores the role of DNA flexibility and free nucleotides on the ability of the system to undergo complex coacervation.

[124]• Viereggs JR, Lueckheide M, Marciel AB, Leon L, Bologna AJ, Rivera JR, et al. Oligonucleotide–Peptide Complexes: Phase Control by Hybridization. *J Am Chem Soc* 2018;140:1632–8. doi:10.1021/jacs.7b03567.

Similar to Ref. [123], this article explores the effect of DNA hybridization, length, and salt concentration on the ability of the system to undergo complex coacervation.

[125]•• Langdon EM, Qiu Y, Niaki AG, McLaughlin GA, Weidmann CA, Gerbich TM, et al. mRNA structure determines specificity of a polyQ-driven phase separation. *Science* 2018;360:922–7. doi:10.1126/science.aar7432.

This article demonstrates how the secondary structure of mRNA affects uptake into a phase separated droplet.