

Bioleaching of cobalt and zinc from pyrite ore in relation to calcitic gangue content

F. Baldi, A. Bralia, F. Riccobono and G. Sabatini

Bioleaching of a pyrite ore containing high concentrations of cobalt (0.1%) and zinc (0.065%) was affected by small amounts of calcitic gangue (from 0.01 to 1.01%). Results from an air-lift percolator and from Erlenmeyer flask experiments show that a small percentage of calcite raises the pH and arrests the growth of the acidophilic bacterium *Thiobacillus ferrooxidans*. In percolator experiments, when calcite is completely removed by the continuous addition of small quantities of acid, and the pH of the liquor becomes acid, the micro-organism begins to grow and to bio-oxidize the pyrite ore. The growth of *T. ferrooxidans* shows different lag phase spans (from 13 to 190 days) depending on carbonate dissolution. The metals Fe, Zn and Co are released into the leaching solution together at different rates after a lag-time which depends on calcite concentrations in pyrite gangue. Metal ratios in the mineral bulk are different from those in the liquor, Zn dissolving 5 times more readily than Co. Bioleaching rates for metal removal from pyrite are higher in percolator (for Fe, from 5 to 15 mg/l/h) than in flask experiments (from 0.5 to 2 mg/l/h), but the lag phases are shorter (from 2 to 65 days). The differences between the two systems are related to calcite dissolution and gypsum precipitation.

The continuing world-wide depletion of metal ore deposits and the accumulation of tailings, which cannot be further processed by conventional means, is encouraging the development of bioleaching technology (bio-hydrometallurgy) for recovering metals such as copper and uranium (Brierley 1978; Kelly *et al.* 1979) and also 'strategic' metals such as gold, silver and cobalt (Ehrlich 1987; Pinches *et al.* 1987; Wichlacz & Thompson 1987).

The bioleaching of sulphide ores may be performed by means of the acidophilic and chemolithotrophic bacterium *Thiobacillus ferrooxidans* or co-cultures of this micro-organism with other *thiobacilli* or acidophilic bacteria (Dugan *et al.* 1970; Groudev *et al.* 1978; Schafer 1983). However, this biotechnological process is not always successful. High concentrations of toxic metals (Hg, As, Sb, etc.) in the sulphide ore lattice inhibit bacterial catalysis (Imai *et al.* 1975; Barbic 1977; Ingledew 1982; Mahapatra & Mishra 1984; Paknikar & Agate 1987) as these metals are released in the leaching solution. Metal-resistant strains of *T. ferrooxidans* can cope with unfavourable conditions of this kind (Tuovinen & Kelly 1974; Sugio *et al.* 1981; Baldi & Olson 1987), and grow well in the presence of high concentrations of these toxic cations. The metabolic activity of acidophilic *T. ferrooxidans* can also be influenced by carbonate compounds (Ishikawa *et al.* 1983; Khalid *et al.* 1987). It is obvious that carbonates buffer the acidic bioleaching solution and inactivate acidophilic bacteria (Wallace *et al.* 1976; Boseker *et al.* 1978). However, it is of industrial interest to investigate the concentrations of carbonates that affect the bioleaching process, since base metal ore deposits often contain carbonate gangue.

In industrial situations, in which tonnes of mineral ores are bioprocessed, a small percentage of carbonates might cause the failure or delay of bioleaching. Consequently, the carbonate content of ores might be an economic limiting factor in an industrial bioleaching plant.

Sulphide ores from different mines in Italy: Funtana Raminosa, Monteneve and Campiano, contain valuable metals including Zn, Cu and Co which may possibly be recovered by biological methods. Preliminary bioleaching experiments with these ores were conducted in our laboratory for several months. The sulphides were inoculated with different strains of *T. ferrooxidans* isolated from the respective

F. Baldi is with the Università di Siena, Dipartimento di Biologia Ambientale, via P. A. Mattioli, 4, I-53100 Siena. A. Bralia, F. Riccobono and G. Sabatini are with the Università di Siena, Istituto di Mineralogia I-53100 Siena, Italy. F. Baldi is the corresponding author.

mineral ores. No bioleaching activity was detected, evidently because carbonates (from 1 to 10%) prevent the biological oxidation of the mineral ores.

The aim of the present research is: (1) to determine the potential recovery of Co and Zn from pyrites of the Campiano mine; (2) to determine the effect of carbonates on the bio-extraction of Co and Zn, with particular reference to carbonate gangue and (3) to investigate how long *T. ferrooxidans* can survive at neutral pH.

Materials and Methods

Pyrite

The pyrite from the Campiano mine (southern Tuscany) was chosen because of its high Co and Zn content. Twenty kilograms of pyrite was ground to obtain 500 g of 250 to 500 μm grain size containing 1.01% of total carbonates. The sample was split into two subsamples: one was treated with 20% (v/v) acetic acid solution to remove carbonates (0.01% carbonate residues). The purity of pyrite and type of carbonate gangue was determined by X-ray diffractometry (Siemens D500) using internal standards. The megacrystal from the Campiano mine was 98.1% pyrite, the remainder being 1.01% CaCO_3 as calcite, 0.1% Co, 0.065% Zn, and other trace metals (Table 1).

Metal Analysis

Metal concentrations of Fe, Zn, Co, Ca and others (Table 1) were determined by holding 0.5 g of sample treated with 50 ml 6 M HCl both as original pyrite and as carbonate-free pyrite, at 90°C overnight. The sample was cooled to room temperature and made up to 100 ml. Metals were determined by flame atomic absorption spectrophotometry (AAS, Perkin Elmer model 5000). The standard deviation was 5.1% for Fe, 6.3% for Ca, 6.1% for Zn and 7.5% for Co. Metal analysis in the leaching solution of percolators and Erlenmeyer flasks was carried out by flame AAS after adding 2 ml conc. HNO_3 and 7 ml of double distilled water to 1 ml of sample.

Organism and Culture Conditions

T. ferrooxidans strain 13661 was kindly supplied by G.J. Olson and grown in 9K medium (Silverman & Lundgren 1959). The bacteria were cultivated routinely in 50 ml of 9K medium in 250 ml Erlenmeyer flasks and agitated at 150 rev/min at 30°C or in 2.0 litres of 9K medium in a 2.5 litre Erlenmeyer flask equipped with a sterile glass tube plugged with glass wool, through which compressed air was passed to vigorously aerate the inoculated medium. When all FeSO_4 was oxidized, 2.0 litres of culture was harvested by centrifuging at $3600 \times g$ for 20 min. The cells were washed twice with 5 mM H_2SO_4 , and then inoculated into air-lift percolators or the Erlenmeyer flasks.

Standards

T. ferrooxidans ATCC 13661 used here is the same as that used in an interlaboratory bioleaching study (Bioleaching working group, in preparation) of a reference pyrite (NIST-8455; National Institute of Standards & Technology Gaithersburg, MD, USA). The average bioleaching rate of the reference pyrite using this strain, according to eight international laboratories, was 12.4 mg/l/h. The average value of our laboratory for three replicates was 7.8 mg/l/h \pm 1.1 (standard deviation).

Microbial Protein Analysis

The cell density in solution was determined by measuring protein content with a protein assay kit (BioRad). Bovine serum albumin (Sigma) solution was used as standard. Pyrite oxidation by cells was determined by measuring soluble iron.

Table 1. Composition of pyrite from Campiano mine.

Components	
FeS_2^*	98.1%
CaCO_3^*	1.01%
Ca†	0.40%
Co†	0.10%
Mn†	215 mg/kg
Zn†	650 mg/kg
Pb†	205 mg/kg
Cu†	25 mg/kg
Ag†	5 mg/kg
Ni†	<10 mg/kg
Cd†	<0.1 mg/kg

* Determined by X-ray diffractometry.

† Determined by flame atomic absorption spectrophotometry.

Air-lift Percolator Experiments

Air-lift percolators, as described elsewhere (Baldi & Olson 1987), were used in the bioleaching experiments. Carbonate-free pyrite (20 g), original pyrite (1.01%) and mixed samples with intermediate carbonate content (0.25, 0.50 and 0.75%) were placed in percolators and immersed in 25 ml of 9K medium (minus FeSO₄). Pulp density was 80%. All five percolators were inoculated with 0.25 ml of a suspension of a *T. ferrooxidans* culture containing 3.7 mg protein/ml. Two percolators with sterile pyrite were not inoculated for use as controls. All percolators were continuously aerated, with humidified sterile air from an air-compressor, for one year at room temperature. The liquor (bioleaching solution) was sampled periodically (at intervals of 3 to 10 days) and analysed for Ca, Co, Fe, Zn and pH. At the outset, other metals were also measured: Ag, Cd, Cu, Mn, Ni and Pb. Losses from the removal of sample aliquots (4% of total volume) and evaporation were 20 to 25% per week. The volume of the liquid in the percolators was maintained by refilling with 5 mM H₂SO₄. This led to the progressive dissolution of carbonates.

Colloid Phase

The colloid phase was analysed by draining all the liquid from the percolators at the end of the experiment. The liquor was centrifuged at 3600 × *g* for 30 min to remove cells and inorganic particles. The supernatant was spun at 242,500 × *g* for 4 h with an ultracentrifuge. An aliquot of the residue was analysed for metal content and another aliquot was analysed by X-ray diffractometry.

Salt Precipitate in Percolators

When the experiments had been underway for several weeks, a white precipitate was observed on the glass walls of percolators at the air-liquid interface. This compound was dried and analysed by X-ray diffractometry.

Erlenmeyer Flask Experiments

The bioleaching experiments were repeated in Erlenmeyer flasks (125 ml) for a period of 3 months at the optimal temperature (30°C) (Kelly & Harrison 1989).

Pyrite (3 g) was immersed in 30 ml of 9K medium (minus FeSO₄), with a pulp density of 10% (w/v). The carbonate content of the pyrite samples was: 0.01, 0.05, 0.10, 0.20, 0.30, 0.40, 0.60, and 1.01% (original pyrite). The intermediate carbonate contents were obtained by mixing the original pyrite with different quantities of carbonate-free pyrite. The pyrite samples were inoculated with 0.3 ml of a dense *T. ferrooxidans* culture containing 4.4 mg protein/ml. Two uninoculated samples were used as experiment controls. One ml of solution was collected each week and centrifuged at 12,000 × *g* to remove particles. Then the supernatant was analysed for metals as described above. In this case evaporation losses were negligible, but sampling took 3.3% of the total volume. The initial addition of 30 ml of 9K medium to 3 g of pyrite was sufficient to dissolve up to 0.30% of the carbonates.

Acidity

The titratable acidity in flask experiments was determined by titrating the sample with 0.01 M NaOH solution in the presence of phenolphthalein (Skoog & West 1979).

Results

Percolator Experiments

The continuous additions of acid to the percolators was not sufficient to completely dissolve the carbonate residue except in the pyrite sample with 0.01% of calcite




Figure 1. Effect of pH (○) on Fe (●) solubilization by *T. ferrooxidans* from a pyrite ore containing 0.25% of calcitic gangue after 3 months of incubation in air-lift percolators.

(pulp density 80%). The bioleaching process was first followed by determining metal concentrations in solution and by measuring pH values (Figure 1). Later only the concentration of Fe released into solution was used as an index of bioleaching activity. The pyrite containing 0.01, 0.25 and 0.50% of calcite was leached by *T. ferrooxidans* strain ATCC 13661, but not the samples with 0.75 and 1.01% of carbonates. For pyrite with a given calcite content, the soluble metals, Fe, Zn and Co, were first detected in solution at the same time, but for different calcite contents. The start of the bio-oxidation was directly related to carbonate concentration. The lag phases detected were: 13 days for 0.01% of calcite content, 38 days for 0.25% and 190 days for 0.50%. The maximum concentrations of Fe, Zn and Co in solution were reached after 80, 120 and 315 days, respectively, after inoculation and ranged from 4600 to 7500 mg Fe/l, 45 to 62 mg Zn/l and 14 to 18 mg Co/l (Figures 2-4). In uninoculated samples and in those with 0.75 and 1.01% of calcite, no metals were detected in solution. In the latter, pH was still neutral after one year.

Table 2. Bioleaching rates (mg/l/h) for metals at different concentrations of calcite gangue in the percolator study.

Metals	Calcite in pyrite ore			
	0.01%	0.25%	0.50%	1.01%
Fe	5.1	5.05	14.7	0
Zn	0.038	0.045	0.052	0
Co	0.008	0.013	0.023	0

For soluble Fe (Table 2), the bioleaching rate was closer (5.05 to 14.7 mg/l/h) to the rates reported in the interlaboratory calibration (12 mg/l/h). The bioleaching rate for Fe, Co and Zn (Table 2) increased significantly with the percentage of dissolved calcite. There is probably an increase in CO₂ concentrations from calcite dissolution in the interstitial water of the pyrite bulk. This excess CO₂ would favour the metabolism of the chemolithotroph *T. ferrooxidans*, which uses this gas as a carbon source (Ingledew 1982).

The concentration ratio of soluble metals was different from the metal content of pyrite ore (Table 3). Zinc is more soluble than Co and Fe, because it is probably




Figure 2. Bioleaching of Fe in air-lift percolators from pyritic ores containing 0.01% (□), 0.25% (○), 0.50% (△), and 1.01% (▲) of calcite and showing different lag phase spans directly correlated to calcite content.

ultraincluded as sphalerite (ZnS), a more soluble sulphide than pyrite (Yakhontova 1985). Cobalt on the other hand, replaces Fe in the pyrite lattice.

The dissolution pattern of Ca was completely different from that of other metals (Figure 5). First, the 9K medium and then the continuous refilling with acid water (pH 2) dissolved calcite. In the first weeks, dissolved Ca concentrations did not depend on the calcite content of the pyrite, and reached 350 to 420 mg/l in all percolator liquors. This range depended on continuous sampling, evaporation and refilling with acid solution. Conversely, the time required to entirely dissolve the calcite by acid additions depended on the content of calcite in the pyrite ore. *T. ferrooxidans* began to grow in the mineral bulk after the calcite had completely disappeared and the optimal growth pH was attained. However, the Ca²⁺ in solution remained relatively constant, until the soluble metal concentrations

Table 3. Ratio between metals in pyrite ore and in leaching solution.

Metal couples	Ratio in pyrite ore	Ratio in leachate	Concentration factor
Co/Fe	0.0016	0.003	1.9
Zn/Fe	0.0011	0.011	10.0
Zn/Fe	0.70	3.5	5.0




Figure 3. Bioleaching of Zn in air-lift percolators from pyritic ores containing 0.01% (□), 0.25% (○), 0.50% (△), and 1.01% (▲) of calcite and showing different lag phase spans directly correlated to calcite content.

reached a maximum, after which Ca^{2+} concentrations decreased (Figure 5) due to the depletion of CaCO_3 source, and continuous sampling which lasted several months.

Determination of total metals in the colloid phase (1.08 mg/ml), in the presence of carbonate-free pyrite, showed high concentrations of Fe (157 mg/g dry wt), Zn (1.25 mg/g) and Co (0.37 mg/g). Thus, 5.6% of Fe was in colloidal form and the remaining 94.4% was soluble; 4.2% of Zn and 4.4% of Co occurred as colloids. Colloidal co-precipitation of metals may take place, resulting in the trapping of small particles in the ore bulk, but accounts only for about 5% of the decline in metal concentrations in the later stage of the leaching bioprocess (Figures 2 to 4), with respect to a major metal loss due to the continuous liquor sampling. This decline was mostly accounted for by liquor sampling and was observed to depend on the number of samples taken.

Flask Experiments

This experiment was performed to confirm the effect of calcite on pyrite bioleaching. Only Fe, Ca and titratable acidity were determined in the liquor as indexes for bioleaching and calcite dissolution.

Calcium dissolution data is not reported because it followed the same pattern as in percolators. In the flask experiments, the lag phase spans were significantly different from those in the percolator study and were characterized by Fe




Figure 4. Bioleaching of Co in air-lift percolators from pyritic ores containing 0.01% (□), 0.25% (○), 0.50% (△) and 1.01% (▲) of calcite and showing different lag phase spans directly correlated to calcite content.

concentrations in the liquor. In fact, the bioleaching of pyrite occurred more rapidly. The lag phases determined from Fe solubilization curves (Figure 6), were 2 days for 0.01% calcite content, 15 days for 0.05 to 0.10%, 20 days for 0.20 to 0.30%, 32 days for 0.40%, and 65 days for 0.60%. The original pyrite (1.01% calcite) was not oxidized by *T. ferrooxidans* strain ATCC 13661 after 90 days of incubation. The Fe concentrations were inversely correlated to calcite content in pyrite. The maximum concentration of Fe (1700 mg/l) in solution occurred in the sample without calcite, whereas in the pyrite with more calcite, Fe concentration dropped to 250 mg/l, as, for example, with 0.60% of calcite (Figure 5).

The Fe bioleaching rates were lower than in the percolator study, ranging from 2 mg/l/h in the sample with carbonate-free pyrite down to 0.36 mg/l/h in the sample with 0.60% of carbonate (Figure 6). The acid production rate from pyrite bio-oxidation also diminished in the bioleaching liquor depending on the calcite content of the pyrite ores (Figure 7).

Discussion

Thiobacillus ferrooxidans strain ATCC 13661 can oxidize pyrites provided they contain only traces of calcite. However, this acidophilic micro-organism can survive at neutral pH for a long time, and as soon as conditions are favourable,




Figure 5. Concentrations of Ca in the bioleaching liquor of air-lift percolators with different pyrite ores containing 0.01% (□), 0.25% (○), 0.50% (△) and 1.01% (▲) of calcite.

it starts oxidizing the mineral bulk. The survival of the organism at neutral pH is not surprising because of its isolation from high pH natural environments. Olson *et al.* (1979, 1981) regularly found an abundance of acidophilic iron- and sulphur-oxidizing autotrophs around alkaline pyrite-containing coal mines in southern Montana (USA), despite the high pH of drainage waters. In addition, strains of *T. ferrooxidans* have been isolated by us from calcareous sulphide deposits in Sardinia (Italy). *T. ferrooxidans* probably survives in a state of dormancy or is localized in acidic microzones (Van Voast & Hedges 1975).

The results of the two studies were contradictory for the following reasons: (1) in the percolator system, the bioleaching rates of Fe were higher and increased with the amount of dissolved calcite, the same was true of Zn and Co; (2) in the flask experiments, the Fe bioleaching rate was about half that in the percolator system for minimum calcite content (up to 0.15%), and about 30 times less when the calcite content was above 0.25%; (3) on the other hand, the lag phase spans for *T. ferrooxidans* in the flask study were significantly shorter. These differences in metal extraction between the percolator and flask experiments can be explained by the different characteristics of the two systems and depend on if the acid solution is added, on different sites of gypsum precipitation (outside or in the mineral bulk), and on the final pH of the bioleaching solution.

In the percolators, a few ml of acidified water per week were added to maintain the constant volume of the leaching liquor, and the larger lag time is linked to the more gradual dissolution of calcite, which keeps the micro-organism in a dormant state.




Figure 6. Dissolution of Fe in Erlenmeyer flasks from different samples of pyrite ore containing variable concentrations of calcite: 0.01% (□), 0.05% (○), 0.10% (△), 0.20% (■), 0.30% (●), 0.40% (▲), 0.60% (—□—), and 1.01% (—○—).

In the flask study, the larger amount of acidified medium added at the beginning dissolved more calcite (0.40%) and the lag phase spans were consequently shorter.

The bioleaching rates of metals tended to be higher in percolators with pyrite ore containing more dissolved calcite, probably because the CO₂ generated by dissolving carbonates in the interstitial water of the pyrite bulk is utilized by the chemolithotroph *T. ferrooxidans* as a carbon source. In addition calcite is transformed to gypsum which precipitated on the percolator wall at the water-air interface, outside the mineral bulk. The optimal pH to bio-oxidize the mineral ore is also reached in the liquor.

In the flasks, on the other hand, the bioleaching rates decreased with calcite content because the newly formed gypsum precipitated in the mineral bulk. The pyrite assumed a milky-brown colour and the bio-available surface of the mineral was diminished. The acidity in the liquor is not optimal, especially in those with high calcite content, and consequently affects the Fe concentrations, which tend to precipitate from the liquor as jarosite.

Regarding the biological extraction of Co and Zn, Zn was more readily extracted than Co.

The removal of carbonates could provide a solution in cases in which pyrite contains high concentrations of more soluble strategic metals. Chemical or biological pretreatment to remove the carbonic gangue could be considered in cases of promising good metal recovery from sulphide ores.




Figure 7. Bioleaching rates of Fe (□) and acid production (△) calculated by ml NaOH 1.0 M added to the sample, in Erlenmayer flasks for different calcite concentrations in the pyrite ores.

In addition, Ca^{2+} concentrations in the bioleaching solution are a good indicator of the efficiency of the bioprocess and are more useful than carbonate concentrations in ores, because calcite can occur as lumps in sulphide deposits.

References

- BALDI, F. & OLSON, G.J. 1987 Effects of cinnabar on pyrite oxidation by *Thiobacillus ferrooxidans* and cinnabar mobilization by a mercury resistant strain. *Applied Environmental Microbiology* **53**, 772-774.
- BARBIC, F.F. 1977 Effects of different compounds of metals and of their mixtures on the growth and survival of *Thiobacillus ferrooxidans*. *Zeitschrift für allgemeine Mikrobiologie* **17**, 277-281.
- BOSEKER, K., NEUSCHUTZ, D. & SCHEFFLER, U. 1978 Microbiological leaching of carbonate-rich German copper-shale. In *Metallurgical Applications of Bacterial Leaching and Related Microbiological Phenomena*, eds Murr, L.E., Torma, A.E., & Brierley, J.A., pp. 389-401, New York: Academic Press.
- BRIERLEY, C.L. 1978 Bacterial leaching. *Critical Review of Microbiology* **6**, 207-262.
- DUGAN, P. P., MACMILLAN, C.B. & PFISTER, R.M. 1970 Aerobic heterotrophic bacteria indigenous to pH 2.8 acid mine water: predominant slime producing bacteria in acid streamers. *Journal of Bacteriology* **101**, 982-988.
- EHRlich, H.L. 1987 Bioleaching of silver from mixed sulphide ore in a stirred reactor. In *Bi hydrometallurgy: Proceedings of an International Symposium*, University of Warwick, 1987, eds Norris, P.R. & Kelly, D.P., pp. 223-231. Chippenham, Wiltshire, UK: Antony Rowe Ltd.
- GROUDEV, S.N., GENCHEV, F.N. & GAIDARJIEV, S.S. 1978 Observation of the microflora in an industrial copper dump leaching operation. In *Metallurgical Application of Bacterial Leaching and Related Microbiological Phenomena*, eds Murr, L.E., Torma, A.E. & Brierley, J.A. pp. 253-274. New York: Academic Press.

- IMAI, K., SUGIO, T., TSUCHIDA, T. & TANO, T. 1975 Effects of heavy metal ions on the growth and iron-oxidizing activity of *Thiobacillus ferrooxidans*. *Agricultural and Biological Chemistry* **39**, 1349–1354.
- INGLEDEW, J.W. 1982 *Thiobacillus ferrooxidans*. The bioenergetics of an acidophilic chemolithotroph. *Biochimica et Biophysica Acta* **683**, 89–117.
- ISHIKAWA, T., MURAYAMA, T., KAWAHARA, I. & IMAZUMI, T. 1983 Treatment of acid mine drainage utilizing bacterial oxidation. In *Recent Progress in Bihydrometallurgy*, eds Rossi, G. & Torma, A.E. pp. 393–407. Iglesias, Italy: Associazione Mineraria Sarda.
- KELLY, D.P. & HARRISON, A.P. 1989 Genus *Thiobacillus*. In *Bergey's Manual of Systematic Bacteriology*, Vol. 3. ed. Staley, J.T., pp. 1842–1858. Baltimore, MD: Williams and Wilkins.
- KELLY, D.P., NORRIS, P.R. & BRIERLEY, C.L. 1979 Microbiological methods for the extraction and recovery of metals. In *Microbial Technology: current state, future prospects*, Vol. 29, *Symposium of the Society for General Microbiology*, eds Bull, A.T., Ellwood, D.C. & Ratledge, C. pp. 263–308. Cambridge: Cambridge University Press.
- KHALID, Z.M., MAHMMOD, T. & MALIK, K.A. 1987 Leaching of a carbonate bearing uranium ore with a selected strain of *Thiobacillus thiooxidans*. In *Bihydrometallurgy: Proceedings of an International Symposium*, University of Warwick, 1987, eds Norris, P.R. & Kelly, D.P. p. 524. Chippenham, Wiltshire, UK: Antony Rowe Ltd.
- MAHAPATRA, R.S.S. & MISHRA, A.K. 1984 Inhibition in *Thiobacillus ferrooxidans* by toxic metals and its alleviation by EDTA. *Current Microbiology* **11**, 1–6.
- OLSON, G.J., MCFETERS, G.A. & TEMPLE, K.L. 1981 Occurrence and activity of iron- and sulfur-oxidizing microorganisms in alkaline coal strip mine spoils. *Microbial Ecology* **7**, 39–50.
- OLSON, G.J., TURBAK, S.C. & MCFETERS, G.A. 1979 Impact of Western coal mining—II. Microbiological studies. *Water Research* **13**, 1033–1041.
- PAKNIKAR, K.M. & AGATE, A.D. 1987 Occurrence of a *Thiobacillus ferrooxidans* strain tolerating unusually high concentrations of metals and an associated metal-tolerant acidophilic heterotrophic bacterium. In *Bihydrometallurgy: Proceedings of an International Symposium*, University of Warwick, 1987, eds Norris, P.R. & Kelly, D.P., pp. 223–231. Chippenham, Wiltshire, UK: Antony Rowe Ltd.
- PINCHES, A., CHAPMAN, J.T., TE RIELE, W.A.M. & VAN STADEN, M. 1987 The performance of bacterial leach reactors for the preoxidation of refractory gold-bearing sulphide concentrates. In *Bihydrometallurgy: Proceedings of an International Symposium*, University of Warwick, 1987, eds Norris, P.R., & Kelly, D.P., pp. 329–344. Chippenham, Wiltshire, UK: Antony Rowe Ltd.
- SCHAFFER, W. 1983 Leaching of industrial wastes products with *thiobacilli* and heterotrophic microorganisms. In *Recent Progress in Bihydrometallurgy*, eds Rossi, G. & Torma, A.E. pp. 427–440. Iglesias, Italy: Associazione Mineraria Sarda.
- SILVERMAN, M.P. & LUNDGREN, D.G. 1959 Studies on the chemoautotrophic iron bacterium *Ferrobacillus ferrooxidans*—I. An improved medium and harvesting procedure for securing high cell yields. *Journal of Bacteriology* **77**, 642–647.
- SKOOG, D.A. & WEST, D.M. 1979 *Analytical Chemistry*. New York: Holt, Rinehart and Winston.
- SUGIO, T., TANO, T. & IMAI, K. 1981 Isolation and some properties of silver ion-resistant iron-oxidizing bacterium *Thiobacillus ferrooxidans*. *Agricultural Biological Chemistry* **45**, 2037–2051.
- TUOVINEN, O.H. & KELLY, D.P. 1974 Studies on the growth of *Thiobacillus ferrooxidans*—II. Toxicity of uranium to growing cultures and tolerance conferred by mutation, other metal cations and EDTA. *Archiv für Mikrobiologie* **95**, 153–164.
- VAN VOAST, W.A. & HEDGES, R.B. 1975 Hydrogeological aspects of existing and proposed strip coal mines near Decker, southeastern Montana. Bulletin No. 97. State of Montana, Bureau of Mines and Geology, Butte, MT.
- WALLACE, W.A., MUELLER, R.T., DATEL, P.M. & SOUFI, S.M. 1976 Use of waste pyrites from mine operations on highly calcareous soil. *Communication in Soil Science and Plant Analysis* **7**, 57–60.
- WICHLACZ, P.L. & THOMPSON, D.L. 1987 The effects of acidophilic heterotrophic bacteria on the leaching of cobalt by *Thiobacillus ferrooxidans*. In *Bihydrometallurgy: Proceedings of an International Symposium*, University of Warwick, 1987, eds Norris, P.R. & Kelly, D.P., pp. 77–86. Chippenham, Wiltshire, UK: Antony Rowe Ltd.
- YAKHONTOVA, L.K. 1985 The role of the sulphide constitution in the process of their bacterial leaching. ed. Karavaiko, G.I. & Groudev, S.N. pp. 216–226. Moscow: Centre International Project GKNT.

(Received 10 August 1990; revised 17 October 1990; accepted 14 November 1990)