

## Loading Dependent Diffusion Studies on Aromatic Hydrocarbons Adsorbed in MOF-5 via PFG NMR

*Markus Wehring<sup>1</sup>, Stefan Hertel<sup>1</sup>, Saeed Amirjalayer<sup>2</sup>, Rochus Schmid<sup>2</sup>, Frank Stallmach<sup>1</sup>*

<sup>1</sup> University Leipzig, Faculty of Physics and Earth Science, Linnéstr. 5,  
04103 Leipzig, Germany, E-Mail: [wehring@physik.uni-leipzig.de](mailto:wehring@physik.uni-leipzig.de)

<sup>2</sup> Ruhr-University Bochum, Faculty of Chemistry and Biochemistry, Germany

### 1. Introduction

This study focuses on one of the promising metal-organic frameworks, the MOF-5 (*also abbreviated: IRMOF-1*), which is built of zinc oxide clusters as metal coordination centers and terephthalic acid as organic linkers [1]. For realization of the prospective applications, knowledge about mobility of aromatic hydrocarbons adsorbed in MOF-5 is necessary. For this reason the self-diffusion coefficients of aromatic hydrocarbons in MOF-5 are studied via pulseD field gradient (PFG) NMR and compared with molecular dynamic simulations.

### 2. Sample and Results

MOF-5 crystals were synthesized and loaded with benzene and toluene from Saeed Amirjalayer, under completely hermetically sealed conditions. We measured three different loadings (20%, 32% and 56% of the fully filled pore volume) for each guest molecule.

The self-diffusion of benzene adsorbed in MOF-5 were investigated using proton (<sup>1</sup>H) pulsed field gradient (PFG) NMR [2]. The measurements carried out in a temperature range of 233 K to 328 K, yielded activation energies of self-diffusion of 11.2 kJ/mol. This result agrees very well with the simulated activation energy for a flexible framework of Amirjalayer et al., who found a value of 13.6 kJ/mol [3]. For a temperature of 273 K the experimentally determined self-diffusion coefficients are in the range of  $2.6 \cdot 10^{-10}$  m<sup>2</sup>/s (56% benzene) to  $3.2 \cdot 10^{-10}$  m<sup>2</sup>/s (20% benzene). This trend of slower diffusivity for higher loading is also shown by the simulations.

Measurements of toluene adsorbed in MOF-5 are currently under process.

### 3. Conclusion

This work shows the temperature and loading dependence of self-diffusion of aromatic hydrocarbons adsorbed in MOF-5. The good agreement of the experimental values for the activation energy of self-diffusion with the simulated values confirms the assumption of a flexible MOF-5 lattice.

### References

- [1] M. Eddaoudi, J. Kim, N. Rosi, D. Vodak, J. Wachter, M. O'Keefe, O. M. Yaghi, *Science* 295 (2002) 469-472
- [2] F. Stallmach, P. Galvosas, *Annual Reports in NMR Spectroscopy* 61 (2007) 51-131
- [3] S. Amirjalayer, M. Tafipolsky, R. Schmid, *Angew. Chem.-Int. Edit.* 46 (2006) 463-466