

Lithium Permeation Through Thin Silicon Layers

Erwin Hüger¹, Jochen Stahn², Harald Schmidt^{1,3}

¹ Institut für Metallurgie, Technische Universität Clausthal, Robert-Koch-Str. 42, 38678 Clausthal-Zellerfeld, Germany; ² Laboratory for Neutron Scattering and Imaging, Paul Scherrer Institut, 5232 Villigen PSI, Switzerland; ³ Clausthaler Zentrum für Materialtechnik, Technische Universität Clausthal, Leibnizstr. 9, 38678 Clausthal-Zellerfeld, Germany

E-Mail: erwin.hueger@tu-clausthal.de

Lithium permeation through amorphous silicon layers with thicknesses between 2 and 100 nm and adjacent interface layers was measured by secondary ion mass spectrometry (SIMS) and *in situ* by neutron reflectometry (NR). Such experiments are interesting for research on nanostructured electrode materials in Li based batteries, Li ion selective electrodes, and sensors [1, 2]. Interface limited Li transport was recently proven to account for irreversible capacity losses [3].

Stacks with a repetition of [Si / ⁷LiNbO₃ / Si / ⁶LiNbO₃] multilayer units were used for analysis. Here, two isotope enriched lithium niobate layers are adjacent to a silicon layer. The lithium niobate layers serve as solid state Li reservoirs. Annealing leads to a mutual exchange of the two Li isotopes through the silicon layer and the interfaces by Li permeation. This process modifies the Li isotope fraction in the solid state Li reservoirs, which is used to derive the permeability (diffusivity × solubility).

The presence of a diffusion controlled process was proven by a significant dependence of the Li isotope exchange time on silicon layer thickness. Li permeability in silicon is approximately constant at thicknesses above 30 nm and is strongly enhanced below 30 nm. The activation enthalpy for Li permeation through silicon amounts to $\Delta H = (1 \pm 0.2)$ eV for silicon layers with a thickness below 30 nm, and to $\Delta H = (2 \pm 0.2)$ eV for larger silicon layer thicknesses.

Possible explanations for the measured higher Li permeability (diffusivity × solubility) in thinner silicon layers may be a higher Li diffusivity due to a larger concentration of fast diffusing Li species and/or a higher Li solubility due to, *e.g.*, size confinement [4].

- [1] Lithium Transport through Nanosized Amorphous Silicon Layers, E. Hüger, L. Dörrer, J. Rahn, T. Panzner, J. Stahn, G. Lilienkamp, H. Schmidt., *Nano Lett.* 13 (2013) 1237.
- [2] Neutron Reflectometry to Measure *in situ* Li Permeation through Ultrathin Silicon Layers and Interfaces, E. Hüger, J. Stahn, H. Schmidt, *J. Electrochem. Soc.* 162 (2015) A7104.
- [3] Interface Limited Lithium Transport in Solid-State Batteries, D. Santhanagopalan, D. Qian, T. McGilvray, Z. Wang, F. Wang, F. Camino, J. Graetz, N. Dudney, Y. S. Meng, *Phys. Chem. Lett.* 5 (2014) 298.
- [4] Dynamic Solubility Limits in Nanosized Olivine LiFePO₄, M. Wagemaker, D. P. Singh, W. J. H. Borghols, U. Lafont, L. Haverkate, V. K. Peterson, F. M. Mulder, *J. Am. Chem. Soc.* 133 (2011) 10222.