



The "Go Big or Go Home" Club: Molecular Dynamics Modelling of Bulk Heterojunctions

Gertsen, Anders S.; Sørensen, Michael Korning; Fernández Castro, Marcial; Nelson, Jenny; Andreasen, Jens W.

Publication date:
2018

Document Version
Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

Citation (APA):

Gertsen, A. S., Sørensen, M. K., Fernández Castro, M., Nelson, J., & Andreasen, J. W. (2018). *The "Go Big or Go Home" Club: Molecular Dynamics Modelling of Bulk Heterojunctions*. 1. Poster session presented at DTU Energy's annual PhD symposium 2018, Lyngby, Denmark.

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

The “Go Big or Go Home” Club: Molecular Dynamics Modelling of Bulk Heterojunctions

Anders S. Gertsen,^{†,‡} Michael Korning Sørensen,[†] Marcial Fernández Castro,[†]

Jenny Nelson,[‡] Jens W. Andreasen[†]

[†] Technical University of Denmark, Department of Energy Conversion and Storage, 4000 Roskilde, Denmark


[‡] Imperial College London, Department of Physics, London SW7 2AZ, United Kingdom

Motivation

The “Go Big or Go Home” club is a collaboration within the SEEWHI H2020 project which aims upscale the manufacturing of organic photovoltaics (OPVs) without compromising the device efficiency. Usually, the efficiency is halved when moving from non-scalable spin-coating to roll-to-roll (R2R) deposition techniques, but combining the strengths of molecular dynamics (MD) modelling and *in situ* X-ray scattering enables the analysis of blend microstructure formation during post-deposition drying, in turn allowing us to identify the processing parameters that are key to overcome the scalability lag and move towards cheap, large-scale, and non-toxic solar cells with record efficiencies.

Simulating post-deposition drying

The efficiency of solution processed OPVs is crucially dependent on the 3D mesoscale thin-film morphology, which in turn is greatly influenced by solvent properties and evaporation rate.



In order to reliably simulate active layer morphologies from MD simulations, we have scripted a range of evaporation schemes incorporating e.g. potential walls mimicking substrate- and air interfaces as well as including a suspended solvent vapour above the film from which solvent molecules are continuously removed.¹




Figure 1: Solvent evaporation simulation of all-atom O-IDTBR small-molecule acceptors in coarse-grained chloroform.

Acknowledgements

ASG thanks Otto Mønstedts Fond for financial support and Prof. Natalie Stingelin for facilitating a six months stay at Imperial College London. ASG, MKS, MFC, and JWA acknowledge financial support from the H2020 European Research Council through the SEEWHI Consolidator grant, ERC-2015-CoG-681881, and ASG thanks the team responsible for the Niflheim supercomputer at DTU where all calculations were performed.

Methodology

We have used the GROMACS 2016.3 package⁵ for all MD simulations. The OPLS-AA force field⁶ formed the basis for the all atom simulations of IDTBT and O-IDTBR with our own parameterizations of e.g. most angles and in particular the IDT-BT torsional potential and sidechain couplings – these were based on quantum chemical DFT calculations. The coarse-grained simulations were based on the MARTINI force field² and in part Ref. 4.

Approaching experimental time-scales

Using the MARTINI force field² to coarse-grain our systems, the time- and length-scales relevant for morphology evolution are within reach of MD simulations:^{3,4}

~1000 times speed-up




Figure 2: All-atom and MARTINI coarse-grained models for chloroform (CF), PCBM,⁴ and a dimer of C₁₆-IDTBT.




Figure 3: Thin-film of C₁₆-IDTBT 12mers (red) and PCBM (semi-transparent grey) annealed at 600 K and cooled down to 300 K. Sidechains are not shown.

References

- [1] V. Negi *et al.*, *Macromol. Theory Simul.* 2016, 25, 550-558.
- [2] S. J. Marrink *et al.*, *J. Phys. Chem. B* 2007, 111, 7812-7824.
- [3] C.-K. Lee and C.-W. Pao, *J. Phys. Chem. C* 2014, 118, 11224-11233.
- [4] R. Alessandri *et al.*, *J. Am. Chem. Soc.* 2017, 139, 3697-3705.
- [5] M. J. Abraham *et al.*, *SoftwareX* 2015, 1-2, 19-25.
- [6] W. L. Jorgensen Group, Yale University, Department of Chemistry.

