


22nd International Conference on
Solid State Ionics

Program Book

평창  2019
SSI
Solid State Ionics

June 16(Sun)-21(Fri), 2019
PyeongChang Alpensia Resort, Korea





PROGRAM DETAILS

Poster Presentation

June 17(Mon)

| Poster Number | Paper Title | Presenter | Organization |
|---------------|--|-----------------------|--|
| P-MON-184 | Microstructural and Electrochemical Properties of Impregnated $\text{La}_{0.4}\text{Sr}_{0.6}\text{Ti}_{0.8}\text{Mn}_{0.2}\text{O}_{3.2d}$ into a Partially Removed Ni SOFC Anode Substrate | Jung Hyun Kim | Hanbat National Univ. |
| P-MON-185 | X-ray Photoelectron Spectroscopic Study of Impregnated $\text{La}_{0.4}\text{Sr}_{0.6}\text{Ti}_{0.8}\text{Mn}_{0.2}\text{O}_{3.2d}$ Anode Material for High Temperature-operating Solid Oxide Fuel Cell | Jung Hyun Kim | Hanbat National Univ. |
| P-MON-186 | Microstructural Effect on Charge Relaxation Phenomenon of Doped Ceria as Electrolyte for IT-SOFCs | Smita Atul Acharya | RTMNU |
| P-MON-187 | Investigation of potential catalytic compounds for direct synthesis of methane from $\text{H}_2\text{O}-\text{CO}_2$ co-electrolysis | Beata Maria Bochentyn | Gdansk Univ. Tech. |
| P-MON-188 | Electrochemical CO_2 Hydrogenation to Syn-Fuels at Atmospheric Pressure in co-Ionic Membrane Reactors | Ioannis Garagounis | Aristotle Univ. of Thessaloniki |
| P-MON-189 | Augmenting the catalytic activity of Pt-CeO ₂ catalyst by heat treatment in H ₂ atmosphere for CO oxidation | Asif Jan | KIST |
| P-MON-190 | Atomistic investigation of doping effects on electrocatalytic properties of cobalt oxides for water oxidation | Byunghoon Kim | Seoul National Univ. |
| P-MON-191 | Surface and Interface Studies of Ni doped BZY for Catalysis Applications | Dylan Jennings | Colorado School of Mines |
| P-MON-192 | Steam reforming of methane at low-temperature supported by bimetallic catalysts for high fuel utilization of proton-conducting ceramic fuel cells | Kyungpyo Hong | Yonsei Univ. |
| P-MON-193 | Real-time control of size distribution of cobalt nanoparticles grown on ceria surface for CO oxidation | Sangwoo Kim | KAIST |
| P-MON-194 | Exploration of the reaction pathway of ceria-based catalyst for CH ₄ conversion | Siwon Lee | KAIST |
| P-MON-195 | Reaction kinetics of catalytic dry reforming of methane on Ni/Al ₂ O ₃ at low-temperature using an in-situ stagnation-flow reactor | Yonggyun Bae | Yonsei Univ. |
| P-MON-196 | Tuning the efficiency of oxygen evolution catalyst with alkaline ions | Hyunah Kim | Seoul National Univ. |
| P-MON-197 | Feasibility of Ni-based bimetallic catalysts anchored on ceramic supports for dry reforming of methane at low-temperature | JeongA Lee | Yonsei Univ. |
| P-MON-198 | Nickel catalyst generated by perovskite exsolution for enhanced CO oxidation | Rui Huang | POSTECH |
| P-MON-199 | Long-term Thermal Stability of Pt@SiO ₂ Catalyst in High-temperature CH ₄ Combustion | Seunghyun Kim | KAIST |
| P-MON-200 | Atomic-Resolution Operando Study of Triple-Phase Boundary Dynamics during Catalytic Oxidation Reactions | Peter A. Crozier | Arizona State Univ. |
| P-MON-201 | Oxygen-Deficient $(\text{Nd}_{0.4}\text{Sr}_{0.6})_2\text{Ni}_{0.8}\text{M}_{0.2}\text{O}_{4.6}$ Nickelates as Oxygen Electrode Materials for SOFC/SOEC | Aleksey Yaremchenko | CICECO - Aveiro Institute of Materials, Univ. Aveiro |
| P-MON-202 | Oxygen transport properties and in-situ characterization of $\text{La}_{0.75}\text{X}_{0.25}\text{Cr}_{0.5}\text{Mn}_{0.5}\text{O}_3$ (X = Sr, Ca) | Caroline Pirovano | ENSCL / Univ. de Lille |

Oxygen-Deficient $(\text{Nd}_{0.4}\text{Sr}_{0.6})_2\text{Ni}_{0.8}\text{M}_{0.2}\text{O}_{4-\delta}$ Nickelates as Oxygen Electrode Materials for SOFC/SOEC

Aleksey Yaremchenko^{(a)}, Blanca I. Arias-Serrano^(a), Ekaterina Kravchenko^(b), Kiryl Zakharchuk^(a), Jekabs Grins^(c), Gunnar Svensson^(c), Vladimir Pankov^(b)*

^(a) CICECO - Aveiro Institute of Materials, DEMAC, University of Aveiro, Aveiro, Portugal

^(b) Faculty of Chemistry, Belarusian State University, Minsk, Belarus

^(c) Department of Materials and Environmental Chemistry, Stockholm University, Sweden

* ayaremchenko@ua.pt

Abstract

Perovskite-related $\text{Ln}_2\text{NiO}_{4+\delta}$ (Ln = La, Pr, Nd) nickelates with layered Ruddlesden-Popper combine redox stability with noticeable oxygen stoichiometry changes, yielding enhanced mixed transport and electrocatalytic properties. These unique features are promising for applications as oxygen electrodes with good electrochemical performance in reversible SOFC/SOEC (solid oxide fuel/electrolysis cell) systems. To date, most efforts were focused on oxygen-hyperstoichiometric $\text{Ln}_2\text{NiO}_{4+\delta}$ -based phases, whereas nickelates with oxygen-deficient lattice remain poorly explored. Recent studies demonstrated that the highest electrical conductivity in $(\text{Ln}_{2-x}\text{Sr}_x)_2\text{NiO}_{4\pm\delta}$ series at elevated temperatures is observed for the compositions containing ~ 60 at.% of strontium in A sublattice [1,2]. The present work was focused on the characterization of $(\text{Nd}_{0.4}\text{Sr}_{0.6})_2\text{Ni}_{0.8}\text{M}_{0.2}\text{O}_{4-\delta}$ (M = Ni, Co, Fe) nickelates for the possible use as materials for reversible oxygen electrodes.

The ceramic materials were prepared by Pechini method with repeated annealings at 650-1200°C and sintered at 1250-1300°C for 5 h under oxygen atmosphere. Variable-temperature XRD studies confirmed that all studied compositions retain tetragonal K_2NiF_4 -type structure in the temperature range 25-900°C. The results of thermogravimetric analysis showed that the prepared nickelates has oxygen-deficient lattice under oxidizing conditions at temperatures above 700°C. Partial substitution of nickel by cobalt or iron results in a decrease of *p*-type electronic conductivity and the concentration of oxygen vacancies in the lattice, but also suppresses dimensional changes associated with microcracking effects (due to anisotropic thermal expansion of tetragonal lattice). Electrochemical performance of porous $(\text{Nd}_{0.4}\text{Sr}_{0.6})_2\text{Ni}_{0.8}\text{M}_{0.2}\text{O}_{4-\delta}$ electrodes in contact with $\text{Ce}_{0.9}\text{Gd}_{0.1}\text{O}_{2-\delta}$ solid electrolyte was evaluated at 600-800°C employing electrochemical impedance spectroscopy and steady-state polarization (anodic and cathodic) measurements.

[1] E. Kravchenko, D. Khalyavin, K. Zakharchuk, J. Grins, G. Svensson, V. Pankov, A. Yaremchenko, *J. Mater. Chem. A* 3 (2015) 23852.

[2] E. Kravchenko, K. Zakharchuk, A. Viskup, J. Grins, G. Svensson, V. Pankov, A. Yaremchenko, *ChemSusChem* 10 (2017) 600.