

酵素修飾ナノチューブ電極を用いた発電デバイスに関する研究

著者	吉野 修平
号	58
学位授与機関	Tohoku University
学位授与番号	工博第004990号
URL	http://hdl.handle.net/10097/58982

氏名	吉野修平
授与学位	博士(工学)
学位授与年月日	平成26年3月26日
学位授与の根拠法規	学位規則第4条第1項
研究科, 専攻の名称	東北大学大学院工学研究科(博士課程) バイオロボティクス専攻
学位論文題目	酵素修飾ナノチューブ電極を用いた発電デバイスに関する研究
指導教員	東北大学教授 西澤 松彦
論文審査委員	主査 東北大学教授 西澤 松彦 東北大学教授 小野 崇人 東北大学教授 桑野 博喜 東北大学准教授 梶 弘和

論文内容要旨

Enzymatic fuel cells (EFCs) are power devices in which enzymes are used as electrocatalysts to directly convert biochemical energy into electricity, in contrast to metallic catalysts commonly used for conventional fuel cells. The extremely high reaction selectivity of enzymes eliminates the need for fuel purification and allows a separator-free design that consists of just a pair of anode and cathode electrodes exposed to solutions containing both fuel and oxygen; thus EFCs have attracted much attention as extremely safe and miniature power sources for wearable or implantable medical devices such as a health monitoring system, a drug delivery system and artificial organs. However, due to low power output (mW cm^{-2} range) and short lifetime (a few days), EFCs were thought insufficient for practical applications. In order to overcome these drawbacks, in this thesis, the author describes novel techniques, e.g., nanoengineering of enzyme electrode using well-aligned carbon nanotube film. Summaries of each chapter are provided below.

Chapter 1. Introduction

In this chapter, the background and purpose of this thesis are described. The principle of an enzymatic biofuel cell, the property of components, the trends in preparation technique for enzyme electrodes are described in detail. In addition, the trends and problems of enzyme electrodes fabricated by nano-materials are reviewed.

Chapter 2. Composite of direct electron transfer-type enzyme and carbon nanotube films

A variety of nanoengineered carbon electrodes for biofuel cells have recently been developed in rapid succession. For example, the use of the carbon nanotube (CNT) or the carbon nano particles for electrode preparation resulted in a higher-power biofuel cells. However, because they are random aggregates of nano-carbons, the post-modification of enzymes to their

intra-nanospace is generally hard to control. If the nanostructure of the electrode can be regulated in response to the enzyme to be immobilized, then the resultant enzymatic ensemble would avoid the difficulty in postmodification of enzymes. In this chapter, a fabrication of biofuel cell using film of carbon nanotube forest (CNTF) is described. When liquids are introduced into the as-grown CNTF (CNTs with a pitch of 16 nm) and dried, the CNTF shrinks to a close-packed structure (CNTs with a pitch of 3.7 nm) because of the surface tension of the liquids. By using an enzyme solution as the liquid, the CNTF is expected to dynamically entrap the enzymes during the shrinkage.

Firstly, the entrapment of enzymes into CNTF through liquid-induced shrinkage is described. The in situ monitoring of electrocatalytic activity of the CNTF films on soaking in a buffer containing FDH with d-fructose showed currents corresponding to their thickness, indicating that the FDH molecule can entirely penetrate inside the CNTF films that have suitable intra-structure and size for enzyme penetration. On the other hands, the catalytic activity of the conventional random CNT electrode was a tithe of the CNTF.

Controlling the content of FDH inside a CNTF could be achieved by changing concentration of the FDH solution. Such controlled entrapment of enzymes could be also examined via the degree of CNTF shrinkage. The degree of shrinkage was found to depend on the size and content of the enzymes. These results are proof of the in situ regulation of intra-nanospace of CNTF by the amount and size of entrapped enzymes.

The electrode performance was found to depend on the content of FDH. The best performance was reproducibly obtained from the FDH-entrapped CNTF electrode prepared from 3 mg mL⁻¹ FDH solution, which contains ca. 1.5 μg FDH. This value of FDH content can be modeled as a linear arrangement of FDH molecules trapped between the CNTs. The current density of FDH-entrapped CNTF for fructose oxidation reached 16 mA cm⁻² that is one of the highest values in FDH electrodes. The preparation of a laccase (LAC)-entrapped CNTF cathode for O₂ reduction is also described. The LAC-entrapped CNTF was archived by methodology of in situ regulation of intrananospace of CNTF. The electrode film showed O₂ reduction current density of ~2 mA cm⁻². A further increase in current density to ~4 mA cm⁻² was achieved by overlapping two pieces of CNTF by taking advantage of their free-standing character.

The performance of the biofuel cell constructed with the cathode of LAC-entrapped CNTF and the anode of FDH-entrapped CNTF are described. The biofuel cell performed a power density of 1.8 mW cm⁻² (at 0.45 V) in stirred conditions, 84% of which could be maintained after continuous operation for 24 h. Additionally, The prepared enzyme-entrapped CNTF film was the first free-standing, flexible enzyme electrode which could be patched on a flexible substrates, or could be wound on the electric leads.

The proposed “in-situ regulation” is a straightforward approach to avoid the longstanding difficulty in the post modification of enzymes into conventional nanostructured electrodes.

Chapter 3. Composite of mediated electron transfer-type enzyme and carbon nanotube films

Electrical contact between a redox enzyme and an electrode is a critical issue for designing biosensors and biofuel cells. Especially, electrodes modified with glucose oxidase (GOD) have been actively studied, since glucose is important blood sugar and is the most abundant fuel for ubiquitous power generation. This chapter describes an enzyme/mediator/electrode nano-ensemble that shows both “high turnover rate” and “large catalytic current”. In order to satisfy both of these requirements, large amounts of enzymes should be immobilized, while keeping effective contact with electrodes. This ideal condition can be realized by taking advantage of a well-ordered carbon nanotube forest (CNTF) consisting of single-walled CNTs arrayed with a pitch of 16 nm. A stepwise process for the modification of polyvinylimidazole - [Os (bipyridine)₂ Cl] (PVI-[Os(bpy)₂Cl]) and subsequently GOD have been developed.

Firstly, the CNTF film was soaked in a stirred PVI-[Os(bpy)₂Cl] solution. The amount of PVI-[Os(bpy)₂Cl] in a CNTF film increased with the soaking time and these values are proportional to the CNTF film thickness, indicating that even the polymeric PVI-[Os(bpy)₂Cl] can entirely and uniformly adsorbed inside the CNTF films. A part of the free imidazole groups of the mediator polymer would adsorb on CNT surfaces via π - π interaction.

Subsequent loading of the GOD enzyme was conducted by immersing the PVI-[Os(bpy)₂Cl]-adsorbed CNTF films in a stirred GOD solution. The CVs of GOD/PVI-[Os(bpy)₂Cl] /CNTF ensemble films shows the catalytic current for glucose oxidation increased in response to the thickness of CNTF films, indicating that also GOD can entirely penetrate inside the PVI-[Os(bpy)₂Cl]-modified CNTF films. Importantly, the apparent electron turnover rate was ca. 650 s⁻¹, being comparable with that of GOD in bulk solution containing an electron acceptor of O₂ (700 s⁻¹). These results indicate that most of ca. 3 × 10¹² GOD units within the film could efficiently work to the full, presumably owing to the controlled alignment of enzyme/mediator/electrode in the ensemble. Such a high efficiency of the present GOD electrode resulted in a resistance to oxygen inhibition, even under the lower glucose concentration (~ 1 mM).

Owing to the ordered positional relationship between GOD, PVI-[Os(bpy)₂Cl], and CNT, the composite film showed both high activity for glucose oxidation (ca. 15 mA cm⁻²) and high electron-transfer turnover rate (ca. 650 s⁻¹), indicating almost every enzyme molecules within the film could work to the fullest extent.

Chapter 4. Fabrication of sheet-shaped biofuel cell

Enzyme-based biofuel cells have made rapid improvements in their power performance up to mW cm⁻² levels by employing nanostructured carbon electrodes. However, the brittle carbon electrodes, which are generally aggregates of particulate or tubular nanocarbons, often limit the design and uses of such biofuel cells. In this chapter, a totally flexible, sheet-shaped biofuel cell was prepared by using a carbon fabric (CF) as the flexible, conductive base for the enzyme electrodes. The sheet-shaped biofuel cell was composed of bioanode CF strips modified with fructose dehydrogenase (FDH) for fructose oxidation, hydrogel sheets containing

electrolyte and fuel (fructose), and biocathode CF strips modified with bilirubin oxidase (BOD) for O₂ reduction in the ambient air. Additionally, a CF strip was modified with Carbon nanotubes (CNT) to achieve high specific surface area that are contributed to effective enzyme immobilization.

The oxidation current density of a CF strip modified with CNT and FDH depended on the concentration of the Triton X-100 surfactant used for the CNT dispersion. The CNT dispersion with 0.5% surfactant was capable of entirely penetrating into the CF strip. This uniform modification with CNT would be a reason for the enhanced anode performance. In addition, increasing the buffer concentration in the measurement solutions from 50 mM to 0.5 M drastically enhanced the electrode performance. This is made possible by the existence of adequate buffer capacities that prevent local pH changes caused by oxidation products. The maximum current of the optimized bioanode produced ~28 mA cm⁻² in stirred 500 mM fructose solution.

The reduction current density of a CF strip modified with CNT and BOD reached ~4.6 mA cm⁻², by utilizing an oxygen supply from the ambient air through the CF, and by optimizing the buffer concentration. The FDH-modified CF strip and the BOD-modified CF strip were stacked with a double network gel film that retained an electrolyte solution and fuel (fructose) to construct a totally flexible sheet-shaped biofuel cell. This assembly allowed bending without affecting the maximum output power density, 969 μW cm⁻² obtained at 0.36 V.

Chapter 5. Fabrication of needle-type biofuel cell

An enzyme-based biofuel cell has attracted much attention as portable and medical power supply. Among various advantages of such biofuel cell, high reaction selectivity of enzyme catalyst is quite unique because it enables to direct generation of electrical power from living organisms (e.g. animal, natural foods and raw fruits). However, natural organisms are covered by membrane. In addition, the cell operation in such organisms is subject to some limitation: e.g., low activity of the enzyme catalysts due to reaction inhibitors and limited mass flow of the biofluids.

This chapter describes the enzymatic biofuel cells designed for direct power generation from biofluids in living organisms such as animals, natural foods and raw fruits. Generally, natural organisms have a skin, and the oxygen concentration in the organisms is lower than that of biofuels like sugars. Therefore, I fabricated a new miniature assembly that consists of a needle bioanode for accessing biofuels in organisms through their skins, a gas-diffusion biocathode for utilizing the abundant oxygen in air, and an agarose hydrogel providing ion conductivity between the anode/cathode. The performance of the biocathode was fourfold improved by optimizing its hydrophobicity. The assembled device with four needle anodes for fructose oxidation was inserted into a raw grape, producing a maximum power of 26.5 μW (115 μWcm⁻²) at 0.34 V. A light-emitting diode (LED) with the cell served as a self-powered indicator of the sugar level in the grape. Power generation from blood sugar was also investigated by inserting a needle anode for glucose oxidation into a blood vessel in a rabbit ear. Prior coating of to an anti-biofouling agent the tip of the needle anode was effective to stabilize the output power.

Chapter 6. Summary

This chapter summarized the results obtained in each chapter and mentioned the prospects of this research. The typical nano-carbon materials are generally hard to form an uniform composite with enzymes due to their own aggregation. Additionally, brittleness of carbon electrodes often limits the design and use of biofuel cells. In this thesis, a flexible and high performance biofuel cell, which is constructed by carbon nanotube ensembles that have suitable spaces for enzyme immobilization, is developed. The sheet-type and needle-type biofuel cells, were also developed with carbon nanotubes and hydrogels, which would be suitable for generating electricity by placing the cell on surface or inside of living organisms.

論文審査結果の要旨

生体酵素を電極触媒に用いるバイオ燃料電池は、安全で無害な小型電源であり、医療・環境分野での応用に向けて酵素電極の改良が進められている。本論文は、カーボンナノチューブを利用する高出力で柔軟な酵素電極の開発、およびシート型や刺入型のバイオ燃料電池の作製に取り組んだ成果をまとめたものであり、全編6章からなる。

第1章は序論であり、本研究の背景、目的および構成を述べている。

第2章では、カーボンナノチューブ(CNT)のフィルム状構造体であるカーボンナノチューブフォレスト(CNTF)を用いて酵素電極の開発が行われている。CNTF内部のナノ空間が酵素のサイズに合わせて自発的に調節される現象が見出され、これによって酵素電極の活性が著しく向上することが示されている。また、CNTFの自立性を利用して、柔軟で貼付可能な酵素電極の作製も行われている。これらは、電極の構造を酵素に合わせて調節した高活性で柔軟な酵素電極の創出であり、重要な成果である。

第3章では、CNTFを用いる酵素電極の作製を、電子メディエータが必要な酵素系に拡張した結果が述べられている。電子メディエータの分子構造を最適化してCNTF内部に均一に導入すると、CNT/電子メディエータ/酵素の適度な相互作用によって構造が安定化し、さらに酵素の利用効率がほぼ100%まで向上することが示されている。これらはバイオ燃料電池の実用化につながる重要な成果である。

第4章では、炭素繊維のファブリックにCNTと酵素を修飾することによって、柔軟で大面積な酵素電極の作製が行われている。この酵素電極を、燃料である糖を含んだハイドロゲルシートと貼り合わせることによって、屈曲状態でも出力が低下しないシート型バイオ燃料電池が作製できている。これは、柔軟性や安全性が求められるウェアラブルデバイスなどへのバイオ燃料電池の応用につながる有益な成果である。

第5章では、生体や食物に挿入する刺入型のバイオ燃料電池の作製が行われている。アノード極とカソード極を一体化するために必要な電池作製技術の開発、および大気中の酸素をカソード極で反応させるための新しい電池構造の提案などが行われている。作製したバイオ燃料電池を用いて、ブドウの実およびウサギの血管に刺入した状態で発電できることが実証されている。また、LEDデバイスと組み合わせることで、発電と計測を同時に行うセンサの開発も行われている。これらは、生体の健康状態や、植物の生育状態をモニタリングする電源不要のセンサなどへの展開が期待できる重要な成果である。

第6章は結論である。

以上要するに本論文は、カーボンナノチューブを駆使する様々な酵素電極の作製方法を創出し、出力性能の大幅な向上を達成したものである。シート型や刺入型のバイオ燃料電池の作製も行っており、バイオロボティクス及びバイオマイクロマシン工学の発展に寄与するところが少なくない。

よって、本論文は博士(工学)の学位論文として合格と認める。