

SYNGAS PRODUCTION VIA CO₂ REFORMING OF CH₄ OVER Zr-Ni/SBA-15

N. Abdullah,¹ H. Ellapan,¹ H. A. Razak,¹ H. D. Setiabudi,^{1,2} N. Ainirazali^{1*}

¹ Faculty of Chemical & Natural Resources Engineering,

² Centre of Excellence for Advanced Research in Fluid Flow (CARIFF), Universiti Malaysia Pahang,
26300 Gambang, Kuantan, Pahang, Malaysia..

*Corresponding author: ainirazali@ump.edu.my

Abstract:

In the present study, the effect of Zirconium (Zr) loading (1-7wt %) as promoter on the properties of Ni/SBA-15 catalyst for production of syngas by CO₂ reforming of CH₄ were studied. Zirconium promoted Ni/SBA-15 catalyst was prepared using one pot sol-gel method as described in the literature [1]. The physiochemical properties of Zr-Ni/SBA-15 catalysts were characterized using XRD, BET and FTIR meanwhile the catalytic performances of the catalyst was carried out in a stainless steel fixed bed reactor at 800°C, atmospheric pressure and CO₂/CH₄ feed ratio of 1/1. The ordered mesoporous structure of SBA-15 was proven by N₂ adsorption desorption isotherms. The surface area and pore volume of catalyst were decreased with the increase of Zr loading as ZrO₂ particles were occupied in SBA-15 frameworks and thus destroyed SBA-15 structured [2]. ZrO₂ peak of 1Zr-Ni/SBA-15 was not detected in XRD result (Fig. 1) indicates to well dispersion of the Zr species on the SBA-15 surfaces [3]. The catalytic activity test revealed that the optimum Zr loading was at 1 wt% with CH₄ conversion, CO₂ conversion and H₂/CO ratio were 87.07%, 74.01%, and 0.42, respectively as illustrated in Fig. 2. This was due to the well dispersion of Zr that promote the Nickel (Ni) species to confine in the SBA-15 pores as proven by XRD and FTIR analysis. All catalysts showed a good stability up 900oC with less than 5 % weight loss as analyzed by TGA. The addition of 1wt % of Zr enhance the Ni dispersion which create a proper active site for CH₄ and CO₂ accessibility and also reduce carbon formation.

Keywords: Dry reforming; Zr promoter; Sol gel; Syngas

ACKNOWLEDGMENT

This study was supported by UMP Research Grant Scheme (RDU170330 & RDU1803184) and Postgraduate Research Grant (PGRS180302).