

Title	Perpendicular orientation between dispersed rubber and polypropylene molecules in an oriented sheet
Author(s)	Phulkerd, Panitha; Funahashi, Yoshiaki; Ito, Asae; Iwasaki, Shohei; Yamaguchi, Masayuki
Citation	Polymer Journal, 50: 309-318
Issue Date	2018-01-23
Type	Journal Article
Text version	author
URL	<a href="http://hdl.handle.net/10119/16124">http://hdl.handle.net/10119/16124</a>
Rights	This is the author-created version of Springer, Panitha Phulkerd, Yoshiaki Funahashi, Asae Ito, Shohei Iwasaki, Masayuki Yamaguchi, Polymer Journal, 50, 2018, 309-318. The original publication is available at <a href="http://www.springerlink.com">www.springerlink.com</a> , <a href="http://dx.doi.org/10.1038/s41428-017-0017-3">http://dx.doi.org/10.1038/s41428-017-0017-3</a>
Description	

1 Perpendicular Orientation of Dispersed Rubber in an  
2 Oriented Polypropylene Sheet  
3  
4  
5

6 Panitha Phulkerd<sup>1\*</sup>, Yoshiaki Funahashi<sup>1</sup>, Shohei Iwasaki<sup>2</sup>, and  
7 Masayuki Yamaguchi<sup>1</sup>  
8  
9

10 <sup>1</sup>School of Materials Science,  
11 Japan Advanced Institute of Science and Technology  
12 1-1 Asahidai, Nomi, Ishikawa 923-1292, JAPAN

13 <sup>2</sup> New Japan Chemical Co., Ltd.,  
14 13 Yoshijima, Yaguracho, Fushimi, Kyoto 612-8224, JAPAN  
15  
16  
17

18 \_\_\_\_\_  
19 \* Corresponding author:

20 Panitha Phulkerd

21 School of Materials Science, Japan Advanced Institute of Science and Technology,

22 1-1 Asahidai, Nomi, Ishikawa 923-1292, Japan

23 Phone: +81-761-51-1623; Fax: +81-761-51-1149;

24 E-mail: panitha@jaist.ac.jp  
25

## 26 Abstract

27 An immiscible blend of isotactic polypropylene (PP) and ethylene-butene-1  
28 copolymer (EB) (PP/EB = 70/30) containing a small amount of *N,N'*-dicyclohexyl-2,6-  
29 naphthalenedicarboxamide as a nucleating agent for  $\beta$ -form crystals was prepared by T-  
30 die extrusion. We successfully prepared an extruded sheet, in which the orientation of the  
31 PP molecules is perpendicular to the deformation of the EB particles; i.e., the  $\beta$ -form  
32 crystals of PP are predominantly oriented perpendicular to the flow direction of the sheet  
33 plane (the transverse direction, TD), whereas the EB droplets are strongly deformed in  
34 the flow direction. It should be noted that the EB barely affects the crystalline form and  
35 orientation of PP. This extraordinary structure provides unique mechanical anisotropy.  
36 The tear strength in the TD sample is significantly enhanced with the anomalous crack  
37 propagation in the machine direction (MD). Moreover, the anisotropy in tensile properties  
38 such as Young's modulus, yield stress, strain at break, and dynamic tensile modulus  
39 becomes reduced.

40

41 Keywords: polypropylene; ethylene-butene-1 copolymer; T-die extrusion; mechanical  
42 anisotropy

43

44

45

46

47

48

49

50

## Introduction

51

52 Isotactic polypropylene (PP) is widely used in various applications because it is  
53 inexpensive and lightweight. In particular, the trend in the automobile industry to use  
54 PP will continue because weight reduction is an inevitable future priority. Generally  
55 speaking, both rigidity and high impact strength are required for a material design of PP  
56 [1]. Therefore, the technology of the blend with rubber [1-17] and fillers [18,19] and the  
57 addition of a nucleating agent [20-25] has been intensively studied. Various types of  
58 elastomeric materials have been employed as impact modifiers. In particular, after the  
59 development of metallocene catalyst, ethylene-butene-1, ethylene-hexene-1, and  
60 ethylene-octene-1 copolymers have been preferred for this purpose, because they have  
61 low interfacial tension with PP compared with traditional ethylene-propylene copolymers.  
62 Such miscibility and/or compatibility have been predicted by the difference in statistical  
63 segment length [1,12,17] and packing length [8,14,17], and have been summarized from  
64 the perspective of the species and content of the  $\alpha$ -olefin [2,3,7,15]. The rheological  
65 properties [4,5,9], crystallization behavior [6,16], and processability [10,11] of PP blends  
66 with ethylene- $\alpha$ -olefin copolymers have also been elucidated. Accordingly, controlling  
67 the particle size of a rubber dispersion in a PP continuous phase improves the mechanical  
68 properties of the material. In general, low interfacial tension, and viscosity matching  
69 between components enable the formation of small particles with uniform dispersion by  
70 melt blending. Furthermore, the nucleation process of PP plays a key role in the  
71 processing operation because its mechanical properties are largely dependent on the form  
72 and degree of crystallinity. As well known, PP has various crystalline forms such as  
73 monoclinic  $\alpha$  modification, trigonal  $\beta$  modification, orthorhombic  $\gamma$  modification, and

74 smectic form, which are determined by crystallization conditions and additives  
75 [2,3,7,8,12,14,17]. Of all the crystalline structures, recent attention has focused on  $\beta$ -form  
76 crystals owing to the development of highly efficient nucleating agents such as 1,3,5-  
77 benzenetrisamide [26] and *N,N'*-dicyclohexyl-2,6-naphthalenedicarboxamide [27,28].  
78 These nucleating agents enhance the modulus, which was considered one of the  
79 unfavorable properties of  $\beta$ -form crystals. Moreover, a recent report on the enhancement  
80 of the melting point using  $\beta$ -form crystals [29] should encourage the industrial  
81 applications.

82 *N,N'*-dicyclohexyl-2,6-naphthalenedicarboxamide has been used to ensure the  
83 molecular orientation of the PP chains in the transverse direction (TD) [30-35]. Under  
84 suitable processing conditions, the nucleating agent appears as needle-shaped crystals in  
85 PP, and is aligned with the direction of flow by hydrodynamic force. Owing to the unique  
86 crystallization behavior of PP, in which the *c*-axis of the PP crystals grows perpendicular  
87 to the long axis of the needle-shaped nucleating agent by epitaxial crystallization, the PP  
88 chains orient perpendicular to the flow direction during T-die extrusion [31]. The resulting  
89 product has unique mechanical properties. Orientation control using nucleating agents is  
90 applicable to injection-molding. The peculiar orientation of the PP chains, i.e., in a  
91 plywood-like structure, prohibits crack propagation and reduces anisotropy in modulus  
92 and in thermal expansion [32,35]. A combined approach involving the addition of rubber  
93 and the control of orientation using a specific  $\beta$  nucleating agent is expected to maximize  
94 the mechanical performance of PP. Although several papers have been published  
95 regarding polymer blends of PP and ethylene- $\alpha$ -olefin copolymers, there have been few  
96 reports describing in detail of PP blends containing a  $\beta$  nucleating agent [36-39].

97 Furthermore, in industrial applications the molecular orientation of the PP and the rubber  
98 dispersion are controlled independently.

99 The present research focuses on an extruded sheet comprising PP and ethylene-  
100 butene-1 copolymer (EB) with the nucleating agent, *N,N'*-dicyclohexyl-2,6-naphthalene-  
101 dicarboxamide. The orientation of the PP molecular chains and the deformation direction  
102 of the rubber particles are investigated in detail with an evaluation of the mechanical  
103 properties.

104

## 105 **Materials and Methods**

106

### 107 **Materials**

108 The raw materials used in the present study were: a commercially available  
109 isotactic polypropylene homopolymer (PP) (SunAllomer, PM600A, melt flow rate (MFR)  
110 7.5 [g/10 min at 230°C], Mn 63,000, Mw 360,000), and an ethylene-butene-1 copolymer  
111 (EB) (Mitsui Chemicals, TAFER DF610, MFR 2.2 [g/10 min at 230°C], density 860  
112 kg/m<sup>3</sup>, ethylene content 54 wt.%). *N,N'*-dicyclohexyl-2,6-naphthalenedicarboxamide  
113 (New Japan Chemical, NJ Star NU-100) was used as a  $\beta$  nucleating agent without further  
114 purification.

115

### 116 **Sample preparation**

117 Melt-mixing of PP with 0.1 wt.% of the  $\beta$  nucleating agent was performed by a  
118 counter-rotating twin-screw extruder (Technovel, KZW15TW-45MG-NH) with 0.05  
119 wt.% of 3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate (Ciba, Irganox 1010) and 0.1  
120 wt.% of tris(2,4-di-tert-butyl-phenyl)phosphate (Ciba, Irgafos 168) as thermal stabilizers,

121 and 0.05 wt.% of calcium stearate (Nitto Kasei Kogyo) as a neutralizing agent. The screw  
122 diameter of the extruder was 15 mm and the length-to-diameter ratio was 45. The machine  
123 was operated at a screw rotation speed of 250 rpm. The mixing was performed at 260°C  
124 to completely dissolve the nucleating agent in molten PP. The extruded strands were  
125 dipped in a water-bath and cut into pellets approximately 2.3 mm in diameter.

126 The pellets of PP containing the nucleating agent and EB were fed into a single-  
127 screw extruder (Technovel, SZW25GT-28VG-STD) equipped with a T-die (300 mm wide  
128 with a 0.5 mm die lip) at a blend ratio of 70/30 (PP/EB) by weight. The out-put rate was  
129 3 kg/h. The screw diameter and the length-to-diameter ratio were 25 mm and 28,  
130 respectively. The speed of screw rotation was 40 rpm. The sheet was stretched in the air  
131 gap (10 mm) between the die lip and the chill roll. The temperatures of the die and chill  
132 roll were maintained at 200°C and 103°C, respectively. The diameter of the chill roll was  
133 250 mm and the rotational speed was 1 rpm. Reference samples comprising extruded  
134 sheets of PP containing the nucleating agent and PP/EB without the nucleating agent were  
135 also prepared under conditions identical to those described above.

136

### 137 Measurements

138 Thermal analysis was conducted using a differential scanning calorimeter (DSC)  
139 (Perkin Elmer, DSC 8000) under a nitrogen atmosphere to avoid thermal-oxidative  
140 degradation. Samples weighing approximately 3 mg were sealed in aluminum pans. The  
141 melting and crystallization profiles were recorded at a heating rate of 10°C min<sup>-1</sup> and a  
142 cooling rate of 10°C min<sup>-1</sup>.

143 The temperature dependence of the dynamic tensile moduli of the extruded  
144 sheets was measured between -80°C and 175°C using a dynamic mechanical analyzer

145 (UBM, Rheologel-E4000-DVE). The frequency was 10 Hz and the heating rate was 2°C  
146 min<sup>-1</sup>. The extruded sheet was cut into small rectangular pieces, 5 mm wide and 20 mm  
147 long, that were mounted between gauges with a distance of 10 mm. The measurements  
148 were carried out on two types of sample to investigate the mechanical anisotropy: one  
149 was cut parallel to the flow direction (the machine direction (MD) sample), and the other  
150 was perpendicular to the flow direction (the transverse direction (TD) sample). In the case  
151 of the MD sample, the direction of the applied oscillatory strain coincided with the flow  
152 direction.

153 To analyze the orientation and crystalline form of the PP molecules, wide-angle  
154 X-ray diffraction (WAXD) patterns were collected using a high-speed two-dimensional  
155 X-ray detector (Rigaku, PILATUS 3R 100K). The measurements were carried out using  
156 CuK $\alpha$  radiation operated at 40 kV and 30 mA with a scanning range of 2 $\theta$  (the Bragg  
157 angle) from 10° to 30°. Small pieces of the sample (approximately 1.0 mm thick) were  
158 mounted on the diffractometer. The X-ray beam was irradiated normal to the MD-ND  
159 plane (edge view: EV) and the MD-TD plane (through view: TV). For the EV  
160 measurements, ten sheets of the sample were laminated with polystyrene solution,  
161 whereas only one sheet was used for the TV measurements.

162 The orientation of the PP lamellae was investigated using a transmission electron  
163 microscopy (TEM) (JEOL, JEM-2100FX) at an acceleration voltage of 200 kV. The  
164 samples were embedded in epoxy resin and sectioned using an ultramicrotome (RMC-  
165 Boeckeler, Ultramicrotome MT-XL) equipped with a diamond knife after exposure to the  
166 vapor of ruthenium tetroxide at 40°C for a day. Cross-sectional specimens (100 nm  
167 thick) were cut from the stained sample in the MD-ND plane.



168           The deformation of the EB dispersed phase was observed by means of a scanning  
169 electron microscopy (SEM) (Hitachi, S4100) with an acceleration voltage of 20 kV. For  
170 non-conductive samples, the specimens were coated with Pt/Pd alloy for 60 seconds by  
171 an ion sputtering machine (Hitachi, E1010). The surface of specimen was removed using  
172 a rotary microtome (Yamato Kohki Industrial, RX-860) and immersed in xylene at room  
173 temperature for 3 days to elute the rubber particles.

174           Stress-strain curves were investigated at room temperature using a tensile  
175 machine (Tokyo Testing Machine, LSC-05/300) following ASTM D638. The specimens  
176 were cut into dumbbell-shaped pieces (10 mm wide and 40 mm long) using dumbbell  
177 cutter No.3 referenced from JIS K6251, in which the sample size was reduced by 40%.  
178 The initial distance between the gauges was 30 mm, and one of the crossheads was moved  
179 up at a constant speed of 10 mm min<sup>-1</sup>. Stretching was performed in two directions: one  
180 was parallel to the flow direction (the machine direction (MD) sample) and the other was  
181 perpendicular to the flow direction (the transverse direction (TD) sample). All  
182 measurements were performed at least five times, and the average values were calculated.  
183 The elongation at break was evaluated by measuring the final gauge length of the narrow  
184 part of the dumbbell.

185           The tear test was investigated by the Trouser method using a tensile machine  
186 (Tokyo Testing Machine, LSC-05/300). Two types of sample were cut from the extruded  
187 sheet; one had a notch parallel to the flow direction, that is, the machine direction (MD),  
188 and the other had a vertical notch, that is, the transverse direction (TD). The specimens  
189 were stretched at room temperature at a speed of 200 mm min<sup>-1</sup>. The distance between  
190 the gauges was 20 mm.

191

## Results and Discussion

192

193

194 Characterization of blend sheets

195

196

197

198

199

200

201

202

203

204

205

206

The melting and crystallization behaviors of the extruded sheets are shown in Fig. 1. As shown in Fig. 1a, the pure PP sheet exhibits a main melting peak at 165°C, suggesting  $\alpha$ -form crystals with a small shoulder peak of  $\beta$ -form crystals at 150°C. A similar melting profile is observed in the PP/EB sheet. For the sheet containing the nucleating agent, two distinct peaks are detected at 145°C and 151°C, which can be attributed to  $\beta$ -form crystals. Furthermore, a sharp peak due to the  $\alpha$ -form crystals appears at a slightly higher temperature than that for pure PP. The recrystallization after melting of thick  $\beta$ -form crystals is responsible for thick lamellae of  $\alpha$ -form crystals leading to the enhanced melting point as explained by Phulkerd et al. [29]. The same phenomenon is observed for the PP/EB sheet containing the nucleating agent. Under suitable cooling conditions, an annealed sheet of PP containing the nucleating agent has a melting point due to  $\alpha$ -form crystals nearly at 170°C [29].

207

208

209

210

211

212

213

214

215

The crystallization behavior during the cooling process from 200°C is shown in Fig. 1b. There is no significant difference in the exothermic crystallization temperature (ca. 117°C) between the pure PP and PP/EB sheets. After the addition of the nucleating agent, the crystallization peak shifts to a higher temperature at 128°C in both the PP and PP/EB sheets. In this experiment, the crystallization temperature of PP is barely affected by EB irrespective of the addition of the nucleating agent, which also indicates that EB particles hardly affect the nucleating ability of the nucleating agent.

[Fig. 1]

216 Fig. 2 shows the X-ray diffraction curves in the equatorial direction of the MD-  
217 TD plane, which are transformed and corrected using Lorentz and polarization (Lp)  
218 factors. Both  $\alpha$ - and  $\beta$ -form crystals are detected but the  $\beta$ -form crystals are predominant  
219 in the sheets containing the nucleating agent. In the sheets without the nucleating agent,  
220 the strong peak ascribed to the  $\alpha$ -form crystals are detected, although  $\beta(110)$  and  $\beta(111)$   
221 peaks are still confirmed. Relatively high cooling temperature (the chill roll was  
222 maintained at 103°C) induces the  $\beta$ -form crystallization to some extent. The XRD  
223 patterns also suggest that the addition of EB to PP has a negligible effect on crystal  
224 formation. Furthermore, there is an indication that the crystallinity of EB is significantly  
225 low in the extruded sheets, because both (110) and (200) planes, which are attributable to  
226 polyethylene crystals, are absent.

227

[Fig. 2]

229

230 Fig. 3 shows the 2D-WAXD patterns of the extruded sheets, obtained by  
231 directing the X-ray beam in the normal direction for the edge view and in the transverse  
232 direction for the through view. The  $\alpha$ -form crystals in the pure PP show weak orientation,  
233 as seen in Fig. 3a. The diffraction patterns of the PP/EB sheet (Fig. 3b) are almost  
234 identical to those of the PP sheet, in which a diffraction peak attributed to the (040) plane  
235 of the  $\alpha$ -form crystals is detected in the equatorial direction, demonstrating that the PP  
236 molecular chains are oriented in the MD direction. For the PP sheet containing the  
237 nucleating agent (Fig. 3c), the PP chains in the  $\beta$ -form crystals were oriented in the TD  
238 direction. Such molecular orientation is also detected in the PP/EB sheet containing the  
239 nucleating agent, in which distinct arcs ascribed to (110) reflection of the  $\beta$ -form crystals

240 are observed as shown in Fig. 3d. This result demonstrates that PP chains preferentially  
241 orient perpendicular to the flow direction. It also indicates that the nucleating agent  
242 promotes the growth of  $\beta$ -form crystals with the TD orientation of the PP molecular chains,  
243 irrespective of the presence of EB.

244

245 [Fig. 3]

246

247 Fig. 4 shows a TEM image of a thin slice of the TD-ND plane cut from the PP/EB  
248 sheet containing the nucleating agent. Phase-separated morphology is clearly seen in this  
249 sample, in which the dark region is the EB phase. Furthermore, the crystalline lamellae  
250 of PP are detected in the matrix as white lines, which preferentially orient along the ND.  
251 Therefore, the growth direction of the PP chains is perpendicular to the ND, i.e., the TD  
252 orientation, which corresponds well with the XRD patterns. The compressed stress  
253 applied during the chill roll process is responsible for the preferential TD orientation of  
254 PP chains, not the ND orientation. The slight deformation of EB particles to the TD would  
255 be also attributed to the compression stress at the chill roll, although the deformation of  
256 EB particles will be explained in detail later. Furthermore, PP lamellae are incorporated  
257 into EB phase, which will provide the strong adhesion between them. This phenomenon  
258 is attributed to the low interfacial tension between PP and EB, leading to large interphase  
259 thickness in the molten state.

260

261 [Fig. 4]

262

263 Fig. 5 shows SEM images for the PP/EB sheet containing the nucleating agent.

264 The dark regions are attributable to the elongated pores formed by elution of the EB  
265 particles with xylene. As seen in Fig. 5a, the numerous pores are mainly deformed in the  
266 flow direction. The length of the pores is found to be approximately 3.0  $\mu\text{m}$  and the  
267 diameter is about 0.5  $\mu\text{m}$ . On the other hand, a slight deformation in the TD direction with  
268 an averaged pore size of 1.0  $\mu\text{m}$  for the length and 0.5  $\mu\text{m}$  for the diameter is detected in  
269 the TD-ND plane, owing to the pressure applied by the chill roll, which corresponds with  
270 the TEM image. The marked difference in the pore size between the MD and TD  
271 directions demonstrates that EB preferentially orients in the flow direction. This is  
272 understandable because the elongational stress in the air gap as well as the shear stress in  
273 the die deform the EB particles in the flow direction by the hydrodynamic force. Similar  
274 SEM images were obtained for the PP/EB sheet without the nucleating agent (but they  
275 are not presented here). This suggests that the nucleating agent hardly affects the rubber  
276 dispersion and deformation.

277

278 [Fig. 5]

279

280 Mechanical properties

281 Because the molecular orientation of PP is different from that of EB, the sample  
282 sheet exhibits anomalous mechanical properties. Fig. 6 shows the dynamic mechanical  
283 properties of extruded sheets employing two specimens to apply the oscillatory strain in  
284 the different directions, i.e., the machine direction (MD) and transverse direction (TD).  
285 As seen in Fig. 6a, both the MD and TD samples for the pure PP sheet show almost the  
286 same dynamic tensile moduli over the whole range of temperature. A similar behavior is  
287 also detected in the PP/EB sheet, in which PP molecules orient to the flow direction. Since

288 the molecular orientation is weak, no obvious mechanical anisotropy is observed for the  
289 sample sheets without the nucleating agent. Moreover,  $E'$  in PP/EB falls off markedly  
290 around 165°C which is attributed to melting of  $\alpha$ -form crystals. For the PP sheet  
291 containing the nucleating agent, in contrast,  $E'$  in TD is higher than that in MD at low  
292 temperatures and vice versa at high temperatures. Based on the mechanical model  
293 proposed by Takayanagi et al. [40], the anisotropy of the tie chain fractions, which are  
294 deformed in the flow direction by hydrodynamic force during extrusion, is responsible  
295 for the crossing behavior in the sample containing the nucleating agent [33]. A similar  
296 mechanical behavior is detected for the PP/EB sheet containing the nucleating agent,  
297 albeit the crossing behavior is weaker and shifted to the lower temperature region. As  
298 compared with the PP/EB sheet, the addition of the nucleating agent enhances  $E'$  for the  
299 MD sample over a wide temperature range above the glass transition ( $T_g$ ), owing to a high  
300 degree of crystallinity resulting from the nucleating effect. Furthermore, a sharp drop of  
301  $E'$  is detected around 150°C due to the melting of the  $\beta$ -form crystals, which corresponds  
302 to the DSC and WAXD results. It is found from Fig. 6b that both the PP/EB sheets with  
303 or without the nucleating agent exhibit double peaks in the  $E''$  curve in the temperature  
304 range from -75°C to 40°C; the peak at the higher temperature is attributed to  $T_g$  of PP and  
305 the other at the lower one is to that of EB.

306

307 [Fig. 6]

308

309 The stress-strain curves at the strain rate of 0.006 s<sup>-1</sup> are shown in Fig. 7. The  
310 tensile force is applied along the MD or the TD. The difference in the tensile behavior  
311 between stretching in the MD and TD is detected in all samples. As seen in Fig. 7a, the

312 pure PP sheet experiences a brittle fracture in the TD stretching beyond the yield point.  
313 In the case of MD stretching, however, ductile deformation occurs under a low yield  
314 stress. The PP containing the nucleating agent (Fig. 7b) shows high Young's modulus,  
315 which corresponds to the tensile storage modulus. Moreover, yield stress in the MD  
316 stretching is greatly enhanced with a ductile manner. The low modulus of EB is  
317 responsible for marked decrease in Young's modulus and yield stress for both the PP/EB  
318 and PP/EB containing the nucleating agent as seen in Figs. 7c and 7d. In the PP/EB sheet  
319 containing the nucleating agent, the anisotropy in Young's modulus and yield stress is  
320 considerably weaker than that in the PP sheet containing the nucleating agent. The strain  
321 at break in the TD stretching for PP containing the nucleating agent is considerably larger  
322 than that for pure PP. The ductile behavior is also observed in MD stretching, although  
323 the yield stress is high. As a result, the anisotropy of strain at break becomes reduced  
324 following the addition of the nucleating agent. The reduction of the mechanical anisotropy  
325 becomes more apparent for the blend containing EB, although it is interesting to note that  
326 the PP/EB exhibits ductile behavior not only in MD but also in TD stretching. Since the  
327 yield stress in TD stretching is lower than that in MD stretching, the deformation of EB  
328 particles into flow direction affects the stress-strain behavior greatly, although the  
329 deformation behavior of the EB phase is not revealed in this study. The details of  
330 mechanical anisotropy in terms of crack propagation are discussed below.

331

332

[Fig. 7]

333

334

335

Trouser tear test was carried out at room temperature employing two types of the sheet samples; one has a parallel notch in the flow direction (MD), and the other has a

336 vertical notch (TD). As seen in Fig. 8a, the pure PP sheet shows higher tear strength in  
337 the TD sample. For PP containing the nucleating agent (Fig. 8b), the order is opposite  
338 with an enhanced anisotropy in tear strength. In the case of the blend, the tear strength in  
339 the TD sample is markedly enhanced, irrespective of the nucleating agent. Furthermore,  
340 the direction of crack propagation changes to the MD immediately after the stretching as  
341 demonstrated in Figs. 8c and 8d. These results demonstrate that PP orientation has no  
342 marked impact on the tear property. The deformation of EB particles plays a dominant  
343 role on the tearing. Such information has never been reported before to the best of our  
344 knowledge, because the deformation direction of a dispersion is always the same as the  
345 molecular orientation direction of matrix in general. Regarding the effect of the nucleating  
346 agent, the tear strength of the MD sample is slightly enhanced, although the effect is not  
347 as obvious as in the pure PP.

348

349

[Fig. 8]

350

351

352

### Conclusions

353

354

355

356

357

358

359

An extruded sheet with unique structure was developed using a blend comprising PP, EB, and a small amount of *N,N'*-dicyclohexyl-2,6-naphthalenedicarboxamide. It was found that the nucleating agent promotes the formation of  $\beta$ -form crystals and causes the PP chains orient perpendicular to the flow direction in an extruded sheet, i.e., in the transverse direction, as confirmed by 2D-XRD and TEM characterization. On the contrary, EB is deformed in the flow direction, as revealed by SEM images. As a result, the chain



360 orientation of the PP molecules is perpendicular to the deformation direction of the EB  
361 droplets, which affects the mechanical anisotropy to a great extent. With regard to the  
362 tensile properties, the anisotropy in yield stress and strain at break is significantly  
363 decreased owing to this peculiar structure. It is proved by the tear test that the strength of  
364 the TD sample is increased with a crack growth in the flow direction. This result  
365 demonstrates that the deformation of the EB particles in the MD direction exhibits more  
366 pronounced effect than the molecular orientation of the PP chains in the TD direction.

367

368

### References

369

- 370 1. F.S. Bates, G.H. Fredrickson, Conformational asymmetry and polymer-polymer  
371 thermodynamics, *Macromolecules* 27 (1994) 1065-1067.
- 372 2. M. Yamaguchi, H. Miyata, K-H Nitta, Compatibility of binary blends of  
373 polypropylene with ethylene- $\alpha$ -olefin copolymer, *J. Appl. Polym. Sci.* 62 (1996) 87-  
374 97.
- 375 3. P.A. Weimann, T.D. Jones, M.A. Hillmyer, F.S. Bates, J.D. Londono, Y. Melnichenko,  
376 G.D. Wignall, K. Almdal, Phase behavior of isotactic polypropylene-  
377 poly(ethylene/ethylethylene) random copolymer blends, *Macromolecules* 30 (1997)  
378 3650-3657.
- 379 4. C.J. Carriere, H.C. Silvis, The effects of short-chain branching and comonomer type  
380 on the interfacial tension of polypropylene-polyolefin elastomer blends, *J. Appl.*  
381 *Polym. Sci.* 66 (1997) 1175-1181.

- 382 5. M. Yamaguchi, K-H Nitta, H. Miyata, T. Masuda, Rheological properties for binary  
383 blends of i-PP and ethylene-1-hexene copolymer, *J. Appl. Polym. Sci.* 63 (1997) 467-  
384 474.
- 385 6. M. Yamaguchi, H. Miyata, K-H Nitta, Structure and properties for binary blends of  
386 isotactic polypropylene with ethylene- $\alpha$ -olefin copolymer. 1. Crystallization and  
387 morphology, *J. Polym. Sci. B Polym. Phys.* 35 (1997) 953-961.
- 388 7. Y. Thomann, J. Suhm, R. Thomann, G. Bar, R.D. Maier, R. Mülhaupt, Investigation of  
389 morphologies of one- and two-phase blends of isotactic poly(propene) with random  
390 poly(ethene-co-1-butene), *Macromolecules* 31 (1998) 5441-5449.
- 391 8. D.J. Lohse, W.W. Graessley, Thermodynamics of polyolefin blends, in: D.R. Paul,  
392 C.B. Bucknall (Eds.), *Polymer Blends*, John Wiley & Sons Inc., New York, 1999, pp.  
393 219-237.
- 394 9. M. Yamaguchi, H. Miyata, Influence of stereoregularity of polypropylene on  
395 miscibility with ethylene-1-hexene copolymer, *Macromolecules* 32 (1999) 5911-5916.
- 396 10. M. Yamaguchi, K-I Suzuki, H. Miyata, Structure and mechanical properties for binary  
397 blends of polypropylene and ethylene-1-hexene copolymer, *J. Polym. Sci. B Polym.*  
398 *Phys.* 37 (1999) 701-713.
- 399 11. E.L. Bedia, S. Murakami, K. Senoo, S. Kohjiya, *Polymer* 43 (2002) 749-755.
- 400 12. T.D. Jones, K.A. Chaffin, F.S. Bates, Effect of tacticity on coil dimensions and  
401 thermodynamic properties of polypropylene, *Macromolecules* 35 (2002) 5061-5068.
- 402 13. N. Pasquini, *Polypropylene Handbook*, second ed., Hanser, Munich, 2005.
- 403 14. D.J. Lohse, The Influence of chemical structure on polyolefin melt rheology and  
404 miscibility, *J. Macromol. Sci. Polymer. Rev.* 45 (2005) 289-308.

- 405 15. M. Yamaguchi, Morphology and mechanical properties in iPP/polyolefin-based  
406 copolymer blends, in: D. Nwabunma, T. Kyu (Eds.), Polyolefin Blends, John Wiley &  
407 Sons Inc., New Jersey, 2008, pp. 224-268.
- 408 16. J. Yang, J.L. White, Crystallization behavior of polypropylene/ethylene butene  
409 copolymer blends, *J. Appl. Polym. Sci.* 126 (2012) 2049-2058.
- 410 17. J. Xu, V. Mittal, F.S. Bates, Toughened isotactic polypropylene: Phase behavior and  
411 mechanical properties of blends with strategically designed random copolymer  
412 modifiers, *Macromolecules* 49 (2016) 6497-6506.
- 413 18. Y. Lin, H. Chen, C-M Chan, J. Wu, High impact toughness polypropylene/CaCO<sub>3</sub>  
414 nanocomposites and the toughening mechanism, *Macromolecules* 41 (2008) 9204-  
415 9213.
- 416 19. R. Wiwattananukul, B. Fan, M. Yamaguchi, Improvement of rigidity for rubber-  
417 toughened polypropylene via localization of carbon nanotubes, *Comp. Sci. Technol.*  
418 141 (2017) 106-112.
- 419 20. Y. Feng, X. Jin, J.N. Hay, Effect of nucleating agent addition on crystallization of  
420 isotactic polypropylene, *J. Appl. Polym. Sci.* 69 (1998) 2089-2095.
- 421 21. J. Varga, I. Mudra, G.W. Ehrenstein, Highly active thermally stable  $\beta$ -nucleating  
422 agents for isotactic polypropylene, *J. Appl. Polym. Sci.* 74 (1999) 2357-2368.
- 423 22. G-S Jang, W-J Cho, C-S Ha, Crystallization behavior of polypropylene with or without  
424 sodium benzoate as a nucleating agent, *J. Polym. Sci. B Polym. Phys.* 39 (2001) 1001-  
425 1016.
- 426 23. C. Marco, M.A. Gomez, G. Ellis, J.M. Arribas, Activity of a  $\beta$ -nucleating agent for  
427 isotactic polypropylene and its influence on polymorphic transitions, *J. Appl. Polym.*  
428 *Sci.* 86 (2002) 531-539.

- 429 24. P-W Zhu, J. Tung, A. Phillips, G. Edward, Morphological development of oriented  
430 isotactic polypropylene in the presence of a nucleating agent, *Macromolecules* 39  
431 (2006) 1821-1831.
- 432 25. M. Liu, B. Guo, M. Du, F. Chen, D. Jia, Halloysite nanotubes as a novel  $\beta$ -nucleating  
433 agent for isotactic polypropylene, *Polymer* 50 (2009) 3022-3030.
- 434 26. M. Kerscha, H.W. Schmidt, V. Altstädt, Influence of different beta-nucleating agents  
435 on the morphology of isotactic polypropylene and their toughening effectiveness,  
436 *Polymer* 98 (2016) 320-326.
- 437 27. A. Romankiewicz, T. Sterzynski, W. Brostow, Structural characterization of  $\alpha$ - and  $\beta$ -  
438 nucleated isotactic polypropylene, *Polym. Int.* 53 (2004) 2086-2091.
- 439 28. Y.F. Zhang, X.X. Luo, L. Zhu, X.J. Yang, Y. Chang, Effects of  $\alpha/\beta$  compound nucleating  
440 agents on mechanical properties and crystallization behaviors of isotactic  
441 polypropylene, *J. Macromol. Sci. B.* 51 (2012) 2352-2360.
- 442 29. P. Phulkerd, S. Arayachukeat, T. Huang, T. Inoue, S. Nobukawa, M. Yamaguchi,  
443 Melting point elevation of isotactic polypropylene, *J. Macromol. Sci. B.* 53 (2014)  
444 1222-1230.
- 445 30. Y. Uchiyama, S. Iwasaki, C. Ueoka, T. Fukui, K. Okamoto, M. Yamaguchi, Molecular  
446 orientation and mechanical anisotropy of polypropylene sheet containing *N,N'*-  
447 dicyclohexyl-2,6-naphthalenedicarboxamide, *J. Polym. Sci. B Polym. Phys.* 47 (2009)  
448 424-433.
- 449 31. M. Yamaguchi, T. Fukui, K. Okamoto, S. Sasaki, Y. Uchiyama, C. Ueoka, Anomalous  
450 molecular orientation of isotactic polypropylene sheet containing *N,N'*-dicyclohexyl  
451 2,6-naphthalenedicarboxamide, *Polymer* 50 (2009) 1497-1504.
- 452 32. M. Yamaguchi, Y. Irie, P. Phulkerd, H. Hagihara, S. Hirayama, S. Sasaki, Plywood-like

- 453 structure of injection-moulded polypropylene, *Polymer* 51 (2010) 5983-5989.
- 454 33. P. Phulkerd, S. Nobukawa, Y. Uchiyama, M. Yamaguchi, Anomalous mechanical  
455 anisotropy of  $\beta$  form polypropylene sheet with *N,N'*-dicyclohexyl-2,6-naphthalene-  
456 dicarboxamide, *Polymer* 52 (2011) 4867-4872.
- 457 34. P. Phulkerd, H. Hagihara, S. Nobukawa, Y. Uchiyama, M. Yamaguchi, Plastic  
458 deformation behavior of polypropylene sheet with transversal orientation, *J. Polym.*  
459 *Sci. B Polym. Phys.* 51 (2013) 897-906.
- 460 35. P. Phulkerd, S. Hirayama, S. Nobukawa, T. Inoue, M. Yamaguchi, Structure and  
461 mechanical anisotropy of injection-molded polypropylene with a plywood structure,  
462 *Polym. J.* 46 (2014) 226-233.
- 463 36. J. Varga, I. Mudra, G. W. Ehrensten, Highly active thermally stable  $\beta$ -nucleating agents  
464 for isotactic polypropylene, *J. Appl. Polym. Sci.* 74 (1999) 2357-2368.
- 465 37. C. Grein, M. Gahleitner, On the influence of nucleation on the toughness of iPP/EPR  
466 blends with different rubber molecular architectures, *Express. Polym. Lett.* 2 (2008)  
467 392-397.
- 468 38. Y. Chen, S. Yang, H. Yang, M. Zhang, Q. Zhang, Z. Li, Toughness reinforcement in  
469 carbon nanotube-filled high impact polypropylene copolymer with  $\beta$ -nucleating  
470 agent, *Ind. Eng. Chem. Res.* 55 (2016) 8733-8742.
- 471 39. S. Sato, T. Maeda, M. Yamaguchi, Control of chain orientation in blends of  
472 polypropylene and polybutene-1, *Macromol. Mater. Eng.* 302 (2017) 1600413-  
473 1600421.
- 474 40. M. Takayanagi, K. Imada, T. Kajiyama, Mechanical properties and fine structure of  
475 drawn polymers, *J. Polym. Sci., Part C* 15 (1967) 263-281.
- 476




Fig.1 DSC profiles of extruded sheets; (a) heating curves and (b) cooling curves.




Fig. 2 Lp-corrected XRD curves obtained from the through view beam for extruded sheets.






Fig. 3 WAXD patterns of the edge views (MD-ND) and the through views (MD-TD) in the samples; (a) PP, (b) PP/EB, (c) PP containing the nucleating agent, and (d) PP/EB containing the nucleating agent.






Fig. 4 TEM image of the TD-ND plane ( $\times 15,000$ ) for PP/EB containing the nucleating agent.





Fig. 5 SEM images of PP/EB containing the nucleating agent. (a) MD-ND plane and (b) TD-ND plane.






Fig. 6 Temperature dependence of dynamic tensile modulus of extruded sheets at 10 Hz; (a) tensile storage modulus  $E'$  and (b) tensile loss modulus  $E''$ . The applied strain was (grey symbol) parallel to the flow direction (MD) and (black symbol) perpendicular to the flow direction (TD).




Fig. 7 Stress-strain curves of (a) PP, (b) PP containing the nucleating agent, (c) PP/EB, and (d) PP/EB containing the nucleating agent at a strain rate of  $0.006 \text{ s}^{-1}$ .




Fig. 8 Tear-propagation resistance (TPR) versus the applied displacement of notched specimens in MD and TD directions; (a) PP, (b) PP containing the nucleating agent, (c) PP/EB, and (d) PP/EB containing the nucleating agent.