

## EFFECT OF EQUAL CHANNEL ANGULAR PRESSING DIE ANGLE ON CORROSION BEHAVIOR OF BULK NANOSTRUCTURED METAL

*N. A. N. Mokhtar<sup>1,2</sup> D. N. Awang Shri<sup>1</sup> and M.M. Mahat<sup>3</sup>*

<sup>1</sup>Human Engineering Group, Faculty of Mechanical Engineering, University Malaysia Pahang, 26600 Pekan, Pahang, Malaysia

<sup>2</sup>Institute of Postgraduate Studies, University Malaysia Pahang, Lebuhraya Tun Razak, 26300 Gambang, Kuantan, Pahang, Malaysia

<sup>3</sup>School of Physics and Material Studies, Faculty of Applied Sciences, Universiti Teknologi MARA, 40450 Shah Alam, Selangor, Malaysia

### ABSTRACT

Equal channel angular pressing technique was used to process bulk nanostructured commercial pure titanium Cp2(Ti Cp2) and aluminium alloy 6061(Al6061). The samples were processed at two different die channel angles of 120 ° and 126 °. Hardness test shows that the hardness for Al6061, using channel angle 120° ECAP-ed, has increase 15.55% while using channel angle 126° the increase was 14.89% compared to non-ECAP-ed sample. Hardness test for Ti Cp2 ,using channel angle 120° ECAP-ed has increase 32.89% while using channel angle 126° the increase was 27.05%. The hardness for this both materials have shown that Ti Cp2 has higher hardness compared to Al6061 since the highest increment is 5.84% for 120°ECAP-ed than 126°ECAP-ed for Ti Cp2 samples. The corrosion behavior of the ECAP-ed Al6061 was investigated in 3.5% sodium chloride (NaCl) solution relative to seawater concentration while Ti Cp2 was investigated in phosphate buffered saline (PBS) solution. Corrosion resistance on 120° ECAP-ed for both Al6061 and Ti Cp2 have shown improved corrosion behavior indicated by the least value of corrosion current density when compared to non-ECAP. By using channel angle 120°, Al6061 have shown the lowest corrosion current density (Icorr) value of 1.61E-7 while Ti Cp2 has also shown lowest Icorr value of 1.19E-08. This means ECAP-ed using 120° is the most noble sample with lowest corrosion value, when applied with current, among all samples.

### KEYWORDS

Pure Titanium, Aluminium alloys, Equal Channel Angular Pressing (ECAP), corrosion behavior, mechanical properties

## ACKNOWLEDGEMENT

This paper was fully supported by facilities and resources from University Malaysia Pahang. The authors would like to acknowledge the support of grants from University Malaysia Pahang No. RDU180318 and Fundamental Research Grant Scheme, Ministry of Higher Education, Malaysia No. RDU190110.

## REFERENCES

- [1] E. Marin, M. Pressacco, S. Fusi, A. Lanzutti, S. Turchet, and L. Fedrizzi, "Characterization of grade 2 commercially pure Trabecular Titanium structures," *Materials Science and Engineering: C*, vol. 33, pp. 2648-2656, 2013.
- [2] J. A. Santiago, I. Fernandez-Martinez, A. Wennberg, J. Molina-Aldareguia, M. Castillo-Rodríguez, T. Rojas, *et al.*, "Adhesion enhancement of DLC hard coatings by HiPIMS metal ion etching pretreatment," *Surface and Coatings Technology*, vol. 349, 05/01 2018.
- [3] N. Saleema, D. K. Sarkar, R. W. Paynter, D. Gallant, and M. Eskandarian, "A simple surface treatment and characterization of AA 6061 aluminum alloy surface for adhesive bonding applications," *Applied Surface Science*, vol. 261, pp. 742-748, 2012/11/15/ 2012.
- [4] Z. S. Zahari, D. N. Awang Sh'ri, M. A. H. Abu Hassan, and W. S. Wan Harun, "Effect of ECAP die angle to the microstructure and mechanical properties of bulk nanostructured Al-6061," *IOP Conference Series: Materials Science and Engineering*, vol. 469, p. 012054, 2019/01/16 2019.
- [5] P. Sureshkumar, V. C. Uvaraja, and S. Rajakarunakaran, "Addition of metallic reinforcement enhanced deformation and properties of ceramic reinforced composite by adapting ECAP with increment number of passes," *Materials Research Express*, vol. 6, p. 086502, 2019/05/01 2019.
- [6] I. Ansarian, M. H. Shaeri, M. Ebrahimi, P. Minárik, and K. Bartha, "Microstructure evolution and mechanical behaviour of severely deformed pure titanium through multi directional forging," *Journal of Alloys and Compounds*, vol. 776, pp. 83-95, 2019/03/05/ 2019.
- [7] R. Z. Valiev and T. G. Langdon, "Principles of equal-channel angular pressing as a processing tool for grain refinement," *Progress in Materials Science*, vol. 51, pp. 881-981, 2006.
- [8] A. Sotniczuk, D. Kuczyńska-Zemła, P. Kwaśniak, M. Thomas, and H. Garbacz, "Corrosion behavior of Ti-29Nb-13Ta-4.6Zr and commercially pure Ti under simulated inflammatory conditions – comparative effect of grain refinement and non-toxic  $\beta$  phase stabilizers," *Electrochimica Acta*, vol. 312, pp. 369-379, 2019/07/20/ 2019.
- [9] V. S. de Viteri and E. Fuentes, "Titanium and titanium alloys as biomaterials," *Tribology—Fundamentals and advancements. InTech*, pp. 155-181, 2013.

- [10] M. K. Abbass, K. S. Hassan, and A. S. Alwan, "Study of corrosion resistance of aluminum alloy 6061/SiC composites in 3.5% NaCl solution," *International Journal of Materials, Mechanics and Manufacturing*, vol. 3, pp. 31-35, 2015.
- [11] M. Natesan, S. Selvaraj, T. Manickam, and G. Venkatachari, "Corrosion behavior of metals and alloys in marine-industrial environment," *Science and Technology of Advanced Materials*, vol. 9, p. 045002, 2008/12 2008.
- [12] B. Gao, X. Zhang, and Y. Sheng, "Studies on preparing and corrosion inhibition behaviour of quaternized polyethyleneimine for low carbon steel in sulfuric acid," *Materials Chemistry and physics*, vol. 108, pp. 375-381, 2008.
- [13] M. I. A. EL AAL and M. Sadawy, "Influence of ECAP as grain refinement technique on microstructure evolution, mechanical properties and corrosion behavior of pure aluminum," *Transactions of Nonferrous Metals Society of China*, vol. 25, pp. 3865-3876, 2015.
- [14] E. Porcayo-Palafox, S. Carrera-Chavez, S. Casolco, J. Porcayo-Calderon, and V. Salinas-Bravo, "Electrochemical Performance of Ti-Based Commercial Biomaterials," *Advances in Materials Science and Engineering*, vol. 2019, 2019.
- [15] B. Burnat, M. Walkowiak-Przybyło, T. Błaszczyk, and L. Klimek, "Corrosion behaviour of polished and sandblasted titanium alloys in PBS solution," *Acta of Bioengineering and Biomechanics*, vol. 15, 2013.
- [16] A. Balyanov, J. Kutnyakova, N. Amirhanova, V. Stolyarov, R. Valiev, X. Liao, *et al.*, "Corrosion resistance of ultra fine-grained Ti," *Scripta Materialia*, vol. 51, pp. 225-229, 2004.
- [17] M. Bahraminasab, M. Bozorg, S. Ghaffari, and F. Kavakebian, "Corrosion of Al<sub>2</sub>O<sub>3</sub>-Ti composites under inflammatory condition in simulated physiological solution," *Materials Science and Engineering: C*, vol. 102, pp. 200-211, 2019.