

Formation of Ni[C₄(CN)₈] from the reaction of Ni(COD)₂ (COD = 1,5-cyclooctadiene) with TCNE in THF

Joel S. Miller* and Konstantin I. Pokhodnya

Received 7th June 2007, Accepted 25th July 2007

First published as an Advance Article on the web 2nd August 2007

DOI: 10.1039/b708675j

The dissolution of Ni(COD)₂ (COD = 1,5-cyclooctadiene) into dichloromethane leads to decomposition and formation of a room temperature magnetic material, whereas the reaction of Ni(COD)₂ and tetracyanoethylene (TCNE) in THF forms paramagnetic materials including Ni^{II}[C₄(CN)₈](THF)₂·xTHF. These results are discussed in context with a recent report of a room temperature magnet based upon the reaction of Ni(COD)₂ and TCNE in dichloromethane.

Introduction

Since the report of the first organic-based magnet, [Fe(C₅Me₅)₂]⁺[TCNE]⁻ (TCNE = tetracyanoethylene),^{1,2} several other families of [TCNE]⁻-based magnets have been reported. These include M[TCNE]_x·zCH₂Cl₂ {x ~ 2; z ~ 0.5; M = V,³ Mn,^{4,5} Fe,^{4,6} Co,^{4,7} Ni,^{4,8}}, [MnTPP][TCNE]·z(solvent) (H₂TPP = *meso*-tetraphenylporphyrin),⁹ and recently [Fe^{II}(TCNE)(NCMe)₂]-[Fe^{III}Cl₄] with a 2 : 1 Fe : TCNE ratio.¹⁰ The highest T_c observed is 400 K (127 °C) for V[TCNE]_x·zCH₂Cl₂; however, these materials exhibit degraded T_cs upon heating above ~350 K and/or exposure to air.

Recently Hicks and co-workers reported a major enhancement with respect to the air stability as well as a higher T_c for a Ni(II)-[TCNE]⁻-based magnet.¹¹ These authors claim that reaction of bis(1,5-cyclooctadiene)nickel(0), Ni(COD)₂, with TCNE, 7,7,8,8-tetracyano-*p*-quinodimethane (TCNQ), or 2,3-dichloro-5,6-dicyano-nobenzoquinone (DDQ) dissolved in dichloromethane, and after exposure to air, forms an 'ill-defined' metal-organic magnet of, for example, Ni₂(TCNE)O(OH)(OH)₂(CH₂Cl₂)_{1/8} composition that magnetically orders above room temperature.

Results and discussion

While Ni(COD)₂¹² is known to decompose in air,^{13a} even within an inert atmosphere glove box (<0.5 ppm O₂ and H₂O), Ni(COD)₂ immediately decomposes upon dissolution into dichloromethane to form a black powder, and a resultant colorless solution possessing 1,5-cyclooctadiene. This black powder is immediately attracted to a magnetic stirring bar (Fig. 1). Formation of colloidal Ni has been reported from the reaction of Ni(COD)₂ and dichloromethane in the presence of polyvinylpyrrolidone (which is used to control the particle size).^{13c,d} The temperature dependent magnetization, M(T), of this black powder (Fig. 2) is comparable to that reported in Fig. 1 of reference 11, as




Fig. 1 Black powder reaction product, which forms when Ni(COD)₂ is dissolved in dichloromethane, is attracted to a magnet. Photograph by William W. Shum.

well as Fig. 3 in reference 13(d) for colloidal Ni made from Ni(COD)₂.

Ni(COD)₂ is inherently unstable^{13a} and autocatalytically decomposes in the presence of Ni(0).^{13b} Even in the solid state bright-yellow Ni(COD)₂ stored in a freezer exhibits slow decomposition (as we note the presence of ~200 and ~700 ppm Ni⁰,¹⁴




Fig. 2 M(T) for black particles formed from Ni(COD)₂ dissolved in dichloromethane.

Department of Chemistry, University of Utah, Salt Lake City, UT, 84112-0850, USA. E-mail: jsmiller@chem.utah.edu

respectively, for different sources). Note that these $\text{Ni}^0(\text{COD})_2$ samples appear to be pure to the eye—even in solution—as upon dissolution in THF or toluene they immediately give a transparent yellow solution. However, light from a HeNe laser does exhibit light scattering (Tyndall effect) suggesting a colloidal character of the solutions due to Ni particles comparable in size to the 633 nm wavelength of the light. Additionally, upon longer standing in either THF or toluene at room temperature within a glove box, decomposition forming a Ni mirror occurs.

Reaction of TCNE and $\text{Ni}(\text{COD})_2$ in THF in a 2 : 1 ratio forms a green product exhibiting ν_{CN} 2238 and 2187 cm^{-1} absorptions (Fig. 3). Based upon the elemental analysis this material is formulated as $\text{Ni}(\text{TCNE})_2 \cdot 3.45\text{THF}$.¹⁵ Similar ν_{CN} absorptions at 2242 and 2191 cm^{-1} were observed for the green product of the reaction of $[\text{Ni}^{\text{II}}(\text{NCMe})_6]^{2+}$ ¹⁶ and $[\text{TCNE}]^-$ in MeCN. Related reactions involving $[\text{M}^{\text{II}}(\text{NCMe})_6]^{2+}$ ($\text{M} = \text{Mn}, \text{Fe}$) yield $\text{M}[\text{C}_4(\text{CN})_8](\text{NCMe})_2 \cdot \text{S}$ ($\text{S} = \text{solvent}$) with ν_{CN} peaks at 2205 and 2153 cm^{-1} and at 2213 and 2154 cm^{-1} , respectively.¹⁷ The $\sim 30 \text{ cm}^{-1}$ blue shift is consistent with that observed in $[\text{M}^{\text{II}}(\text{NCMe})_6][\text{SbF}_6]_2$ ($\text{M} = \text{Mn}, \text{Fe}, \text{Co}, \text{Ni}$) when either Mn or Fe is replaced by Ni.¹⁶ Thus, this compound formed *via* the 2 : 1 TCNE : Ni ratio is formulated as $\text{Ni}[\text{C}_4(\text{CN})_8](\text{THF})_2 \cdot 1.45(\text{THF})$, and possesses $\mu_4-[\text{C}_4(\text{CN})_8]^{2-}$.

The observed ν_{CN} absorptions, however, may also be due to the presence of $\mu_4-[\text{TCNE}]^-$ as observed for $[\text{Fe}(\text{TCNE})(\text{NCMe})_2][\text{FeCl}_4]$ (*i.e.* 2222 and 2178 cm^{-1}),¹⁰ or both $\mu_4-[\text{TCNE}]^-$ and $\mu_4-[\text{C}_4(\text{CN})_8]^{2-}$ as reported for $\text{Fe}[\text{TCNE}][\text{C}_4(\text{CN})_8]_{1/2} \cdot z(\text{CH}_2\text{Cl}_2)$ (*i.e.* 2221 and 2172 cm^{-1}).¹⁸ The observed frequencies are $15 \pm 5 \text{ cm}^{-1}$ higher than those of $\text{Ni}[\text{TCNE}]_2 \cdot z\text{CH}_2\text{Cl}_2$ prepared from TCNE and $\text{Ni}(\text{CO})_4$ (*i.e.* 2218 and 2178 cm^{-1}),⁸ but nominally comparable to this material prepared from $\text{NiI}_2 \cdot z\text{MeCN}$ and TCNE (*i.e.* 2237 and 2194 cm^{-1}).⁴

In contrast, the reaction of TCNE and $\text{Ni}(\text{COD})_2$ in THF in a 1 : 2 ratio forms a brown product exhibiting ν_{CN} absorptions at 2201 and 2116 cm^{-1} (Fig. 3).¹⁹ Analysis of the elemental composition as well as the color suggest that this product is a mixture of more than one component, which includes some $\text{Ni}(\text{TCNE})_2 \cdot x\text{THF}$ as well as perhaps $\mu_4-[\text{TCNE}]^{2-}$ based upon the low energy ν_{CN} absorption.




Fig. 3 The ν_{CN} region of the IR spectra of the reaction products of TCNE and $\text{Ni}(\text{COD})_2$ in THF in 1 : 2 (b) and 2 : 1 (c) ratios. The spectrum of $\text{Ni}[\text{C}_4(\text{CN})_8](\text{NCMe})_2$ (a) is shown for comparison.




Fig. 4 $\chi T(T)$ for $\text{Ni}[\text{C}_4(\text{CN})_8](\text{THF})_2 \cdot 1.45(\text{THF})$ (○) that includes a temperature independent contribution of $\sim 300 \text{ ppm}$ of Ni (●). $\chi T(T)$ for $\text{Ni}[\text{C}_4(\text{CN})_8](\text{NCMe})_2 \cdot \text{MeCN}$ (×) is shown for comparison.

The 5 to 300 K temperature dependent magnetic susceptibility, χ , of $\text{Ni}(\text{TCNE})_2 \cdot 3.45\text{THF}$ is reported as $\chi T(T)$, Fig. 4. Above 15 K $\chi T(T)$ increases almost linearly suggesting a substantial temperature independent component, most probably ferromagnetic in origin. As noted above, $\text{Ni}(\text{COD})_2$ slowly decomposes at room temperature in THF solution, and more than 200 ppm of ferromagnetic Ni^0 impurities are expected. The susceptibility of nanosize Ni^0 particles are temperature dependent, especially when approaching critical temperature.²⁰ This temperature independent component corresponds to $\sim 300 \text{ ppm}$ Ni, and upon correcting the $\chi T(T)$ data, $\chi T(T)$ is temperature independent in the $10 < T < 170 \text{ K}$ region. Above 170 K $\chi T(T)$ decreases as a consequence of the temperature dependence of the ferromagnetic contribution. The χT value at 170 K for $\text{Ni}(\text{TCNE})_2 \cdot 3.45\text{THF}$ is $1.41 \text{ emu K mol}^{-1}$, which is typical for high-spin Ni(II) ions ($S = 1$, $g = 2.37$).²¹ This is in accord with the presence of diamagnetic $[\text{C}_4(\text{CN})_8]^{2-}$ in agreement with the IR spectra. The drop in $\chi T(T)$ below 10 K is most probably due to a weak antiferromagnetic coupling between Ni(II) ions.

The product of the reaction of TCNE and $\text{Ni}(\text{COD})_2$ in a 1 : 2 ratio reaction also exhibits a susceptibility composed of a paramagnetic component and a temperature independent component (below 200 K) attributed to the Ni^0 present from the starting $\text{Ni}(\text{COD})_2$ material. It does not order magnetically, and its multiphase composition makes the detailed analysis inconclusive.

Furthermore, the presence of reduced TCNE, as claimed in reference 11, is quite unlikely since the reduced radical anion of TCNE, $[\text{TCNE}]^{\cdot -}$, very quickly reacts with water/oxygen to form $[\text{C}_2(\text{CN})_3\text{O}]^-$ and other species²² that unlike $[\text{TCNE}]^{\cdot -}$ do not enable magnetic ordering.²³ The $[\text{C}_2(\text{CN})_3\text{O}]^-$ species has diagnostic infrared absorptions at $\sim 2225 \pm 20$ (ν_{CN}), $\sim 2197 \pm 17$ (ν_{CN}), and $\sim 1585 \pm 35 \text{ cm}^{-1}$ (ν_{CO}),^{23,24} which appear to be consistent with spectra reported as supplementary Fig. 2c of reference 11. Metal complexes of $[\text{C}_2(\text{CN})_3\text{O}]^-$ are typically unintentionally made and are isolated from the hydrolysis of either TCNE or $[\text{TCNE}]^{\cdot -}$, and their presence has surprised several research groups.^{23,24} Similarly, related $[\text{TCNQ}]^{\cdot -}$ and

$[\text{C}_4(\text{CN})_6]^{4-}$ have been reported to undergo this hydrolysis to form diamagnetic $[(\text{NC})_2\text{C}_6\text{H}_4\text{C}(\text{O})\text{CN}]^{2-}$ ^{25a} and $[\text{C}_4(\text{CN})_5\text{O}]^{3-}$ ^{25b} respectively.

Conclusion

Presumably the magnetic material made upon dissolution of $\text{Ni}(\text{COD})_2$ in CH_2Cl_2 consists of 'nano'- or greater-sized particles of nickel metal. This black powder magnetic material may also have chlorine, carbon, and/or hydrogen present, but it certainly lacks the organic species used in the aforementioned paper. The identification of the magnetically active component of organic- and molecule-based magnets remains challenging,²⁶ as several reports have failed to stand the test of time^{27–29} in spite of publicity they have garnered.

Acknowledgements

We appreciate the helpful discussions with Janis Louie, Michael Strem (Strem Chemicals, Inc.), Maurice Brookhart (North Carolina), and William Shum, in addition to his photography, the continued partial support by the Department of Energy Division of Material Science (Grant Nos. DE-FG03-93ER45504 and DE-FG02-01ER4593), U. S. Air Force Office of Scientific Research (Grant No. F49620-03-1-0175), and the U. S. National Science Foundation (Grant No. 0553573).

Notes and references

- 1 J. S. Miller, J. C. Calabrese, A. J. Epstein, R. W. Bigelow, J. H. Zhang and W. M. Reiff, *J. Chem. Soc., Chem. Commun.*, 1986, 1026; J. S. Miller, J. C. Calabrese, H. Rommelmann, S. Chittipeddi, A. J. Epstein, J. H. Zhang and W. M. Reiff, *J. Am. Chem. Soc.*, 1987, **109**, 769.
- 2 G. T. Yee and J. S. Miller, *Magnetism - Molecules to Materials*, ed. J. S. Miller and M. Drillon, Wiley-VCH, Weinheim, 2005, **5**, 223; E. Coronado, J. R. Galán-Mascarós and J. S. Miller, *Comprehensive Organometallic Chemistry III*, ed. R. H. Crabtree and D. M. P. Mingos, Oxford, 2006, vol. 12, p. 413.
- 3 (a) J. M. Manriquez, G. T. Yee, R. S. McLean, A. J. Epstein and J. S. Miller, *Science*, 1991, **252**, 1415; J. S. Miller, G. T. Yee, J. M. Manriquez and A. J. Epstein, in Proceedings of Nobel Symposium #NS-81: *Conjugated Polymers and Related Materials: The Interconnection of Chemical and Electronic Structure*, Oxford University Press, Oxford, UK, 1993, p. 461; J. S. Miller, G. T. Yee, J. M. Manriquez and A. J. Epstein, *Chim. Ind.*, 1992, **74**, 845; (b) J. Zhang, J. S. Miller, C. Vazquez, P. Zhou, W. B. Brinckerhoff and A. J. Epstein, *ACS Symp. Ser.*, 1996, **644**, 311.
- 4 J. Zhang, J. Ensling, V. Ksenofontov, P. Gülich, A. J. Epstein and J. S. Miller, *Angew. Chem., Int. Ed.*, 1998, **37**, 657, (*Angew. Chem.*, 1998, **110**, 676).
- 5 C. M. Wynn, M. A. Girtu, J. Zhang, J. S. Miller and A. J. Epstein, *Phys. Rev. B*, 1998, **58**, 8508.
- 6 M. A. Girtu, C. M. Wynn, J. Zhang, J. S. Miller and A. J. Epstein, *Phys. Rev. B*, 2000, **61**, 492; K. I. Pokhodnya, E. B. Vickers, M. Bonner, A. J. Epstein and J. S. Miller, *Chem. Mater.*, 2004, **16**, 3218; K. I. Pokhodnya, N. Petersen and J. S. Miller, *Inorg. Chem.*, 2002, **41**, 1996.
- 7 K. I. Pokhodnya, V. Burtman, A. J. Epstein, J. W. Raebiger and J. S. Miller, *Adv. Mater.*, 2003, **15**, 1211.
- 8 E. B. Vickers, A. Senesi and J. S. Miller, *Inorg. Chim. Acta*, 2004, **357**, 3889.
- 9 J. S. Miller and A. J. Epstein, *Chem. Commun.*, 1998, 1319.
- 10 K. I. Pokhodnya, M. Bonner, J.-H. Her, P. W. Stephens and J. S. Miller, *J. Am. Chem. Soc.*, 2006, **128**, 15592.
- 11 R. Jain, K. Kabir, J. B. Gilroy, K. A. R. Mitchell, K.-c. Wong and R. G. Hicks, *Nature*, 2007, **445**, 291.
- 12 As reported in reference 11, $\text{Ni}(\text{COD})_2$ was kept in a freezer and used as received, but not purified by recrystallization: D. J. Krysan and P. B. Mackenzie, *J. Org. Chem.*, 1990, **55**, 4229.
- 13 (a) R. A. Shunn, R. Baker, R. J. Cole, J. D. Gilbert and D. P. Madden, *Inorg. Synth.*, 1974, **15**, 5; R. A. Shunn, S. D. Ittel, M. A. Cushing, R. Baker, R. J. Cole, J. D. Gilbert and D. P. Madden, *Inorg. Synth.*, 1990, **28**, 95(b) J. Louis, personal communication; (c) D. d. Caro and J. S. Bradley, *Langmuir*, 1997, **13**, 3967; (d) T. O. Ely, C. Amiens, E. Snoeck, M. Verelst, M. Respaud and J.-M. Broto, *Chem. Mater.*, 1999, **11**, 526.
- 14 The magnetization field dependence, $M(H)$, at room temperature of $\text{Ni}(\text{COD})_2$, obtained from two different sources, shows a clear tendency to saturate at low fields (<2500 Oe). At higher field $M(H)$ starts to decrease linearly due to a growing contribution from diamagnetic COD. The Ni^0 impurities content was determined by comparing the saturation $M(H)$ value with $55.6 \text{ emu Oe g}^{-1}$ for metallic nickel.
- 15 Calculated (observed) for $\text{Ni}(\text{TCNE})_2 \cdot 3.45\text{THF}$, $\text{C}_{75.8}\text{H}_{27.6}\text{N}_8\text{NiO}_{3.45}$: %C = 54.98 (55.10), %H = 4.94 (4.72), and %N = 19.88 (19.92).
- 16 J. S. Miller and W. E. Buschmann, *Chem.-Eur. J.*, 1999, **4**, 1731.
- 17 J. Zhang, L. M. Liable-Sands, A. L. Rheingold, R. E. Del Sesto, D. C. Gordon, B. M. Burkhardt and J. S. Miller, *Chem. Commun.*, 1998, 1385.
- 18 J.-H. Her, P. W. Stephens, K. I. Pokhodnya, M. Bonner and J. S. Miller, *Angew. Chem., Int. Ed.*, 2007, **46**, 1543, (*Angew. Chem.*, 2007, **119**, 1521).
- 19 Reaction of TCNE and $\text{Ni}(\text{COD})_2$ in toluene in either a 1 : 2 or 2 : 1 ratio leads to a product with a mixture of the four IR absorptions noted in Fig. 3.
- 20 P. Zhang, F. Zuo, F. K. Urban, A. Khabari, P. Griffiths and A. Hosseini-Tehrani, *J. Magn. Magn. Mater.*, 2001, **225**, 337.
- 21 A. T. Casey and S. Mitra, in *Theory and Application of Molecular Paramagnetism*, ed. E. A. Boudreaux and L. N. Mulay, John Wiley & Sons, New York, 1976. The reported range for $\text{Ni}(\text{II})$ is $1.20 \leq \chi T \leq 1.45$ (p. 227).
- 22 O. W. Webster, W. Mahler and R. E. Benson, *J. Am. Chem. Soc.*, 1962, **80**, 3678; W. J. Middleton, E. I. Little, D. D. Coffman and V. A. Engelhardt, *J. Am. Chem. Soc.*, 1958, **84**, 3796.
- 23 E. J. Brandon, G. P. A. Yap, A. L. Rheingold, A. Arif and J. S. Miller, *Inorg. Chim. Acta*, 1995, **240**, 515 and references therein.
- 24 H. Zhou, J. Basca, A. Prosvirin, N. Lopez and K. R. Dunbar, *Polyhedron*, 2005, **24**, 1907.
- 25 (a) W. R. Hertler, H. D. Hartzler, D. S. Acker and R. E. Benson, *J. Am. Chem. Soc.*, 1962, **84**, 3387; (b) D. K. Rittenberg, K.-i. Sugiura, A. M. Arif, C. D. Incarvito, A. L. Rheingold, Y. Sakata and J. S. Miller, *Chem.-Eur. J.*, 2000, **6**, 1811.
- 26 J. S. Miller, *Adv. Mater.*, 1992, **4**, 298; J. S. Miller, *Adv. Mater.*, 1992, **4**, 435.
- 27 T. L. Makarova, B. Sundqvist, R. Höhne, P. Esquinazi, Y. Kopelevich, P. Scharff, V. Davydov, L. S. Kashevarova and A. V. Rakhmania, *Nature*, 2006, **440**, 707.
- 28 J. S. Miller, D. T. Glatzhofer, R. Laversanne, S. Chittipeddi, T. B. Brill, M. Timken, C. J. O'Connor, J. H. Zhang, J. C. Calabrese, A. J. Epstein, S. Chittipeddi and P. Vaca, *Chem. Mater.*, 1990, **2**, 60.
- 29 G. Blackman, E. Boyes, D. B. Chase, I. R. Hartmann, G. Hyatt, E. Matthews, R. S. McLean, J. S. Miller, C. Vazquez and J. P. Wyre, *Chem. Mater.*, 1992, **4**, 504.